

(19)



(11)

EP 1 724 272 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
21.08.2013 Bulletin 2013/34

(51) Int Cl.:
C07D 495/14 ^(2006.01) **C07D 517/14** ^(2006.01)
C09K 11/06 ^(2006.01) **H05B 33/14** ^(2006.01)

(21) Application number: **05720278.0**

(86) International application number:
PCT/JP2005/004006

(22) Date of filing: **08.03.2005**

(87) International publication number:
WO 2005/087780 (22.09.2005 Gazette 2005/38)

(54) **CHALCOGEN-CONTAINING FUSED-RING POLYCYCLIC ORGANIC MATERIAL AND PROCESS FOR PRODUCING THE SAME**

POLYCYCLISCHES ORGANISCHES MATERIAL MIT CHALCOGENHALTIGEM KONDENSIERTEM RING UND VERFAHREN ZU DESSEN HERSTELLUNG

SUBSTANCE ORGANIQUE POLYCYCLIQUE A ANNEAU FUSIONNE CONTENANT DU CHALCOGENURE ET SON PROCEDE DE PRODUCTION

(84) Designated Contracting States:
DE FR GB NL

(30) Priority: **10.03.2004 JP 2004068039**

(43) Date of publication of application:
22.11.2006 Bulletin 2006/47

(73) Proprietor: **Japan Science and Technology Agency**
Kawaguchi-shi,
Saitama 332-0012 (JP)

(72) Inventors:
• **YAMAGUCHI, Shigehiro**
Nagoya-shi, Aichi 464-0083 (JP)
• **OKAMOTO, Toshihiro**
Nagoya-shi, Aichi 464-0035 (JP)

(74) Representative: **Müller - Hoffmann & Partner**
Patentanwälte
Innere Wiener Strasse 17
81667 München (DE)

(56) References cited:
JP-A- 2001 261 794

• **OYAIKU K. ET AL:** 'Lineal Ladder-Type pi Conjugated Polymers Composed of Fused Thiophene Ring Systems.' **MACROMOLECULES.** vol. 37, 24 February 2004, pages 1257 - 1270, XP002989426

- **ZHUANG X. ET AL:** 'Effect of Ring Fusion on the Electronic Absorption and Emission Properties of Oligothiophenes.' **J.ORG.CHEM.** vol. 68, 2003, pages 9813 - 9815, XP002989427
- **SATO N. ET AL:** 'Linearly condensed Polythiophenes: Characteristic Molecular Aggregation of Thieno(2'',3'':4',5')thieno(2',3'-d)thieno(3, 2-b)thiophene Crystals Revealed by Ultraviolet Photoelectron Spectroscopy.' **J.CHEM.SOC.PEIKIN TRANS.** vol. 2, 1992, pages 765 - 770, XP002989428
- **MAZAKI Y. ET AL:** 'Synthesis of Tetrahydro-Acene and Pentathieno-Acene: UV-spectral Trend in a Homologous Series of Thieno-Acenes.' **TETRAHEDRON LETTERS.** vol. 30, no. 25, 1989, pages 3315 - 3318, XP002989429
- **KOBAYASHI K. ET AL:** 'Sulfur Heterocycles for Organic Conductors and Superconductors.' **PHOSPHOROUS, SULFUR AND SILICA.** vol. 43, no. 1-2, 1989, pages 187 - 208, XP002989430
- **SCHROTH W. ET AL:** 'Bis(benzo(4,5)thieno) (3,2-c:2',3',-e)(1,2)dithiin, ein Valenzisomer von "Dithioxo-thioindigo".' **CHEM.BER.** vol. 127, 1994, pages 401 - 408, XP002989431
- **SCHRPTH W. ET AL:** 'Zur fragwürdigen Existenz von thioxo-indigoiden Verbindungen.' **ANGEW.CHEM.** vol. 106, no. 7, 1994, pages 808 - 810, XP002989432
- **SCHROTH W. ET AL:** 'On the Equilibrium between Hetareno-annulated 1,2-Dithiines and 12-Membered Cyclic Bis (butadienyli) Disulfides. NMR and Molecular Modelling Studies.' **TETRAHEDRON.** vol. 51, no. 32, 1995, pages 8853 - 8862, XP002989433

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 724 272 B1

- SCHROTH W. ET AL: '1,2-Dithiins and Precursors, XVII: Synthesis and Properties of Thieno Anellated 1,2-Dithiins, Structural Influence on Colour.' TETRAHEDRON. vol. 53, no. 22, 1997, pages 7509 - 7528, XP004105748
- YOSHIKI MIZUKAMI ET AL: "CCL17 and CCL22 chemokines within tumor microenvironment are related to accumulation of Foxp3+ regulatory T cells in gastric cancer", INTERNATIONAL JOURNAL OF CANCER, vol. 122, no. 10, 15 May 2008 (2008-05-15) , pages 2286-2293, XP055052296, ISSN: 0020-7136, DOI: 10.1002/ijc.23392

Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to: (i) a chalcogen-containing fused polycyclic organic material which can be applied to an organic thin-film transistor and an organic electroluminescence (hereinafter abbreviated as "EL") element and which has a highly efficient charge-transporting property; and (ii) a method for producing the chalcogen-containing fused polycyclic organic material.

10 BACKGROUND ART

[0002] In the field of organic electronics, it is a task of highest priority to develop a material which can be applied to an organic thin-film transistor (TFT) and an organic electroluminescence (EL) element and which exhibits excellent charge-transporting properties, regardless of whether the material is a p-type material or an n-type material. There has
15 been fierce global-scale competition for the development of such a material.

[0003] A promising example of the molecular designing of the material is to build a highly planar n-conjugated skeleton, which will realize an effective intermolecular interaction. In fact, pentacene, which is an acenic compound having such a structure, is known to exhibit good charge-transporting properties, and has been studied in a wide range of researches.

20 **[0004]** The following materials are expected to serve as the material: (i) heteroacenes having a hetero atom introduced therein and (ii) fused polycyclic aromatic compounds having a dichalcogenide bond, which are similar to heteroacenes.

(Patent Document 1)

Japanese Unexamined Patent Publication No. 261794/2001 (*Tokukai* 2001-261794; published on September 26, 2001)

25 (Non-patent Document 1)

K. Oyaizu, T. Iwasaki, Y. Tsukahara, E. Tsuchida, *Macromolecules*, 2004, ASAP.

(Non-patent Document 2)

S. Naoki, Y. Mazaki, K. Kobayashi, T. Kobayashi, *J. Chem. Soc., Perkin Trans. 2*, 1992, pp. 765.

(Non-patent Document 3)

30 Y. Mazaki, K. Kobayashi, *Tetrahedron Lett.* 1989, 30, pp. 3315.

(Non-patent Document 4)

K. Kobayashi, *Phosphorus, Sulfur, and Silicon and the Related Elements*, 1989, 43, pp. 187.

(Non-patent Document 5)

35 W. Schroth, E. Hintzsche, H. Viola, R. Winkler, H. Klose, R. Boese, R. Kempe, J. Sieler, *Chem. Ber.*, 1994, 127, pp. 401.

(Non-patent Document 6)

W. Schroth, E. Hintzsche, M. Felicetti, R. Spitzner, J. Sieler, R. Kempe, *Angew. Chem., Int. Ed. Engl.*, 1994, 33, pp. 739.

(Non-patent Document 7)

40 W. Schroth, D. Ströhl, I. Thondorf, W. Brandt, M. Felicetti, T. Gelbrich, *Tetrahedron*, 1995, 51, pp. 8853.

(Non-patent Document 8)

W. Schroth, E. Hintzsche, H. Jordan, T. Jende, R. Spitzner, I. Thondorf, *Tetrahedron*, 1997, 53, pp. 7509.

(Non-patent Document 9)

R. D. Adams, B. Captain, J. L. Smith Jr., *J. Organomet. Chem.*, 2004, 689, 65.


45 Zhuang X. et al. (*J. Org. Chem.* (2003) 9813 - 9815) and Sato N. et al. (*J. Chem. Soc. Perkin Trans* (1992) 765 - 770) relate to oligothiophenes.

DISCLOSURE OF INVENTION

50 **[0005]** The present invention is defined in its broadest sense by the appended claims.

(Problem to be solved by the Invention)

55 **[0006]** However, because there is no effective and general method for synthesizing the fused polycyclic aromatic compound having a dichalcogenid bond, there have been only a few cases where the compound is applied to the field of organic electronics (Patent Document 1 and Non-patent Documents 1 to 4). Therefore, there has been a demand for an effective and general method for synthesizing the compound.



5

10

[0007] Schroth et al. have reported on a synthesis and structure of an unsubstituted benzo fused-ring derivative (represented by formula (6)) (Non-patent Documents 5 to 8). This is the only research associated with the fused polycyclic aromatic compound having the dichalcogenid bond. However, the report neither discloses nor suggests the application of the structure to the field of organic electronics.

15


[0008] Further, Kobayashi and Tsuchida et al. have reported on the synthesis of the following heteroacenes: (i) an unsubstituted heteroacene compound represented by following formula (9) where R^1 , R^2 , R^3 , and R^4 are H; and (ii) a monomethyl substituted heteroacene compound represented by following formula (9) where R^1 is Me and R^2 , R^3 , and R^4 are H (Non-patent Documents 2 to 4 and Patent Document 1). Further, Tsuchida et al have reported on a synthesis of polymeric polythiacenes ((Patent Document 1 and Non-patent Document 2). However, a synthesis method by which a heteroacene having a substituent can be synthesized precisely as desired has not been attained, and therefore there has been a demand for such a method.

20

[0009] The present invention has been made in view of the foregoing problems. The inventors of the present invention made an effort to develop a conceptually novel synthetic method. As a result, the inventors has successfully developed an effective and general method for synthesizing the group of important compounds, i.e., the series of chalcogen-containing fused-ring polycyclic organic materials. It is an object of the present invention to provide the group of compounds and a producing method thereof.

25

[0010] In order to solve the foregoing problems, a chalcogen-containing fused polycyclic organic material described in the present invention has a structure represented by following formula (1):



30

35

where E^1 is S or Se, and Ar is one selected from the group consisting of a benzene group, a substituted benzene group, a naphthalene group, a substituted naphthalene group, an anthracene group, a substituted anthracene group, a thiophene group, a substituted thiophene group, a furan group, a substituted furan group, a pyrrole group, a substituted pyrrole group, a selenophene group, a substituted selenophene group, a pyridine group, a substituted pyridine group, a thiazole group, a substituted thiazole group, a benzothiophene group, a substituted benzothiophene group, a benzofuran group, a substituted benzofuran group, an indole group, and a substituted indole group, where Ar is fused thereto at one double bond moiety, excluding that Ar is a benzene group when E^1 is S.



40

[0011] In order to solve the foregoing problems, a method for producing a chalcogen-containing fused polycyclic organic material includes the step of producing the foregoing chalcogen-containing fused polycyclic organic material by intramolecularly forming three rings in a diacetylene compound as expressed in following formula (5):

45


50

55



20 where X is I, Br, or Cl, wherein the diacetylene compound is allowed to react with a chalcogen element E_1 after the diacetylene compound is dimetalated by a halogen-metal exchange reaction in which an organic metallic base is used.

25 **[0012]** In order to solve the foregoing problems, another chalcogen-containing fused polycyclic organic material is a heteroacene compound represented by following formula (9):



35 where E^1 is S or Se, and Ar is one selected from the group consisting of a benzene group, a substituted benzene group, a naphthalene group, a substituted naphthalene group, an anthracene group, a substituted anthracene group, a thiophene group, a substituted thiophene group, a furan group, a substituted furan group, a pyrrole group, a substituted pyrrole group, a selenophene group, a substituted selenophene group, a pyridine group, a substituted pyridine group, a thiazole group, a substituted thiazole group, a benzothiophene group, a substituted benzothiophene group, a benzofuran group, a substituted benzofuran group, an indole group, and a substituted indole group, where, Ar is fused thereto at its one double bond moiety, excluding that Ar is one selected from the group consisting of a benzene group a thiophene group and an alkyl group substituted thiophene group when E^1 is S.

40

(Effects of the Invention)

45 **[0013]** As described above, the chalcogen-containing fused polycyclic organic material has the structure represented by formula (1) or (9). Accordingly, the material is expected to exhibit excellent charge-transporting properties. Therefore, the material can be applied to the field of organic electronics, e.g., to an organic thin-film transistor (TFT) and an organic electroluminescence (EL) element.



50 **[0014]** As described above, the method described in the present invention for producing a chalcogen-containing fused polycyclic organic material makes it possible that a chalcogen-containing fused polycyclic organic material supposed to exhibit excellent charge-transporting properties is obtained by an intramolecular triple cyclization reaction. Therefore, the method can simplify and generalize the production of a chalcogen-containing fused polycyclic organic material suitable to the field of organic electronics, e.g., to an organic thin-film transistor (TFT) and an organic electroluminescence (EL) element.

55 BEST MODE FOR CARRYING OUT THE INVENTION

[0015] An embodiment described in the present invention will be described below. The following explains a method for synthesizing a compound represented by formula (1). See reaction formula (8) below. A diacetylene compound

represented by following formula (7) is used as a starting material, and is dimetalated by a halogen-metal exchange reaction using an organic metallic base. Thereafter, the dimetalated product is allowed to react with a chalcogen element E¹. As a result, the compound (chalcogen-containing fused polycyclic organic material) represented by formula (1) can be synthesized by an intramolecular triple cyclization reaction.

5



[0016] Examples of the organic metallic base used herein include: (i) an organolithium reagent such as n-BuLi, s-BuLi, or t-BuLi; and (ii) an organomagnesium reagent such as an alkyl Grignard reagent. Metalization in THF using t-BuLi gives the highest yield. Further, examples of the chalcogen element E¹ used herein include (i) a highly reactive chalcogen element, i.e., S₈, (b) a commercially available S (sulfur) or Se (selenium) crystal (S₈ or Se₈), and (c) a powder made of the crystal.

25

[0017] Further, a molar ratio of the chalcogen element E¹ to the diacetylene compound is preferably 2:1 to 10:1 and, more preferably, 4:1 to 6:1. The starting material is preferably a diacetylene compound having at least two halogenated ring compound groups. It is preferable that the 2-position of each of the ring compound groups be halogenated. The ring compound group may be, but are not limited to, (i) a phenyl group corresponding to benzene and (ii) a thiophene-derived group. Further, the ring compound group may have a substituent.

30

[0018] In the following, Examples will be described, by which the present invention will be described more specifically. It should be noted that the present invention is not limited to these Examples. The following shows synthetic schemes, actual operations, and results of identification of the compounds. Note that all the reactions described above and below is/was carried out under an atmosphere of argon gas.

35


(Synthesis of Compound 2) (not part of the present invention)

40 [0019]

45

50

55



[0020] To a solution in which Compound 1 (2.3 g, 5.5 mmol) was mixed with THF (25 mL), *t*-BuLi (1.43 M heptane solution, 15.4 mL, 22 mmol) was added over a period of 5 minutes at -78°C. The reaction mixture was stirred for 90 minutes at the same temperature. Thereafter, to the reaction mixture, sulfur (crystal, S₈) (705 mg, 22 mmol) serving as the chalcogen element E¹ was added in the form of a solid. The reaction mixture so obtained was stirred for 10 minutes. Thereafter, the temperature was allowed to rise room temperature. Then, the reaction mixture was further stirred for 10 hours.




[0021] The reaction mixture was concentrated under reduced pressure. After a 10% aqueous solution of sodium hydroxide and then dichloromethane were added into the mixture so obtained, extraction was performed with shaking. Thereafter, an organic layer of the dichloromethane and an aqueous layer were separated. An aqueous solution of potassium ferricyanide was added to the separated aqueous layer. This precipitated a red solid. The red solid so obtained was extracted with dichloromethane.

[0022] The organic layer of the dichloromethane obtained by extraction of the red solid was washed with distilled water, and then was dried with magnesium sulfate. Thereafter, the solvent was distilled off from the organic layer. As a result, targeted Compound 2 was obtained in the form of a red powder. The properties of Compound 2 are as follows.

[0023] Compound 2: C₁₈H₁₂O₂S₄; red powder. ¹H NMR (500 MHz, CDCl₃) δ 7.69 (d, 2H, J = 8.5 Hz), 7.21 (d, 2H, J = 2.5 Hz), 7.04 (dd, 2H, J = 8.5 Hz, 2.5 Hz), 3.92 (s, 6H). ¹³C NMR (67.5 MHz, CDCl₃) δ 158.32, 138.02, 135.30, 130.65, 123.40, 120.09, 116.40, 104.93, 55.64.

(Synthesis of Compound 4) (not part of the present invention)

[0024]




[0025] To a solution in which Compound 3 (360 mg, 1.0 mmol) was mixed with THF (10 mL), *t*-BuLi (1.45 M heptane solution, 2.8 mL, 4.0 mmol) was added over a period of five minutes at -78°C. The reaction mixture was stirred for 30 minutes at the same temperature. Thereafter, to the reaction mixture, selenium (powder, Se₈) (474 mg, 6.0 mmol) serving as the chalcogen element E¹ was added in the form of a solid. The reaction mixture so obtained was stirred for 10 minutes at -78°C. Thereafter, the temperature was allowed to rise to room temperature. Then, the reaction mixture was further stirred for 8 hours.

[0026] The reaction mixture was mixed with distilled water, and then was extracted with dichloromethane. As a result, an organic layer was obtained. The organic layer so obtained was washed with distilled water, and was dried using magnesium sulfate. Thereafter, the solvent was distilled off under reduced pressure. As a result, a purplish red mixture was obtained. The purplish red mixture so obtained was separated and purified by alumina column chromatography (developing solvent: dichloromethane). As a result, target Compound 4 (262 mg, 0.51 mmol, 51% yield) was obtained in the form of a purplish solid. The properties of Compound 4 are as follows.

[0027] Compound 4: C₁₆H₈Se₄; purple plates (recrystallized from dichloromethane-hexane). ¹H NMR (500 MHz, CDCl₃) δ 7.89-7.86 (m, 4H), 7.49 (m, 2H), 7.33 (m, 2H). ¹³C NMR (67.5 MHz, CDCl₃) δ 140.97, 140.41, 127.00, 125.78, 125.67, 125.58, 116.15. MS (EI): 520 (M⁺).

(Synthesis of Compounds 6 and 7) (not part of the present invention)

[0028]



25 **[0029]** To a solution in which Compound 5 (200 mg, 0.39 mmol) having TMS (trimethylsilyl) groups was mixed with THF (5 mL), *t*-BuLi (1.48 M heptane solution, 1.05 mL, 1.55 mmol) was added dropwise over a period of 5 minutes at -78°C. The reaction mixture was stirred for 80 minutes at the same temperature. Thereafter, to the reaction mixture, sulfur (crystal) (50 mg, 1.55 mmol) was added in the form of a solid. The reaction mixture so obtained was stirred for 1 hour. Thereafter, the temperature was allowed to rise to room temperature. Then, the reaction mixture was further stirred for 3.5 hours.

30 **[0030]** After a 10% aqueous solution of sodium hydroxide was added therein, the reaction mixture was treated with potassium ferricyanide. Thereafter, the resulting mixture was extracted with dichloromethane. As a result, an organic layer was obtained. The organic layer so obtained was washed with distilled water, and was dried using sodium sulfate. Thereafter, the solvent was distilled off under reduced pressure. As a result, a red mixture was obtained. The red mixture so obtained was allowed to pass through a short alumina column (developing solvent: dichloromethane), and then was separated and purified by using GPC (chloroform). As a result, target Compound 6 (78 mg, 0.16 mmol, 41% yield) was obtained in the form of a red solid. The properties of Compound 6 are as follows.

35 **[0031]** Compound 6: $C_{18}H_{20}S_6Si_2$; red plates (recrystallized from chloroform-ethanol). 1H NMR (500 MHz, $CDCl_3$) δ 7.33 (s, 2H), 0.39 (s, 18H). ^{13}C NMR (67.5 MHz, $CDCl_3$) δ 145.38, 143.20, 136.86, 132.80, 125.54, 115.79, -0.25. MS (EI): 484 (M^+).

40 **[0032]** Compound 7 was synthesized in the same manner as Compound 6, except that selenium was used instead of sulfur. As a result, Compound 7 was obtained in a 56% yield. The properties of Compound 7 are as follows.


45 **[0033]** Compound 7: $C_{18}H_{20}S_2Se_4Si_2$; purple plates (recrystallized from chloroform-ethanol). 1H NMR (500 MHz, $CDCl_3$) δ 7.42 (s, 2H), 0.37 (s, 18H). ^{13}C NMR (67.5 MHz, $CDCl_3$) δ 147.43, 144.62, 144.62, 142.03, 137.35, 129.52, 128.85, -0.23. MS (EI): 676 (M^+).

(Synthesis of Compounds 9 and 10) (not part of the present invention)

50 **[0034]**


55

55



10

1) *t*-BuLi, THF
2) E¹ = S₈ or Se₈



25

[0035] To a solution in which Compound 8 (1.42 g, 3.0 mmol) was mixed with THF (60 mL), *t*-BuLi (1.48 M heptane solution, 8.1 mL, 1.2.0 mmol) was added over a period of 5 minutes at -78°C. The reaction mixture was stirred for 100 minutes at the same temperature. Thereafter, to the reaction mixture, sulfur (crystal) (385 mg, 12.0 mmol) was added in the form of a solid.

30

[0036] The reaction mixture so obtained was stirred for 60 minutes. Thereafter, the temperature was allowed to rise to room temperature. Then, the reaction mixture was further stirred for 10 hours. The reaction mixture so obtained was mixed with a 10% aqueous solution of sodium hydroxide, and then was treated with potassium ferricyanide. As a result, a solid precipitate was obtained. Thereafter, the solid was filtered out. The solid so obtained was washed with distilled water and ethanol, and then was dried under reduced pressure in the presence of diphosphorus pentoxide. The solid so obtained was recrystallized in *o*-dichlorobenzene. As a result, Compound 9 (900 mg, 2.04 mmol, 68% yield) was obtained in the form of a red purple powder. The properties of Compound 9 are as follows.

35

[0037] Compound 9: C₂₀H₈S₆; red purple powder. ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/9) δ 7.86-7.80 (m, 4H), 7.47-7.38 (m, 4H). MS (EI): 440 (M⁺).

[0038] Compound 10 was synthesized in the same manner as Compound 9, except that selenium was used instead of sulfur. As a result, Compound 10 was obtained in a 24% yield. The properties of Compound 10 are as follows.

[0039] Compound 10: C₂₀H₈S₂Se₄; purple powder. MS (EI): 629 (M⁺).



40

[0040] Among these compounds thus successfully synthesized, Compound 4 was examined by X-ray crystallographic analysis. It was found that Compound 4 has a herringbone packing structure. This structure is very advantageous for good charge-transporting properties.




45

[0041] A heteroacene compound (chalcogen-containing fused polycyclic organic material) according to an embodiment of the present invention will be described below. The following explains a method for synthesizing a compound represented by formula (9). By the dechalcogenation reaction described in Non-patent Documents 5 and 9 carried out with a compound represented by formula (1) as a starting material as illustrated in reaction formula (13) below, the compound represented by formula (9) can be synthesized as a heteroacene compound. specifically, for example, the reaction may be carried out by heating the compound represented by formula (1) in the presence of a transition metal such as a platinum complex (Pt(COD)₂ or copper powder, where COD is 1,5-cyclooctadiene.

50



... (13)



50

[0042] An Example of the embodiment of the present invention will be described below. Compound 2 (50 mg, 0.13 mmol) was heated by a heat gun (at approximately 200°C) for 15 minutes under an atmosphere of argon in the presence of copper (nanoscale powder) (32 mg, 0.50 mmol, 3.9 mol. amt.), and then was cooled down. Thereafter, Compound 2 was mixed with hot chloroform. After the insoluble was filtered out, the filtrate was concentrated. As a result, Compound 11 (32 mg, 70% yield) was obtained, which was a heteroacene compound in the form of a colorless solid. The properties of Compound 11 are as follows.

55

[0043] Compound 11: C₁₈H₁₂O₂S₃; colorless powders; ¹H NMR (270 MHz, CDCl₃) δ 7.74 (d, 2H, J = 8.9 Hz), 7.29 (d, 2H, J = 2.6 Hz), 7.01 (dd, 2H, J = 8.9 Hz, 2.6 Hz), 3.94 (s, 6H).


[0044] A chalcogen-containing fused polycyclic organic material according to the present invention is a novel compound that can be used as a charge-transporting material.

(Means to solve the problem)

[0045] In order to solve the foregoing problems, a chalcogen-containing fused polycyclic organic material described in the present invention has a structure represented by following formula (1):

5

10



15


where E¹ is S or Se, and Ar is one selected from the group consisting of a benzene group, a substituted benzene group, a naphthalene group, a substituted naphthalene group, an anthracene group, a substituted anthracene group, a thiophene group, a substituted thiophene group, a furan group, a substituted furan group, a pyrrole group, a substituted pyrrole group, a selenophene group, a substituted selenophene group, a pyridine group, a substituted pyridine group, a thiazole group, a substituted thiazole group, a benzothiophene group, a substituted benzothiophene group, a benzofuran group, a substituted benzofuran group, an indole group, and a substituted indole group, where Ar is fused thereto at one double bond moiety, excluding that Ar is a benzene group when E¹ is S.

20

[0046] The chalcogen-containing fused polycyclic organic material may have a structure represented by following formula (2):

25

30



where R¹, R², R³, and R⁴ are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxy carbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom.


35

40

[0047] The chalcogen-containing fused polycyclic organic material may have a structure represented by following formula (3):

45

50




where R¹, R², R³, R⁴, R⁵, R⁶, R⁷, and R⁸ are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an aryl-

55


lkyllthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxycarbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom, excluding that $R^1 = R^2 = R^3 = R^4 = R^5 = R^6 = R^7 = R^8 =$ a hydrogen atom when E^1 is S.

[0048] The chalcogen-containing fused polycyclic organic material may have a structure represented by following formula (4):



where $R^1, R^2, R^3, R^4, R^5, R^6, R^7,$ and R^8 are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxycarbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom.

[0049] In order to solve the foregoing problem, a method described in the present invention for producing a chalcogen-containing fused polycyclic organic material includes the step of producing the foregoing chalcogen-containing fused polycyclic organic material by intramolecularly forming three rings in a diacetylene compound as expressed in following formula (5):




where X is I, Br, or Cl.

[0050] According to the foregoing producing method, the diacetylene compound is allowed to react with a chalcogen element E^1 after the diacetylene compound is dimetalated by a halogen-metal exchange reaction in which an organic metallic base is used.

[0051] In order to solve the foregoing problems, another chalcogen-containing fused polycyclic organic material de-

scribed in the present invention is a heteroacene compound represented by following formula (9):



10


where E¹ is S or Se, and Ar is one selected from the group consisting of a benzene group, a substituted benzene group, a naphthalene group, a substituted naphthalene group, an anthracene group, a substituted anthracene group, a thiophene group, a substituted thiophene group, a furan group, a substituted furan group, a pyrrole group, a substituted pyrrole group, a selenophene group, a substituted selenophene group, a pyridine group, a substituted pyridine group, a thiazole group, a substituted thiazole group, a benzothiophene group, a substituted benzothiophene group, a benzofuran group, a substituted benzofuran group, an indole group, and a substituted indole group, where Ar is fused thereto at one double bond moiety, excluding that Ar is one selected from the group consisting of a benzene group a thiophene group, and an alkyl group substituted thiophene group E¹ is S.

15

20

[0052] The chalcogen-containing fused polycyclic organic material may be a heteroacene compound having a structure represented by following formula (10):

25



30


where R¹, R², R³, and R⁴ are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxy carbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom, excluding that R¹ = R² = R³ = R⁴ = a hydrogen atom when E¹ is S, and that R¹ is a methyl group and R² = R³ = R⁴ = a hydrogen atom when E¹ is S.

35

40

[0053] The foregoing chalcogen-containing fused polycyclic organic material may be a heteroacene compound having a structure represented by following formula (11):

45




50

where R¹, R², R³, R⁴, R⁵, R⁶, R⁷, and R⁸ are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group,

55

an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxycarbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom, excluding that $R^1 = R^2 = R^3 = R^4 = R^5 = R^6 = R^7 = R^8 =$ a hydrogen atom when E^1 is S.

[0054] The foregoing chalcogen-containing fused polycyclic organic material may be a heteroacene compound having a structure represented by following formula (12):



where $R^1, R^2, R^3, R^4, R^5, R^6, R^7,$ and R^8 are independently an aryl group, a substituted aryl group, an oligoaryl group, a substituted oligoaryl group; a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group, a carboxyl group, an acyl group, an alkoxycarbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom.


INDUSTRIAL APPLICABILITY

[0055] A chalcogen-containing fused polycyclic organic material according to the present invention is capable of exhibiting excellent charge-transporting properties. Therefore, the material can be applied to an organic thin-film transistor and an organic EL element, which are used for attaining thinner thickness or lighter weight in electronic devices such as a display device.

[0056] A method described in the present invention for producing a chalcogen-containing fused polycyclic organic material makes it possible to easily and reliably obtain various chalcogen-containing fused polycyclic organic materials capable of exhibiting excellent charge-transporting properties.

Claims

1. A chalcogen-containing fused polycyclic having a structure represented by following formula (11):




where E^1 is S or Se, and $R^1, R^2, R^3, R^4, R^5, R^6, R^7,$ and R^8 are independently an aryl group, a substituted aryl

group, an oligoaryl group, a substituted oligoaryl group, a monovalent heterocyclic group, a monovalent substituted heterocyclic group, a monovalent oligoheterocyclic group, a monovalent substituted oligoheterocyclic group, a hydrogen atom, an alkyl group, an alkoxy group, an alkylthio group, an aryloxy group, an arylthio group, an arylalkyl group, an arylalkoxy group, an arylalkylthio group, an alkenyl group, a substituted alkenyl group, an alkynyl group, a substituted alkynyl group, an allyl group, an amino group, a substituted amino group, an azo group; a carboxyl group, an acyl group, an alkoxy carbonyl group, a formyl group, a nitro group, a cyano group, a silyl group, a substituted silyl group, a stannyl group, a substituted stannyl group, a boryl group, a substituted boryl group, a phosphanyl group, a substituted phosphanyl group, a silyloxy group, a substituted silyloxy group, an arylsulfonyloxy group, an alkylsulfonyloxy group, or a halogen atom, excluding that $R^1 = R^2 = R^3 = R^4 = R^5 = R^6 = R^7 = R^8 =$ a hydrogen atom when E¹ is S.

Patentansprüche


1. Eine Chalcogen-enhaltende kondensierte polycyclische Verbindung mit der in der nachfolgenden Formel (11) angegebenen Struktur:



wobei E¹ für S oder Se steht und R¹, R², R³, R⁴, R⁵, R⁶, R⁷ und R⁸ unabhängig stehen für eine Aryl-Gruppe, eine substituierte Aryl-Gruppe, eine Oligoaryl-Gruppe, eine substituierte Oligoaryl-Gruppe, eine monovalente heterocyclische Gruppe, eine monovalente substituierte heterocyclische Gruppe, eine monovalente oligoheterocyclische Gruppe, eine monovalente substituierte oligoheterocyclische Gruppe, ein Wasserstoffatom, eine Alkyl-Gruppe, eine Alkoxy-Gruppe, eine Alkylthio-Gruppe, eine Aryloxy-Gruppe, eine Arylthio-Gruppe, eine Arylalkyl-Gruppe, eine Arylalkoxy-Gruppe, eine Arylalkylthio-Gruppe, eine Alkenyl-Gruppe, eine substituierte Alkenyl-Gruppe, eine Alkynyl-Gruppe, eine substituierte Alkynyl-Gruppe, eine Allyl-Gruppe, eine Amino-Gruppe, eine substituierte Amino-Gruppe, eine Azo-Gruppe; eine Carboxyl-Gruppe, eine Acyl-Gruppe, eine Alkoxy carbonyl-Gruppe, eine Formyl-Gruppe, eine Nitro-Gruppe, eine Cyano-Gruppe, eine Silyl-Gruppe, eine substituierte Silyl-Gruppe, eine Stannyl-Gruppe, eine substituierte Stannyl-Gruppe, eine Boryl-Gruppe, eine substituierte Boryl-Gruppe, eine Phosphanyl-Gruppe, eine substituierte Phosphanyl-Gruppe, eine Silyloxy-Gruppe, eine substituierte Silyloxy-Gruppe, eine Arylsulfonyloxy-Gruppe, eine Alkylsulfonyloxy-Gruppe oder ein Halogen-Atom, wobei ausgenommen ist, dass $R^1 = R^2 = R^3 = R^4 = R^5 = R^6 = R^7 = R^8 =$ ein Wasserstoffatom, wenn E¹ für S steht.

Revendications

1. Composé polycyclique fusionné contenant un chalcogène ayant une structure représentée par la formule (11) suivante :



15 dans laquelle E¹ représente un atome de S ou de Se, et R¹, R², R³, R⁴, R⁵, R⁶, R⁷ et R⁸ représentent indépendamment un groupe aryle, un groupe aryle substitué, un groupe oligoaryle, un groupe oligoaryle substitué, un groupe hétéro-

20 cyclique monovalent, un groupe hétérocyclique monovalent substitué, un groupe oligohétérocyclique monovalent, un groupe oligohétérocyclique monovalent substitué, un atome d'hydrogène, un groupe alkyle, un groupe alcoxy, un groupe alkylthio, un groupe aryloxy, un groupe arylthio, un groupe arylalkyle, un groupe arylalcoxy, un groupe arylalkylthio, un groupe alcényle, un groupe alcényle substitué, un groupe alcynyle, un groupe alcynyle substitué, un groupe allyle, un groupe amino, un groupe amino substitué, un groupe azo ; un groupe carboxyle, un groupe acyle, un groupe alcoxycarbonyle, un groupe formyle, un groupe nitro, un groupe cyano, un groupe silyle, un groupe silyle substitué, un groupe stannyle, un groupe stannyle substitué, un groupe boryle, un groupe boryle substitué, un groupe phosphanyle, un groupe phosphanyle substitué, un groupe silyloxy, un groupe silyloxy substitué, un groupe arylsulfonyloxy, un groupe alkylsulfonyloxy, ou un atome d'halogène, en excluant que R¹ = R² = R³ = R⁴ = R⁵ = R⁶ = R⁷ = R⁸ = un atome d'hydrogène lorsque E¹ est un atome de S.

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2001261794 A [0004]

Non-patent literature cited in the description

- K. OYAIZU ; T. IWASAKI ; Y. TSUKAHARA ; E. TSUCHIDA. *Macromolecules*, 2004 [0004]
- S. NAOKI ; Y. MAZAKI ; K. KOBAYASHI ; T. KOBAYASHI. *J. Chem. Soc., Perkin Trans.*, 1992, vol. 2, 765 [0004]
- Y. MAZAKI ; K. KOBAYASHI. *Tetrahedron Lett.*, 1989, vol. 30, 3315 [0004]
- K. KOBAYASHI. *Phosphorus, Sulfur, and Silicon and the Related Elements*, 1989, vol. 43, 187 [0004]
- W. SCHROTH ; E. HINTZSCHE ; H. VIOLA ; R. WINKLER ; H. KLOSE ; R. BOESE ; R. KEMPE ; J. SIELER. *Chem. Ber.*, 1994, vol. 127, 401 [0004]
- W. SCHROTH ; E. HINTZSCHE ; M. FELICETTI ; R. SPITZNER ; J. SIELER ; R. KEMPE. *Angew. Chem., Int. Ed. Engl.*, 1994, vol. 33, 739 [0004]
- W. SCHROTH ; D. STRÖHL ; I. THONDORF ; W. BRANDT ; M. FELICETTI ; T. GELBRICH. *Tetrahedron*, 1995, vol. 51, 8853 [0004]
- W. SCHROTH ; E. HINTZSCHE ; H. JORDAN ; T. JENDE ; R. SPITZNER ; I. THONDORF. *Tetrahedron*, 1997, vol. 53, 7509 [0004]
- R. D. ADAMS ; B. CAPTAIN ; J. L. SMITH JR. *J. Organomet. Chem.*, 2004, vol. 689, 65 [0004]
- ZHUANG X. et al. *J. Org. Chem.*, 2003, 9813-9815 [0004]
- SATO N. et al. *J. Chem. Soc. Perkin Trans*, 1992, 765-770 [0004]