



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2338775 C 2009/09/08

(11)(21) **2 338 775**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 2000/05/26
(87) Date publication PCT/PCT Publication Date: 2000/12/07
(45) Date de délivrance/Issue Date: 2009/09/08
(85) Entrée phase nationale/National Entry: 2001/01/25
(86) N° demande PCT/PCT Application No.: JP 2000/003398
(87) N° publication PCT/PCT Publication No.: 2000/073524
(30) Priorité/Priority: 1999/05/27 (JP11/148325)

(51) Cl.Int./Int.Cl. *C22C 38/00* (2006.01),
C21D 8/12 (2006.01), *C21D 9/46* (2006.01)
(72) Inventeur/Inventor:
ABIKO, KENJI, JP
(73) Propriétaire/Owner:
JAPAN SCIENCE AND TECHNOLOGY AGENCY, JP
(74) Agent: SMART & BIGGAR

(54) Titre : FEUILLE D'ACIER ELECTROMAGNETIQUE LAMINEE A CHAUD PRESENTANT DES CARACTERISTIQUES
MAGNETIQUES ET UNE RESISTANCE A LA CORROSION EXCELLENTE, ET PROCEDE DE FABRICATION
CORRESPONDANT

(54) Title: HOT ROLLED ELECTROMAGNETIC STEEL SHEET HAVING EXCELLENT MAGNETIC PROPERTIES AND
CORROSION RESISTANCE AND METHOD OF PRODUCING THE SAME

(57) Abrégé/Abstract:

A hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance is obtained by heating a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity to γ -zone and subjecting in this γ -zone to hot rolling at a total rolling reduction of not less than 50% and under condition that at least one pass is a friction coefficient between roll and rolling material of not more than 0.3 and thereafter cooling at an average cooling rate of 0.5~150°C over A_{r_3} transformation point ~300°C.



ABSTRACT

A hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance is obtained by heating a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity to γ -zone and subjecting in this γ -zone to hot rolling at a total rolling reduction of not less than 50% and under condition that at least one pass is a friction coefficient between roll and rolling material of not more than 0.3 and thereafter cooling at an average cooling rate of 0.5-150°C over Ar, transformation point -300°C.

SPECIFICATION

HOT ROLLED ELECTROMAGNETIC STEEL SHEET HAVING EXCELLENT MAGNETIC PROPERTIES AND CORROSION RESISTANCE AND METHOD OF PRODUCING THE SAME

TECHNICAL FIELD

This invention relates to a hot rolled electromagnetic steel sheet, and more particularly to a pure iron based hot rolled electromagnetic steel sheet having excellent magnetic properties by aligning $\langle 100 \rangle$ axis in a direction perpendicular to a sheet surface at as-rolled state in a high density and an excellent corrosion resistance and a method of producing the same.

BACKGROUND ART

Silicon steel sheets having excellent electromagnetic properties are used in a core for a transformer or a generator from the old time. As such a silicon steel sheet, there are two kinds of a unidirectional silicon steel sheet utilizing a secondary recrystallization to develop $\{110\}\langle 001 \rangle$ oriented grains or so-called Goss oriented grains, and a non-directional silicon steel sheet developing crystal grains with $\{100\}$ face parallel to a sheet surface. Among them, the non-directional silicon steel sheets have particularly good properties when magnetic field is applied to various directions in the sheet surface and are frequently used in the generator, electric motor and the like.

In case of producing the non-directional silicon steel sheet used for such applications, it has hitherto been required to conduct decarburization annealing in a controlled atmosphere, cross rolling changing a rolling direction during the cold rolling or the like for gathering $\{100\}$ face parallel to the sheet surface in a higher density.

70756-18

For example, JP-A-1-108345 relating to silicon steel containing Si: 0.2-6.5 wt% or JP-A-4-224624 relating to steel containing Al+Si: 0.2-6.5 wt% discloses a technique that the steel is cold-rolled and annealed in a weak decarburizing atmosphere, for example, under vacuum of not more than 0.1 torr or in an atmosphere having a dew point of not more than 0°C and composed of one or more of H₂, He, Ne, Nr, Ar, Xe, Rn and N₂ to form α -single phase region in a zone corresponding to a depth of 5-50 μ m from the sheet surface and then annealed in a strong
10 decarburizing atmosphere, for example, H₂ having a dew point of not less than -20°C or a gas obtained by adding an inert gas or CO, CO₂ to H₂ having a dew point of not less than -20°C at 650-900°C for 5-20 minutes to grow the α -single phase region formed on the surface layer portion into the inside in the thickness direction to thereby improve the magnetic properties.

Thus, complicated steps inclusive the decarburization annealing have been required in addition to
20 the hot rolling - cold rolling steps for gathering the {100} face parallel to the sheet surface in a high density from the old time. And also, the conventional electromagnetic steel sheets including 3% Si steel are low in the corrosion resistance, so that an insulating film having an excellent corrosion resistance is applied onto a final product, which is a factor raising the product cost.

However, it is recently demanded to have high performances at a cheaper cost with the popularization of electrical goods, which is impossible to cope with the
30 aforementioned conventional technique. Although it is considered to more simplify the production steps for satisfying the above demand, the conventional technique is difficult to enhance the gathering of {100} orientation parallel to the sheet surface as hot-rolled.

It is, therefore, an object of the invention to propose a hot rolled electromagnetic steel sheet having

70756-18

improved magnetic properties and corrosion resistance by gathering the {100} orientation parallel to the sheet surface at a time of completing hot rolling and a method of producing the same.

DISCLOSURE OF INVENTION

The inventors have made various studies for solving the above problems in the hot rolled electromagnetic steel sheet and found that the formation of {100} orientation parallel to sheet surface, i.e. <100>//ND orientation of the steel sheet (direction perpendicular to sheet surface) is promoted by highly purifying steel to form a pure iron based component composition and rationalizing hot rolling conditions (particularly rolling reduction at given temperature region, friction coefficient) and cooling rate at α -zone after hot rolling, and as a result the invention has been accomplished.

That is, the invention is a hot rolled electromagnetic steel sheet consisting of a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity, and having excellent magnetic properties and corrosion resistance.

As a method of producing the above hot rolled electromagnetic steel sheet, the invention also proposes a method of producing a hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance, characterized in that a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity is heated to γ -zone and subjected in this γ -zone to hot rolling at a total rolling reduction of not less than 50% and under condition that at least one pass is a friction coefficient between roll and rolling material of not more than 0.3 and thereafter cooled at an average cooling rate of 0.5-150°C over Ar₃

70756-18

transformation point -300°C .

As a preferable method, the invention proposes a method of producing a hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance, characterized in that a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity is heated to γ -zone and subjected in this γ -zone to hot rolling at a total rolling reduction of not less than 50% and under condition that at least one pass is a friction coefficient between roll and rolling material of not more than 0.3 and a strain rate of not less than 150 1/second and thereafter cooled at an average cooling rate of $0.5\text{-}150^{\circ}\text{C}$ over Ar, transformation point -300°C .

BEST MODE FOR CARRYING OUT THE INVENTION

An embodiment of the invention will be described below.

At first, the reason on the limitation of chemical composition in the pure iron based electromagnetic steel sheet according to the invention is described.

.Fe: not less than 99.95 mass%

A raw material of high purity Fe is hot rolled in γ -zone and then cooled in α -zone, during which $\langle 100 \rangle // \text{ND}$ oriented grains grow. The purity of Fe is particularly important in the invention. When the purity is less than 99.95 mass%, the $\langle 100 \rangle // \text{ND}$ oriented grains hardly grow in the cooling. Therefore, Fe is not less than 99.95 mass%, preferably not less than 99.98 mass%.

.C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm

These gas components in the pure iron form carbide, oxide and the like with metallic elements (Al, Ti, Nb, Mn and the like) contained at extremely slight amounts of few - few tens mass ppm in the pure iron to obstruct occurrence

70756-18

and growth of nucleus for $\langle 100 \rangle // ND$ oriented grains. And also, the corrosion of pure iron based material is mainly caused by starting from C, N, S segregated in a grain boundary or oxides existing in the grain boundary or in the grains to create rust.

Such a bad influence of C, N, S and O appears even when C+N+S exceeds 10 mass ppm or even when O exceeds 50 mass ppm, so that it is necessary to satisfy C+N+S: not more than 10 mass ppm and O: not more than 50 mass ppm together. Moreover, preferable content ranges are C+N+S: not more than 5 mass ppm and O: not more than 20 mass ppm.

Then, production conditions of the pure iron based electromagnetic steel sheet according to the invention are described.

.Hot rolling

When the raw material of pure iron based steel having the above component composition is hot rolled in α -zone, crystal grains are fined and $\langle 100 \rangle // ND$ oriented grains do not quite grow. Therefore, the hot rolling is necessary to be carried out at a temperature of γ -zone. When friction coefficient between roll and raw material exceeds 0.3 in the rolling of γ -zone, $\langle 110 \rangle // ND$ oriented grains are apt to be easily generated at a position near 1/10 of the sheet thickness and hence the occurrence and growth of $\langle 100 \rangle // ND$ oriented grains are controlled. For this end, the hot rolling is carried out at a friction coefficient of not more than 0.3, preferably not more than 0.2. When the rolling under such a condition (so-called lubrication rolling) is conducted in at least one pass of the hot rolling, the effect is developed. Particularly, when it is conducted in a final pass, a more larger effect is developed because shearing strain does not concentrate in the surface layer of the steel sheet before transformation. Furthermore, when the strain rate of the rolling is made not less than 150 1/second in the

'70756-18

lubrication rolling, the formation of $\langle 100 \rangle // ND$ oriented grains is promoted. Such a tendency is considered due to the fact that the formation of oriented grains other than $\langle 100 \rangle // ND$ such as $\langle 110 \rangle // ND$ easily formed on the surface layer portion of the steel sheet or the like is controlled. Moreover, when the strain rate is made not less than 200 1/second, a further larger effect is obtained.

In the above hot rolling in the γ -zone, the total rolling reduction is required to be not less than 50%.
10 Because, when the total rolling reduction in the hot rolling of γ -zone is not less than 50%, the recrystallization in the hot rolling is promoted to fine γ -grain size and the $\langle 100 \rangle // ND$ oriented grains are preferentially grown in a direction of sheet thickness in the cooling course after $\gamma \rightarrow \alpha$ transformation. When the total rolling reduction is less than 50%, equiaxed crystal grains having a random direction remain in a central portion of the sheet thickness to degrade the magnetic properties.

20 .Cooling after hot rolling

The $\langle 100 \rangle // ND$ oriented grains in the super-high purity iron grow from the surface of the steel sheet toward a center thereof at α -zone after $\gamma \rightarrow \alpha$ transformation while eroding α -grains newly created through transformation. In this case, when the cooling rate over $Ar_3-300^\circ C$ exceeds $150^\circ C/min$, the grain growing rate does not follow the cooling rate and equiaxed grains remain in the central portion of the sheet thickness. On the other hand, when the cooling rate is slower than $0.5^\circ C/min$, the $\langle 100 \rangle // ND$
30 oriented grains are coarsened to rather bring about the degradation of the magnetic properties. Therefore, the cooling rate within a temperature range of $Ar_3-300^\circ C$ after the rolling is required to be $0.5-150^\circ C/min$. Moreover, the preferable cooling rate is $1.0-100^\circ C/min$.

As mentioned above, according to the invention, the effect is first developed by using the pure iron based

70756-18

steel as a raw material and carrying out the production under given conditions, but if any one of the conditions is not satisfied, the gathering degree of <100>//ND oriented grains can not be enhanced. Moreover, the corrosion resistance is not substantially affected by the production conditions and is dependent upon the component composition.

EXAMPLE

10 The invention is concretely described with respect to examples.

A pure iron based steel having a chemical composition shown in Table 1 was melted in a melting furnace of super-high vacuum (10^{-8} Torr) provided with a water-cooled type copper crucible to form an ingot of 10 kg. The ingot was hot forged in γ -zone to form a rod-shaped raw material of 25 mm in thickness. The rod-shaped raw material was heated to 1100°C and hot rolled to a sheet thickness of 1 mm (partly thickness of 5 mm and 13 mm). In
20 this case, the hot rolling was carried out by changing friction coefficient between roll and the raw material, strain rate and the like in the final pass. Further, the cooling rate after the rolling was varied within a wide range. These production conditions are shown in Table 2.

Table 1

Steel	Fe /mass %	C /mass ppm	N /mass ppm	S /mass ppm	C+N+S /mass ppm	O /mass ppm	Ar ₃ transformation point (°C)	Remarks
A	99.99	0.2	0.5	1.2	1.9	21	908	Example
B	99.98	1.1	1.3	1.7	4.1	18	905	Example
C	99.96	2.1	1.9	4.3	8.3	33	900	Example
D	99.97	8.4	9.2	12.1	29.7	28	898	Comparative Example
E	99.96	3.1	2.7	4.1	9.9	80	900	Comparative Example
F	99.91	4.2	2.3	3.1	9.6	16	895	Comparative Example

Table 2

No	Steel	Final pass of hot rolling			Total rolling reduction of hot rolling (%)	Finishing sheet thickness (mm)	Cooling rate over Ar ₃ ~300°C (°C/minute)	Diffraction rate of X-ray I ₁₀₀ /I ₀	Magnetic flux density B ₅₀ (T)	Iron loss W _{15/50} (W/kg)	Corrosion loss (g/m ²)	Remarks
		Temperature of hot rolling (°C)	Friction coefficient	Strain rate (1/second)								
1	A	930	0.1	250	96	1.0	20	53	1.78	1.5	0.55	Example
2	A	930	0.3	210	95	1.0	70	49	1.77	1.6	0.51	Example
3	A	910	0.1	320	96	1.0	1.5	61	1.79	1.4	0.45	Example
4	A	850	0.2	180	96	1.0	20	1.1	1.55	3.3	0.87	Comparative Example
5	A	910	no lubrication (0.6)	180	96	1.0	20	1.6	1.55	3.4	0.96	Comparative Example
6	B	920	0.2	210	96	1.0	40	45	1.76	1.7	0.68	Example
7	B	940	0.2	160	48	13.0	80	1.2	1.52	3.6	0.98	Comparative Example
8	C	920	0.1	260	96	1.0	90	40	1.75	1.7	0.79	Example
9	C	920	0.2	260	96	1.0	0.3	13	1.68	2.1	0.98	Comparative Example
10	C	940	0.2	210	80	5.0	40	21	1.75	1.8	0.98	Example
11	D	920	0.2	240	96	1.0	50	1.3	1.38	8.5	21.4	Comparative Example
12	E	920	0.1	260	96	1.0	50	3.4	1.60	2.9	14.2	Comparative Example
13	F	930	0.3	260	96	1.0	50	1.2	1.53	3.5	36.2	Comparative Example

70756-18

The texture of the resulting hot rolled sheet was measured at a position corresponding to 1/4 of the sheet thickness by an X-ray. And also, a test piece of 1.0 mm in thickness was cut out from a central portion of the thickness of the hot rolled sheet and then a ring-shaped specimen having an inner diameter of 50 mm and an outer diameter of 60 mm was punched out therefrom and thereafter a primary coil and a secondary coil were wound on the specimen every 100 turns to measure magnetic properties. As the magnetic properties, there were adopted a magnetic flux density (B50) when an external magnetic field of 5000 A/m is applied and an iron loss (W15/50) when it is magnetized to 1.5 T in an alternating magnetic field of 50 Hz.

The corrosion resistance was evaluated by immersing in aqua regia of 20°C (mixed solution of concentrated nitric acid and concentrated hydrochloric acid at a volume ratio of 1:3) for 100 seconds to measure corrosion rate. It can be said that when the corrosion rate is not more than 1.0 g/m², the corrosion resistance is satisfactory under usual use environment.

The test results are also shown in Table 2. As seen from Table 2, the invention examples are excellent in both the magnetic properties and corrosion resistance. On the contrary, the comparative examples are largely poor in at least one of the magnetic properties and the corrosion resistance as compared with the invention examples.

INDUSTRIAL APPLICABILITY

As mentioned above, according to the invention, it is possible to gather {100} orientation parallel to the sheet surface after the completion of the hot rolling without passing through complicated steps such as decarburization annealing after cold rolling and the like, so that it is possible to cheaply provide hot rolled electromagnetic steel sheets having excellent magnetic

properties.

70756-18

CLAIMS:

1. A hot rolled electromagnetic steel sheet consisting of a super-high purity iron:

(a) comprising Fe: not less than 99.95 mass%,
5 C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity, and

(b) having $\langle 100 \rangle // ND$ oriented grains in a sheet thickness direction,

wherein the hot rolled electromagnetic steel sheet
10 has excellent magnetic properties and corrosion resistance.

2. The hot rolled electromagnetic steel sheet according to claim 1, which has an X-ray diffraction rate (I_{100}/I_0) of not less than 21 as measured at a position corresponding to $\frac{1}{4}$ of a sheet thickness.

15 3. The hot rolled electromagnetic steel sheet according to claim 1 or 2, wherein the magnetic properties comprise an iron loss ($W_{15/50}$) of 1.8 W/kg or less as measured by magnetizing the sheet to 1.5 T in an alternating magnetic field of 50 Hz.

20 4. The hot rolled electromagnetic steel sheet according to any one of claims 1 to 3, wherein the magnetic properties comprise a magnetic flux density (B_{50}) of 1.75 T to 1.79 T as measured by applying an external magnetic field of 5,000 A/m.

25 5. The hot rolled electromagnetic steel sheet according to any one of claims 1 to 4, which has a corrosion loss of 1.0 g/m^2 or less as measured by immersing the sheet

70756-18

in a mixed solution of concentric nitric acid and concentric hydrochloric acid at a volume ratio of 1:3 for 100 seconds.

6. The hot rolled electromagnetic steel sheet according to any one of claims 1 to 5, wherein the super-
5 high purity iron contains Fe: not less than 99.98 mass%.

7. The hot rolled electromagnetic steel sheet according to any one of claims 1 to 6, wherein the super-
high purity iron contains C+N+S: not more than 5 mass ppm.

8. The hot rolled electromagnetic steel sheet
10 according to any one of claims 1 to 7, wherein the super-
high purity iron contains O: not more than 20 mass ppm.

9. A method of producing a hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance, which comprises:

15 heating a super-high purity iron comprising Fe: not less than 99.95 mass%, C+N+S: not more than 10 mass ppm, O: not more than 50 mass ppm and the remainder being inevitable impurity, to γ -zone;

20 subjecting the super-high purity iron in this γ -zone to hot rolling at a total rolling reduction of not less than 50% and under a condition so that at least one pass is conducted at a friction coefficient between a roll and the super-high purity iron of not more than 0.3; and

25 thereafter cooling the hot rolled iron at an average cooling rate of 0.5 to 150°C over Ar₃ transformation point to 300°C.

70756-18

10. A method of producing a hot rolled electromagnetic steel sheet having excellent magnetic properties and corrosion resistance, which comprises:

heating a super-high purity iron comprising Fe:
5 not less than 99.95 mass%, C+N+S: not more than 10 mass ppm,
O: not more than 50 mass ppm and the remainder being
inevitable impurity, to γ -zone;

subjecting the super-high purity iron in this γ -
zone to hot rolling at a total rolling reduction of not less
10 than 50% and under a condition so that at least one pass is
conducted at a friction coefficient between a roll and the
super-high purity iron of not more than 0.3 and a strain
rate of not less than 150 1/second; and

thereafter cooling the hot-rolled iron at an
15 average cooling rate of 0.5 to 150°C over Ar_3 transformation
point to 300°C.

11. A method for producing the hot rolled electromagnetic steel sheet as defined in any one of claims 1 to 8, which comprises:

20 heating the super-high purity iron to γ -zone;

subjecting the super-high purity iron in this γ -
zone to hot rolling at a total rolling reduction of not less
than 50% and under a condition so that at least one pass is
conducted at a friction coefficient between a roll and the
25 super-high purity iron of not more than 0.3; and

thereafter cooling the hot rolled iron at an
average cooling rate of 0.5 to 150°C over Ar_3 transformation
point to 300°C.

70756-18

12. The method according to claim 11, wherein the hot rolling is conducted at a strain rate of not less than 150 1/second.

13. The method according to claim 10 or 12, wherein
5 the strain rate is 180 to 320 1/second.

14. The method according to any one of claims 9 to 13, wherein the total rolling reduction of the hot rolling is 96% or less.

15. The method according to any one of claims 9 to 14,
10 wherein the γ -zone is from 910°C to 940°C.

SMART & BIGGAR
OTTAWA, CANADA
PATENT AGENTS