



(12) **EUROPEAN PATENT APPLICATION**
 published in accordance with Art. 158(3) EPC

(43) Date of publication:
04.12.2002 Bulletin 2002/49

(21) Application number: **01908120.7**

(22) Date of filing: **28.02.2001**

(51) Int Cl.7: **C07C 15/20, C07C 25/22,**
C07C 5/367, C07B 61/00,
C07C 17/00, C07C 67/347,
C07C 69/76, H01B 1/12,
H01B 1/20, C08K 5/01,
C08L 101/00

(86) International application number:
PCT/JP01/01479

(87) International publication number:
WO 01/064611 (07.09.2001 Gazette 2001/36)

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR

(30) Priority: **29.02.2000 JP 2000054666**
25.08.2000 WOPCT/JP00/05768


(71) Applicant: **JAPAN SCIENCE AND TECHNOLOGY**
CORPORATION
Kawaguchi-shi, Saitama 332-0012 (JP)

(72) Inventor: **TAKAHASHI, Tamotsu**
Sapporo-shi, Hokkaido 064-0913 (JP)

(74) Representative:
Gille Hrabal Struck Neidlein Prop Roos
Patentanwälte,
Brucknerstrasse 20
40593 Düsseldorf (DE)

(54) **POLYACENE DERIVATIVES AND PRODUCTION THEREOF**

(57) The present invention relates to polyacene derivatives represented by general formula (I) below:



(wherein R¹ to R¹⁰, etc. each represents hydrogen at-

om, hydrocarbon group, or an alkoxy group; A¹ and A² are hydrogen atom, a halogen atom, a hydrocarbon group, an alkoxy group, cyano group, etc.; n is an integer of not less than 1; R⁶ and R⁷ may be linked to each other to form a ring); and a process for preparing the polyacene derivatives from polyhydro compounds as well as electrically conductive materials comprising the polyacene derivatives. According to the process for preparing the polyacene derivatives of the present invention, optional substituents can be introduced into any carbon atoms of the polyacene, and the number of aromatic rings can be increased.

Description

FIELD OF THE INVENTION

5 **[0001]** The present invention relates to polyacene derivatives and a process of producing the same.

BACKGROUND ART

10 **[0002]** It is known that conductive materials are obtained by doping electron donating molecules or electron accepting molecules into conjugated polymers as organic conductive materials, including polyacetylene, polypyrrole, polyallylenevinylene, polythienylenevinylene, etc. It is also known that electron transfer complexes formed by the combination of electron donating molecules such as tetrathiafulvalene, bisethylenedithiotetrathiafulvalene, etc. and electron accepting molecules such as tetracyanoquinodimethane, tetracyanoethylene, etc. exhibit a conductive property. Some of these organic conductive materials show high conductivity but can form a thin film only with difficulty. Furthermore, these conductive materials involve a problem in terms of stability, since they are readily oxidized in the air.

15 **[0003]** Since condensed polycyclic aromatic compounds like polyacenes such as anthracene, naphthacene, pentacene, etc. are conjugated polymers, it is known that these compounds exhibit a conductive property by doping electron donating molecules or electron accepting molecules into these compounds. It has thus been expected to use these compounds as electronic industry materials. Also, as the number of condensed benzene rings in polyacenes increases, the band gap between HOMO and LUMO decreases theoretically so that it is expected to increase the conductive property of polyacenes. Therefore, even if the concentration of dopants is low, it is likely to exhibit a sufficient conductive property.

20 **[0004]** Condensed polycyclic aromatic compounds such as polyacenes, however, have a very poor solubility and are hardly soluble, when no substituent is introduced therein. For this reason, there is a limit to synthesis methods using such condensed polycyclic aromatic compounds, and it was extremely difficult to process these compounds. It has thus been desired to introduce substituents on the side chains of condensed polycyclic aromatic compounds to improve the solubility strikingly, and to produce polyacenes suitable for easy synthesis and processing. In particular, any process for synthesis of sequentially increasing the number of condensed benzene rings while introducing substituents therein was unknown.

25 **[0005]** Heretofore, a means for introducing optional substituents at optional positions of polyacenes such as anthracene, naphthacene, pentacene, etc. has been limited to the Diels-Alder reaction.

30 **[0006]** For example, a process of producing decamethylantracene is described in Harold Hart, et al., "Decamethylantracene and its 10-'Dewar' Isomer," Tetrahedron Letter, No. 36, pp. 3143-3146. According to this process, the Diels-Alder reaction was applied to introduce methyl group into anthracene. Likewise in Tetrahedron, Vol. 43, No. 22, pp. 5403-5214, methyl group or the like was introduced into polyacenes by using the Diels-Alder reaction.

35 **[0007]** In the Diels-Alder reaction, there was a limit to substituents that can be introduced onto side chains. With respect to carbon atoms that can be substituted onto side chains, their latitude was limited as well. Further in the Diels-Alder reaction, it is impossible to increase the number of condensed benzene rings sequentially. In the Diels-Alder reaction, it is necessary to design a scheme of synthesis, respectively, considering the individual structures of target compounds.

40 **[0008]** JPA Nos. H4-335087, H6-167807, H6-330032 and H10-36832 disclose substituted naphthacenes, and JPA No. H11-354277 discloses substituted pentacenes. However, these compounds were all synthesized based on classic methods of synthesis, and substituents that could be introduced or positions at which substituents could be introduced were limited. And any process of synthesis for sequentially increasing the number of condensed benzene rings while introducing substituents was not disclosed, either.


DISCLOSURE OF THE INVENTION

45 **[0009]** In one aspect of the present invention, it is an object to introduce optional substituents into polyacenes at optional carbon atoms thereby to improve the solubility. By introducing substituents on the side chains of polyacenes, not only the solubility can be improved but further synthesis can be readily performed by introducing desired substituents so that the side chains of the polyacenes can be modified in various ways. Thus, the number of condensed aromatic rings can be increased sequentially while introducing substituents on the side chains of polyacenes.

50 **[0010]** It is described in K. P.C. Vollhardt et al., Journal of American Chemical Society, 1985, 107, 5670 that 1,2-bis(trimethylsilyl)acetylene is reacted with 1,2-diethynylbenzene in the presence of a catalyst such as cyclopentadienylbiscarbonylcobalt, etc. to simultaneously form the two rings of 4-membered ring condensed to benzene and benzene ring condensed to this 4-membered ring. That is, 3 rings are formed, taking into account the benzene ring originally present. Since two trimethylsilyl groups are present on the ortho-position on the 3 ring-product, it is described that

iodine chloride (IC1) is reacted with the product followed by reacting with trimethylsilylacetylene under basic conditions in the presence of palladium catalyst. There is described such a scheme that the reaction is similarly repeated as such to increase the number of condensed rings two at a time.

[0011] In one aspect of the present invention, there is provided a polyacene derivative represented by general formula (I) below:



(wherein:

each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 and R^{10} , which may be the same or different, independently represents hydrogen atom; a C_1 - C_{40} hydrocarbon group which may optionally be substituted; a C_1 - C_{40} alkoxy group which may optionally be substituted; a C_6 - C_{40} aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R^6 and R^7 may be cross-bridged with each other to form a C_4 - C_{40} saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: $-N(R^{11})-$ (wherein R^{11} is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

each of A^1 and A^2 , which may be the same or different, independently represents hydrogen atom; a halogen atom; a C_1 - C_{40} hydrocarbon group which may optionally be substituted; a C_1 - C_{40} alkoxy group which may optionally be substituted; a C_6 - C_{40} aryloxy group which may optionally be substituted; a C_7 - C_{40} alkylaryloxy group which may optionally be substituted; a C_2 - C_{40} alkoxy-carbonyl group which may optionally be substituted; a C_7 - C_{40} aryloxy-carbonyl group which may optionally be substituted; cyano group ($-CN$); carbamoyl group ($-C(=O)NH_2$); a haloformyl group ($-C(=O)-X$, wherein X represents a halogen atom); formyl group ($-C(=O)-H$); isocyanate group; thiocyanate group or thioisocyanate group; provided that A^1 and A^2 may be cross-bridged with each other to form a ring shown by formula: $-C(=O)-B-C(=O)-$ (wherein B is oxygen atom or a group shown by formula $-N(B^1)-$ (wherein B^1 is hydrogen atom, a C_1 - C_{40} hydrocarbon group or a halogen atom));

n is an integer of not less than 1;

with proviso that, except for the case wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 are all hydrogen atoms;

when n is 1,

at least R^1 , R^2 , R^4 and R^9 are groups other than hydrogen atom, or at least R^3 , R^5 , R^8 and R^{10} are groups other than hydrogen atom; and,

the cases of (a), (b), (c) and (d) below are excluded:

(a) when R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 are all methyl groups;


(b) when R^3 , R^4 , R^9 and R^{10} are all aryl groups that may optionally be substituted;

(c) when R^1 , R^2 , R^4 and R^9 are all alkoxy or aryloxy groups, and R^3 , R^5 , R^6 , R^7 , R^8 , R^{10} , A^1 and A^2 are all hydrogen atoms;

(d) when R^3 , R^5 , R^8 and R^{10} are all alkoxy or aryloxy groups, and R^1 , R^2 , R^4 , R^6 , R^7 , R^9 , A^1 and A^2 are all hydrogen atoms;

and, when n is 2, the cases of (a'), (b'), (c') and (d') below are excluded:

(a') a pentacene derivative represented by formula (Ia) below:




10

wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are all methyl groups; or R¹, R², R³, R⁴, R^{5a}, R^{5b}, R^{8a}, R^{8b}, R⁹ and R¹⁰ are all hydrogen atoms and at least one of R⁶, R⁷, A¹ and A² is an aryl group; or at least one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² is a dialkylamine group;

15


(b') a pentacene derivative represented by formula (lb) below:



25

wherein R¹, R², R^{5b} and R^{8b} are all alkoxy or aryloxy groups;

(c) a pentacene derivative represented by formula (lc) below:




35

wherein at least 2 of R³, R^{5a}, R^{8a} and R¹⁰ are aryl or arylalkynyl groups; or at least one of R³, R^{5a}, R^{8a} and R¹⁰ is an arylalkenyl group; or R³, R^{5a}, R^{8a} and R¹⁰ are all alkoxy or aryloxy groups;

40

(d') a pentacene derivative represented by formula (ld) below:




wherein R⁴ and R⁹ are hydrogen atom, a hydrocarbon group, an alkoxy group, an aryloxy group, a halogen atom or hydroxy group.)

55

[0012] In a further aspect of the present invention, preferably at least 5 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, and more preferably at least 6 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

[0013] The polyacene derivative described above is preferably a pentacene derivative represented by formula (la):



(wherein:

each of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

each of A¹ and A², which may be the same or different, independently represents hydrogen atom; a halogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; a C₇-C₄₀ alkylaryloxy group which may optionally be substituted; a C₂-C₄₀ alkoxy carbonyl group which may optionally be substituted; a C₇-C₄₀ aryloxy carbonyl group which may optionally be substituted; cyano group (-CN); carbamoyl group (-C(=O)NH₂); a haloformyl group (-C(=O)-X, wherein X represents a halogen atom); formyl group (-C(=O)-H); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group; provided that A¹ and A² may be cross-bridged with each other to form a ring shown by formula: -C(=O)-B-C(=O)- (wherein B is oxygen atom or a group shown by formula -N(B¹)- (wherein B¹ is hydrogen atom, a C₁-C₄₀ hydrocarbon group or a halogen atom)), and

at least 5 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, more preferably at least 6 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, further more preferably at least 7 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, much more preferably at least 8 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, further much more preferably at least 9 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, and most preferably at least 10 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.


[0014] In one aspect of the present invention, any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R⁵ and R⁸, R⁶ and R⁷, and A¹ and A² are preferably the same substituents; in one aspect of the present invention wherein the polyacene derivative is the pentacene derivative represented by the formula (1a) above, any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R^{5a} and R^{8a}, R^{5b} and R^{8b}, R⁶ and R⁷, and A¹ and A² are preferably the same substituents.

[0015] In one aspect of the present invention, any one of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰ is preferably a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted; in one aspect of the present invention, when the polyacene derivative is the pentacene derivative represented by the formula (1a) above, any one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰ is preferably a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

[0016] In one aspect of the present invention, when n is 1, A¹ and A² may be an alkoxy carbonyl group, and R¹, R², R⁴ and R⁹ may be an alkyl or aryl group; or when n is 1, A¹, A², R¹, R², R⁴ and R⁹ may be an alkyl or aryl group; or further when n is 1, A¹ and A² may be a halogen atom and R³, R⁵, R⁶, R⁷, R⁸ and R¹⁰ may be an alkyl or aryl group.

[0017] In one aspect of the present invention, when the polyacene derivative is the pentacene derivative represented by the formula (1a) above, A¹ and A² may be an alkoxy carbonyl group and R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ may be an alkyl or aryl group; or when the polyacene derivative is the pentacene derivative represented by the formula (1a) above, A¹, A², R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ may be an alkyl or aryl group; or, when the polyacene derivative is the pentacene derivative represented by the formula (1a) above, A¹ and A² may be a halogen group and R³, R^{5a}, R^{8a} and R¹⁰ may be an alkyl or aryl group.

[0018] In another aspect of the present invention, there is provided a process of producing the polyacene derivative represented by formula (I) below:




(wherein:

15 each of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

20 each of A¹ and A², which may be the same or different, independently represents hydrogen atom; a halogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; a C₇-C₄₀ alkylaryloxy group which may optionally be substituted; a C₂-C₄₀ alkoxy-carbonyl group which may optionally be substituted; a C₇-C₄₀ aryloxy-carbonyl group which may optionally be substituted; cyano group (-CN); carbamoyl group (-C(=O)NH₂); a haloformyl group (-C(=O)-X, wherein X represents a halogen atom); formyl group (-C(=O)-H); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group; provided that A¹ and A² may be cross-bridged with each other to form a ring shown by formula: -C(=O)-B-C(=O)- (wherein B is oxygen atom or a group shown by formula -N(B¹)- (wherein B¹ is hydrogen atom, a C₁-C₄₀ hydrocarbon group or a halogen atom)); and,

30 n is an integer of not less than 1),

which comprises aromatizing hydrocarbon condensed rings represented by formula (II) below:



(wherein R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹, A² and n have the same significance as defined above;


45 _____ the bond shown by formula below represents a single bond or a double bond;

provided that when the bond is a single bond, hydrogen atom is further bound directly to the carbon atoms which are directly bound to R⁵, R⁶, R⁷ and R⁸);

in the presence of a dehydrogenation reagent.

50 **[0019]** In one embodiment of the present invention, the dehydrogenation reagent is a combination of a lithium dopant and a lithium-removing reagent. It is preferred to add first the lithium dopant to the hydrocarbon condensed rings and then add the lithium-removing reagent. Preferably, the lithium dopant is an alkyl lithium and the lithium-removing reagent is an alkyl halide.

55 **[0020]** In another embodiment of the present invention, the dehydrogenation reagent described above is preferably a compound represented by formula (III) given below:




10 (wherein each of X¹, X², X³ and X⁴, which may be the same or different, independently represents a halogen atom or cyano group).

[0021] In another embodiment of the present invention, the dehydrogenation reagent described above preferably contains palladium.

15 **[0022]** It is also preferred that at least 5 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, more preferably, at least 6 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

[0023] It is also preferred that the polyacene derivative described above is the pentacene derivative shown by formula (Ia) below:



30 (wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² have the same significance as defined above), and

at least 5 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom. More preferably, at least 6 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; further more preferably, at least 7 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; much more preferably, at least 8 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; further much more preferably, at least 9 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; and most preferably, at least 10 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

35 **[0024]** Or, any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R⁵ and R⁸, R⁶ and R⁷, and A¹ and A² are preferably the same substituents; in another aspect of the present invention, when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, either the sets of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R^{5a} and R^{8a}, R^{5b} and R^{8b}, R⁶ and R⁷, or the set of A¹ and A² are preferably the same substituents.

40 **[0025]** Or, any one of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰ is preferably a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; or a C₆-C₄₀ aryloxy group which may optionally be substituted; in one aspect of the present invention, when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, any one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰ is preferably a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

45 **[0026]** In the formula (I) above, the case that R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all hydrogen atoms may be excluded.

50 **[0027]** In the formula (I) above, when n is 1, at least R¹, R², R⁴ and R⁹ may be groups other than hydrogen atom, or at least R³, R⁵, R⁸ and R¹⁰ may be groups other than hydrogen atom, and the cases of (a), (b), (c) and (d) below may be excluded.

(a) when R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all methyl groups;

(b) when R³, R⁴, R⁹ and R¹⁰ are all aryl groups that may optionally be substituted;

(c) when R¹, R², R⁴ and R⁹ are all alkoxy or aryloxy groups, and R³, R⁵, R⁶, R⁷, R⁸, R¹⁰, A¹ and A² are all hydrogen atoms;

(d) when R³, R⁵, R⁸ and R¹⁰ are all alkoxy or aryloxy groups, and R¹, R², R⁴, R⁶, R⁷, R⁹, A¹ and A² are all hydrogen


atoms.

[0028] When the polyacene derivative is the pentacene derivative represented by formula (1a) above, the cases of (a'), (b'), (c') and (d') below may be excluded:

5

(a') the pentacene derivative represented by formula (1a) below:

10




15

wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are all methyl groups; or R¹, R², R³, R⁴, R^{5a}, R^{5b}, R^{8a}, R^{8b}, R⁹ and R¹⁰ are all hydrogen atoms and at least one of R⁶, R⁷, A¹ and A² is an aryl group; or at least one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² is a diarylamine group;

20

(b') the pentacene derivative represented by formula (1b) below:

25




30

wherein R¹, R², R^{5b} and R^{8b} are all alkoxy or aryloxy groups;

(c') the pentacene derivative represented by formula (1c) below:

35




40

wherein at least 2 of R³, R^{5a}, R^{8a} and R¹⁰ are aryl or arylalkynyl groups; or at least one of R³, R^{5a}, R^{8a} and R¹⁰ is an arylalkenyl group; or R³, R^{5a}, R^{8a} and R¹⁰ are all alkoxy or aryloxy groups;

45

(d') the pentacene derivative represented by formula (1d) below:

50



55

wherein R⁴ and R⁹ are hydrogen atom, a hydrocarbon group, an alkoxy group, an aryloxy group, a halogen atom or hydroxy group.

[0029] Further in one aspect of the present invention, when n is 1, A^1 and A^2 may be an alkoxy carbonyl group, and R^1 , R^2 , R^4 and R^9 may be an alkyl or aryl group; or when n is 1, A^1 , A^2 , R^1 , R^2 , R^4 and R^9 may be an alkyl or aryl group; or further when n is 1, A^1 and A^2 may be a halogen atom and R^3 , R^5 , R^6 , R^7 , R^8 and R^{10} may be an alkyl or aryl group.

[0030] Further in one aspect of the present invention, when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A^1 and A^2 may be an alkoxy carbonyl group and R^1 , R^2 , R^4 , R^{5b} , R^6 , R^7 , R^{8b} and R^9 may be an alkyl or aryl group; or when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A^1 , A^2 , R^1 , R^2 , R^4 , R^{5b} , R^6 , R^7 , R^{8b} and R^9 may be an alkyl or aryl group; or, when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A^1 and A^2 may be a halogen group and R^3 , R^{5a} , R^{8a} and R^{10} may be an alkyl or aryl group.

[0031] In another aspect of the present invention, there are provided conductive materials including the polyacene derivatives described above or the polyacene derivatives obtained by the process described above.

[0032] In another aspect of the present invention, there are provided resin compositions comprising the polyacene derivative described above or the polyacene derivative obtained by any process described above, and other synthetic organic polymers.

BRIEF DESCRIPTION OF THE DRAWINGS

[0033]

FIG. 1 illustrates an example of the synthesis scheme of polyacene derivatives in accordance with the present invention.

FIG. 2 illustrates an example of the synthesis scheme of polyacene derivatives in accordance with the present invention.

FIG. 3 shows an X-ray crystal structure analysis of dimethyl 5,12-dihydro-1,4,6,11-tetrapropyl naphthacene-2,3-dicarboxylate.


FIG. 4 shows an X-ray crystal structure analysis of dimethyl 1,4,6,11-tetrapropyl naphthacene-2,3-dicarboxylate.

FIG. 5 illustrates an example of the synthesis scheme of polyacene derivatives in accordance with the present invention.

FIG. 6 shows an X-ray crystal structure analysis of dimethyl 1,4,6,8,9,10,11,13-octaethyl-5,14-dihydropentacene-2,3-dicarboxylate.

PREFERRED EMBODIMENTS OF THE INVENTION

[0034] In one aspect of the present invention, there are provided polyacene derivatives represented by formula (I) described below:



(wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , n , A^1 and A^2 have the same significance as defined above).

[0035] In the specification, the C_1 - C_{40} hydrocarbon group may be a saturated or unsaturated acyclic group, or a saturated or unsaturated cyclic group. Where the C_1 - C_{40} hydrocarbon group is acyclic, the group may be linear or branched. The C_1 - C_{40} hydrocarbon group includes a C_1 - C_{40} alkyl group, a C_2 - C_{40} alkenyl group, a C_2 - C_{40} alkynyl group, a C_3 - C_{40} allyl group, a C_4 - C_{40} alkyldienyl group, a C_4 - C_{40} polyenyl group, a C_6 - C_{18} aryl group, a C_6 - C_{40} arylaryl group, a C_6 - C_{40} arylalkyl group, a C_4 - C_{40} cycloalkyl group, a C_4 - C_{40} cycloalkenyl group, and the like.

[0036] The C_1 - C_{40} alkyl group, C_2 - C_{40} alkenyl group, C_2 - C_{40} alkynyl group, C_3 - C_{40} allyl group, C_4 - C_{40} alkyldienyl group and C_4 - C_{40} polyenyl group are preferably a C_1 - C_{20} alkyl group, a C_2 - C_{20} alkenyl group, a C_2 - C_{20} alkynyl group, a C_3 - C_{20} allyl group, a C_4 - C_{20} alkyldienyl group and a C_4 - C_{20} polyenyl group, respectively; and more preferably a C_1 - C_{10} alkyl group, a C_2 - C_{10} alkenyl group, a C_2 - C_{10} alkynyl group, a C_3 - C_{10} allyl group, a C_4 - C_{10} alkyldienyl group and a C_4 - C_{10} polyenyl group, respectively.

[0037] Examples of the alkyl group useful for practicing the present invention, which may optionally be substituted,

are, but not limited thereto, methyl, ethyl, propyl, n-butyl, t-butyl, dodecanyl, trifluoromethyl, perfluoro-n-butyl, 2,2,2-trifluoroethyl, benzyl, 2-phenoxyethyl, etc.

[0038] Examples of the aryl group, which is useful for practicing the present invention, are, but not limited thereto, phenyl, 2-tolyl, 3-tolyl, 4-tolyl, naphthyl, biphenyl, 4-phenoxyphenyl, 4-fluorophenyl, 3-carbomethoxyphenyl, 4-carbomethoxyphenyl, etc.

[0039] Examples of the alkoxy group useful for practicing the present invention, which may optionally be substituted, are, but not limited thereto, methoxy, ethoxy, 2-methoxyethoxy, t-butoxy, etc.

[0040] Examples of the aryloxy group useful for practicing the present invention, which may optionally be substituted, are, but not limited thereto, phenoxy, naphthoxy, phenylphenoxy, 4-methylphenoxy, etc.

[0041] Examples of the amino group useful for practicing the present invention, which may optionally be substituted, are, but not limited thereto, amino, dimethylamino, methylamino, methylphenylamino, phenylamino, etc.

[0042] The silyl group useful for practicing the present invention, which may optionally be substituted, includes groups shown by formula: $-\text{Si}(\text{R}^{12})(\text{R}^{13})(\text{R}^{14})$ (wherein each of R^{12} , R^{13} and R^{14} , which may be the same or different, independently represents a $\text{C}_1\text{-C}_{40}$ alkyl group which may optionally be substituted with a halogen atom; a $\text{C}_6\text{-C}_{40}$ arylalkyl group which may optionally be substituted with a halogen atom; a $\text{C}_1\text{-C}_{40}$ alkoxy group which may optionally be substituted with a halogen atom; or a $\text{C}_6\text{-C}_{40}$ arylalkyloxy group which may optionally be substituted with a halogen atom).

[0043] Examples of the silyl group useful for practicing the present invention, which may optionally be substituted, are, but not limited thereto, trimethylsilyl, triethylsilyl, trimethoxysilyl, triethoxysilyl, diphenylmethylsilyl, triphenylsilyl, triphenoxysilyl, dimethylmethoxysilyl, dimethylphenoxy-silyl, methylmethoxyphenyl, etc.

[0044] The $\text{C}_1\text{-C}_{40}$ hydrocarbon group, $\text{C}_1\text{-C}_{40}$ alkoxy group, $\text{C}_6\text{-C}_{40}$ aryloxy group, amino group, silyl group, etc. may optionally be substituted, and the substituents are, for example, a halogen atom, hydroxy group, amino group, etc.

[0045] Examples of the halogen atom include fluorine atom, chlorine atom, bromine atom and iodine atom. When the hydrogen atom(s) of the $\text{C}_1\text{-C}_{40}$ hydrocarbon group, $\text{C}_1\text{-C}_{40}$ alkoxy group, $\text{C}_6\text{-C}_{40}$ aryloxy group, etc. are substituted with fluorine atom(s), the solubility of the polyacene derivatives increases, which is preferred.

[0046] R^6 and R^7 may be cross-bridged with each other to form a $\text{C}_4\text{-C}_{40}$ saturated or unsaturated ring. The unsaturated ring may be an aromatic ring such as a benzene ring, etc. The ring formed by linking R^6 and R^7 together is preferably a 4-membered ring to a 16-membered ring, more preferably a 4-membered ring to a 12-membered ring. The ring may be an aromatic ring or an aliphatic ring. The ring may optionally be substituted with substituents such as a $\text{C}_1\text{-C}_{20}$ hydrocarbon group, a $\text{C}_1\text{-C}_{20}$ alkoxy group, a $\text{C}_6\text{-C}_{20}$ aryloxy group, an amino group, hydroxy group, a silyl group, etc.

[0047] The saturated or unsaturated ring described above may be intervened by oxygen atom, sulfur atom or the group shown by formula $-\text{N}(\text{R}^{11})-$ (wherein R^{11} is hydrogen atom or a hydrocarbon group). Preferably R^{11} is hydrogen atom or a $\text{C}_1\text{-C}_6$ alkyl group, more preferably hydrogen atom or a $\text{C}_1\text{-C}_4$ alkyl group.

[0048] Each of A^1 and A^2 , which may be the same or different, independently represents hydrogen atom; a halogen atom; a $\text{C}_1\text{-C}_{40}$ hydrocarbon group which may optionally be substituted; a $\text{C}_1\text{-C}_{40}$ alkoxy group which may optionally be substituted; a $\text{C}_6\text{-C}_{40}$ aryloxy group which may optionally be substituted; a $\text{C}_7\text{-C}_{40}$ alkylaryloxy group which may optionally be substituted; a $\text{C}_2\text{-C}_{40}$ alkoxy-carbonyl group which may optionally be substituted; a $\text{C}_7\text{-C}_{40}$ aryloxy-carbonyl group which may optionally be substituted; cyano group ($-\text{CN}$); carbamoyl group ($-\text{C}(=\text{O})\text{NH}_2$); a haloformyl group ($-\text{C}(=\text{O})-\text{X}$, wherein X represents a halogen atom); formyl group ($-\text{C}(=\text{O})-\text{H}$); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group.

[0049] The cyano group ($-\text{CN}$); carbamoyl group ($-\text{C}(=\text{O})\text{NH}_2$); haloformyl group ($-\text{C}(=\text{O})-\text{X}$, wherein X represents a halogen atom); formyl group ($-\text{C}(=\text{O})-\text{H}$); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group can be converted from, e.g., an alkoxy-carbonyl, in a conventional manner of the organic chemistry. The carbamoyl group ($-\text{C}(=\text{O})\text{NH}_2$), haloformyl group ($-\text{C}(=\text{O})-\text{X}$, wherein X represents a halogen atom), formyl group ($-\text{C}(=\text{O})-\text{H}$) or the like can be converted into cyano group or the alkoxy-carbonyl group, and vice versa.

[0050] A^1 and A^2 may be cross-bridged with each other to form a ring shown by formula: $-\text{C}(=\text{O})-\text{B}-\text{C}(=\text{O})-$ (wherein B is oxygen atom or a group shown by formula $-\text{N}(\text{B}^1)-$ (wherein B^1 is hydrogen atom, a $\text{C}_1\text{-C}_{40}$ hydrocarbon group or a halogen atom). For example, when A^1 and A^2 are alkoxy-carbonyl groups, the groups can be converted into the carboxy groups in a conventional manner of the organic chemistry, and the adjacent carboxyl groups can be dehydrated and thus converted into the carboxylic anhydride, namely, a ring shown by formula: $-\text{C}(=\text{O})-\text{O}-\text{C}(=\text{O})-$. Similarly, the carboxylic anhydride can be converted into the imide, i.e., a ring shown by formula: $-\text{C}(=\text{O})-\text{N}(\text{B}^1)-\text{C}(=\text{O})-$ (wherein B^1 has the same significance as defined above) in a conventional manner of the organic chemistry.

[0051] n is an integer of not less than 1. When n is 1 and 2, the polyacene derivative represents a 4-cyclic derivative and a 5-cyclic derivative, namely, a naphthacene derivative and a pentacene derivative, respectively.

[0052] Heretofore, as the number of aromatic rings in condensed polycyclic aromatic compounds increased, the solubility tended to become poor. In the present invention, however, the solubility can be maintained by introducing a variety of appropriate substituents therein. Thus, n is not limited to 1 and 2 but may be an integer of 3 or more, may be an integer of 4 or more, or may be an integer of 5 or more. For example, a 7 benzene ring-condensed polyacene

derivative (which corresponds to the case wherein n is 4) has been produced.

[0053] n may be 200 or less, 100 or less, 80 or less, 50 or less, 30 or less, 20 or less, 15 or less, or 10 or less, because it is sufficient to simply repeat this scheme, since the number of n increases two at a time by applying the process of production later described. And, as described above, even though the number of n increases, the solubility can be maintained by appropriately introducing substituents and thus the number of n can be increased.

[0054] In the present invention, such compounds that R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all hydrogen atoms are not intended as the invention of product, since some of these compounds include those that can be isolated from coal or the like and are publicly known. However, the process of producing such compounds falls within the present invention.

[0055] In the present invention, when n is 1 in the formula (I) above, the compounds as the invention of product are intended to include those wherein at least R¹, R², R⁴ and R⁹ are groups other than hydrogen atom or at least R³, R⁵, R⁸ and R¹⁰ are groups other than hydrogen atom, but are not intended to include the cases of (a), (b), (c) and (d) described below.

(a) when R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all methyl groups;

(b) when R³, R⁴, R⁹ and R¹⁰ are all aryl groups that may optionally be substituted;


(c) when R¹, R², R⁴ and R⁹ are all alkoxy or aryloxy groups, and R³, R⁵, R⁶, R⁷, R⁸, R¹⁰, A¹ and A² are all hydrogen atoms;

(d) when R³, R⁵, R⁸ and R¹⁰ are all alkoxy or aryloxy groups, and R¹, R², R⁴, R⁶, R⁷, R⁹, A¹ and A² are all hydrogen atoms.

[0056] Naturally, the process of producing these compounds is within the present invention.


[0057] In the present invention, as the invention of product, the compounds of the formula (I) wherein n is 2 are not intended to include the cases of (a'), (b'), (c') and (d') described below. However, the process of producing these compounds is within the present invention.

(a') the pentacene derivative represented by formula (Ia) below;




wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are all methyl groups; or R¹, R², R³, R⁴, R^{5a}, R^{5b}, R^{8a}, R^{8b}, R⁹ and R¹⁰ are all hydrogen atoms and at least one of R⁶, R⁷, A¹ and A² is an aryl group; or at least one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² is a diarylamine group;

(b') the pentacene derivative represented by formula (Ib) below:




wherein R¹, R², R^{5b} and R^{8b} are all alkoxy or aryloxy groups;

(c') the pentacene derivative represented by formula (Ic) below:




10 wherein at least 2 of R³, R^{5a}, R^{8a} and R¹⁰ are aryl or arylalkynyl groups; or at least one of R³, R^{5a}, R^{8a} and R¹⁰ is an arylalkenyl group; or R³, R^{5a}, R^{8a} and R¹⁰ are all alkoxy or aryloxy groups;
 (d') the pentacene derivative represented by formula (ld) below:



25 wherein R⁴ and R⁹ are hydrogen atom, a hydrocarbon group, an alkoxy group, an aryloxy group, a halogen atom or hydroxy group.

30 **[0058]** In the polyacene derivatives represented by formula (I), preferably at least 5 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, more preferably at least 6 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, much more preferably at least 8 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom, and most preferably at least 10 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom. This is because there is a tendency that as the number of hydrogen atom in R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² increases, the yield occasionally decreases when dehydrogenation is carried out using the combination of a lithium dopant and a lithium-removing reagent.

35 **[0059]** When the polyacene derivatives represented by formula (I) are the pentacene derivatives shown by formula (la) below:



(wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² have the same significance as defined above), preferably at least 5 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom. More preferably, at least 6 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; further more preferably, at least 7 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; much more preferably, at least 8 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; further much more preferably, at least 9 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom; and most preferably, at least 10 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

55 **[0060]** In one embodiment of the present invention, any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R⁵ and R⁸, R⁶ and R⁷, and A¹ and A² are preferably the same substituents, and more preferably, R¹ and R² are the same substituents, R³ and R¹⁰ are the same substituents, R⁴ and R⁹ are the same substituents, R⁵ and R⁸ are

the same substituents, R⁶ and R⁷ are the same substituents, and A¹ and A² are the same substituents. This is because it becomes easy to synthesize such polyacene derivatives with the improved yield.


[0061] For the same reason, in another aspect of the invention, when the polyacene derivatives described above are the pentacene derivatives shown by formula (Ia) above, any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R^{5a} and R^{8a}, R^{5b} and R^{8b}, R⁶ and R⁷, and A¹ and A² are preferably the same substituents, and more preferably, R¹ and R² are the same substituents, R³ and R¹⁰ are the same substituents, R⁴ and R⁹ are the same substituents, R^{5a} and R^{8a} are the same substituents, R^{5b} and R^{8b} are the same substituents, R⁶ and R⁷ are the same substituents, and A¹ and A² are the same substituents. This is because it becomes easy to synthesize such polyacene derivatives with the improved yield.

[0062] Alternatively, from the viewpoints that the synthesis of the polyacene derivatives becomes easy and the yield is improved, R¹ and R² are preferably the same substituents, R³ and R¹⁰ are preferably the same substituents, R⁴ and R⁹ are preferably the same substituents, R⁵ and R⁸ (R^{5a} and R^{8a} or R^{5b} and R^{8b} when the polyacene derivatives described above are the pentacene derivatives shown by formula (Ia) above) are preferably the same substituents, R⁶ and R⁷ are preferably the same substituents, and A¹ and A² are preferably the same substituents.

[0063] In one embodiment of the invention, when n is 1, A¹ and A² may be an alkoxy carbonyl group, and R¹, R², R⁴ and R⁹ may be an alkyl or aryl group. Also, when n is 1, A¹, A², R¹, R², R⁴ and R⁹ may be an alkyl or aryl group. Further when n is 1, A¹ and A² are a halogen atom and R³, R⁵, R⁶, R⁷, R⁸ and R¹⁰ may be an alkyl or aryl group.

[0064] In one embodiment of the present invention, when the polyacene derivatives are the pentacene derivatives represented by the formula (Ia) above, A¹ and A² may be an alkoxy carbonyl group and R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ may be an alkyl or aryl group. Also, when the polyacene derivatives are the pentacene derivatives represented by the formula (Ia) above, A¹, A², R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ may be an alkyl or aryl group. Furthermore, when the polyacene derivatives are the pentacene derivatives represented by the formula (Ia) above, A¹ and A² may be a halogen atom and R³, R^{5a}, R^{8a} and R¹⁰ may be an alkyl or aryl group.

[0065] In one aspect of the present invention, there is provided a process of producing the polyacene derivatives represented by formula (I) above, which comprises aromatizing the hydrocarbon condensed rings represented by formula (II) below:




(wherein R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹, A² and n have the same significance as defined above;



the bond shown by formula below represents a single bond or a double bond;

—

), in the presence of a dehydrogenation reagent.

[0066] The hydrocarbon condensed rings shown by formula (II) above include, e.g., the following hydrocarbon condensed rings represented by (IIa), (IIb) and (IIc), depending upon the kind of bonding:





25 (wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^{5a} , R^{5b} , R^6 , R^7 , R^8 , R^{8a} , R^{8b} , R^9 , R^{10} , A^1 , A^2 and n have the same significance as defined above).

30 **[0067]** When n represents an odd number and the hydrocarbon condensed rings shown by formula (II) described above are those shown by formula (IIb) above, k is an integer shown by $(n+1)/2$, and when n represents an even number and the hydrocarbon condensed rings shown by formula (II) described above are those shown by formula (IIc) above, m is an integer shown by $n/2$.

[0068] In the hydrocarbon condensed rings shown by formula (IIa), it turns out that one ring is aromatized. On the other hand, in the hydrocarbon condensed rings shown by formula (IIb) and formula (IIc), it turns out that two or more rings are aromatized.

[0069] As a matter of course, the hydrocarbon condensed rings shown by formula (II) also include the cases wherein the rings in a repeating unit being an aromatic ring and a non-aromatic ring are repeated at random.

35 **[0070]** In one embodiment of the invention, the dehydrogenation reagent is a combination of a lithium dopant and a lithium-removing reagent. It is preferred to add the lithium dopant first to the hydrocarbon condensed rings followed by adding the lithium-removing reagent.


[0071] This scheme is illustratively shown with the cases of the hydrocarbon condensed rings shown by formula (IIa), (IIb) and (IIc) below.

40

45


50

55




(wherein $R^1, R^2, R^3, R^4, R^5, R^6, R^7, R^8, R^9, R^{10}, A^1, A^2$ and n have the same significance as defined above; D^1 represents a nucleophilic group such as a $C_1\text{-}C_6$ alkyl group, etc.; D^2 represents a $C_1\text{-}C_{20}$ hydrocarbon group such as a $C_1\text{-}C_6$ alkyl group, etc.; and Z^1 represents an eliminable group such as a halogen atom, etc.).

[0072] In this reaction, R^3 and R^{10} in formula (IIa) are preferably hydrogen atoms, in view of easy synthesis of the polyacene derivatives.



(wherein $R^1, R^2, R^3, R^4, R^5, R^6, R^7, R^8, R^9, R^{10}, A^1, A^2$ and k have the same significance as defined above; D^1 represents a nucleophilic group such as a $C_1\text{-}C_6$ alkyl group, etc.; D^2 represents a $C_1\text{-}C_{20}$ hydrocarbon group such as a $C_1\text{-}C_6$ alkyl group, etc.; and Z^1 represents an eliminable group such as a halogen atom, etc.).

[0073] In this reaction, R^3, R^5, R^8 and R^{10} in formula (IIb) are preferably hydrogen atoms, in view of easy synthesis of the polyacene derivatives.



(wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 , A^2 and m have the same significance as defined above; D^1 represents a nucleophilic group such as a C_1 - C_6 alkyl group, etc.; D^2 represents a C_1 - C_{20} hydrocarbon group such as a C_1 - C_6 alkyl group, etc.; and Z^1 represents an eliminable group such as a halogen atom, etc.).

[0074] In this reaction, R^3 , R^{5a} , R^{8a} and R^{10} in formula (IIc) are preferably hydrogen atoms, in view of easy synthesis of the polyacene derivatives.

[0075] In the schemes described above, the hydrocarbon condensed rings represented by formula (IIa), (IIb) or (IIc) are employed, for the sake of explanation to clarify the carbon atoms on which the lithium dopant (IV) shown by $Li-D^1$ acts. It goes without saying that the dehydrogenation reagent in the combination of the lithium dopant and the lithium-removing reagent is widely applicable to the hydrocarbon condensed rings shown by formula (II) described above.

[0076] The lithium dopant (IV) is reacted with the hydrocarbon condensed rings represented by formulae (IIa), (IIb) and (IIc) to obtain the lithium-provided hydrocarbon condensed rings shown by formula (Va), (Vb) and (Vc), respectively. Preferred lithium dopants include a C_1 - C_{20} hydrocarbon lithium such as an alkyl lithium, an aryl lithium, etc. For example, a C_1 - C_6 alkyl lithium such as butyl lithium, etc., a C_6 - C_{20} aryl lithium such as phenyl lithium, etc. are preferably used.

[0077] It is preferred that an activator of the lithium dopant co-exists together with the lithium dopant (IV). As the activator, tertiary amines are preferred and, N,N,N',N' -tetraalkylalkylenediamines such as N,N,N',N' -tetramethylethylenediamine (TMEDA), are employed. It is likely that the alkyl lithium would be present in a solution as an oligomer like a tetramer. When a tertiary amine is co-present, it is assumed that the nitrogen atom of the amine would be coordinated on the lithium atom of the alkyl lithium to cleave the oligomer structure, whereby the lithium atom in the alkyl lithium would be exposed to the solution to improve the reactivity.

[0078] A preferred solvent is an organic solvent. In particular, a non-polar organic solvent is employed. For example, an alkane such as hexane, etc. and an aromatic compound such as benzene, etc. are preferred.

[0079] A preferred reaction temperature is from $0^\circ C$ to $200^\circ C$, more preferably $20^\circ C$ to $100^\circ C$, and most preferably $30^\circ C$ to $80^\circ C$.


[0080] When the lithium-removing reagent (VI) is reacted with the hydrocarbon condensed rings shown by formulae (Va), (Vb) and (Vc), it is surmised to form the intermediates shown by formulae (VIIa), (VIIb) and (VIIc), respectively. The intermediates are decomposed to give the polyacene derivatives shown by formula (I), (Ib) or (Ia).

[0081] As the lithium-removing reagent (VI), for example, alkyl halides are advantageously used. Preferred examples of alkyl halides are alkyl halides having 6 or less carbon atoms, such as methyl iodide, ethyl bromide, etc.

[0082] Where the lithium dopant (IV) and the lithium-removing reagent (VI) having less carbon atoms, such as, butyl lithium and methyl iodide are used as the lithium dopant (IV) and the lithium-removing reagent (VI), respectively, lithium iodide and hexane will be split off. Hexane can be removed at the same time when the solvent is removed. Lithium iodide can be removed by washing the resulting reaction mixture with water. Thus, the combination of the lithium dopant and the lithium-removing reagent renders purification of the reaction mixture extremely easy and is desirable.

[0083] When a large number of hydrogen atoms are introduced on R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 , e.g., when at least 8 of these groups are hydrogen atoms, the yield of the polyacene derivative shown by formula (I) based on the hydrocarbon condensed rings of formula (IIa) is approximately 50%. On the other hand, when at least 6, especially 8 or more groups other than hydrogen atom are introduced on R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 , there is a tendency that the yield increases. For example, the yield occasionally reaches 90% or more, or sometimes becomes 95% or more.

[0084] In another embodiment of the present invention, the dehydrogenation reagent described above is preferably a compound shown by formula (III) below:



(wherein each of X¹, X², X³ and X⁴, which may be the same or different, independently represents a halogen atom or cyano group).

15 [0085] The quinones shown by formula (III) above are reacted with the compounds represented by formula (II) above to become 1,4-dihydroxy-cyclohexane derivatives.

[0086] In the quinones shown by formula (III) above, the halogen atom is preferably chlorine atom, bromine atom or iodine atom, more preferably chlorine atom or bromine atom, and most preferably chlorine atom.

20 [0087] For example, all of X¹, X², X³ and X⁴ may be chlorine atoms. That is, the quinone may be chloranil. Or, X¹ and X² may be cyano group, and X³ and X⁴ may be chlorine atoms. That is, it may be 2,3-dichloro-5,6-dicyanoquinone. Or again, X¹, X², X³ and X⁴ may all be cyano groups. That is, it may be 2,3,5,6-tetracyanoquinone.

[0088] When the quinones shown by formula (III) above are used, the quinones shown by formula (III) above may occasionally undergo Diels-Alder reaction with the polyacene derivative products to produce by-products. If desired, the by-products are removed by column chromatography, etc.


25 [0089] In order to prevent the production of such by-products, the quinones shown by formula (III) above are used preferably in 0.9 to 1.2 equivalents, more preferably 0.9 to 1.15 equivalents, and most preferably 0.95 to 1.05 equivalents, based on the compounds shown by formula (II) described above.

[0090] As the solvent, an organic solvent is preferred, and an aromatic compound such as benzene, etc. is particularly preferred.

30 [0091] The reaction temperature is preferably between -80°C to 200°C, more preferably 0°C to 100°C, and most preferably 10°C to 80°C. If desired, the reaction may be performed under light shielding.

35 [0092] In other embodiment of the present invention, it is preferred that the dehydrogenation reagent described above includes palladium. For example, palladium carried on carbon such as activated carbon, which is commercially available as so-called palladium carbon, may preferably be employed. Pd/C is a catalyst that has been widely used for dehydrogenation, and can be used in the present invention as in a conventional manner. The reaction temperature is, e.g., from 200°C to 500°C. Of course, the reaction temperature may appropriately be set forth, depending upon various conditions such as starting materials, etc.

[0093] The hydrocarbon condensed rings can be obtained, e.g., by the following scheme.





(wherein R^1 , R^2 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 and n have the same significance as defined above; each of A^{1a} and A^{2a} , which may be the same or different, independently represents a C_6 - C_{40} alkoxy carbonyl group which may optionally be substituted with a substituent comprising a halogen atom, or a C_6 - C_{40} aryloxy carbonyl group which may optionally be substituted with a substituent comprising a halogen atom; and X is an eliminable group such as a halogen atom, etc.;

the bond shown by formula below represents a single bond or a double bond;

M represents a metal belonging to Group III to Group V or a lanthanide metal;

each L^1 and L^2 , which may be the same or different, independently represents an anionic ligand, provided that L^1 and L^2 may be cross-bridged with each other; and,

each of Y^1 and Y^2 , which may be the same or different, independently represents an eliminable group).



(wherein R^1 , R^2 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , n , A^{1a} and A^{2a} have the same significance as defined above;

the bond shown by formula below represents a single bond or a double bond;

).

[0094] First, the diester (VIII) is reduced with a reducing agent to give the diol (IX). As the reducing agent, lithium aluminum hydride can be used. As a solvent, an organic solvent is preferably used, and a polar organic solvent may be used. For example, an ether such as diethyl ether, THF, etc. may be used.

[0095] The reaction temperature is preferably between -80°C and 200°C , more preferably between -50°C and 100°C , and most preferably between -20°C and 80°C . After the reducing agent is added, the reaction may be quenched by adding water, a weak acid, etc.

[0096] If desired, the diester (VIII) may be hydrated under acidic or alkaline conditions to convert into the dicarboxylic acid, the dicarboxylic acid may be reduced to the diketone and then the diketone may be reduced to the diol.

[0097] Subsequently, the diol (IX) is reacted with a phosphorus trihalide such as phosphorus tribromide, etc., or with SOCl_2 , etc. to convert into the dihalogen (X). It is preferred to use an organic solvent as the solvent, wherein a polar organic solvent may be used. For example, an ether such as THF may be used. The reaction temperature is preferably between -80°C and 200°C , more preferably between -50°C and 100°C , and most preferably between -20°C and 80°C .

[0098] Next, an alkynyl lithium is reacted with the dihalogen (X) to give the dialkyne (XI). Preferably, the coupling reaction is carried out in the co-presence of a stabilizer such as N,N' -dimethylpropyleneurea, hexamethylphosphamide, etc. As a solvent, it is preferred to use an organic solvent, in which a polar organic solvent is preferably employed. For example, an ether such as THF may be used. The reaction temperature is preferably between -80°C and 200°C , more preferably between -50°C and 100°C , and most preferably between -20°C and 80°C .

[0099] The dialkyne (XI) is reacted with an organic metal compound shown by $L^1L^2MY^1Y^2$ such as a bicyclopentadienylzirconium dialkyl to form the metallacyclopentadiene (XII). The formation of a metallacyclopentadiene from an organic metal compound shown by $L^1L^2MY^1Y^2$ is described in, e.g., T. Takahashi, et al., J. Org. Chem., 1995, 60, 4444, and the reaction proceeds under the same conditions as the literature, or under conditions closely similar to the literature.

[0100] As a solvent, either an aliphatic or aromatic solvent is used, preferably a polar solvent. An ethereal solvent, e.g., tetrahydrofuran or diethyl ether; a halogenated hydrocarbon such as methylene chloride; a halogenated aromatic

hydrocarbon such as o-dichlorobenzene; an amide such as N,N-dimethylformamide, etc., a sulfoxide such as dimethyl sulfoxide, etc., are used. Alternatively, an aromatic hydrocarbon such as benzene, toluene, xylene, etc. may be used as the aromatic solvent.

[0101] The reaction is preferably carried out at a temperature ranging from -80°C to 300°C, more preferably from 0°C to 150°C. The pressure is within 0.1 bar to 2500 bars, preferably within 0.5 bar to 10 bars. The reaction may be carried out continuously or batch-wise, in one step or a multiple step, in a solution or in a suspension, in a gaseous phase or in a supercritical medium.

[0102] M represents a metal belonging to Group III to Group V or a lanthanide metal. Preferred examples of M include metals of Group IV or the lanthanide group in the Periodic Table, more preferably, the metals of Group IV, namely, titanium, zirconium and hafnium.

[0103] Each L¹ and L², which may be the same or different, independently represents an anionic ligand.

[0104] The anionic ligand above is preferably a non-localized cyclic η⁵-coordinated ligand, a C₁-C₂₀ alkoxy group, a C₆-C₂₀ aryloxy group or a diakylamide group.

[0105] L¹ and L² is preferably a non-localized cyclic η⁵-coordinated ligand. The non-localized cyclic η⁵-coordinated ligand includes unsubstituted cyclopentadienyl group and a substituted cyclopentadienyl group. Examples of the substituted cyclopentadienyl group are methylcyclopentadienyl, ethylcyclopentadienyl, isopropylcyclopentadienyl, n-butylcyclopentadienyl, t-butylcyclopentadienyl, dimethylcyclopentadienyl, diethylcyclopentadienyl, diisopropylcyclopentadienyl, di-t-butylcyclopentadienyl, tetramethylcyclopentadienyl, indenyl, 2-methylindenyl, 2-methyl-4-phenylindenyl, tetrahydroindenyl, benzindenyl, fluorenyl, benzofluorenyl, tetrahydrofluorenyl and octahydrofluorenyl.

[0106] In the non-localized cyclic η⁵-coordinated ligand, one or more atom(s) in the non-localized cyclic π system may be substituted with a hetero atom(s). In addition to hydrogen, the hetero atoms may include one or more hetero atoms such as the elements of Group XIV of the Periodic Table and/or the elements of Groups XV, XVI and XVII of the Periodic Table.

[0107] The non-localized cyclic η⁵-coordinated ligand, e.g., cyclopentadienyl group, may form a ring together with the central metal, or may be cross-bridged by one or more cross-bridging ligands. Examples of the cross-bridging ligands are CH₂, CH₂CH₂, CH(CH₃)CH₂, CH(C₄H₉)C(CH₃)₂, C(CH₃)₂, (CH₃)₂Si, (CH₃)₂Ge, (CH₃)₂Sn, (C₆H₅)₂Si, (C₆H₅)(CH₃)Si, (C₆H₅)₂Ge, (C₆H₅)₂Sn, (CH₂)₄Si, CH₂Si(CH₃)₂, o-C₆H₄ or 2,2'-(C₆H₄)₂.

[0108] Two or more non-localized cyclic η⁵-coordinated ligands, e.g., cyclopentadienyl groups, may be cross-bridged by one or more cross-bridging groups which may contain ring(s). Examples of the cross-bridging groups include CH₂, CH₂CH₂, CH(CH₃)CH₂, CH(C₄H₉)C(CH₃)₂, C(CH₃)₂, (CH₃)₂Si, (CH₃)₂Ge, (CH₃)₂Sn, (C₆H₅)₂Si, (C₆H₅)(CH₃)Si, (C₆H₅)₂Ge, (C₆H₅)₂Sn, (CH₂)₄Si, CH₂Si(CH₃)₂, o-C₆H₄ or 2,2'-(C₆H₄)₂.

[0109] The metallacyclopentadiene further includes compounds containing two or more metallacyclopentadiene moieties. Such compounds are known as a polynuclear metallocene. The polynuclear metallocene may take any mode of substitution or any cross-bridged form. In the independent metallocene moiety of the polynuclear metallocene above, the respective moieties may be the same or different. Examples of the polynuclear metallocene are described in, e.g., EP-A No. 632,063, JPA Nos. H4-80214 and H4-85310 and EP-A No. 654,476.

[0110] Each of Y¹ and Y², which may be the same or different, independently represents an eliminable group. Examples of the eliminable group include a halogen atom such as F, Cl, Br or I, a C₁-C₂₀ alkyl group such as n-butyl, etc., a C₆-C₂₀ aryl group such as phenyl, etc.

[0111] The reaction described above is carried out preferably at a temperature ranging from -120°C to 50°C, more preferably from -120°C to 0°C.

[0112] Next, in one embodiment of the present invention, the metallacyclopentadiene (XII) is reacted with an alkyne to form a benzene ring, whereby the hydrocarbon condensed rings (IId). Typically, an alkyne is added to the reaction mixture, without isolating the metallacyclopentadiene (XII).

[0113] A metallacyclopentadiene such as zirconacyclopentadiene is reacted with an alkyne in the presence of CuCl to form a benzene ring, which is described in T. Takahashi, et al., J. Am. Chem. Soc., 1998, 120, 1672-1680. The reaction can be proceeded under the same conditions as the literature, or under conditions closely similar to the literature.

[0114] Not only CuCl but a metal compound may also be used. Preferably, the metal compound is the metal compound of Groups IV through XV in the Periodic Table. The metal compound above may be a salt like CuCl or may be an organic metal complex.

[0115] Examples of the salt include a metal salt such as CuX, NiX₂, PdX₂, ZnX₂, CrX₂, CrX₃, CoX₂ or BiX₃ (wherein X represents a halogen atom such as chlorine atom, bromine atom, etc.).

[0116] As the metal compound, there may be employed an organic metal complex, especially a nickel complex. As the organic metal complex, there are employed those wherein ligands such as phosphines; aromatic amines, e.g., pyridine, bipyridine, etc., halogen atoms, or the like are coordinated to the central metals of Groups III through XI of the Periodic Table, preferably to the central metals of Groups VI to XI of the Periodic Table. The central metals are preferably so-called 4- to 6-coordinated, and the metals of Group X in the Periodic Table are particularly preferred.

Phosphines include triphenylphosphine, methyl-diphenylphosphine, etc. and are not particularly limited. Examples of the organic metal complex include bis(triphenylphosphine)dichloronickel, dichloro(2,2'-bipyridyl)nickel and PdCl₂(2,2'-bipyridine). It is described in T. Takahashi, et al., J. Am. Chem. Soc., Vol. 121, No. 48, 1999, 11095 that a metallacyclopentadiene such as zirconacyclopentadiene is reacted with an alkyne in the presence of a nickel phosphine complex to form a benzene ring.


[0117] The reaction is carried out preferably at a temperature ranging from -80°C to 300°C, more preferably from 0°C to 150°C. The pressure is within 0.1 bar to 2500 bars, preferably within 0.5 bar to 10 bars. The reaction may be carried out continuously or batch-wise, in one step or a multiple step, in a solution or in a suspension, in a gaseous phase or in a supercritical medium.

[0118] As a solvent, an aliphatic or aromatic solvent is used, preferably a polar solvent. An ethereal solvent, e.g., tetrahydrofuran or diethyl ether; a halogenated hydrocarbon such as methylene chloride; a halogenated aromatic hydrocarbon such as o-dichlorobenzene; an amide such as N,N-dimethylformamide, etc., a sulfoxide such as dimethyl sulfoxide, etc., are used.

[0119] The reaction is carried out preferably in the presence of a stabilizer, which stabilizes the metal compound in the solvent. Especially when the metal compound is a metal salt and the solvent is an organic solvent, the stabilizer can stabilize the metal salt in the organic solvent. Examples of the stabilizer include N,N'-dimethylpropyleneurea, hexamethylphosphamide, etc.

[0120] Then, the hydrocarbon condensed rings (IId) are aromatized through the aromatizing reaction described above to give the polyacene derivative (Ie).

[0121] According to the scheme described above, the polyacene derivative (Ie) wherein R³ and R¹⁰ are hydrogen atoms can be produced. The polyacene derivative wherein R³ and R¹⁰ are groups other than hydrogen atom can be produced, e.g., by the following scheme.



(wherein R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, n, A^{1a} and A^{2a} have the same significance as defined above;

_____ the bond shown by formula below represents a single bond or a double bond;

).

[0122] The diester (VIIIa) is reduced to the dialdehyde (VIIIb), using a reducing agent such as diisobutyl aluminum hydride, etc. Using an organic solvent, e.g., toluene, etc., the reaction is allowed to proceed at -100°C to -50°C, preferably at -78°C. It is preferred to use precisely one equivalent each of the diester and the reducing agent.

[0123] Or, the diester (VIIIa) is hydrolyzed under acidic or basic conditions to form the dicarboxylic acid. The dicarboxylic acid may be reduced to the dialdehyde (VIIIb), using a reducing agent.

[0124] The dialdehyde (VIIIb) is then reacted with Grignard reagent to form the diol (IXa). After that, the diol (IXa) may be reacted as described above.

[0125] Or again, in one embodiment of the present invention, the metallacyclopentadiene (XII) described above may be reacted with an ortho-dihalogenoarene such as 1,2-diiodobenzene, or a tetrahalogenoarene such as a 1,2,4,5-tetrahalogenobenzene to form the arene ring.

[0126] The coupling reaction is carried out typically in the presence of a metal compound such as CuCl and a sta-

bilizer. The metal compound is preferably the metal compound of Groups IV to XV in the Periodic Table. The metal compound described above may be a salt such as CuCl or an organic metal complex. Examples of the salt include a metal salt such as CuX, NiX₂, PdX₂, ZnX₂, CrX₂, CrX₃, CoX₂ or BiX₃ (wherein X represents a halogen atom such as chlorine atom, bromine atom, etc.).

5 **[0127]** Preferably, a stabilizer such as N,N'-dimethylpropyleneurea, hexamethylphosphoamide, etc. is allowed to be co-present as the stabilizer. As a solvent, it is preferred to use an organic solvent, in which a polar organic solvent is preferably employed. For example, an ether such as THF may be used. The reaction temperature is preferably between -80°C and 200°C, more preferably between -50°C and 100°C, and most preferably between -20°C and 80°C.

10 **[0128]** In one embodiment of the present invention, electrically conductive materials are provided. The form of the conductive materials is not limited but may be a thin film. The conductive materials may contain dopants. For example, electron-accepting molecules may be introduced. In this case, for example, when the thin film is prepared by the vacuum deposition method, condensed polycyclic aromatic compound as well as the electron-accepting molecule may be supplied onto a substrate to effect thin film doping. Where the thin film is prepared by sputtering, the sputtering is performed using a binary target of the condensed polycyclic aromatic compound and the electron-accepting molecule to effect the thin film doping. Doping is effected as described above. The composition of the conductive material can be varied depending upon doping conditions. As the dopant, electron-donating molecules or electron-accepting molecules, which are used as dopants in conjugated polymers, e.g., polyacetylene, polypyrrole, polyallylenevinylene, polythienylenevinylene, etc. are preferably employed.

20 **[0129]** When the conductive material is in a thin film, a thickness of the film may be prepared in the range of 50 angstrom to the order of a micron, depending upon purpose of using the film. If necessary, protective layers for preventing dopants from spreading/scattering or for improving mechanical strength or layers of other materials may be provided on the thin film. Also, a multilayer film consisting of the thin film of the present invention and thin films of other materials may be used as functional materials by applying thin films thereto.

25 **[0130]** The conductivity of the conductive material can be assessed by the conventional direct current 2-terminal or 4-terminal method. The conductivity can be varied depending upon the kind or content of dopants according to the purpose of use. The conductivity of the conductive material of the present invention is, for example, 10¹⁵ S/cm or more.

30 **[0131]** In another aspect of the present invention, there is provided a resin composition, e.g., a blend, comprising the polyacene derivative described above and other synthetic organic polymer. For example, a resin composition comprising 1 wt% to 99 wt% of the polyacene derivative and 99 wt% to 1 wt% of a synthetic organic polymer is provided. A resin composition comprising 10 wt% to 90 wt% of the polyacene derivative and 90 wt% to 10 wt% of a synthetic organic polymer is also provided.

35 **[0132]** The synthetic organic polymer includes a thermoplastic polymer, a thermosetting polymer, engineering plastics, a conductive polymer, and the like. The synthetic organic polymer may also be a copolymer. Examples of the thermoplastic polymer include a polyolefin such as polyethylene, polypropylene, polycycloolefin, ethylene-propylene copolymer, etc., polyvinyl chloride, polyvinylidene chloride, polyvinyl acetate, polyacrylic acid, polymethacrylic acid, polystyrene, polyamide, polyester, polycarbonate, etc. Examples of the thermosetting polymer include a phenol resin, a urea resin, a melamine resin, an alkyd resin, an unsaturated polyester resin, an epoxy resin, a silicone resin, a polyurethane resin, etc. Examples of the engineering plastics include polyimide, polyphenylene oxide, polysulfone, etc. The synthetic organic polymer may be a synthetic rubber such as styrene-butadiene, etc., or a fluoro resin such as polytetrafluoroethylene, etc.

40 **[0133]** The conductive polymers include conjugated polymers such as polyacetylene, polypyrrole, polyallylenevinylene, polythienylenevinylene, etc. and those in which electron-donating molecules or electron-accepting molecules are doped. The conductive polymers further include electron donating molecules such as tetrathiafulvalene, bisethylenedithiotetrathiafulvalene, etc., or electron transfer complexes of such electron-donating molecules in combination with electron accepting molecules such as tetracyanoquinodimethane, tetracyanoethylene, etc.

45 **[0134]** The resin composition may further contain a variety of additives. Examples of the additives are a plasticizer, an antistatic agent, a colorant, a dopant, etc. Furthermore, the resin composition may also contain a reinforcing material such as glass fibers, carbon fibers, aramid fibers, boron fibers, carbon nanotubes, etc.

50 **[0135]** The resin composition described above may be prepared into the form of fibers, films or sheets, using methods known to one skilled in the art. These methods include, but are not limited thereto, melt spinning, spinning from a solution, dry jet wet spinning, extrusion, flow casting and molding techniques. The fibers, films or sheets may further be processed by roll molding, embossing, postforming or other methods known to one skilled in the art.

[0136] As the organic metal compounds shown by L¹L²MY¹Y², for example, the following compounds may be employed.

55 **[0137]** With dihalogeno compounds such as bis(cyclopentadienyl)dichlorozirconium, bis(methylcyclopentadienyl)dichlorozirconium, bis(butylcyclopentadienyl)dichlorozirconium, bis(indenyl)dichlorozirconium, bis(fluorenyl)dichlorozirconium, (indenyl)(fluorenyl)dichlorozirconium, bis(cyclopentadienyl)dichlorotitanium, (dimethylsilanediyl)bis(indenyl)dichlorozirconium, (dimethylsilanediyl)bis(tetrahydroindenyl)dichlorozirconium, (dimethylsilanediyl)(indenyl)

dichlorozirconium, (dimethylsilanediyl)bis(2-methylindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-ethylindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-methyl-4,5-benzindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-ethyl-4,5-benzindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-methyl-4-phenylindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-ethyl-4-phenylindenyl)dichlorozirconium, (dimethylsilanediyl)bis(2-methyl-4,6-diisopropylindenyl)dichlorozirconium, it is preferred to form the metallacyclopentadienes either after reducing the dihalogeno compounds with a strong base such as an alkali metal, e.g., sodium, etc., an alkaline earth metal such as magnesium, etc. or after converting the dihalogeno compounds into the dialkyl compounds.

bis(cyclopentadienyl)dibutylzirconium;
 bis(butylcyclopentadienyl)dibutylzirconium;
 bis(methylcyclopentadienyl)dibutylzirconium;
 bis(indenyl)dibutylzirconium;
 bis(fluorenyl)dibutylzirconium;
 (indenyl)(fluorenyl)dibutylzirconium;
 (3-methyl-5-naphthylindenyl)(2,7-di-tert-butylfluorenyl)dibutylzirconium;
 (3-methyl-5-naphthylindenyl)(3,4,7-trimethoxyfluorenyl)dibutylzirconium;
 (pentamethylcyclopentadienyl)(tetrahydroindenyl)dibutylzirconium;
 (cyclopentadienyl)(1-octene-8-ylcyclopentadienyl)dibutylzirconium;
 (indenyl)(1-butene-4-ylcyclopentadienyl)dibutylzirconium;
 [1,3-bis(trimethylsilyl)cyclopentadienyl](3,4-benzofluorenyl)dibutylzirconium;
 bis(cyclopentadienyl)dibutyltitanium;
 dimethylsilanediylbis(indenyl)dibutylzirconium;
 dimethylsilanediylbis(tetrahydroindenyl)dibutylzirconium;
 dimethylsilanediyl(cyclopentadienyl)(indenyl)dibutylzirconium;
 dimethylsilanediylbis(2-methylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-ethylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 dimethylsilanediylbis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutylzirconium;
 dimethylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediyl(2-ethyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediyl(2-methyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediyl(2-ethylindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediyl(2-methylindenyl)(4-phenylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-methyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-ethyl-4-phenylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-methyl-4-naphthylindenyl)dibutylzirconium;
 dimethylsilanediylbis(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(indenyl)dibutylzirconium;
 methylphenylsilanediyl(cyclopentadienyl)(indenyl)dibutylzirconium;
 methylphenylsilanediylbis(tetrahydroindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-methylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-ethylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 methylphenylsilanediylbis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutylzirconium;
 methylphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediyl(2-ethylindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediyl(2-methylindenyl)(4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-methyl-4-phenylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(dibutylzirconium);
 methylphenylsilanediylbis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(4-naphthylindenyl)dibutylzirconium;
 methylphenylsilanediylbis(2-ethyl-4-naphthylindenyl)dibutylzirconium;

diphenylsilanediylbis(indenyl)dibutylzirconium;
 diphenylsilanediylbis(2-methylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-ethylindenyl)dibutylzirconium;
 5 diphenylsilanediyl(cyclopentadienyl)(indenyl)dibutylzirconium;
 diphenylsilanediylbis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 diphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 diphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylzirconium;
 10 diphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylzirconium;
 diphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 diphenylsilanediyl(2-methylindenyl)(4-phenylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-methyl-4-phenylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-ethyl-4-phenylindenyl)dibutylzirconium;
 15 diphenylsilanediylbis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-methyl-4-naphthylindenyl)dibutylzirconium;
 diphenylsilanediylbis(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(indenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-methylindenyl)dibutylzirconium;
 20 1-silacyclopentane-1,1-bis(2-ethylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 1-silacyclopentane-1-(2-methyl-4,5-benzindenyl)-1-(2-methyl-4-phenylindenyl)dibutylzirconium;
 1-silacyclopentane-1-(2-ethyl-4,5-benzindenyl)-1-(2-methyl-4-phenylindenyl)dibutylzirconium;
 25 1-silacyclopentane-1-(2-methyl-4,5-benzindenyl)-1-(2-ethyl-4-phenylindenyl)dibutylzirconium;
 1-silacyclopentane-1-(2-ethyl-4,5-benzindenyl)-1-(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 1-silacyclopentane-1-(2-methylindenyl)-1-(4-phenylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-methyl-4-phenylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-ethyl-4-phenylindenyl)dibutylzirconium;
 30 1-silacyclopentane-1,1-bis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-methyl-4-naphthylindenyl)dibutylzirconium;
 1-silacyclopentane-1,1-bis(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 ethylene-1,2-bis(indenyl)dibutylzirconium;
 35 ethylene-1,2-bis(tetrahydroindenyl)dibutylzirconium;
 ethylene-1-(cyclopentadienyl)-2-(1-indenyl)dibutylzirconium;
 ethylene-1-(cyclopentadienyl)-2-(2-indenyl)dibutylzirconium;
 ethylene-1-(cyclopentadienyl)-2-(2-methyl-1-indenyl)dibutylzirconium;
 ethylene-1,2-bis(2-methylindenyl)dibutylzirconium;
 40 ethylene-1,2-bis(2-ethylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 ethylene-1,2-bis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutylzirconium;
 ethylene-1-(2-methyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutylzirconium;
 45 ethylene-1-(2-ethyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutylzirconium;
 ethylene-1-(2-methyl-4,5-benzindenyl)-2-(2-ethyl-4-phenylindenyl)dibutylzirconium;
 ethylene-1-(2-ethyl-4,5-benzindenyl)-2-(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 ethylene-1-(2-methylindenyl)-2-(4-phenylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-methyl-4-phenylindenyl)dibutylzirconium;
 50 ethylene-1,2-bis(2-ethyl-4-phenylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-methyl-4-naphthylindenyl)dibutylzirconium;
 ethylene-1,2-bis(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 55 propylene-2,2-bis(indenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(1-indenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(4-phenyl-1-indenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(9-fluorenyl)dibutylzirconium;

propylene-2-cyclopentadienyl-2-(2,7-dimethoxy-9-fluorenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(2,7-di-tert-butyl-9-fluorenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(2,7-dibromo-9-fluorenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-(2,7-diphenyl-9-fluorenyl)dibutylzirconium;
 5 propylene-2-cyclopentadienyl-2-(2,7-dimethyl-9-fluorenyl)dibutylzirconium;
 propylene-2-(3-methylcyclopentadienyl)-2-(2,7-dibutyl-9-fluorenyl)dibutylzirconium;
 propylene-2-(3-tert-butylcyclopentadienyl)-2-(2,7-dibutyl-9-fluorenyl)dibutylzirconium;
 propylene-2-(3-trimethylsilylcyclopentadienyl)-2-(3,6-di-tert-butyl-9-fluorenyl)dibutylzirconium;
 propylene-2-cyclopentadienyl-2-[2,7-bis(3-butene-1-yl)-9-fluorenyl]dibutylzirconium;
 10 propylene-2-cyclopentadienyl-2-(3-tert-butyl-9-fluorenyl)dibutylzirconium;
 propylene-2,2-bis(tetrahydroindenyl)dibutylzirconium;
 propylene-2,2-bis(2-methylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-ethylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-methyl-4,5-benzindenyl)dibutylzirconium;
 15 propylene-2,2-bis(2-ethyl-4,5-benzindenyl)dibutylzirconium;
 propylene-2,2-bis(4,5-dihydro-8-methyl-7H-cyclopent[*e*]acenaphthylene-7-ylidene)dibutylzirconium;
 propylene-2-(2-methyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutylzirconium;
 propylene-2-(2-ethyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutylzirconium;
 propylene-2-(2-methyl-4,5-benzindenyl)-2-(2-ethyl-4-phenylindenyl)dibutylzirconium;
 20 propylene-2-(2-ethyl-4,5-benzindenyl)-2-(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 propylene-2-(2-methylindenyl)-2-(4-phenylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-methyl-4-phenylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-ethyl-4-phenylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium;
 25 propylene-2,2-bis(2-ethyl-4,6-diisopropylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-methyl-4-naphthylindenyl)dibutylzirconium;
 propylene-2,2-bis(2-ethyl-4-naphthylindenyl)dibutylzirconium;
 1,6-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylzirconium]hexane;
 1,6-bis[methylsilylbis(2-methyl-4,5-benzindenyl)dibutylzirconium]hexane;
 30 1,6-bis[methylsilylbis(2-ethyl-4-phenylindenyl)dibutylzirconium]hexane;
 1,6-bis[methylsilylbis(2-methyl-4-naphthylindenyl)dibutylzirconium]hexane;
 1,6-bis[methylsilylbis(2-methyl-4,6-diisopropylindenyl)dibutylzirconium]hexane;
 1,6-bis[methylsilyl(2-methyl-4-phenylindenyl)(4,5-benzindenyl)dibutylzirconium]hexane;
 1-[methylsilylbis(tetrahydroindenyl)dibutylzirconium]-6-[ethylstannyl(cyclopentadienyl)(fluorenyl)dibutylzirconium]
 35 hexane;
 1,6-disila-1,1,6,6-tetramethyl-1,6-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylzirconium]hexane;
 1,4-disila-1,4-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylzirconium]cyclohexane;
 [1,4-bis(1-indenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(pentamethylcyclopentadienyldibutylzirconium);
 [1,4-bis(9-fluorenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(cyclopentadienyldibutylzirconium);
 40 [1,4-bis(1-indenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(cyclopentadienyldibutylzirconium);
 [1-(1-indenyl)-6-(2-phenyl-1-indenyl)-1,1,6,6-tetraethyl-1,6-disila-4-oxahexane]bis(tert-butylcyclopentadienyldibutylzirconium);
 [1,10-bis(2,3-dimethyl-1-indenyl)-1,1,10,10-tetramethyl-1,10-digermadecane]bis(2-methyl-4-phenylindenyl)dibutylzirconium);
 45 (1-methyl-3-tert-butylcyclopentadienyl)(1-phenyl-4-methoxy-7-chlorofluorenyl)dibutylzirconium;
 (4,7-dichloroindenyl)(3,6-dimesitylfluorenyl)dibutylzirconium;
 bis(2,7-di-tert-butyl-9-cyclohexylfluorenyl)dibutylzirconium;
 (2,7-dimesitylfluorenyl)[2,7-bis(1-naphthyl)fluorenyl]dibutylzirconium;
 dimethylsilylbis(fluorenyl)dibutylzirconium;
 50 dibutylstannylbis(2-methylfluorenyl)dibutylzirconium;
 1,1,2,2-tetraethyldisilanediy(2-methylindenyl)(4-phenylfluorenyl)dibutylzirconium;
 propylene-1-(2-indenyl)-2-(9-fluorenyl)dibutylzirconium;
 1,1-dimethyl-1-silaethylenebis(fluorenyl)dibutylzirconium;
 [4-(cyclopentadienyl)-4,7,7-trimethyl(tetrahydroindenyl)dibutylzirconium];
 55 [4-(cyclopentadienyl)-4,7-dimethyl-7-phenyl(5,6-dimethyltetrahydroindenyl)dibutylzirconium];
 [4-(cyclopentadienyl)-4,7-dimethyl-7-(1-naphthyl)(7-phenyltetrahydroindenyl)]dibutylzirconium;
 [4-(cyclopentadienyl)-4,7-dimethyl-7-butyl(6,6-diethyltetrahydroindenyl)]dibutylzirconium;
 [4-(3-tert-butylcyclopentadienyl)-4,7,7-trimethyl(tetrahydroindenyl)dibutylzirconium];

[4-(1-indenyl)-4,7,7-trimethyl(tetrahydroindenyl)]dibutylzirconium;
 bis(cyclopentadienyl)dibutylhafnium;
 bis(indenyl)dibutylvanadium;
 bis(fluorenyl)dibutylscandium;
 5 (indenyl)(fluorenyl)dibutylniobium;
 (2-methyl-7-naphthylindenyl)(2,6-di-tert-butylfluorenyl)dibutyltitanium;
 (pentamethylcyclopentadienyl)(tetrahydroindenyl)butylhafnium bromide;
 (cyclopentadienyl)(1-octene-8-ylcyclopentadienyl)dibutylhafnium;
 (indenyl)(2-butene-4-ylcyclopentadienyl)dibutyltitanium;
 10 [1,3-bis(trimethylsilyl)cyclopentadienyl](3,4-benzofluorenyl)dibutylniobium;
 dimethylsilanediylbis(indenyl)dibutyltitanium;
 dimethylsilanediylbis(tetrahydroindenyl)dibutylhafnium;
 dimethylsilanediyl(cyclopentadienyl)(indenyl)dibutyltitanium;
 dimethylsilanediylbis(2-methylindenyl)dibutylhafnium;
 15 dimethylsilanediylbis(2-ethylindenyl)methylscandium;
 dimethylsilanediylbis(2-butyl-4,5-benzindenyl)dibutylniobium;
 dimethylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutyltitanium;
 dimethylsilanediylbis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutyltitanium;
 dimethylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutyltitanium;
 20 dimethylsilanediyl(2-ethyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutylhafnium;
 dimethylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)methylscandium;
 dimethylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 dimethylsilanediyl(2-methylindenyl)(4-phenylindenyl)dibutylhafnium;
 dimethylsilanediylbis(2-methyl-4-phenylindenyl)dibutylniobium;
 25 dimethylsilanediylbis(2-ethyl-4-phenylindenyl)dibutylvanadium;
 dimethylsilanediylbis(2-methyl-4,6-diisopropylindenyl)dibutylhafnium;
 dimethylsilanediylbis(2-ethyl-4,6-diisopropylindenyl)dibutylvanadium;
 dimethylsilanediylbis(2-methyl-4-naphthylindenyl)butylhafnium bromide;
 dimethylsilanediylbis(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 30 methylphenylsilanediylbis(indenyl)dibutyltitanium;
 methylphenylsilanediyl(cyclopentadienyl)(indenyl)hafnium;
 methylphenylsilanediylbis(tetrahydroindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-methylindenyl)dibutyltitanium;
 methylphenylsilanediylbis(2-ethylindenyl)dibutylhafnium;
 35 methylphenylsilanediylbis(2-methyl-4,5-benzindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutylvanadium;
 methylphenylsilanediylbis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutyltitanium;
 methylphenylsilanediylbis(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)butyltitanium bromide;
 methylphenylsilanediylbis(2-ethyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)dibutyltitanium;
 40 methylphenylsilanediylbis(2-methyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-ethyl-4,5-benzindenyl)(2-ethyl-4-phenylindenyl)dibutylhafnium;
 methylphenylsilanediyl(2-methylindenyl)(4-phenylindenyl)dibutyltitanium;
 methylphenylsilanediylbis(2-methyl-4-phenylindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-ethyl-4-phenylindenyl)dibutylvanadium;
 45 methylphenylsilanediylbis(2-methyl-4,6-diisopropylindenyl)dibutyltitanium;
 methylphenylsilanediylbis(2-ethyl-4,6-diisopropylindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-methyl-4-naphthylindenyl)dibutylhafnium;
 methylphenylsilanediylbis(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 diphenylsilanediylbis(indenyl)dibutyltitanium;
 50 diphenylsilanediylbis(2-methylindenyl)dibutylhafnium;
 diphenylsilanediylbis(2-ethylindenyl)dibutyltitanium;
 diphenylsilanediylbis(cyclopentadienyl)(indenyl)dibutylhafnium;
 diphenylsilanediylbis(2-methyl-4,5-benzindenyl)dibutyltitanium;
 diphenylsilanediylbis(2-ethyl-4,5-benzindenyl)dibutylhafnium;
 55 diphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4,5-phenylindenyl)dibutylhafnium;
 diphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-methyl-4,5-phenylindenyl)dibutyltitanium;
 diphenylsilanediyl(2-methyl-4,5-benzindenyl)(2-ethyl-4,5-phenylindenyl)dibutylhafnium;
 diphenylsilanediyl(2-ethyl-4,5-benzindenyl)(2-ethyl-4,5-phenylindenyl)dibutyltitanium;

diphenylsilanediy(2-methylindenyl)(4-phenylindenyl)dibutyltitanium;
 diphenylsilanediybis(2-methyl-4-phenylindenyl)dibutyltitanium;
 diphenylsilanediybis(2-ethyl-4-phenylindenyl)dibutylhafnium;
 diphenylsilanediybis(2-methyl-4,6-diisopropylindenyl)dibutylhafnium;
 5 diphenylsilanediybis(2-ethyl-4,6-diisopropylindenyl)dibutylhafnium;
 diphenylsilanediybis(2-methyl-4-naphthylindenyl)dibutylhafnium;
 diphenylsilanediybis(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 1-silacyclopentane-1,1-bis(indenyl)dibutylhafnium;
 1-silacyclopentane-1,1-bis(2-methylindenyl)dibutylhafnium;
 10 1-silacyclopentane-1,1-bis(2-ethylindenyl)dibutylhafnium;
 1-silacyclopentane-1,1-bis(2-methyl-4,5-benzindenyl)dibutyltitanium;
 1-silacyclopentane-1,1-bis(2-ethyl-4,5-benzindenyl)dibutylhafnium;
 1-silacyclopentane-1-(2-methyl-4,5-benzindenyl)-1-(2-methyl-4-phenylindenyl)methylscandium;
 1-silacyclopentane-1-(2-ethyl-4,5-benzindenyl)-1-(2-methyl-4-phenylindenyl)dibutylhafnium;
 15 1-silacyclopentane-1-(2-methyl-4,5-benzindenyl)-1-(2-ethyl-4-phenylindenyl)dibutyltitanium;
 1-silacyclopentane-1-(2-ethyl-4,5-benzindenyl)-1-(2-ethyl-4-phenylindenyl)dibutylhafnium;
 1-silacyclopentane-1-(2-methylindenyl)-1-(4-phenylindenyl)dibutylhafnium;
 1-silacyclopentane-1,1-bis(2-methyl-4-phenylindenyl)dibutylhafnium;
 1-silacyclopentane-1,1-bis(2-ethyl-4-phenylindenyl)dibutyltitanium bromide;
 20 1-silacyclopentane-1,1-bis(2-methyl-4,6-diisopropylindenyl)dibutyltitanium;
 1-silacyclopentane-1,1-bis(2-ethyl-4,6-diisopropylindenyl)dibutyltitanium;
 1-silacyclopentane-1,1-bis(2-methyl-4-naphthylindenyl)methylscandium;
 1-silacyclopentane-1,1-bis(2-ethyl-4-naphthylindenyl)dibutylhafnium;
 ethylene-1,2-bis(indenyl)methylscandium;
 25 ethylene-1,2-bis(tetrahydroindenyl)dibutyltitanium;
 ethylene-1-(cyclopentadienyl)-2-(1-indenyl)dibutylhafnium;
 ethylene-1-(cyclopentadienyl)-2-(2-indenyl)butyltitanium bromide;
 ethylene-1-(cyclopentadienyl)-2-(2-methyl-1--indenyl)dibutylhafnium;
 ethylene-1,2-bis(2-methylindenyl)dibutylhafnium;
 30 ethylene-1,2-bis(2-ethylindenyl)dibutylhafnium;
 ethylene-1,2-bis(2-methyl-4,5-benzindenyl)dibutylhafnium;
 ethylene-1,2-bis(2-ethyl-4,5-benzindenyl)dibutyltitanium;
 ethylene-1,2-bis(4,5-dihydro-8-methyl-7H-cyclopent[*e*]acenaphthylene-7-ylidene)dibutyltitanium;
 ethylene-1-(2-methyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutyltitanium;
 35 ethylene-1-(2-ethyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutyltitanium;
 ethylene-1-(2-methyl-4,5-benzindenyl)-2-(2-ethyl-4-phenylindenyl)methylscandium;
 ethylene-1-(2-ethyl-4,5-benzindenyl)-2-(2-ethyl-4-naphthylindenyl)dibutylhafnium;
 ethylene-1-(2-methylindenyl)-2-(4-phenylindenyl)dibutyltitanium;
 ethylene-1,2-bis(2-methyl-4-phenylindenyl)dibutylhafnium;
 40 ethylene-1,2-bis(2-ethyl-4-phenylindenyl)dibutylhafnium;
 ethylene-1,2-bis(2-methyl-4,6-diisopropylindenyl)dibutylhafnium;
 ethylene-1,2-bis(2-ethyl-4,6-diisopropylindenyl)dibutyltitanium;
 ethylene-1,2-bis(2-methyl-4-naphthylindenyl)dibutyltitanium;
 ethylene-1,2-bis(2-ethyl-4-naphthylindenyl)dibutylhafnium;
 45 propylene-2,2-bis(indenyl)dibutylhafnium;
 propylene-2-cyclopentadienyl-2-(1-indenyl)dibutyltitanium;
 propylene-2-cyclopentadienyl-2-(4-phenyl-1-indenyl)dibutyltitanium;
 propylene-2-cyclopentadienyl-2-(9-fluorenyl)dibutylhafnium;
 propylene-2-cyclopentadienyl-2-(2,7-dimethoxy-9-fluorenyl)dibutylhafnium;
 50 propylene-2-cyclopentadienyl-2-(2,7-di-tert-butyl-9-fluorenyl)dibutylhafnium;
 propylene-2-cyclopentadienyl-2-(2,7-dibromo-9-fluorenyl)dibutyltitanium;
 propylene-2-cyclopentadienyl-2-(2,7-diphenyl-9-fluorenyl)dibutylhafnium;
 propylene-2-cyclopentadienyl-2-(2,7-dimethyl-9-fluorenyl)dibutyltitanium;
 propylene-2-(3-methylcyclopentadienyl)-2-(2,7-dibutyl-9-fluorenyl)dibutylhafnium;
 55 propylene-2-(3-tert-butylcyclopentadienyl)-2-(2,7-dibutyl-9-fluorenyl)dibutyltitanium;
 propylene-2-(3-trimethylsilylcyclopentadienyl)-2-(3,6-di-tert-butyl-9-fluorenyl)dibutyltitanium;
 propylene-2-cyclopentadienyl-2-[2,7-bis(3-butene-1-yl)-9-fluorenyl]dibutylhafnium;
 propylene-2-cyclopentadienyl-2-(3-tert-butyl-9-fluorenyl)dibutyltitanium;

- propylene-2,2-bis(tetrahydroindenyl)dibutylhafnium;
 propylene-2,2-bis(2-methylindenyl)dibutylhafnium;
 propylene-2,2-bis(2-ethylindenyl)dibutyltitanium;
 propylene-2,2-bis(2-methyl-4,5-benzindenyl)dibutyltitanium;
 5 propylene-2,2-bis(2-ethyl-4,5-benzindenyl)dibutylhafnium;
 propylene-2,2-bis(4,5-dihydro-8-methyl-7H-cyclopent[e]acenaphthylene-7-ylidene)dibutylhafnium;
 propylene-2-(2-methyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutylhafnium;
 propylene-2-(2-ethyl-4,5-benzindenyl)-2-(2-methyl-4-phenylindenyl)dibutyltitanium;
 propylene-2-(2-methyl-4,5-benzindenyl)-2-(2-ethyl-4-phenylindenyl)dibutylhafnium;
 10 propylene-2-(2-ethyl-4,5-benzindenyl)-2-(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 propylene-2-(2-methylindenyl)-2-(4-phenylindenyl)dibutylhafnium;
 propylene-2,2-bis(2-methyl-4-phenylindenyl)dibutyltitanium;
 propylene-2,2-bis(2-ethyl-4-phenylindenyl)dibutylhafnium;
 propylene-2,2-bis(2-methyl-4,6-diisopropylindenyl)dibutyltitanium;
 15 propylene-2,2-bis(2-ethyl-4,6-diisopropylindenyl)dibutylhafnium;
 propylene-2,2-bis(2-methyl-4-naphthylindenyl)dibutyltitanium;
 propylene-2,2-bis(2-ethyl-4-naphthylindenyl)dibutyltitanium;
 1,6-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylhafnium] hexane;
 1,6-bis[methylsilylbis(2-methyl-4,5-benzindenyl)dibutyltitanium] hexane;
 20 1,6-bis[methylsilylbis(2-ethyl-4-phenylindenyl)dibutylhafnium] hexane;
 1,6-bis[methylsilylbis(2-methyl-4-naphthylindenyl)dibutyltitanium] hexane;
 1,6-bis[methylsilylbis(2-methyl-4,6-diisopropylindenyl)dibutylhafnium] hexane;
 1,6-bis[methylsilyl(2-methyl-4-phenylindenyl)(4,5-benzindenyl)dibutyltitanium] hexane;
 1-[methylsilylbis(tetrahydroindenyl)dibutylhafnium]-6-[ethylstannyl(cyclopentadienyl)(fluorenyl)dibutyltitanium] hex-
 25 ane;
 1,6-disila-1,1,6,6-tetramethyl-1,6-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylhafnium] hexane;
 1,4-disila-1,4-bis[methylsilylbis(2-methyl-4-phenylindenyl)dibutylhafnium] cyclohexane;
 [1,4-bis(1-indenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(pentamethylcyclopentadienyldibutylhafnium);
 [1,4-bis(9-fluorenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(cyclopentadienyldibutylhafnium);
 30 [1,4-bis(1-indenyl)-1,1,4,4-tetramethyl-1,4-disilabutane]bis(cyclopentadienyldibutyltitanium);
 [1-(1-indenyl)-6-(2-phenyl-1-indenyl)-1,1,6,6-tetraethyl-1,6-disila-4-oxahexane]bis(tert-butylcyclopentadienyldibutylti-
 tanium);
 [1,10-bis(2,3-dimethyl-1-indenyl)-1,1,10,10-tetramethyl-1,10-digermadecane]bis(2-methyl-4-phenylindenyl)dibutylhaf-
 35 nium);
 (1-methyl-3-tert-butylcyclopentadienyl)(1-phenyl-4-methoxy-7-chlorofluorenyl)dibutyltitanium;
 (4,7-dichloroindenyl)(3,6-dimethylfluorenyl)dibutyltitanium;
 bis(2,7-di-tert-butyl-9-cyclohexylfluorenyl)dibutylhafnium;
 (2,7-dimesitylfluorenyl)[2,7-bis(1-naphthyl)fluorenyl]dibutylhafnium;
 dimethylsilylbis(fluorenyl)dibutyltitanium;
 40 dibutylstannylbis(2-methylfluorenyl)dibutylhafnium;
 1,1,2,2-tetraethyldisilanediy(2-methylindenyl)(4-phenylfluorenyl)dibutyltitanium;
 propylene-1-(2-indenyl)-2-(9-fluorenyl)dibutylhafnium;
 1,1-dimethyl-1-silaethylenebis(fluorenyl)dibutyltitanium;
 [4-(cyclopentadienyl)-4,7,7-trimethyl(tetrahydroindenyl)]dibutyltitanium;
 45 [4-(cyclopentadienyl)-4,7-dimethyl-7-phenyl(5,6-dimethyltetrahydroindenyl)]dibutylhafnium;
 [4-(cyclopentadienyl)-4,7-dimethyl-7-(1-naphthyl)(7-phenyltetrahydroindenyl)]dibutyltitanium;
 [4-(cyclopentadienyl)-4,7-dimethyl-7-butyl(6,6-diethyltetrahydroindenyl)]dibutylhafnium;
 [4-(3-tert-butylcyclopentadienyl)-4,7,7-trimethyl(tetrahydroindenyl)]dibutylhafnium;
 [4-(1-indenyl)-4,7,7-trimethyl(tetrahydroindenyl)]dibutyltitanium;
 50 bis(indenyl)dichlorozirconium;
 bis(fluorenyl)dichlorozirconium;
 (indenyl)(fluorenyl)dichlorozirconium;
 bis(cyclopentadienyl)dichlorotitanium;
 (dimethylsilanediy)bis(indenyl)dichlorozirconium;
 55 (dimethylsilanediy)bis(tetrahydroindenyl)dichlorozirconium;
 (dimethylsilanediy)(indenyl)dichlorozirconium;
 (dimethylsilanediy)bis(2-methylindenyl)dichlorozirconium;
 (dimethylsilanediy)bis(2-ethylindenyl)dichlorozirconium;

(dimethylsilanediy)bis(2-methyl-4,5-benzindenyl)dichlorozirconium;
 (dimethylsilanediy)bis(2-ethyl-4,5-benzindenyl)dichlorozirconium;
 (dimethylsilanediy)bis(2-methyl-4-phenylindenyl)dichlorozirconium;
 (dimethylsilanediy)bis(2-ethyl-4-phenylindenyl)dichlorozirconium;
 5 (dimethylsilanediy)bis(2-methyl-4,6-diisopropylindenyl)dichlorozirconium;
 bis(cyclopentadienyl)(η^4 -butadiene)zirconium;
 bis(methylcyclopentadienyl)(η^4 -butadiene)zirconium;
 bis(n-butylcyclopentadienyl)(η^4 -butadiene)zirconium;
 bisindenyl(η^4 -butadiene)zirconium;
 10 (tert-butylamido)dimethyl(tetramethyl- η^5 -cyclopentadienyl)silane(η^4 -butadiene)zirconium;
 bis(2-methylbenzindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-indenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybisindenyl(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylindenyl)(η^4 -butadiene)zirconium;
 15 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-indenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 20 dimethylsilanediybis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 isopropylidene(cyclopentadienyl)(fluorenyl)(η^4 -butadiene)zirconium;
 isopropylidene(cyclopentadienyl)(indenyl)(η^4 -butadiene)zirconium;
 (4- η^5 -cyclopentadienyl)-4,7,7-trimethyl-(η^5 -4,5,6,7-tetrahydroindenyl)(η^4 -butadiene) zirconium;
 dimethylsilanediybis(2-methyl-indenyl)(η^4 -butadiene)zirconium;
 25 dimethylsilanediybisindenyl(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylbenzindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-indenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 30 dimethylsilanediybis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybisindenyl(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylbenzindenyl)(η^4 -butadiene)zirconium;
 35 dimethylsilanediy(2-methylbenzindenyl)(2-methylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-benzindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 40 dimethylsilanediybis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybisindenyl(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methylbenzindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(2-methylindenyl)(η^4 -butadiene)zirconium;
 45 dimethylsilanediy(2-methylbenzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(2-methylbenzindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediybis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 50 methylphenylmethylenefluorenyl(cyclopentadienyl)(η^4 -butadiene)zirconium;
 diphenylmethylenefluorenyl(cyclopentadienyl)(η^4 -butadiene)zirconium;
 isopropylidene(3-methylcyclopentadienyl)(fluorenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediy(3-tert-butylcyclopentadienyl)(fluorenyl)(η^4 -butadiene)zirconium;
 diphenylsilanediy(3-(trimethylsilyl)cyclopentadienyl)(fluorenyl)(η^4 -butadiene)zirconium;
 55 phenylmethylsilanediybis(2-methylindenyl)(η^4 -butadiene)zirconium;
 phenylmethylsilanediybisindenyl(η^4 -butadiene)zirconium;
 phenylmethylsilanediybis(2-methyl-4,5-benzindenyl)(η^4 -butadiene)zirconium;
 phenylmethylsilanediy(2-methyl-4,5-benzindenyl)(2-methylindenyl)(η^4 -butadiene)zirconium;

phenylmethylsilanediyl(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 phenylmethylsilanediyl(2-methylindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 phenylmethylsilanediylbis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 phenylmethylsilanediylbis(2-ethyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 5 phenylmethylsilanediylbis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium ;
 phenylmethylsilanediylbis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-methylindenyl)(η^4 -butadiene)zirconium;
 ethylenebisindenyl(η^4 -butadiene)zirconium;
 ethylenebis(2-methyl-4,5-benzindenyl)(η^4 -butadiene)zirconium;
 10 ethylene(2-methyl-4,5-benzindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 ethylene(2-methylindenyl)(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 ethylene(2-methylindenyl)(4-phenylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-methyl-4,5-benzindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 15 ethylenebis(2-methyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-ethyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-ethyl-4,6-diisopropylindenyl)(η^4 -butadiene)zirconium;
 ethylenebis(2-ethyl-4-naphthylindenyl)(η^4 -butadiene)zirconium;
 20 dimethylsilanediylbis(2-ethyl-4-phenylindenyl)(η^4 -butadiene)zirconium;
 dimethylsilanediylbis(2,3,5-trimethylcyclopentadienyl)(η^4 -butadiene)zirconium;
 1,6-{bis[methylsilylbis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium]} hexane;
 1,6-{bis[methylsilylbis(2-ethyl-4-phenylindenyl)(η^4 -butadiene)zirconium]} hexane;
 1,6-{bis[methylsilylbis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium]}hexane;
 25 1,6-{bis[methylsilylbis(2-methyl-4,5-benzindenyl)(η^4 -butadiene)zirconium]} hexane;
 1,6-{bis[methylsilyl(2-methyl-4-phenylindenyl)(2-methylindenyl)(η^4 -butadiene)zirconium]}hexane;
 1,2-{bis[methylsilylbis(2-methyl-4-phenylindenyl)(η^4 -butadiene)zirconium]}ethane;
 1,2-{bis[methylsilylbis(2-ethyl-4-phenylindenyl)(η^4 -butadiene)zirconium]}ethane;
 1,2-{bis[methylsilylbis(2-methyl-4-naphthylindenyl)(η^4 -butadiene)zirconium]}ethane
 30 1,2-{bis[methylsilylbis(2-methyl-4,5-benzindenyl)(η^4 -butadiene)zirconium]}ethane;
 1,2-{bis[methylsilyl(2-methyl-4-phenylindenyl)(2-methylindenyl)(η^4 -butadiene)zirconium]}ethane.

EXAMPLES

35 **[0138]** Hereinafter the present invention will be described with reference to EXAMPLES but is not deemed to be limited to the following EXAMPLES.

[0139] All of the reactions were carried out under a nitrogen atmosphere. THF, diethyl ether, hexane and benzene, which were used as solvents, were distilled to dehydration in a nitrogen flow in the presence of sodium metal and benzophenone, and 1,2-dichloroethane was used after distillation with phosphorus pentoxide under nitrogen pressure.
 40 Zirconocene dichloride was purchased from Aldrich Chemical Company, Inc. and Nichia Corporation and provided for use. The other reagents were purchased from Kanto Kagaku, Tokyo Kasei Kogyo and Aldrich. $^1\text{H-NMR}$ and $^{13}\text{C-NMR}$ spectra were measured using Bruker ARX-400 or JEOL JNM-LA300. In the measurements, the internal standard was tetramethylsilane for $^1\text{H-NMR}$ and deuterated chloroform for $^{13}\text{C-NMR}$. Gas chromatography was measured on SHIMADZU GC-14A gas chromatograph equipped with SHIMADZU CBP1-M25-025 fused silica capillary column. For recording, SHIMADZU CR6A-Chromatopac integrator was employed. When the yield was determined by GC, mesitylene and n-dodecane were used as the internal standard. As a packing material for the column chromatography, Kanto Kagaku Silica gel 60N (spherical, neutral) 40-100 micrometer was used.

REFERENCE EXAMPLE 1

50 Dimethyl 1,4,5,6,7,8-hexapropyl-9,10-dihydroanthracene-2,3-dicarboxylate

[0140] Bis(η^5 -cyclopentadienyl)dichlorozirconium (1.2 mmol) and THF (10 ml) were charged in a Schlenk tube. This solution was cooled to -78°C , and n-butyl lithium (2.4 mmols) was then added to the solution. The solution was stirred
 55 at -78°C for an hour to give bis(η^5 -cyclopentadienyl)dibutylzirconium.


[0141] After 1,2-bis(2-hexynyl)-3,4,5,6-tetrapropylbenzene (1.0 mmol) was added to the reaction mixture at -78°C , the mixture was warmed to room temperature and allowed to stand for an hour to give 1-zirconacyclopenta-2,4-diene derivative.

[0142] To a solution of the thus obtained l-zirconacyclopenta-2,4-diene (1.0 mmol) derivative in THF (10 ml), CuCl (2.0 mmols) and dimethyl acetylenedicarboxylate (3.0 mmols) were added followed by stirring at room temperature for an hour. Then, the reaction was quenched with 3N hydrochloric acid. Next, the reaction mixture was extracted with diethyl ether, and washed with sodium hydrogencarbonate aqueous solution and brine followed by drying over anhydrous magnesium sulfate. After concentrating under reduced pressure, the residue was subjected to column chromatography using silica gel as the packing material to give the title compound.

[0143] The scheme for synthesis of the title compound of EXAMPLE 1 or similar compounds starting from the title compound of REFERENCE EXAMPLE 2 or similar compounds, which were obtained by aromatizing the title compound of REFERENCE EXAMPLE 1 or similar compounds, is illustrated in FIG. 1.

REFERENCE EXAMPLE 2

[0144]




Dimethyl 1,4,5,6,7,8-hexapropylantracene-2,3-dicarboxylate

[0145] Dimethyl 1,4,5,6,7,8-hexapropyl-9,10-dihydroanthracene-2,3-dicarboxylate obtained in REFERENCE EXAMPLE 1 was used. 2,3-Dichloro-5,6-dicyanobenzoquinone (0.729 g, 3.21 mmols) was added to a solution of dimethyl 1,4,5,6,7,8-hexapropyl-9,10-dihydroanthracene-2,3-dicarboxylate (1.554 g, 2.832 mmols) in benzene (25 ml). Subsequently, the mixture was refluxed for an hour. After filtration, the solvent in the mixture was removed in vacuum. Hexane was added to disintegrate into powders, whereby 1.393 g of the title compound was obtained as a white solid. The isolation yield was 90%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.13 (t, $J=7.2$ Hz, 6H), 1.14 (t, $J=7.3$ Hz, 6H), 1.21 (t, $J=7.3$ Hz, 6H), 1.60-1.66 (m, 4H), 1.76-1.91 (m, 8H), 2.80 (t, $J=8.3$ Hz, 4H), 3.14-3.23 (m, 8H), 3.93 (s, 6H), 8.82 (s, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.77 (2C), 15.01 (2C), 15.03 (2C), 24.61 (2C), 24.74 (2C), 24.88 (2C), 31.69 (2C), 32.71 (2C), 32.81 (2C), 52.25 (2C), 121.42 (2C), 126.48 (2C), 128.81 (2C), 130.52 (2C), 133.85 (2C), 137.50 (2C), 137.90 (2C), 169.78 (2C). Elemental Analysis: Calcd. for $\text{C}_{36}\text{H}_{50}$: C, 79.08; H, 9.22. Found: C, 79.02; H, 9.20. High resolution mass spectrometer: Calcd. for $\text{C}_{38}\text{H}_{50}\text{O}_4$ 546.3709, Found: 546.3709.

REFERENCE EXAMPLE 3

[0146]



2,3-Bis(hydroxymethyl)-1,4,5,6,7,8-hexapropylantracene:


[0147] Dimethyl 1,4,5,6,7,8-hexapropylantracene-2,3-dicarboxylate obtained in REFERENCE EXAMPLE 2 was used. After lithium aluminum hydride was added to the solution of dimethyl 1,4,5,6,7,8-hexapropylantracene-2,3-dicarboxylate in diethyl ether at 0°C , the mixture was warmed to room temperature and stirred for an hour. At room temperature, water was added to terminate the reaction. Next, the reaction mixture was rendered slightly acidic with 2N sulfuric acid and extracted with ether. After washing with brine, the extract was dried over anhydrous magnesium sulfate. Column chromatography with silica gel as the packing material was performed using hexane. Recrystallization from hexane gave 6.637 g (13.846 mmols) of the title compound as a light yellow solid. The isolation yield was 98%.

EP 1 262 469 A1

¹H NMR(CDCl₃, Me₄Si) δ 1.11-1.26 (m,18H), 1.58-1.68 (m, 4H), 1.74-1.81 (m, 8H), 2.78 (t, J=8.3 Hz, 4H), 3.15 (t, J=8.3Hz, 4H), 3.26 (t, J=8.3 Hz, 4H), 5.00 (s, 4H), 8.75 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.81 (2C), 15.05 (4C), 24.56 (2C), 24.94 (2C), 25.08 (2C), 31.37 (2C), 31.75 (2C), 32.81 (2C), 60.18 (2C), 120.44 (2C), 129.30(2C), 129.74 (2C), 133.03 (2C), 133.62 (2C), 136.42 (2C), 136.85 (2C). Elemental analysis: Calcd. for C₃₄H₅₀O₂: C, 83.21; H, 10.27. Found: C, 83.00; H, 10.50. High resolution mass spectrometer: Calcd. for C₃₄H₅₀O₂ 490.3811, Found: 490.3811.

REFERENCE EXAMPLE 4

[0148]




2,3-Bis(bromomethyl)-1,4,5,6,7,8-hexapropylanthracene:

[0149] 2,3-Bis(hydroxymethyl)-1,4,5,6,7,8-hexapropylanthracene obtained in REFERENCE EXAMPLE 3 was used. After phosphorus tribromide (1 eq.) was added to a solution of 2,3-bis(hydroxymethyl)-1,4,5,6,7,8-hexapropylanthracene (1 eq.) in chloroform at room temperature, the mixture stirred at room temperature for an hour. Next, the reaction mixture was extracted with ether. After washing with brine, the extract was dried over anhydrous magnesium sulfate. The solvent was removed and the residue was recrystallized from hexane to give 7.767 g (13.120 mmols) of the title compound as a light yellow solid. The isolation yield was 96%.

¹H NMR (CDCl₃, Me₄ Si) δ 1.13 (t, J=7.3 Hz, 6H), 1.20 (t, J=7.2 Hz, 6H), 1.24 (t, J=7.1 Hz, 6H), 1.60-1.66 (m, 4H), 1.75-1.87 (m, 8H), 2.78 (t, J=8.4 Hz, 4H), 3.15 (t, J=8.3 Hz, 4H), 3.27 (t, J=8.3 Hz, 4H), 4.99 (s, 4H), 8.72 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.96 (2C), 15.03 (4C), 24.38 (2C), 24.60 (2C), 24.90 (2C), 29.91(2C), 31.63 (2C), 31.72 (2C), 32.83 (2C), 120.69 (2C), 129.14 (2C), 129.17 (2C), 130.21 (2C), 133.76 (2C), 137.43 (2C), 138.69 (2C). Elemental Analysis: Calcd. for C₃₄H₄₈Br₂: C, 66.23; H, 7.85; Br, 25.92. Found: C, 66.35; H, 7.92; Br, 25.85.

REFERENCE EXAMPLE 5

[0150]



2,3-Bis(2-hexynyl)-1,4,5,6,7,8-hexapropylanthracene:

[0151] 2,3-Bis(bromomethyl)-1,4,5,6,7,8-hexapropylanthracene obtained in REFERENCE EXAMPLE 4 was employed. N,N'-Dimethylpropyleneurea (DMPU) and 1-pentynyl lithium were added to the solution of 2,3-bis(bromomethyl)-1,4,5,6,7,8-hexapropylanthracene in THF. The reaction mixture was stirred at room temperature for an hour. The reaction was quenched with 3N Hydrochloric acid. Next, the reaction mixture was extracted with ether. After washing with sodium hydrogencarbonate aqueous solution and brine; the extract was dried over anhydrous magnesium sulfate. After the extract was concentrated under reduced pressure, column chromatography with silica gel as the packing material was performed using hexane. Recrystallization from methanol gave 6.372 g (12.338 mmols) of the title compound as a yellow solid. The isolation yield was 87%.


¹H NMR (CDCl₃, Me₄Si) δ 0.93 (t, J=7.4 Hz, 6H), 1.12 (t, J=7.3 Hz, 6H), 1.20 (t, J=7.3 Hz, 6H), 1.21 (t, J=7.4 Hz, 6H), 1.43-1.53 (m, 4H), 1.58-1.66 (m,4H), 1.76-1.86 (m,8H), 2.11 (tt, J=2.1, 7.0 Hz, 4H), 2.77 (t, J=8.3 Hz, 4H), 3.15 (t, J=8.2 Hz, 4H), 3.24 (t, J=8.3 Hz, 4H), 3.86 (t, J=2.1 Hz, 4H), 8.69 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 13.47 (2C), 14.97 (2C), 15.05 (4C), 20.11 (2C), 20.95 (2C), 22.38 (2C), 24.09 (2C), 24.54 (2C), 24.96 (2C), 31.78 (2C), 31.90 (2C),

EP 1 262 469 A1

32.81 (2C), 78.57 (2C), 80.99 (2C), 119.71 (2C), 129.19 (2C), 129.31 (2C), 131.17 (2C), 133.55 (2C), 134.55 (2C), 136.20 (2C). Elemental Analysis: Calcd. for C₄₄H₆₂: C, 89.43; H, 10.57. Found: C, 89.17; H, 10.78.

REFERENCE EXAMPLE 6

[0152]



Dimethyl 5,14-dihydro-1,4,6,8,9,10,11,13-octapropylpentacene-2,3-dicarboxylate

[0153] The reaction was carried out in a manner similar to REFERENCE EXAMPLE 1. Bis(η⁵-cyclopentadienyl) dichlorozirconium (1.2 mmol) and THF (10 ml) were charged in a Schlenk tube. This solution was cooled to -78°C, and n-butyl lithium (2.4 mmols) was then added to the solution. The solution was stirred at -78°C for an hour to give bis(η⁵-cyclopentadienyl)dibutylzirconium.


[0154] At -78°C, 2,3-bis(2-hexynyl)-1,4,5,6,7,8-hexapropylanthracene (1.0 mmol) obtained in REFERENCE EXAMPLE 5 was added to the reaction mixture. The mixture was then warmed to room temperature and allowed to stand for an hour to give 1-zirconacyclopenta-2,4-diene derivative.

[0155] To a solution of the thus obtained 1-zirconacyclopenta-2,4-diene (1.0 mmol) derivative in THF (10 ml), CuCl (2.0 mmols) and dimethyl acetylenedicarboxylate (3.0 mmols) were added followed by stirring at room temperature for an hour. Then, 3N hydrochloric acid was added to terminate the reaction. Next, the reaction mixture was extracted with ether, and washed with sodium hydrogencarbonate aqueous solution and brine followed by drying over anhydrous magnesium sulfate. After concentrating under reduced pressure, the residue was subjected to short column chromatography (elute, CHCl₃) using silica gel. Subsequent recrystallization from a solvent mixture of chloroform and methanol gave 5.528 g (10.782 mmols) of the title compound as a cream-like solid. The isolation yield was 70%.

¹H NMR (CDCl₃, Me₄Si) δ 1.11 (t, J=7.2 Hz, 6H), 1.13 (t, J=7.1 Hz, 6H), 1.22 (t, J=7.3 Hz, 6H), 1.23 (t, J=7.3 Hz, 6H), 1.61-1.73 (m, 8H), 1.78-1.86 (m, 8H), 2.79 (t, J=8.3 Hz, 4H), 2.84 (t, J=8.2 Hz, 4H), 3.17 (t, J=8.2 Hz, 4H), 3.32 (t, J=8.4 Hz, 4H), 3.85 (s, 6H), 4.11 (s, 4H), 8.72 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.66 (2C), 14.93 (2C), 15.03 (2C), 15.06 (2C), 24.31 (2C), 24.52 (2C), 24.60 (2C), 24.96 (2C), 30.39 (2C), 31.30 (2C), 31.78 (2C), 32.80 (2C), 32.89 (2C), 52.18 (2C), 119.57 (2C), 128.82 (2C), 129.17 (2C), 130.23 (2C), 131.12 (2C), 131.68 (2C), 133.50 (2C), 135.11 (2C), 136.20 (2C), 139.80 (2C), 169.48 (2C). Elemental Analysis: Calcd. for C₅₀H₆₈O₄: C, 81.69; H, 9.46. Found: C, 81.92; H, 9.35.

EXAMPLE 1

[0156]



Dimethyl 1,4,6,8,9,10,11,13-octapropylpentacene-2,3-dicarboxylate

[0157] Chloranil (0.054 g, 0.22 mmol) was added to a solution of dimethyl 5,14-dihydro-1,4,6,8,9,10,11,13-octapropylpentacene-2,3-dicarboxylate (0.147 g, 0.2 mmol) obtained in REFERENCE EXAMPLE 6 in benzene (5 ml). The mixture was then refluxed for 24 hours. After concentration, chloroform was added to the residue followed by filtration. After concentration, the concentrate was recrystallized from benzene to give 0.048 g of the title compound as a blue solid. The isolation yield was 33%.


EP 1 262 469 A1

¹H NMR (CDCl₃, Me₄Si) δ 1.15 (t, J=7.2 Hz, 6H), 1.20 (t, J=7.3 Hz, 6H), 1.27 (t, J=7.5 Hz, 6H), 1.29 (t, J=7.4 Hz, 6H), 1.62-1.68 (m, 4H), 1.85-2.07 (m, 12H), 2.78 (t, J=7.5 Hz, 4H), 3.22-3.26 (m, 8H), 3.90 (bs, 4H), 3.94 (s, 6H), 9.06 (s, 2H), 9.17 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.85 (2C), 15.05 (2C), 15.13 (4C), 24.36 (2C), 24.60 (2C), 24.87 (2C), 25.11 (2C), 31.33 (2C), 31.76 (2C), 32.67 (2C), 32.85 (2C), 52.26 (2C), 120.08 (2C), 122.74 (2C), 126.23 (2C), 127.57 (2C), 127.76 (2C), 128.35 (2C), 129.91 (2C), 133.37 (2C), 133.76 (2C), 136.77 (2C), 138.13 (2C), 169.65 (2C). High resolution mass spectrometer: Calcd. for C₅₀H₆₆O₄ 730.4961, Found: 730.4995.

[0158] The scheme for synthesis of the title compound of EXAMPLE 1 starting from the title compound of REFERENCE EXAMPLE 2, and via the title compound of REFERENCE EXAMPLE 5 obtained via the title compound of REFERENCE EXAMPLE 3, then the title compound of REFERENCE EXAMPLE 4 and further via the title compound of REFERENCE EXAMPLE 6, is illustrated in FIG. 2.

REFERENCE EXAMPLE 7

[0159]




Dimethyl 1,4-dipropyl-5,6-dicyano-1,2,3,4-tetrahydronaphthalene-2,3-dicarboxylate

[0160] 2,3-Dichloro-5,6-dicyanobenzoquinone (1.362 g, 6.0 mmols) was added to a solution of dimethyl 1,4-dipropyl-5,6,7,8-tetrahydronaphthalene-2,3-dicarboxylate (0.665 g, 2.0 mmols) in benzene (20 ml). The mixture was then refluxed for 24 hours. After filtration, the solvent in the mixture was removed in vacuum. By column chromatography (ethyl acetate/hexane, 1/20) using silica gel, 0.464 g of the title compound was obtained as colorless crystals. The GC yield was 87% and the isolation yield was 71%.

¹H NMR (CDCl₃, Me₄Si) δ 1.05 (t, J=7.4 Hz, 6H), 1.71-1.81 (m, 4H), 3.07 (t, J=8.1 Hz, 4H), 3.91 (s, 6H), 7.60 (dd, J=3.4, 6.5 Hz, 2H), 8.12 (dd, J=3.4, 6.5 Hz, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.52 (2C), 24.64 (2C), 32.20 (2C), 52.26 (2C), 125.53 (2C), 127.28 (2C), 128.25 (2C), 132.42 (2C), 136.85 (2C), 169.53 (2C). Elemental Analysis: Calcd. for C₂₀H₂₄O₄: C, 73.15; H, 7.37. Found: C, 73.10; H, 7.44.

REFERENCE EXAMPLE 8

[0161]




2,3-bis(hydroxymethyl)-1,4-dipropyl-5,6-dicyano-1,2,3,4-tetrahydronaphthalene

[0162] Dimethyl 1,4-dipropyl-5,6-dicyano-1,2,3,4-tetrahydronaphthalene obtained in REFERENCE EXAMPLE 7 was treated with lithium aluminum hydride in a manner similar to REFERENCE EXAMPLE 3. Thus, 0.219 g (0.898 mmol) of the title compound was obtained as a white solid. Recrystallization from ether/hexane gave a small quantity of the title compound for elemental analysis. The isolation yield was 90%.

[0163] ¹H NMR (CDCl₃, Me₄Si) δ (t, J=7.3 Hz, 6H), 1.59-1.67 (m, 4H), 3.08 (t, J=8.2 Hz, 4H), 3.51 (bs, 2H), 4.87 (s, 4H), 7.47 (dd, J=3.3, 6.5 Hz, 2H), 8.04 (dd, J=3.3, 6.5 Hz, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.52 (2C), 24.96 (2C), 31.52 (2C), 59.71 (2C), 125.05 (2C), 125.77 (2C), 132.12 (2C), 134.53 (2C), 136.48 (2C). Elemental Analysis: Calcd. for C₁₈H₂₄O₂: C, 79.37; H, 8.88. Found: C, 79.43; H, 9.01.

REFERENCE EXAMPLE 9

[0164]




2,3-Bis(bromomethyl)-1,4-dipropylnaphthalene

[0165] 2,3-Bis(hydroxymethyl)-1,4-dipropylnaphthalene obtained in REFERENCE EXAMPLE 8 was treated with phosphorus tribromide in a manner similar to REFERENCE EXAMPLE 4. By column chromatography (ethyl acetate/hexane, 1/50) using silica gel, 0.115 g (0.4 mmol) of the title compound was obtained as a white solid. The isolation yield was 72%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.14 (t, $J=7.3$ Hz, 6H), 1.75 (bs, 4H), 3.12 (t, $J=8.3$ Hz, 4H), 4.92 (s, 4H), 7.49 (dd, $J=3.3$, 6.5 Hz, 2H), 8.02 (dd, $J=3.3$, 6.5 Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.77 (2C), 24.37 (2C), 29.01 (2C), 31.11 (2C), 125.17 (2C), 126.59 (2C), 130.91 (2C), 132.44 (2C), 138.44 (2C). Elemental Analysis: Calcd. for $\text{C}_{18}\text{H}_{22}\text{Br}_2$: C, 54.30; H, 5.57; Br, 40.13. Found: C, 54.21; H, 5.57; Br, 40.24.

REFERENCE EXAMPLE 10

[0166]




2,3-Bis(2-hexynyl)-1,4-dipropylnaphthalene

[0167] 2,3-Bis(bromomethyl)-1,4-dipropylnaphthalene obtained in REFERENCE EXAMPLE 9 was treated with N,N' -dimethylpropyleneurea (DMPU) and 1-pentynyl lithium in a manner similar to REFERENCE EXAMPLE 5. By column chromatography (ethyl acetate/hexane, 1/50) using silica gel, 1.661 g (4.787 mmols) of the title compound was obtained as a white solid. The isolation yield was 93%.

^1H NMR (CDCl_3 , Me_4Si) δ 0.91 (t, $J=7.4$ Hz, 6H), 1.12 (t, $J=7.3$ Hz, 6H), 1.40-1.49 (m, 4H), 1.68-1.78 (m, 4H), 2.07 (tt, $J=2.1$, 7.0 Hz, 4H), 3.10 (t, $J=8.3$ Hz, 4H), 3.84 (t, $J=2.1$ Hz, 4H), 7.41 (dd, $J=3.3$, 6.5 Hz, 2H), 8.01 (dd, $J=3.3$, 6.5 Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 13.43 (2C), 14.77 (2C), 19.96 (2C), 20.88 (2C), 22.32 (2C), 24.11 (2C), 31.40 (2C), 78.25 (2C), 80.95 (2C), 124.64 (2C), 125.02 (2C), 131.66 (2C), 132.48 (2C), 134.99 (2C). Elemental Analysis: Calcd. for $\text{C}_{28}\text{H}_{36}$: C, 90.26; H, 9.74. Found: C, 90.13; H, 9.86.

REFERENCE EXAMPLE 11

[0168]




Dimethyl 5,12-dihydro-1,4,6,11-tetrapropyl-naphthacene-2,3-dicarboxylate

[0169] 2,3-Bis(2-hexynyl)-1,4-dipropyl-naphthalene obtained in REFERENCE EXAMPLE 10 was reacted with bis(η^5 -cyclopentadienyl)dibutylzirconium in a manner similar to REFERENCE EXAMPLE 1. Next, CuCl and dimethyl acetylenedicarboxylate were added at room temperature to the reaction mixture as it was, followed by stirring for further 1 hour at room temperature. Thereafter, 3N hydrochloric acid was added to terminate the reaction. Next, the reaction mixture was extracted with ether, and washed with sodium hydrogencarbonate aqueous solution and brine followed by drying over anhydrous magnesium sulfate. After concentrating under reduced pressure, the residue was subjected to column chromatography (ethyl acetate/hexane, 1/10) using silica gel to give 1.790 g (4.458 mmols) of the title compound as a light yellow solid. The isolation yield was 78%. The X-ray crystal structure analysis of the title compound is shown in FIG. 3.

^1H NMR (CDCl_3 , Me_4Si) δ 1.09 (t, $J=7.3$ Hz, 6H), 1.16 (t, $J=7.3$ Hz, 6H), 1.65-1.75 (m, 8H), 2.82 (t, $J=8.2$ Hz, 4H), 3.19 (t, $J=8.2$ Hz, 4H), 3.84 (s, 6H), 4.08 (s, 4H), 7.45 (dd, $J=3.2, 6.6$ Hz, 2H), 8.06 (dd, $J=3.4, 6.5$ Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.63 (2C), 14.76 (2C), 24.27 (2C), 24.53 (2C), 30.21 (2C), 30.85 (2C), 32.85 (2C), 52.20 (2C), 124.52 (2C), 124.86 (2C), 130.22 (2C), 131.07 (2C), 132.35 (2C), 132.39 (2C), 135.12 (2C), 139.55 (2C), 169.44 (2C). Elemental Analysis: Calcd. for $\text{C}_{34}\text{H}_{42}\text{O}_4$: C, 79.34; H, 8.22. Found: C, 79.21; H, 8.36.

EXAMPLE 2

[0170]



Dimethyl 1,4,6,11-tetrapropyl-naphthacene-2,3-dicarboxylate

[0171] Dimethyl 5,12-dihydro-1,4,6,11-tetrapropyl-naphthacene-2,3-dicarboxylate obtained in REFERENCE EXAMPLE 11 was used.


[0172] 2,3-Dichloro-5,6-dicyanobenzoquinone (0.050 g, 0.22 mmol) was added to a solution of dimethyl 5,12-dihydro-1,4,6,11-tetrapropyl-naphthacene-2,3-dicarboxylate (0.103 g, 0.2 mmol) in 1,4-dioxane (5 ml). Subsequently, the mixture was refluxed for 3 hours. After filtration, the solvent in the mixture was removed in vacuum. Chloroform was added and the mixture was again filtered. Recrystallization from chloroform/methanol gave 0.076 g of the title compound as red needle-like crystals. The NMR yield was 97% and the isolated yield was 71%. The X-ray crystal structure analysis of the title compound is shown in FIG. 4.

^1H NMR (CDCl_3 , Me_4Si) δ 1.19 (t, $J=7.3$ Hz, 6H), 1.23 (t, $J=7.3$ Hz, 6H), 1.92-1.86 (m, 8H), 3.26 (t, $J=8.1$ Hz, 4H), 3.72 (t, $J=8.1$ Hz, 4H), 3.94 (s, 6H), 7.46 (dd, $J=3.2, 7.0$ Hz, 2H), 8.31 (dd, $J=3.2, 7.0$ Hz, 2H), 9.19 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.81 (2C), 14.89 (2C), 24.67 (2C), 24.89 (2C), 30.73 (2C), 32.72 (2C), 52.25 (2C), 122.65 (2C), 125.12 (2C), 125.39 (2C), 126.67 (2C), 128.44 (2C), 128.77 (2C), 129.63 (2C), 134.16 (2C), 137.87 (2C), 169.58 (2C). Elemental Analysis: Calcd. for $\text{C}_{34}\text{H}_{40}\text{O}_4$: C, 79.65; H, 7.86. Found: C, 79.43; H, 8.01. High resolution mass spectrometer: Calcd. for $\text{C}_{34}\text{H}_{40}\text{O}_4$ 512.2937, Found: 512.2937.

[0173] The scheme for synthesis of the title compound of EXAMPLE 2 starting from the title compound of REFERENCE EXAMPLE 7, and via the title compound of REFERENCE EXAMPLE 9 obtained via the title compound of REFERENCE EXAMPLE 8, then via the title compound of REFERENCE EXAMPLE 10 and further via the title compound of REFERENCE EXAMPLE 11, is illustrated in FIG. 5.

REFERENCE EXAMPLE 12

[0174]



1,2,3,4,5,6,7,8-Octapropylantracene


[0175] After 2,3-dichloro-5,6-dicyanoquinone (0.100 g, 0.440 mmol) was added to a solution of 1,2,3,4,5,6,7,8-octapropyl-9,10-dihydroanthracene (0.208 g, 0.400 mmol) in benzene (5 ml), the mixture was refluxed for an hour with heating. The reaction mixture was filtered to remove hydroquinone and purified by silica gel column chromatography (ethyl acetate/hexane, 99/1) to give the title compound (0.164 g) as a white solid. The isolation yield was 79%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.11 (t, $J=7.3$ Hz, 12H), 1.20 (t, $J=7.3$ Hz, 12H), 1.60-1.66 (m, 8H), 1.77-1.83 (m, 8H), 2.77 (t, $J=7.7$ Hz, 4H), 3.15 (t, $J=8.2$ Hz, 8H), 8.66 (s, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 15.06 (4C), 15.09 (4C), 24.57 (4C), 25.02 (4C), 31.83 (4C), 32.83 (4C), 119.40 (2C), 129.03 (4C), 133.47 (4C), 135.80 (4C). Elemental Analysis: Calcd. for $\text{C}_{38}\text{H}_{58}$: C, 88.65; H, 11.35. Found: C, 88.76; H, 11.36.

[0176] 2,3-Dichloro-5,6-dicyanoquinone (0.075 g, 0.440 mmol) was added to a solution of 1,2,3,4,5,6,7,8-octapropyl-9,10-dihydroanthracene (0.155 g, 0.300 mmol) in benzene (5 ml) followed by stirring at room temperature for an hour. Analysis of the reaction solution by NMR revealed that the products were 1,2,3,4,5,6,7,8-octapropylantracene (NMR yield, 49%) and the Diels-Alder adduct (NMR yield, 30%), and 23% of the starting material remained.

REFERENCE EXAMPLE 13

[0177]



$\text{C}_{42}\text{H}_{52}\text{O}_4$
 Exact Mass: 620.3866
 Mol. Wt.: 620.8599
 C, 81.25; H, 8.44; O, 10.31

Dimethyl 1,4,6,8,9,10,11,13-octaethyl-5,14-dihydropentacene-2,3-dicarboxylate

[0178] The title compound was obtained by the same manner as in REFERENCE EXAMPLES 2 to 6. In REFERENCE EXAMPLE 2, dimethyl


1,4,5,6,7,8-hexapropyl-9,10-dihydroanthracene-2,3-dicarboxylate was employed, whereas dimethyl 1,4,5,6,7,8-hexaethyl-9,10-dihydroanthracene-2,3-dicarboxylate was employed in REFERENCE EXAMPLE 13.

[0179] At the final step, 124 mg (0.50 mmol) of the title compound was obtained as colorless single crystals by column chromatography (Et_2O /hexane, 1/10) using silica gel. The isolation yield was 40%. The X-ray crystal structure analysis of the title compound is shown in FIG. 6.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.27-1.36 (m, 12H), 1.41-1.48 (m, 12H), 2.86-2.96 (m, 8H), 3.24-3.32 (m, 4H), 3.39-3.47 (m, 4H), 3.86 (s, 6H), 4.18 (s, 4H), 8.79 (s, 2H). $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 15.22, 15.49, 15.63, 15.89, 21.87, 22.00, 22.99, 23.95, 29.95, 52.29, 119.49, 128.55, 128.99, 130.12, 130.75, 133.11, 134.78, 136.43, 137.10, 139.66, 169.53. High resolution mass spectrometer: Calcd. for $\text{C}_{42}\text{H}_{52}\text{O}_4$: 620.3866, Found: 620.3869.

REFERENCE EXAMPLE 14

[0180]



Dimethyl 1,4,5,6,7,8-hexabutylantracene-2,3-dicarboxylate


20 [0181] The reaction was carried out in a manner similar to REFERENCE EXAMPLE 2. In REFERENCE EXAMPLE 2, dimethyl 1,4,5,6,7,8-hexapropyl-9,10-dihydroanthracene-2,3-dicarboxylate was employed, whereas dimethyl 1,4,5,6,7,8-hexabutyl-9,10-dihydroanthracene-2,3-dicarboxylate was employed in REFERENCE EXAMPLE 14.

[0182] At the final step, 1764 mg (3 mmols) of the title compound was obtained as a light yellow solid by column chromatography (Et_2O /hexane, 1/10) using silica gel. The isolation yield was 93%.

25 1H NMR ($CDCl_3$, Me_4Si) δ 0.98-1.08 (m, 18H), 1.52-1.82 (m, 24H), 2.78-2.85 (m, 4H), 3.16-3.26 (m, 8H), 3.92 (s, 6H), 8.84 (s, 2H). ^{13}C NMR ($CDCl_3$, Me_4Si) δ 13.94, 14.04, 14.1, 23.47, 23.59, 23.72, 29.13, 30.16, 30.39, 33.56, 33.67, 52.30, 121.40, 126.41, 128.81, 130.55, 133.91, 137.64, 137.94. High resolution mass spectrometer: Calcd. for $C_{42}H_{62}O_4$: 630.4648, Found: 630.4645.

EXAMPLE 3

[0183]



Dimethyl 1,4,6,8,9,10,11,13-octaethylpentacene-2,3-dicarboxylate

45 [0184] The 1,4-dioxane solution of the compound obtained in REFERENCE EXAMPLE 13 was dehydrogenated with chloranil. By column chromatography (eluted first with Et_2O /hexane, 1/5 and then with 100% chloroform) using silica gel, 80 mg (0.5 mmol) of the title compound was obtained as a deep blue solid. The isolation yield was 26%.

50 1H NMR ($CDCl_3$, Me_4Si) δ 1.32 (t, $J=7.4$ Hz, 6H), 1.48-1.58 (m, 12H), 1.66 (t, $J=7.5$ Hz, 6H), 2.90 (q, $J=7.5$ Hz, 4H), 3.33 (q, $J=7.5$ Hz, 8H), 3.95 (s, 6H), 4.03 (q, $J=7.5$ Hz, 4H), 9.16 (s, 2H), 9.26 (s, 2H). ^{13}C NMR ($CDCl_3$, Me_4Si) δ 15.36, 15.66, 15.79, 15.87, 22.03, 22.21, 23.09, 23.80, 52.34, 119.92, 122.57, 126.05, 127.28, 127.47, 128.20, 129.78, 134.66, 135.20, 137.69, 139.42, 169.69. High resolution mass spectrometer: Calcd. for $C_{42}H_{50}O_4$: 618.3709, Found: 618.3680.

55 [0185] The foregoing results reveal that according to the process of the present invention, by introducing appropriate substituents on the condensed polycyclic aromatic compounds to improve the solubility while the number of the rings is small, and proceeding further synthesis, the number of the polyacene rings can be increased, while maintaining the solubility.

[0186] Next, the relationship between substituents introduced and polyacene derivatives obtained was examined by way of experiments, the results of which are shown below.









REFERENCE EXAMPLE 15

1,2,3,4,5,6,7,8-Octapropylanthracene

[0187] After 2.2 equivalents of n-BuLi and 2.2 equivalents of tetramethylethylenediamine were added to the hexane solution of 9,10-dihydro-1,2,3,4,5,6,7,8-octapropylanthracene at room temperature, the mixture was heated at 50°C for 3 hours. The reaction solution was cooled to room temperature and 1.1 equivalent of methyl iodide was added thereto. Stirring for an hour produced the title compound in the NMR yield of 98%. The compound was treated with 3N hydrochloric acid, and washed with saturated sodium hydrogencarbonate aqueous solution and brine. The organic phase was dried over anhydrous magnesium sulfate. The solvent was removed under reduced pressure to give the pure title compound in the yield of 96%. In this case, purification by column chromatography, etc. was unnecessary.

[0188] Multi-substituted dihydroanthracenes were aromatized by similar experimental procedures. The results are shown in TABLE 1.

TABLE 1

Dihydroanthracene	Anthracene	Yield (%)
		98 (96)
		94 (90)
		96 (92)
		47 (43)

In the table above, Yield denotes the yield by NMR and the numeral within parenthesis denotes the yield when isolated.


[0189] As is evident also from TABLE 1, the system wherein the lithium dopant and the lithium-removing reagent were used in combination was extremely effective for the substituted polyhydropolyacenes, whereas the yield was 47% with the unsubstituted dihydroanthracene.

[0190] Next, various combinations of the lithium dopant and the lithium-removing reagent were examined by way of experiments, the results of which are shown in TABLE 2. In the table, the lithium dopant and the lithium-removing reagent are designated as "RM" and "R'X", respectively.

the system to room temperature, which is followed by reacting with dimethyl acetylenecarboxylate in the presence of CuCl).

REFERENCE EXAMPLE 17


[0195] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.



40 (wherein (a) indicates the reaction with lithium aluminum hydride at 0°C followed by gradually elevating the temperature to room temperature; (b) indicates the reaction with phosphorus bromide at room temperature; (c) indicates the reaction with the alkynyl lithium shown by formula: R-CC-Li in THF solvent in the presence of N,N'-dimethylpropyleneurea; and (d) indicates the reaction with biscyclopentadienylzirconium dibutyl in THF solvent at -78°C followed by warming the system to room temperature, which is followed by reacting with dimethyl acetylenecarboxylate in the presence of CuCl).

REFERENCE EXAMPLE 18


[0196] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.



25 (wherein (a) indicates the reaction with lithium aluminum hydride at 0°C followed by gradually elevating the temperature to room temperature; (b) indicates the reaction with phosphorus bromide at room temperature; (c) indicates the reaction with the alkynyl lithium shown by formula: R-CC-Li in THF solvent in the presence of N,N'-dimethylpropyleneurea; and (d) indicates the reaction with biscyclopentadienylzirconium dibutyl in THF solvent at -78°C followed by warming the system to room temperature, which is followed by reacting with dimethyl acetylenecarboxylate in the presence of CuCl).

REFERENCE EXAMPLE 19

30 [0197] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.




55 (wherein (a) indicates the reaction with lithium aluminum hydride at 0°C followed by gradually elevating the temperature to room temperature; (b) indicates the reaction with phosphorus bromide at room temperature; (c) indicates the reaction with the alkynyl lithium shown by formula: R-CC-Li in THF solvent in the presence of N,N'-dimethylpropyleneurea; and (d) indicates the reaction with biscyclopentadienylzirconium dibutyl in THF solvent at -78°C followed by warming the system to room temperature, which is followed by reacting with dimethyl acetylenecarboxylate in the presence of CuCl).


REFERENCE EXAMPLE 20

[0198] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.

5




10



15

20



25

30

[0199] In this scheme, the following procedures were used. A solution of Cp_2ZrCl_2 (1.2 eq.) in THF was cooled to -78°C on a dry ice-acetone bath, and a solution of *n*-BuLi (2.4 eq.) in hexane was added to the solution. After the reaction solution was kept at -78°C for an hour, the alkyne was added thereto followed by elevating to room temperature. The mixture was maintained at room temperature for 1 to 3 hours thereby to form zirconacyclopentadiene. 4-Octyne (1.5 eq.) and dibromobis(triphenylphosphine)nickel (II) (2.0 eq.) were added to the THF solution of zirconacyclopentadiene (1.0 eq.) at room temperature.

35

[0200] After 24 hours, the mixture was treated with 3N hydrochloric acid and extracted with an appropriate solvent. The organic layers were combined in one and washed with saturated sodium hydrogencarbonate and brine followed by drying over magnesium sulfate. After the solvent was removed through an evaporator, the residue was suitably purified to give the cyclized product.

40

9,10-Dihydro-1,2,3,4,5,6,7,8-octapropylanthracene

45

[0201] Using the starting material (0.407 g, 1.00 mmol), the experiment was performed by the procedures described above. Silica gel column chromatography (ethyl acetate/hexane, 1/99) was conducted and the solid obtained was washed with ethanol to give 9,10-dihydro-1,2,3,4,5,6,7,8-octapropylanthracene as white powders (0.251 g). The isolation yield was 48%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.05 (t, $J=7.3$ Hz, 12H), 1.12 (t, $J=7.3$ Hz, 12H), 1.47-1.61 (m, 16H), 2.54 (t, $J=8.4$ Hz, 8H), 2.70 (t, $J=8.4$ Hz, 8H), 3.80 (s, 4H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 15.06 (4C), 15.12 (4C), 24.57 (4C), 25.10 (4C), 29.90 (2C), 32.26 (4C), 32.31 (4C), 134.33 (4C), 134.93 (4C), 136.30 (4C). Elemental Analysis: Calcd. for $\text{C}_{38}\text{H}_{60}$: C, 88.30; H, 11.70. Found: C, 88.45; H, 11.67.

50

1,2,3,4,6,8,9,10,11,13-Decapropyl-5,7,12,14-tetrahydropentacene

55

[0202] Using the starting material (1.19 g, 2.00 mmols), the experiment was performed by the procedures described above. By recrystallization from a solvent mixture of chloroform/methanol, 1,2,3,4,6,8,9,10,11,13-decapropyl-5,7,12,14-tetrahydropentacene was obtained as white powders (0.699 g). The isolation yield was 50%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.03-1.18 (m, 30H), 1.51-1.59 (m, 20H), 2.55 (t, $J=7.8$ Hz, 8H), 2.71 (t, $J=7.7$ Hz, 8H), 2.90 (t, $J=7.7$ Hz, 4H), 3.87 (s, 8H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.98 (2C), 15.06 (4C), 15.08 (4C), 24.29 (2C), 24.54 (4C), 25.11 (4C), 29.85 (4C), 31.93 (2C), 32.22 (4C), 32.26 (4C), 133.06 (2C), 133.66 (4C), 133.95 (4C), 135.00 (4C), 136.29 (4C). Elemental Analysis: Calcd. for $\text{C}_{52}\text{H}_{78}$: C, 88.82; H, 11.18. Found: C, 88.92; H, 11.37.

5

5,7,8,9,10,12-Hexahydro-1,2,3,4,6,11-hexapropyl-naphthacene

[0203] Using the starting material (0.456 g, 1.21 mmol), the experiment was performed by the procedures described above. By silica gel column chromatography (ethyl acetate/hexane, 1/99), 5,7,8,9,10,12-hexahydro-1,2,3,4,6,11-hexapropyl-naphthacene was obtained as a white solid (0.283 g). The isolation yield was 48%.

10


^1H NMR (CDCl_3 , Me_4Si) δ 1.04 (t, $J=7.3$ Hz, 6H), 1.09-1.13 (m, 12H), 1.47-1.58 (m, 12H), 1.76 (bs, 4H), 2.54 (t, $J=8.2$ Hz, 4H), 2.68-2.72 (m, 8H), 2.75 (bs, 4H), 3.83 (s, 4H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.98 (2C), 15.04 (2C), 15.07 (2C), 23.31 (2C), 23.41 (2C), 24.55 (2C), 25.11 (2C), 27.31 (2C), 29.67 (2C), 31.37 (2C), 32.21 (2C), 32.26 (2C), 132.54 (2C), 133.71 (2C), 134.11 (2C), 134.93 (4C), 136.23 (2C). Elemental Analysis: Calcd. for $\text{C}_{36}\text{H}_{54}$: C, 88.82; H, 11.18. Found: C, 88.68; H, 11.29.

15


REFERENCE EXAMPLE 21

[0204] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.


20



30



35



45

(wherein DMPU denotes N,N'-dimethylpropyleneurea.)

[0205] In this scheme, the following procedures were used. A solution of Cp_2ZrCl_2 (1.2 eq.) in THF was cooled to -78°C on a dry ice-acetone bath, and a solution of *n*-BuLi (2.4 eq.) in hexane was added to the solution. After the reaction solution was kept at -78°C for an hour, the alkyne was added thereto followed by elevating to room temperature. The mixture was maintained at room temperature for 1 to 3 hours thereby to form zirconacyclopentadiene. Copper (I) chloride (2.1 eq.), N,N'-dimethylpropyleneurea (DMPU) (3.0 eq.) and diiodobenzene (1.0 eq.) were added to a THF solution of zirconacyclopentadiene (1.0 eq.) at room temperature. After stirring at 50°C for 24 hours, the mixture was treated with 3N hydrochloric acid. The mixture was extracted with an appropriate solvent, and the organic layers were combined in one, and then washed with saturated sodium hydrogencarbonate and brine. After drying over magnesium sulfate, the solvent was removed through an evaporator and the residue was suitably purified to give the coupling product.

55

EP 1 262 469 A1

5,12-Dihydro-1,2,3,4,6,11 -hexapropyl-naphthacene

[0206] Using the starting material (0.813 g, 2.00 mmols), the experiment was performed by the procedures described above. By silica gel column chromatography (ethyl acetate/hexane, 1/99), 5,12-dihydro-1,2,3,4,6,11-hexapropyl-naphthacene was obtained as an orange solid (0.474 g). The isolation yield was 49%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.14-1.19 (m, 18H), 1.48-1.79 (m, 12H), 2.57 (t, $J=8.4$ Hz, 4H), 2.76 (t, $J=8.4$ Hz, 4H), 3.20 (t, $J=8.3$ Hz, 4H), 4.04 (s, 4H), 7.42 (dd, $J=3.3$, 6.6 Hz, 2H), 8.05 (dd, $J=3.3$, 6.6 Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.88 (2C), 15.06 (2C), 15.10 (2C), 24.29 (2C), 24.69 (2C), 25.08 (2C), 30.42 (2C), 30.98 (2C), 32.26 (2C), 32.35 (2C), 124.47 (4C), 131.03 (2C), 131.92 (2C), 134.11 (2C), 134.26 (2C), 135.03 (2C), 136.57 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{36}\text{H}_{50}$ 482.3913, Found: 482.3902.

1,2,3,4,6,8,13,15-Octapropyl-5,7,14,16-tetrahydrohexene

[0207] Using the starting material (0.296 g, 0.500 mmol), the experiment was performed by the procedures described above. After hexane was added and washing was thoroughly made, the mixture was filtered. Further by washing with ethanol, 1,2,3,4,6,8,13,15-octapropyl-5,7,14,16-tetrahydrohexene of high purity was obtained as light orange powders (0.158 g). The isolation yield was 47%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.05 (t, $J=7.3$ Hz, 6H), 1.12-1.23 (m, 18H), 1.48-1.79 (m, 16H), 2.56 (t, $J=8.3$ Hz, 4H), 2.72 (t, $J=8.3$ Hz, 4H), 2.97 (t, $J=8.3$ Hz, 4H), 3.21 (t, $J=8.2$ Hz, 4H), 3.89 (s, 4H), 4.09 (s, 4H), 7.41 (dd, $J=3.3$, 6.5 Hz, 2H), 8.05 (dd, $J=3.3$, 6.5 Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.87 (2C), 14.98 (2C), 15.08 (4C), 24.31 (2C), 24.46 (2C), 24.58 (2C), 25.12 (2C), 29.93 (2C), 30.39 (2C), 30.96 (2C), 31.97 (2C), 32.24 (2C), 32.29 (2C), 124.48 (4C), 131.03 (2C), 131.95 (2C), 133.12 (2C), 133.73 (2C), 133.94 (2C), 134.02 (2C), 134.15 (2C), 135.02 (2C), 136.36 (2C). Elemental Analysis: Calcd. for $\text{C}_{50}\text{H}_{68}$: C, 89.76; H, 10.24. Found: C, 89.62; H, 10.30.



1,2,3,4,6,13 -Hexahydro-5,7,12,14-tetrapropylpentacene

[0208] Using the starting material (0.377 g, 1.0 mmol), the experiment was performed by the procedures described above. By silica gel column chromatography (ethyl acetate/hexane, 1/99), 1,2,3,4,6,13-hexahydro-5,7,12,14-tetrapropylpentacene was obtained as orange needle-like crystals (0.085 g). The isolation yield was 19%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.14 (t, $J=7.3$ Hz, 6H), 1.17 (t, $J=7.5$ Hz, 6H), 1.56-1.62 (m, 4H), 1.71-1.77 (m, 8H), 2.74-2.78 (m, 8H), 3.19 (t, $J=8.2$ Hz, 4H), 4.06 (s, 4H), 7.41 (dd, $J=3.2$, 6.5 Hz, 2H), 8.05 (dd, $J=3.2$, 6.5 Hz, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.88 (2C), 15.00 (2C), 23.27 (2C), 23.56 (2C), 24.29 (2C), 27.37 (2C), 30.19 (2C), 30.94 (2C), 31.37 (2C), 124.43 (2C), 124.49 (2C), 131.01 (2C), 131.94 (2C), 132.82 (2C), 133.59 (2C), 134.17 (2C), 135.03 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{34}\text{H}_{44}$ 452.3443, Found: 452.3437.

REFERENCE EXAMPLE 22

[0209] The hydrocarbon condensed rings can be produced by the scheme below. The hydrocarbon condensed rings can be further aromatized to give the polyacenes.



(wherein DMPU denotes N,N'-dimethylpropyleneurea).

30 **[0210]** In this scheme, the following procedures were used. A solution of Cp_2ZrCl_2 (2.4 eq.) in THF was cooled to $-78^\circ C$ on a dry ice-acetone bath, and a solution of *n*-BuLi (4.8 eq.) in hexane was added to the solution. After the reaction solution was kept at $-78^\circ C$ for an hour, the alkyne was added thereto followed by elevating to room temperature. The mixture was maintained at room temperature for 1 to 3 hours thereby to form zirconacyclopentadiene; Copper (I) chloride (4.2 eq.), N,N'-dimethylpropyleneurea (DMPU) (6.0 eq.) and tetraiodobenzene (1.0 eq.) were added to a THF solution of zirconacyclopentadiene (2.0 eq.) at room temperature. After stirring at $50^\circ C$ for 24 hours, the mixture was treated with 3N hydrochloric acid. The mixture was extracted with an appropriate solvent, and the organic layers were combined in one, and then washed with saturated sodium hydrogencarbonate and brine. After drying over magnesium sulfate, the solvent was removed through an evaporator and the residue was suitably purified to give the coupling product.

40 1,2,3,4,6,8,10,11,12,13,15,17-Dodecapropyl-5,9,14,18-tetrahydroheptacene

45 **[0211]** Using the starting material (0.606 g, 1.49 mmol), the experiment was performed by the procedures described above. By recrystallization from a solvent mixture of chloroform/methanol, 1,2,3,4,6,8,10,11,12,13,15,17-dodecapropyl-5,9,14,18-tetrahydroheptacene was obtained as light yellow powders (0.165 g). The isolation yield was 25%.

1H NMR ($CDCl_3$, Me_4Si) δ 1.06 (t, $J=7.2$ Hz, 12H), 1.18 (t, $J=7.2$ Hz, 12H), 1.25 (t, $J=7.3$ Hz, 12H), 1.50-1.67 (m, 16H), 1.83-1.89 (m, 8H), 2.57 (t, $J=8.4$ Hz, 8H), 2.78 (t, $J=8.3$ Hz, 8H), 3.35 (t, $J=7.9$ Hz, 8H), 4.09 (s, 8H), 8.76 (s, 2H); ^{13}C NMR ($CDCl_3$, Me_4Si) δ 15.08 (8C), 15.11 (4C), 24.33 (4C), 24.79 (4C), 25.10 (4C), 30.62 (4C), 31.45 (4C), 32.28 (4C), 32.39 (4C), 119.50 (2C), 128.96 (4C), 131.21 (4C), 133.24 (4C), 134.34 (4C), 135.02 (4C), 136.57 (4C). Elemental Analysis: Calcd. for $C_{66}H_{94}$: C, 89.32; H, 10.68. Found: C, 89.03; H, 10.62.

1,2,3,4,6,10,12,13,14,15,17,21-Dodecahydro-5,7,9,11,16,18,20,22-octapropylonene

55 **[0212]** Using the starting material (0.753 g, 2.0 mmols), the experiment was performed by the procedures described above. After ether was added and washing was thoroughly made, the mixture was filtered, and 1,2,3,4,6,8,10,11,12,13,15,17-dodecapropyl-5,9,14,18-tetrahydroheptacene of high purity was obtained as a light green solid (0.062 g). The isolation yield was 7%.


1H NMR($CDCl_3$, Me_4Si) δ 1.16 (t, $J=7.2$ Hz, 12H), 1.25 (t, $J=7.2$ Hz, 12H), 1.58-1.64 (m, 8H), 1.78 (bs, 8H),

1.83-1.88 (m, 8H), 2.78-2.81 (m, 16H), 3.35 (t, J=8.0 Hz, 8H), 4.11 (s, 8H), 8.76 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.99 (4C), 15.05 (4C), 23.31 (4C), 23.65(4C), 24.32 (4C), 27.40 (4C), 30.40 (4C), 31.39 (4C), 119.47 (2C), 128.94 (4C), 131.22 (4C), 132.84 (4C), 133.16 (4C), 133.82 (4C), 135.00 (4C). High resolution mass spectrometer: Calcd. for $\text{C}_{62}\text{H}_{82}$ 826.6412, Found: 826.6389.

[0213] In the scheme described above, 2 equivalents of zirconacyclopenta[b]tetrahydronaphthalene or 2 equivalents of zirconacylopenta[b]hexahydroanthracene and 1 equivalent of 1,2,4,5-tetraiodobenzene undergo coupling reaction. The ratio of these reactants can be changed, and the coupling between 1 equivalent of zirconacyclopenta[b]tetrahydronaphthalene or 1 equivalent of zirconacylopenta[b]hexahydroanthracene and 1 equivalent of 1,2,4,5-tetraiodobenzene can provide the hydrocarbon condensed rings with iodine at the ortho-position of the terminal 6-membered ring. Alternatively, 2,3,6,7-tetraiodonaphthalene, 2,3,6,7-tetraiodoanthracene, 2,3,8,9-tetraiodotetracene, etc. may be used, in place of 1,2,4,5-tetraiodobenzene. These hydrocarbon condensed rings can be further aromatized to give polyacenes.

REFERENCE EXAMPLE 23

[0214]




9,10-Dipropyl-2,3-diiodo-5,6,7,8-tetrahydroanthracene

[0215] To a solution of bis(η^5 -cyclopentadienyl)dichlorozirconium (0.175 g, 0.6 mmol) in THF (25 ml), n-butyl lithium (0.75 ml, 1.2 mmol, 1.6 mol/l) was added at -78°C . After stirring the solution for an hour, 4,10-tetradecadiyne (0.095 ml, 0.5 mmol) was added to the solution. A cooling bath was withdrawn, and the mixture was stirred for an hour. Tetraiodobenzene (0.582 g, 1.0 mmol), DMPU (0.18 ml, 1.5 mmol) and CuCl (0.104 g, 1.1 mmol) were added to the mixture. After stirring at 50°C for an hour, 3N hydrochloric acid was added to terminate the reaction. Next, the mixture was extracted with ether followed by washing with sodium hydrogencarbonate aqueous solution and brine. After concentrating under reduced pressure, the residue was subjected to column chromatography using silica gel as the packing material to give the title compound (0.148 g) as a colorless solid. The isolation yield was 57%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.07 (t, J=7.4 Hz, 6H), 1.51-1.63 (m, 4H), 1.79-1.83 (m, 4H), 2.83-2.89 (m, 8H), 8.47 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.68 (2C), 22.80 (2C), 23.36 (2C), 27.81 (2C), 29.86 (2C), 102.38 (2C), 131.58 (2C), 132.88 (2C), 135.16 (2C), 135.29 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{20}\text{H}_{24}\text{I}_2$ 517.9968, Found: 517.9963.

REFERENCE EXAMPLE 24

[0216]



9,10-Dipropyl-2,3-diiodoanthracene


[0217] 9,10-Dipropyl-2,3-diiodo-5,6,7,8-tetrahydroanthracene (0.259 g, 0.5 mmol), 2,3-dichloro-5,6-dicyanobenzoquinone (0.341 g, 1.5 mmol) and 1,4-dioxane (3 ml) were charged in a reactor. Then, the mixture was refluxed for an hour. After cooling, the precipitates were removed by filtration. The solvent in the mixture was removed in vacuum. Column chromatography (hexane) was performed to give the title compound (0.109 g) as a light yellow solid. The

isolation yield was 42%.

^1H NMR (CDCl_3 , Me_4Si) δ 1.12 (t, $J=7.4$ Hz, 6H), 1.73-1.85 (m, 4H), 3.41 (t, $J=8.1$ Hz, 6H), 7.50 (dd, $J=7.1$, 6.6 Hz, 2H), 8.23 (dd, $J=7.1$, 6.6 Hz, 2H), 8.79 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.67 (2C), 24.65 (2C), 29.87 (2C), 103.11 (2C), 125.33 (2C), 125.69 (2C), 129.72 (2C), 130.08 (2C), 133.19 (2C), 136.19 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{20}\text{H}_{20}\text{I}_2$: 513.9655, Found: 513.9664.

EXAMPLE 4

[0218]




5,14-Bis(p-bromophenyl)-7,12-dipropyl-1,2,3,4-tetrahydropentacene

[0219] 1,8-Bis(p-bromophenyl)-1,7-octadiyne (0.191 g, 0.459 mmol) was added at -78°C to a THF solution of bis(η^5 -cyclopentadienyl)dibutylzirconium in THF, which was prepared from bis(η^5 -cyclopentadienyl)dichlorozirconium (0.161 g, 0.551 mmol) and *n*-butyl lithium (0.7 ml, 1.6 M, 1.1 mol/l). The mixture was then allowed to stand at room temperature for an hour. CuCl (0.095 g, 0.964 mmol), DMPU (0.17 ml, 1.38 mmol) and 2,3-diiodo-9,10-dipropylanthracene (0.236 g, 0.459 mmol) were added to the mixture. After heating at 50°C for an hour, the solvent in the mixture was removed in vacuum. Column chromatography (chloroform) was performed. By recrystallization in chloroform/methanol, the title compound (0.177 g) was obtained as orange red. The isolation yield was 57%.

^1H NMR (CDCl_3 , Me_4Si) δ 0.93 (t, $J=7.2$ Hz, 6H), 1.60-1.76 (m, 8H), 2.72 (bs, 4H), 3.33 (t, $J=8.0$ Hz, 4H), 7.29-7.35 (m, 6H), 7.74 (d, $J=8.1$ Hz, 4H), 8.18 (dd, $J=6.9$, 3.3 Hz, 2H), 8.27 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.51 (2C), 22.83 (2C), 24.45 (2C), 29.30 (2C), 30.52 (2C), 121.23 (2C), 122.16 (2C), 124.34 (2C), 125.27 (2C), 127.70 (2C), 128.67 (2C), 129.78 (2C), 131.83 (4C), 132.13 (4C), 133.26 (2C), 133.66 (2C), 135.74 (2C), 139.04 (2C).

REFERENCE EXAMPLE 25

[0220]



Dimethyl 3,4,5,6-tetrapropylphthalate

[0221] 4-Octyne (5.9 ml, 40.0 mmols) was added at -78°C to a 70 ml THF solution of bis(η^5 -cyclopentadienyl)dibutylzirconium, which was prepared from bis(η^5 -cyclopentadienyl)dichlorozirconium (7.016 g, 24.0 mmols) and *n*-butyl lithium (31.6 ml, 48.0 mmols, 1.52 M). After elevating to room temperature, the reaction mixture was stirred for an hour. DMAD (dimethyl acetylenedicarboxylate) (7.4 ml, 60.0 mmols) and CuCl (3.96 g, 40.0 mmols) were added to the reaction mixture at room temperature. After stirring for an hour, 3N HCl was added for hydrolysis and the mixture was


EP 1 262 469 A1

extracted with hexane. Then, the extract was washed with sodium hydrogencarbonate aqueous solution and brine. After the extract was dried over anhydrous magnesium sulfate, column chromatography was performed using silica gel as the packing material to give the title compound (4.917 g) as light yellow oil. The GC yield was 82% and the isolation yield was 74%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 0.97 (t, $J=7.2$ Hz, 6H), 1.04 (t, $J=7.3$ Hz, 6H), 1.45-1.57 (m, 8H), 2.56-2.62 (m, 8H), 3.83(s, 6H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.68 (2C), 14.86 (2C), 24.60 (2C), 24.99 (2C), 31.70 (2C), 32.59 (2C), 52.06 (2C), 130.34 (2C), 136.84 (2C), 142.11 (2C), 169.73 (2C).

REFERENCE EXAMPLE 26

[0222]




1,2-Bis(hydroxymethyl)-3,4,5,6-tetrapropylbenzene

[0223] Dimethyl 3,4,5,6-tetrapropylphthalate (5.22 g, 14.4 mmols) was added at 0°C to a 50 ml THF solution of LiAlH_4 (1.20 g, 31.7 mmols). After stirring at room temperature for an hour, water was added for hydrolysis. The mixture was treated with 2N H_2SO_4 followed by extraction with diethyl ether. Subsequently, the extract was washed with brine and dried over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (3.67 g) as a white solid. The isolation yield was 91%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.05 (t, $J=7.3$ Hz, 6H), 1.05 (t, $J=7.3$ Hz, 6H), 1.46-1.58 (m, 8H), 2.55 (t, $J=8.4$ Hz, 4H), 2.65 (t, $J=8.4$ Hz, 4H), 3.27 (bs, 2H), 4.76 (s, 4H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.82 (2C), 15.04 (2C), 24.75 (2C), 25.64 (2C), 31.90 (2C), 32.39 (2C), 59.82 (2C), 136.17 (2C), 138.10 (2C), 139.58 (2C).

REFERENCE EXAMPLE 27

[0224]




1,2-Bis(bromomethyl)-3,4,5,6-tetrapropylbenzene

[0225] Tribromophosphine (0.54 ml, 5.70 mmols) was dropwise added to 20 ml of a chloroform solution of 1,2-bis(hydroxymethyl)-3,4,5,6-tetrapropylbenzene (1.75 g, 5.70 mmols) at room temperature. After stirring for an hour, the mixture was treated with water followed by extracting with chloroform. Subsequently, the extract was washed with sodium hydrogencarbonate aqueous solution and brine, followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (1.866 g) as a white solid. The GC yield was 100% and the isolation yield was 87%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.03-1.10 (m, 12H), 1.47-1.59 (m, 8H), 2.52 (t, $J=8.3$ Hz, 4H), 2.66 (t, $J=8.2$ Hz, 4H), 4.71 (s, 4H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.99 (2C), 15.07 (2C), 24.67 (2C), 25.00 (2C), 29.04 (2C), 31.85 (2C), 32.17 (2C), 132.70 (2C), 139.20 (2C), 141.00 (2C). Elemental Analysis: Calcd. for $\text{C}_{20}\text{H}_{32}\text{Br}_2$: C, 55.57; H, 7.46; Br, 36.97. Found: C, 55.46; H, 7.40; Br, 36.98.

REFERENCE EXAMPLE 28

[0226]




1,2-Bis(2-hexynyl)-3,4,5,6-tetrapropylbenzene

[0227] n-Butyl lithium (9.7 ml, 15.56 mmols, 1.6 M) was added to a 30 ml THF solution of 1-pentyne (1.67 ml, 17.12 mmols) at -78°C , and the mixture was stirred at room temperature for an hour. 1,2-Bis(bromomethyl)-3,4,5,6-tetrapropylbenzene (1.68 g, 3.89 mmols) and DMPU (1.9 ml, 15.56 mmols) were added to the mixture at room temperature. After stirring for an hour, 3N HCl was added to terminate the reaction. The reaction mixture was extracted with hexane. The extract was then washed with sodium hydrogencarbonate aqueous solution and brine, followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (1.520 g) as a white solid. The GC yield was 100% and the isolation yield was 97%

^1H NMR (CDCl_3 , Me_4Si) δ 0.93 (t, $J=7.4$ Hz, 6H), 1.05 (t, $J=7.2$ Hz, 6H), 1.06 (t, $J=7.2$ Hz, 6H), 1.43-1.61 (m, 12H), 2.07 (tt, $J=2.2, 7.1$ Hz, 4H), 2.51 (t, $J=8.4$ Hz, 4H), 2.61 (t, $J=8.5$ Hz, 4H), 3.59 (t, $J=2.2$ Hz, 4H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 13.48 (2C), 15.03 (2C), 15.15 (2C), 19.40 (2C), 20.99 (2C), 22.36 (2C), 24.46 (2C), 24.80 (2C), 32.33 (2C), 32.41 (2C), 78.58 (2C), 80.34 (2C), 132.92 (2C), 137.21 (2C), 137.94 (2C). Elemental Analysis: Calcd. for $\text{C}_{30}\text{H}_{46}$: C, 88.60; H, 11.40. Found: C, 88.49; H, 11.47. High resolution mass spectrometer: Calcd. for $\text{C}_{30}\text{H}_{46}$ 406.3600, Found: 406.3626.

REFERENCE EXAMPLE 29

[0228]




6,11-Dihydro-2,3-diiodo-5,7,8,9,10,12-hexapropylnaphthacene

[0229] n-Butyl lithium (3.0 ml, 4.8 mmols, 1.6 mol/l) was added to a THF solution (20 ml) of Cp_2ZrCl_2 (0.702 g, 2.4 mmols) at -78°C . After the mixture was stirred for an hour, 1,2-bis(2-hexynyl)-3,4,5,6-tetrapropylbenzene (0.813 g, 2.0 mmols) was added to the mixture. A cooling bath was withdrawn, and the mixture was stirred for an hour. Tetraiodobenzene (1.16 g, 2.0 mmols), DMPU (0.73 ml, 6.0 mmols) and CuCl (0.416 g, 4.2 mmols) were added to the mixture. After stirring for an hour at 50°C , 3N HCl was added to terminate the reaction. The reaction mixture was extracted with chloroform. The extract was then washed with sodium hydrogencarbonate aqueous solution and brine. After the pressure was reduced, column chromatography was performed using silica gel as the packing material to give the title compound (0.477 g) as a pink solid. The isolation yield was 33%

^1H NMR (CDCl_3 , Me_4Si) δ 1.06 (t, $J=7.2$ Hz, 6H), 1.15 (t, $J=7.2$ Hz, 12H), 1.49-1.72 (m, 12H), 2.56 (t, $J=8.4$ Hz, 4H), 2.74 (t, $J=8.4$ Hz, 4H), 3.07 (t, $J=8.1$ Hz, 4H), 3.98 (s, 4H), 8.52 (s, 2H); ^{13}C NMR (CDCl_3 , Me_4Si) δ 14.78 (2C), 15.07 (2C), 15.13 (2C), 24.25 (2C), 24.68 (2C), 25.04 (2C), 30.47 (2C), 30.59 (2C), 32.21 (2C), 32.34 (2C), 102.71 (2C), 131.01 (2C), 131.97 (2C), 133.47 (2C), 135.09 (2C), 135.50 (2C), 136.08 (2C), 136.84 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{36}\text{H}_{48}\text{I}_2$ 734.1846, Found: 734.1826.

EXAMPLE 5


[0230]

2,3-Diiodo-5,7,8,9,10,12-hexapropylnaphthacene

[0231] 6,11-Dihydro-5,7,8,9,10,12-hexapropyl-2,3-diiodonaphthacene (0.238 g, 0.324 mmol), 2,3-dichloro-5,6-dicyanobenzoquinone (0.081 g, 0.35 mmol) and 1,4-dioxane (2 ml) were charged in a reactor. The mixture was refluxed for 3 hours. After cooling, the precipitates were removed by filtration. The solvent in the mixture was removed in vacuum followed by recrystallization from chloroform/methanol. The orange red title compound (0.081 g) was obtained. The isolation yield was 34%.

¹H NMR (CDCl₃, Me₄Si) δ 1.13 (t, J=7.4 Hz, 6H), 1.21 (t, J=7.2 Hz, 6H), 1.24 (t, J=7.2 Hz, 6H), 1.60-1.67 (m, 4H), 1.80-1.95 (m, 8H), 2.79 (t, J=8.3 Hz, 4H), 3.19 (t, J=8.1 Hz, 4H), 3.60 (t, J=8.0 Hz, 4H), 8.82 (s, 2H), 8.99 (s, 2H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.87 (2C), 15.02 (2C), 15.09 (2C), 24.43 (2C), 24.82 (2C), 24.88 (2C), 30.49 (2C), 31.76 (2C), 32.85 (2C), 102.09 (2C), 120.37 (2C), 127.87 (2C), 128.74 (2C), 130.13 (2C), 133.01 (2C), 133.43 (2C), 136.37 (2C), 137.13 (2C). High resolution mass spectrometer: Calcd. for C₃₆H₄₆I₂: 732.1689, Found: 732.1709.

REFERENCE EXAMPLE 30


[0232]

Dimethyl 1,4-dipropyl-5,6,7,8-tetrahydronaphthalene-2,3-dicarboxylate

[0233] 4,10-Tetradodecadiyne (9.14 g, 48.03 mmols) was added at -78°C to a 200 ml THF solution of bis(η⁵-cyclopentadienyl)dibutylzirconium, which was prepared from bis(η⁵-cyclopentadienyl)dichlorozirconium (16.849 g, 57.64 mmols) and n-butyl lithium (75.8 ml, 115.3 mmols, 1.52 M). After elevating to room temperature, the reaction mixture was stirred for an hour. DMAD (17.4 ml, 144.01 mmols) and CuCl (9.51 g, 96.06 mmols) were added to the reaction mixture at room temperature. After stirring for an hour, 3N HCl was added for hydrolysis and the mixture was extracted with hexane. The extract was then washed with sodium hydrogencarbonate aqueous solution and brine, followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (8.133 g) as colorless crystals by recrystallization from methanol. The GC yield was 58% and the isolation yield was 51%.

¹H NMR (CDCl₃, Me₄Si) δ 0.96 (t, J=7.3 Hz, 6H), 1.50-1.56 (m, 4H), 1.76 (bs, 4H), 2.59 (t, J=8.2 Hz, 4H), 2.74 (bs, 4H), 3.82 (s, 6H); ¹³C NMR (CDCl₃, Me₄Si) δ 14.46 (2C), 22.41 (2C), 23.53 (2C), 26.80 (2C), 31.96 (2C), 51.93 (2C), 129.56 (2C), 136.75 (2C), 138.41 (2C), 169.50 (2C). Elemental Analysis: Calcd. for C₂₀H₂₈O₄: C, 72.26; H, 8.49. Found: C, 72.06; H, 8.60.

REFERENCE EXAMPLE 31


[0234]

Dimethyl 1,4-dipropyl-5,6-dicyanobenzoate

[0235] 2,3-Dichloro-5,6-dicyanobenzoquinone (1.362 g, 6.0 mmols) was added to a solution of dimethyl 1,4-dipropyl-5,6,7,8-tetrahydronaphthalene-2,3-dicarboxylate (0.665 g, 2.0 mmols) in benzene (20 ml). The mixture was then refluxed for 24 hours. After filtration, the solvent in the mixture was removed in vacuum. Column chromatography was performed using silica gel as the packing material to give the title compound (0.464 g) as colorless crystals. The GC yield was 87% and the isolation yield was 71%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.05 (t, $J=7.4$ Hz, 6H), 1.71-1.81 (m, 4H), 3.07 (t, $J=8.1$ Hz, 4H), 3.91 (s, 6H), 7.60 (dd, $J=3.4, 6.5$ Hz, 2H), 8.12 (dd, $J=3.4, 6.5$ Hz, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.52 (2C), 24.64 (2C), 32.20 (2C), 52.26 (2C), 125.53 (2C), 127.28 (2C), 128.25 (2C), 132.42 (2C), 136.85 (2C), 169.53 (2C). Elemental Analysis: Calcd. for $\text{C}_{20}\text{H}_{24}\text{O}_4$: C, 73.15; H, 7.37. Found: C, 73.10; H, 7.44.

25 REFERENCE EXAMPLE 32

[0236]


2,3-bis(hydroxymethyl)-1,4-dipropyl-5,6-dicyanobenzoate

[0237] Dimethyl 1,4-dipropyl-5,6-dicyanobenzoate (0.295 g, 0.898 mmol) was added to a 5 ml THE solution of LiAlH_4 (0.075 g, 1.98 mmol) at 0°C . After stirring at room temperature for an hour, water was added to effect hydrolysis. The mixture was treated with 2N H_2SO_4 followed by extraction with diethyl ether. The extract was washed with brine and dried over anhydrous magnesium sulfate. The extract was concentrated under reduced pressure. The title compound (0.219 g) was obtained as a white solid. The isolation yield was 90%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ (t, $J=7.3$ Hz, 6H), 1.59-1.67 (m, 4H), 3.08 (t, $J=8.2$ Hz, 4H), 3.51 (bs, 2H), 4.87 (s, 4H), 7.47 (dd, $J=3.3, 6.5$ Hz, 2H), 8.04 (dd, $J=3.3, 6.5$ Hz, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.52 (2C), 24.96 (2C), 31.52 (2C), 59.71 (2C), 125.05 (2C), 125.77 (2C), 132.12 (2C), 134.53 (2C), 136.48 (2C). Elemental Analysis: Calcd. for $\text{C}_{18}\text{H}_{24}\text{O}_2$: C, 79.37; H, 8.88. Found: C, 79.43; H, 9.01.

REFERENCE EXAMPLE 33

[0238]




2,3-Bis(bromomethyl)-1,4-dipropylnaphthalene

[0239] Tribromophosphine (0.04 ml, 0.42 mmol) was dropwise added to a 5 ml chloroform solution of 2,3-bis(hydroxymethyl)-1,4-dipropylnaphthalene (0.109 g, 0.40 mmol) at room temperature. After stirring for an hour, the mixture was treated with water followed by extracting with chloroform. The extract was washed with sodium hydrogencarbonate aqueous solution and brine, followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (0.115 g) as a white solid. The isolation yield was 72%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.14 (t, $J=7.3$ Hz, 6H), 1.75 (bs, 4H), 3.12 (t, $J=8.3$ Hz, 4H), 4.92 (s, 4H), 7.49 (dd, $J=3.3, 6.5$ Hz, 2H), 8.02 (dd, $J=3.3, 6.5$ Hz, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.77 (2C), 24.37 (2C), 29.01 (2C), 31.11 (2C), 125.17 (2C), 126.59 (2C), 130.91 (2C), 132.44 (2C), 138.44 (2C). Elemental Analysis: Calcd. for $\text{C}_{18}\text{H}_{22}\text{Br}_2$: C, 54.30; H, 5.57; Br, 40.13, Found: C, 54.21; H, 5.57; Br, 40.24.

REFERENCE EXAMPLE 34

[0240]




2,3-Bis(2-hexynyl)-1,4-dipropylnaphthalene

[0241] *n*-Butyl lithium (7.6 ml, 19.1 mmols, 2.52 M) was added to a 30 ml THF solution of 1-pentyne (2.05 ml, 21.06 mmols) at -78°C , and the mixture was stirred at room temperature for an hour. 2,3-Bis(bromomethyl)-1,4-dipropylnaphthalene (1.91 g, 4.79 mmols) and DMPU (2.3 ml, 19.1 mmols) were added to the mixture at room temperature. After stirring for an hour, the mixture was treated with 3N HCl and extracted with hexane. The extract was then washed with sodium hydrogencarbonate aqueous solution and brine, followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (1.66 g) as a white solid. The isolation yield was 93%

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) 0.91 (t, $J=7.4$ Hz, 6H), 1.12 (t, $J=7.3$ Hz, 6H), 1.40-1.49 (m, 4H), 1.68-1.78 (m, 4H), 2.07 (tt, $J=2.1, 7.0$ Hz, 4H), 3.10 (t, $J=8.3$ Hz, 4H), 3.84 (t, $J=2.1$ Hz, 4H), 7.41 (dd, $J=3.3, 6.5$ Hz, 2H), 8.01 (dd, $J=3.3, 6.5$ Hz, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 13.43 (2C), 14.77 (2C), 19.96 (2C), 20.88 (2C), 22.32 (2C), 24.11 (2C), 31.40 (2C), 78.25 (2C), 80.95 (2C), 124.64 (2C), 125.02 (2C), 131.66 (2C), 132.48 (2C), 134.99 (2C). Elemental Analysis: Calcd. for $\text{C}_{28}\text{H}_{36}$: C, 90.26; H, 9.74. Found: C, 90.13; H, 9.86.

REFERENCE EXAMPLE 35

[0242]




5,12-Dihydro-1,2,3,4,6,11-hexapropylnaphthacene

[0243] 2,3-Bis(2-hexynyl)-1,4-dipropylnaphthalene (0.373 g, 1.0 mmol) was added at -78°C to a 20 ml THF solution of bis(η^5 -cyclopentadienyl)dibutylzirconium, which was prepared from bis(η^5 -cyclopentadienyl)dichlorozirconium (0.351 g, 1.2 mmol) and n-butyl lithium (1.5 ml, 2.4 mmols, 1.6 M). After elevating to room temperature, the reaction mixture was stirred for an hour. 4-Octyne (0.22 ml, 1.5 mmol) and $\text{NiBr}_2(\text{PPh}_3)_2$ (0.892 g, 1.2 mmol) were added to the reaction mixture at room temperature. After stirring for 24 hours, hydrolysis was effected by 3N HCl followed by extraction with hexane. The extract was washed with sodium hydrogencarbonate aqueous solution and brine followed by drying over anhydrous magnesium sulfate. Column chromatography was performed using silica gel as the packing material to give the title compound (0.224 g) as somewhat orange powders by floured with ethanol. The isolation yield was 46%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.14-1.19 (m, 18H), 1.48-1.79 (m, 12H), 2.57 (t, $J=8.4$ Hz, 4H), 2.76 (t, $J=8.4$ Hz, 4H), 3.20 (t, $J=8.3$ Hz, 4H), 4.04 (s, 4H), 7.42 (dd, $J=3.3, 6.6$ Hz, 2H), 8.05 (dd, $J=3.3, 6.6$ Hz, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) δ 14.88 (2C), 15.06 (2C), 15.10 (2C), 24.29 (2C), 24.69 (2C), 25.08 (2C), 30.42 (2C), 30.98 (2C), 32.26 (2C), 32.35 (2C), 124.47 (2C), 131.03 (2C), 131.92 (2C), 134.11 (2C), 134.26 (2C), 135.03 (2C), 136.57 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{36}\text{H}_{50}$ 482.3913, Found: 482.3902.

EXAMPLE 6

[0244]



1,2,3,4,6,11 -Hexapropylnaphthacene

[0245] 5,12-Dihydro-1,2,3,4,6,11-hexapropylnaphthacene (0.503 g, 1.04 mmol), 2,3-dichloro-5,6-dicyanobenzoquinone (0.260 g, 1.14 mmol) and 1,4-dioxane (3 ml) were charged in a reactor. The mixture was refluxed for 24 hours. After cooling, the precipitates were removed by filtration. The solvent in the mixture was removed in vacuum followed by recrystallization from chloroform/methanol. The orange red title compound (0.112 g) was obtained. The NMR yield was 36% and the isolation yield was 22%.

$^1\text{H NMR}$ (CDCl_3 , Me_4Si) δ 1.12 (t, $J=7.3$ Hz, 6H), 1.25 (t, $J=7.4$ Hz, 6H), 1.27 (t, $J=7.3$ Hz, 6H), 1.63-1.69 (m, 4H), 1.85-2.01 (m, 8H), 2.80 (t, $J=8.4$ Hz, 4H), 3.23 (t, $J=8.3$ Hz, 4H), 3.75 (t, $J=8.1$ Hz, 4H), 7.40 (dd, $J=7.1, 3.2$ Hz, 2H), 8.30 (dd, $J=7.1, 3.2$ Hz, 2H), 9.06 (s, 2H); $^{13}\text{C NMR}$ (CDCl_3 , Me_4Si) 14.99 (2C), 15.06 (2C), 15.14 (2C), 24.40 (2C), 24.76 (2C), 24.91 (2C), 30.74 (2C), 31.81 (2C), 32.62 (2C), 32.83 (2C), 120.03 (2C), 124.09 (2C), 125.35 (2C), 127.62 (2C), 128.55 (2C), 129.42 (2C), 133.30 (2C), 133.36 (2C), 136.33 (2C). High resolution mass spectrometer: Calcd. for $\text{C}_{36}\text{H}_{48}$: 480.3756, Found: 480.3747.

[0246] According to the present invention, the solubility of polyacenes can be improved by introducing substituents into the polyacenes on the side chains. Since various substituents can be introduced, the side chains of polyacenes can be modified in various ways and their physical properties can be altered depending upon use.

[0247] Heretofore, there was a tendency that the solubility gradually decreases as the number of aromatic rings in


condensed polycyclic aromatic compounds increases. In the present invention, however, the solubility can be maintained by introducing a variety of substituents, even if the number of aromatic rings in condensed polycyclic aromatic compounds increases. Therefore, latitude in synthesis of various condensed polycyclic aromatic compounds can be markedly improved.

5

Claims

1. A polyacene derivative represented by general formula (I) below:

10



15

20

(wherein:

each of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

25

30

35

40

n is an integer of not less than 1;

with proviso that, except for the case wherein R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all hydrogen atoms;

when n is 1,

at least R¹, R², R⁴ and R⁹ are groups other than hydrogen atom, or at least R³, R⁵, R⁸ and R¹⁰ are groups other than hydrogen atom; and,

45

the cases of (a), (b), (c) and (d) below are excluded:

(a) when R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all methyl groups;

(b) when R³, R⁴, R⁹ and R¹⁰ are all aryl groups that may optionally be substituted;

50


(c) when R¹, R², R⁴ and R⁹ are all alkoxy or aryloxy groups, and R³, R⁵, R⁶, R⁷, R⁸, R¹⁰, A¹ and A² are all hydrogen atoms;

(d) when R³, R⁵, R⁸ and R¹⁰ are all alkoxy or aryloxy groups, and R¹, R², R⁴, R⁶, R⁷, R⁹, A¹ and A² are all hydrogen atoms;

55


and, when n is 2, the cases of (a'), (b'), (c') and (d') below are excluded:

(a') a pentacene derivative represented by formula (Ia) below:




10 wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are all methyl groups; or R¹, R², R³, R⁴, R^{5a}, R^{5b}, R^{8a}, R^{8b}, R⁹ and R¹⁰ are all hydrogen atoms and at least one of R⁶, R⁷, A¹ and A² is an aryl group; or at least one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² is a diarylamine group;

(b') a pentacene derivative represented by formula (1b) below:




25 wherein R¹, R², R^{5b} and R^{8b} are all alkoxy or aryloxy groups;

(c') a pentacene derivative represented by formula (1c) below:



40 wherein at least 2 of R³, R^{5a}, R^{8a} and R¹⁰ are aryl or arylalkynyl groups; or at least one of R³, R^{5a}, R^{8a} and R¹⁰ is an arylalkenyl group; or R³, R^{5a}, R^{8a} and R¹⁰ are all alkoxy or aryloxy groups;

(d') a pentacene derivative represented by formula (1d) below:




55 wherein R⁴ and R⁹ are hydrogen atom, a hydrocarbon group, an alkoxy group, an aryloxy group, a halogen atom or hydroxy group.

2. The polyacene derivative according to claim 1, wherein at least 5 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

3. The polyacene derivative according to claim 1, wherein at least 6 of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

4. The polyacene derivative according to claim 1, wherein the polyacene derivative is a pentacene derivative represented by formula (Ia):



(wherein:

15 each of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

20 each of A¹ and A², which may be the same or different, independently represents hydrogen atom; a halogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; a C₇-C₄₀ alkylaryloxy group which may optionally be substituted; a C₂-C₄₀ alkoxycarbonyl group which may optionally be substituted; a C₇-C₄₀ aryloxycarbonyl group which may optionally be substituted; cyano group (-CN); carbamoyl group (-C(=O)NH₂); a haloformyl group (-C(=O)-X, wherein X represents a halogen atom); formyl group (-C(=O)-H); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group; provided that A¹ and A² may be cross-bridged with each other to form a ring shown by formula: -C(=O)-B-C(=O)- (wherein B is oxygen atom or a group shown by formula -N(B¹)- (wherein B¹ is hydrogen atom, a C₁-C₄₀ hydrocarbon group or a halogen atom))), and,

25 at least 5 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

- 35 5. The polyacene derivative according to claim 4, wherein at least 6 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.
- 40 6. The polyacene derivative according to claim 4, wherein at least 7 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.
7. The polyacene derivative according to claim 4, wherein at least 8 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.
- 45 8. The polyacene derivative according to claim 4, wherein at least 9 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.
- 50 9. The polyacene derivative according to claim 4, wherein at least 10 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.
10. The polyacene derivative according to any one of claims 1 through 3, wherein any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R⁵ and R⁸, R⁶ and R⁷, and A¹ and A² are the same substituents.
11. The polyacene derivative according to any one of claims 4 through 9, wherein any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R^{5a} and R^{8a}, R^{5b} and R^{8b}, R⁶ and R⁷, and A¹ and A² are the same substituents.
- 55 12. The polyacene derivative according to any one of claims 1 through 3, wherein any one of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰ is a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

EP 1 262 469 A1

13. The polyacene derivative according to any one of claims 4 through 9, wherein any one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰ is a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

14. The polyacene derivative according to claim 1, wherein when n is 1, A¹ and A² are an alkoxycarbonyl group, and R¹, R², R⁴ and R⁹ are an alkyl or aryl group.

15. The polyacene derivative according to claim 1, wherein when n is 1, A¹, A², R¹, R², R⁴ and R⁹ are an alkyl or aryl group.


16. The polyacene derivative according to claim 1, wherein when n is 1, A¹ and A² are a halogen atom and R³, R⁵, R⁶, R⁷, R⁸ and R¹⁰ are an alkyl or aryl group.

17. The polyacene derivative according to claim 4, wherein when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A¹ and A² are an alkoxycarbonyl group and R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ are an alkyl or aryl group.

18. The polyacene derivative according to claim 4, wherein when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A¹, A², R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ are an alkyl or aryl group.

19. The polyacene derivative according to claim 4, wherein when the polyacene derivative is the pentacene derivative represented by the formula (Ia) above, A¹ and A² are a halogen group and R³, R^{5a}, R^{8a} and R¹⁰ are an alkyl or aryl group.


20. A process of producing the polyacene derivative represented by formula (I) below:



(wherein:

each of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted; each of A¹ and A², which may be the same or different, independently represents hydrogen atom; a halogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; a C₇-C₄₀ alkylaryloxy group which may optionally be substituted; a C₂-C₄₀ alkoxycarbonyl group which may optionally be substituted; a C₇-C₄₀ aryloxycarbonyl group which may optionally be substituted; cyano group (-CN); carbamoyl group (-C(=O)NH₂); a haloformyl group (-C(=O)-X, wherein X represents a halogen atom); formyl group (-C(=O)-H); isocyano group; isocyanate group; thiocyanate group or thioisocyanate group; provided that A¹ and A² may be cross-bridged with each other to form a ring shown by formula: -C(=O)-B-C(=O)- (wherein B is oxygen atom or a group shown by formula -N(B¹)- (wherein B¹ is hydrogen atom, a C₁-C₄₀ hydrocarbon group or a halogen atom)); and, n is an integer of not less than 1),


which comprises aromatizing hydrocarbon condensed rings represented by formula (II) below:



(wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 , A^2 and n have the same significance as defined above;
 _____ the bond shown by formula below represents a single bond or a double bond;


 provided that when the bond is a single bond, hydrogen atom is further bound directly to the carbon atoms which are directly bound to R^5 , R^6 , R^7 and R^8);
 in the presence of a dehydrogenation reagent.

21. The process of producing the polyacene derivative according to claim 20, wherein the dehydrogenation reagent is a combination of a lithium dopant and a lithium-removing reagent, and the lithium dopant is first added to the hydrocarbon condensed rings followed by adding the lithium-removing reagent.
22. The process of producing the polyacene derivative according to claim 21, wherein the lithium dopant is an alkyl lithium and the lithium-removing reagent is an alkyl halide.
23. The process of producing the polyacene derivative according to claim 20, wherein the dehydrogenation reagent is a compound represented by formula (III):



(wherein each of X^1 , X^2 , X^3 and X^4 , which may be the same or different, independently represents a halogen atom or cyano group).

24. The process of producing the polyacene derivative according to claim 20, wherein the dehydrogenation reagent contains palladium.
25. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein at least 5 of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 are groups other than hydrogen atom.
26. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein at least 6 of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , A^1 and A^2 are groups other than hydrogen atom.
27. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein the polyacene derivative is a pentacene derivative represented by formula (Ia):



(wherein:

each of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰, which may be the same or different, independently represents hydrogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; an amino group which may optionally be substituted; a hydroxy group; or a silyl group which may optionally be substituted; provided that R⁶ and R⁷ may be cross-bridged with each other to form a C₄-C₄₀ saturated or unsaturated ring, and the saturated or unsaturated ring may be intervened by oxygen atom, sulfur atom or a group shown by formula: -N(R¹¹)- (wherein R¹¹ is hydrogen atom or a hydrocarbon group), or may optionally be substituted;

each of A¹ and A², which may be the same or different, independently represents hydrogen atom; a halogen atom; a C₁-C₄₀ hydrocarbon group which may optionally be substituted; a C₁-C₄₀ alkoxy group which may optionally be substituted; a C₆-C₄₀ aryloxy group which may optionally be substituted; a C₇-C₄₀ alkylaryloxy group which may optionally be substituted; a C₂-C₄₀ alkoxycarbonyl group which may optionally be substituted; a C₇-C₄₀ aryloxy carbonyl group which may optionally be substituted; cyano group (-CN); carbamoyl group (-C(=O)NH₂); a haloformyl group (-C(=O)-X, wherein X represents a halogen atom); formyl group (-C(=O)-H); isocyanato group; isocyanate group; thiocyanate group or thioisocyanate group; provided that A¹ and A² may be cross-bridged with each other to form a ring shown by formula: -C(=O)-B-C(=O)- (wherein B is oxygen atom or a group shown by formula -N(B¹)- (wherein B¹ is hydrogen atom, a C₁-C₄₀ hydrocarbon group or a halogen atom))), and,

at least 5 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

28. The process of producing the polyacene derivative according to claim 27, wherein at least 6 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

29. The process of producing the polyacene derivative according to claim 27, wherein at least 7 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

30. The process of producing the polyacene derivative according to claim 27, wherein at least 8 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

31. The process of producing the polyacene derivative according to claim 27, wherein at least 9 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

32. The process of producing the polyacene derivative according to claim 27, wherein at least 10 of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are groups other than hydrogen atom.

33. The process of producing the polyacene derivative according to any one of claims 20 through 26, wherein any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R⁵ and R⁸, R⁶ and R⁷, and A¹ and A² are the same substituents.

34. The process of producing the polyacene derivative according to any one of claims 27 through 32, wherein any one of the combinations of R¹ and R², R³ and R¹⁰, R⁴ and R⁹, R^{5a} and R^{8a}, R^{5b} and R^{8b}, R⁶ and R⁷, and A¹ and A² are the same substituents.

35. The process of producing the polyacene derivative according to any one of claims 20 through 26, wherein any one of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹ and R¹⁰ is a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

36. The process of producing the polyacene derivative according to any one of claims 27 through 32, wherein any one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹ and R¹⁰ is a C₁-C₄₀ hydrocarbon group which may optionally be substituted, a C₁-C₄₀ alkoxy group which may optionally be substituted, or a C₆-C₄₀ aryloxy group which may optionally be substituted.

5

37. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein the case in which R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all hydrogen atoms in the formula (I) above, is excluded.

10 38. The process of producing the polyacene derivative according to any one of claims 20 through 26, wherein n is 1; at least R¹, R², R⁴ and R⁹ are groups other than hydrogen atom or at least R³, R⁵, R⁸ and R¹⁰ are groups other than hydrogen atom and the cases of (a), (b), (c) and (d) are excluded:

(a) when R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, A¹ and A² are all methyl groups;

15

(b) when R³, R⁴, R⁹ and R¹⁰ are all aryl groups that may optionally be substituted;

(c) when R¹, R², R⁴ and R⁹ are all alkoxy or aryloxy groups, and R³, R⁵, R⁶, R⁷, R⁸, R¹⁰, A¹ and A² are all hydrogen atoms;


(d) when R³, R⁵, R⁸ and R¹⁰ are all alkoxy or aryloxy groups, and R¹, R², R⁴, R⁶, R⁷, R⁹, A¹ and A² are all hydrogen atoms.

20

39. The process of producing the polyacene derivative according to claim 27, wherein the polyacene derivative is the pentacene derivative represented by formula (Ia) above, and the cases of (a'), (b'), (c') and (d') below are excluded:

(a') a pentacene derivative represented by formula (Ia) below:

25




30

wherein R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² are all methyl groups; or R¹, R², R³, R⁴, R^{5a}, R^{5b}, R^{8a}, R^{8b}, R⁹ and R¹⁰ are all hydrogen atoms and at least one of R⁶, R⁷, A¹ and A² is an aryl group; or at least one of R¹, R², R³, R⁴, R^{5a}, R^{5b}, R⁶, R⁷, R^{8a}, R^{8b}, R⁹, R¹⁰, A¹ and A² is a diarylamine group;

35

(b') a pentacene derivative represented by formula (Ib) below:

40




45

wherein R¹, R², R^{5b} and R^{8b} are all alkoxy or aryloxy groups;


50

(c') a pentacene derivative represented by formula (Ic) below:

55



10 wherein at least 2 of R³, R^{5a}, R^{8a} and R¹⁰ are aryl or arylalkynyl groups; or at least one of R³, R^{5a}, R^{8a} and R¹⁰ is an arylalkenyl group; or R³, R^{5a}, R^{8a} and R¹⁰ are all alkoxy or aryloxy groups;
 (d') a pentacene derivative represented by formula (ld) below:



25 wherein R⁴ and R⁹ are hydrogen atom, a hydrocarbon group, an alkoxy group, an aryloxy group, a halogen atom or hydroxy group.

30 **40.** The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein when n is 1, A¹ and A² are an alkoxy carbonyl group, and R¹, R², R⁴ and R⁹ are an alkyl or aryl group.

41. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein when n is 1, A¹, A², R¹, R², R⁴ and R⁹ are an alkyl or aryl group.

42. The process of producing the polyacene derivative according to any one of claims 20 through 24, wherein when n is 1, A¹ and A² are a halogen atom and R³, R⁵, R⁶, R⁷, R⁸ and R¹⁰ are an alkyl or aryl group.

35 **43.** The process of producing the polyacene derivative according to claim 27, wherein when the polyacene derivative is the pentacene derivative represented by the formula (la) above, A¹ and A² are an alkoxy carbonyl group and R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ are an alkyl or aryl group.

40 **44.** The process of producing the polyacene derivative according to claim 27, wherein when the polyacene derivative is the pentacene derivative represented by the formula (la) above, A¹, A², R¹, R², R⁴, R^{5b}, R⁶, R⁷, R^{8b} and R⁹ are an alkyl or aryl group.

45 **45.** The process of producing the polyacene derivative according to claim 27, wherein when the polyacene derivative is the pentacene derivative represented by the formula (la) above, A¹ and A² are a halogen atom and R³, R^{5a}, R^{8a} and R¹⁰ are an alkyl or aryl group.

46. An electrically conductive material comprising the polyacene derivative according to any one of claims 1 through 19 or the polyacene derivative obtained by the process according to any one of claims 20 through 45.

50 **47.** A resin composition comprising the polyacene derivative according to any one of claims 1 through 19 or the polyacene derivative obtained by the process according to any one of claims 20 through 45, and other synthetic organic polymers.

Fig. 1




Fig. 2




Fig. 3





Fig. 4







Fig. 5



+ two rings

Fig. 6



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP01/01479

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl ⁷ C07C15/20, C07C25/22, C07C5/367, C07B61/00, C07C17/00, C07C67/347, C07C69/76, H01B1/12, H01B1/20, C08K5/01, C08L101/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl ⁷ C07C15/20, C07C25/22, C07C5/367, C07B61/00, C07C17/00, C07C67/347, C07C69/76, H01B1/12, H01B1/20, C08K5/01, C08L101/00		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CA (STN)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	US, 5077142, A (Ricoh Company, Ltd.), 31 December, 1991 (31.12.91), <compounds in lower Columns 31, 32> (Family: none)	1, 10, 12, 15 2-9, 11, 13, 14, 16-19, 20-44
X A	Chemical Abstracts, Vol. 59, 6332b-f, "Conversion of naphthalenes to anthracenes and to naphthacenes", <1, 4, 5, 7, 10, 12-hexaphenylnaphthacene compounds>	1-3, 10, 12, 15 4-9, 11, 13, 14, 16-19, 20-44
PX PA	WO, 00/56933, A1 (Princeton Separations), 28 September, 2000 (28.09.00), <2, 10-dimethoxypentacene compounds, etc.> (Family: none)	1 2-19, 20-45
X A	Harold HART et al., "Tetrahalobenzenes as Di-Aryne Equivalents in Polycyclic Arene Synthesis", Tetrahedron, Vol. 43, No. 22, pages 5203 to 5224, (1987), <pentacene compound which substantially corresponds to compound 23, as indicated on page 5206>	1-5, 10-13, 18 6-9, 14-17, 19, 20-45
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* "A" "E" "L" "O" "P"	Special categories of cited documents: document defining the general state of the art which is not considered to be of particular relevance earlier document but published on or after the international filing date document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) document referring to an oral disclosure, use, exhibition or other means document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family
Date of the actual completion of the international search 15 May, 2001 (15.05.01)		Date of mailing of the international search report 29 May, 2001 (29.05.01)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP01/01479

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	Shyi-Long LEE et al., "Theoretical Studies of the Molecular Second-Order Hyperpolarizabilities of Polycyclic Aromatics", International Journal of Quantum Chemistry, Quantum Chemistry Symposium 29, pages 509 to 522, (1985), <compounds in table II>	1 2-19,20-45
A	JP, 11-354277, A (NEC Corporation), 24 December, 1999 (24.12.99), Claims (Family: none)	1-19,46-47
A	JP, 4-335087, A (Mitsubishi Kasei Corporation), 24 November, 1992 (24.11.92), Claims (Family: none)	1-19,46-47
PA	JP, 2000-299188, A (Organic Display Technology), 24 October, 2000 (24.10.00), Claims; Par. No. [0046]; chemical compound 8 & WO, 00/31208, A1 & US, 6165383, A	1-19,46-47

Form PCT/ISA/210 (continuation of second sheet) (July 1992)