



(11) **EP 2 270 915 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:  
**03.05.2017 Bulletin 2017/18**

(21) Application number: **09724654.0**

(22) Date of filing: **27.03.2009**

(51) Int Cl.:  
**H01M 8/16** <sup>(2006.01)</sup> **C12N 1/20** <sup>(2006.01)</sup>  
**C12P 3/00** <sup>(2006.01)</sup> **H01M 4/86** <sup>(2006.01)</sup>  
**H01M 4/90** <sup>(2006.01)</sup> **H01M 8/02** <sup>(2016.01)</sup>  
**C12P 1/04** <sup>(2006.01)</sup>

(86) International application number:  
**PCT/JP2009/056385**

(87) International publication number:  
**WO 2009/119846 (01.10.2009 Gazette 2009/40)**

(54) **MICROBIAL FUEL CELL**

MIKROBIELLE BRENNSTOFFZELLE  
PILE À COMBUSTIBLE MICROBIENNE

(84) Designated Contracting States:  
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK TR**

(30) Priority: **28.03.2008 JP 2008086195**  
**26.09.2008 JP 2008249178**

(43) Date of publication of application:  
**05.01.2011 Bulletin 2011/01**

(73) Proprietor: **Japan Science and Technology Agency**  
**Kawaguchi-shi**  
**Saitama 332-0012 (JP)**

(72) Inventors:  
• **HASHIMOTO, Kazuhito**  
**Tokyo 113-8654 (JP)**  
• **NAKAMURA, Ryuhei**  
**Tokyo 113-8654 (JP)**  
• **KAI, Fumiyoshi**  
**Bunkyo-ku,**  
**Tokyo 113-0031 (JP)**  
• **WATANABE, Kazuya**  
**Chofu-shi,**  
**Tokyo**  
**1820004 (JP)**  
• **KATO, Soichiro**  
**Tokyo,**  
**154-0005 (JP)**

(74) Representative: **Vossius & Partner**  
**Patentanwälte Rechtsanwälte mbB**  
**Siebertstrasse 3**  
**81675 München (DE)**

(56) References cited:  
**WO-A1-2007/037228 US-A1- 2007 259 217**

- **SELL D ET AL: "USE OF AN OXYGEN GAS DIFFUSION CATHODE AND A THREE-DIMENSIONAL PACKED BED ANODE IN A BIOELECTROCHEMICAL FUEL CELL", APPLIED MICROBIOLOGY AND BIOTECHNOLOGY, SPRINGER VERLAG, BERLIN, DE, vol. 31, no. 2, 1 January 1989 (1989-01-01), pages 211-213, XP000921214, ISSN: 0175-7598, DOI: 10.1007/BF00262465**
- **D. SELL ET AL.: 'Use of an oxygen gas diffusion cathode and a three-dimensional packed bed anode in a bioelectrochemical fuel cell' APPL MICROBIOL BIOTECHNOL vol. 31, 1989, pages 211 - 213, XP000921214**
- **ORIANNA BRETSCHEGER ET AL.: 'Current Production and Metal Oxide Reduction by Shewanella oneidensis MR-1 Wild Type and Mutants' APPLIED AND ENVIRONMENTAL MICROBIOLOGY vol. 73, no. 21, November 2007, pages 7003 - 7012, XP008142139**
- **ASWIN K. MANOHAR ET AL.: 'The polarization behavior of the anode in a microbial fuel cell' ELECTROCHIMICA ACTA vol. 53, 20 March 2008, pages 3508 - 3513, XP022461319**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 2 270 915 B1**

- CARRICK M. EGGLESTON ET AL.: 'Binding and direct electrochemistry of OmcA, an outer-membrane cytochrome from an iron reducing bacterium, with oxide electrodes: A candidate biofuel cell system' *INORGANICA CHIMICA ACTA* vol. 361, 15 February 2008, pages 769 - 777, XP022397495
- RYUHEI NAKAMURA ET AL.: 'Biseibutsu/Kinzoku Sankabutsu Handotai Kaimen ni Okeru Chokusetsu Denshi Ido Han' o' *DAI 26 KAI KOTAI.HYOMENKO KAGAKU TORONKAI KOEN YOSHISHU* 26 November 2007, pages 68 - 69, XP008145863
- ZHEN HE ET AL.: 'An Upflow Microbial Fuel Cell with an Interior Cathode: Assessment of the Internal Resistance by Impedance Spectroscopy' *ENVIRON. SCI. TECHNOL.* vol. 40, 2006, pages 5212 - 5217, XP002458204
- KORNEEL RABAAY ET AL.: 'Tubular Microbial Fuel Cells for Efficient Electricity Generation' *ENVIRON. SCI. TECHNOL.* vol. 39, 2005, pages 8077 - 8082, XP008142174
- ZHEN HE ET AL.: 'Electricity Generation from Artificial Wastewater Using an Upflow Microbial Fuel Cell' *ENVIRON. SCI. TECHNOL.* vol. 39, 2005, pages 5262 - 5267, XP008142135
- KIM HYUNG JOO ET AL.: 'A Microbial Fuel Cell Type Lactate Biosensor Using a Metal-Reducing Bacterium, *Shewanella putrefaciens*' *J. MICROBIOL. BIOTECHNOL.* vol. 9, no. 3, 1999, pages 365 - 367, XP000862875
- EUN JEONG CHO ET AL.: 'Optimization of the biological component of a bioelectrochemical cell' *BIOELECTROCHEMISTRY* vol. 70, 2007, pages 165 - 172, XP005825067
- Y. A. GORBY: "Electrically conductive bacterial nanowires produced by *Shewanella oneidensis* strain MR-1 and other microorganisms", *PROCEEDINGS OF THE NATIONAL ACADEMY OF SCIENCES*, vol. 103, no. 30, 25 July 2006 (2006-07-25), pages 11358-11363, XP055046674, ISSN: 0027-8424, DOI: 10.1073/pnas.0604517103
- LOGAN B E ET AL: "Electricity-producing bacterial communities in microbial fuel cells", *TRENDS IN MICROBIOLOGY*, ELSEVIER SCIENCE LTD., KIDLINGTON, GB, vol. 14, no. 12, 1 December 2006 (2006-12-01), pages 512-518, XP025014123, ISSN: 0966-842X, DOI: 10.1016/J.TIM.2006.10.003 [retrieved on 2006-12-01]

**Description**

## TECHNICAL FIELD

**[0001]** The present invention relates to a microbial fuel cell.

## BACKGROUND ART

**[0002]** A microbial fuel cell is equipped with a pair of electrodes, an external circuit for electrically connecting the electrodes, and a separating film for separating the pair of the electrodes. Microorganisms with an extracellular electron transfer capability, such as *Shewanella* or the like are held on one electrode. Here, the extracellular electron transfer capability means the capability to obtain biogenic electric energy and at the same time transfer electrons to electron acceptors by utilizing metallic ions and their oxidative products as the electron acceptors to reduce the ions and the products (see nonpatent document 1). The forgoing extracellular electron transfer capability is found in part of bacteria acting as microorganisms. That is, a specific electron transfer mechanism that discharges electrons to the outsides of microorganisms via cytochrome localized in a cell membrane is found in part of bacteria, such as a *Shewanella* group (hereunder, simply referred to as *Shewanella*) such as *Shewanella loihica* and *Shewanella oneidensis*, a *Geobacter* group, a *Rhodospirillum rubrum* group, a *Pseudomonas* group or the like (see nonpatent documents 2, 3, 4).

**[0003]** The microbial fuel cell thus structured is a device in which microorganisms transfer electrons to the above one electrode, thereby producing electric energy. As fuel for producing electric energy, a regenerable biomass and organic pollutants contained in human sewage or the like can be utilized and hence the microbial fuel cell has recently received widespread attention as a sustainable energy source. Besides, there also exist microorganisms with a capability to reduce and fixate a metallic element, which has been noted as means for sewage treatment and environmental purification, too. The microbial fuel cell falls into the two general classifications which are a system for employing a single kind of microorganism, and a mixed bacterial culture system for directly employing a microbial group living in sewage or the like (e.g., see patent document 1). *Shewanella* is a microorganism most extensively employed in the former system.

Patent document 1: Japanese unexamined patent application publication No. 2006-81963.

Nonpatent document 1: *Lovely D. R.; Nat.Rev.Microbiol.*, 2006, 4, 497-508

Nonpatent document 2: *Gralnick, J. A.; Newman, D. K.; Molecul. Microbiol.* 2007, 65, 1-11

Nonpatent document 3: *Hernandez, M. E.; Newman, D. K.; Cell. Mol.Life Sci.* 2001. 58, 1562-1571

Nonpatent document 4: *Journal of Japanese Society of Microbial Ecology* (2008) Vol. 23, No.2, P. 58

Nonpatent document 5: *LOGAN B. E. ET AL: "Electricity-producing bacterial communities in microbial fuel cells", TRENDS IN MICROBIOLOGY, ELSEVIER SCIENCE LTD., KIDLINGTON, GB, vol. 14, no. 12, 1 December 2006 (2006-12-01), pages 512-518.*

## DISCLOSURE OF THE INVENTION

## Problem to be solved by the Invention

**[0004]** Under existing condition, however, in the traditional microbial fuel cell described in the above patent document 1 or the like, as compared to the existing chemical fuel cell which employs the existing platinum as catalyst, its current density is extremely low and has become a problem, thus making the traditional microbial fuel cell off from a stage of practical use. For the last few years, the current density has been continuously improved. As compared to a chemical fuel cell such as a hydrogen fuel cell, however, it is impossible for the microbial fuel cell to advance to its practical use unless its current density is improved by at least on the order of several more digits. For the purpose of increasing the current density, studies have been carried out to add a mediator for transferring electrons. And, as the mediator to be added, a quinone derivative such as anthraquinone-2, 6-disulphonate (AQDS) or the like is known. The mediator itself, however, is expensive and many of them are noxious, accompanied by the problem that the size of the microbial fuel cell tends to be large as a whole.

**[0005]** Therefore, with the view of the problems described above, it is an object of the present invention to provide a microbial fuel cell capable of increasing its current density without employing a mediator.

## Means for solving the Problem

**[0006]** In order to achieve the above object, the invention provides a microbial fuel cell as defined in the claims.

## Effects of the invention

**[0007]** According to the microbial fuel cell of the present invention, a network made up of the conductive fine particles allows electrons to transfer from the microorganisms to the electrode, and thus, electrons can be transferred even from microorganisms suspending far away from the electrode to the electrode. Hence, its current density can be increased.

## BRIEF DESCRIPTION OF THE DRAWINGS

**[0008]**

FIG. 1 is a graph illustrating a relationship between an initial microbial density ( $OD_{600}$ ) and a steady current, in an electrochemical cell.

FIG. 2 is a conceptual diagram illustrating a position-

al relationship of microorganisms on an electrode, (a) microorganisms on the traditional electrode, (b) a model diagram of 3-dimensionally structured agglomerate formed from microorganisms and the conductive fine particles.

FIG. 3 is a view illustrating a structure of an electrochemical cell according to examples, (a) its perspective view and (b) its cross-sectional view.

FIG. 4 is a graph illustrating a generated current value measured using the electrochemical cell in the example 1.

FIG. 5 is an SEM image after 28 hours since a water solution of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles was added, (a) a view illustrating a condition in the vicinity of the electrode and (b) an enlarged view of agglomerates

FIG. 6 is a CV curve obtained by measuring using the electrochemical cell.

FIG. 7 is a view illustrating an effect of irradiating white light in the example 1, (a) a current change at the time of the irradiation and (b) a magnitude of a photocurrent.

FIG. 8 is a graph illustrating a generated current value measured using the electrochemical cell in the example 2.

FIG. 9 is a graph illustrating a generated current value measured using the electrochemical cell in the example 3.

FIG. 10 is a view illustrating a photograph of precipitates and an absorption spectrum of the precipitates in the example 4.

FIG. 11 is a graph illustrating a generated current value measured using the electrochemical cell in the example 4.

FIG. 12 is a graph illustrating a current density measured using the electrochemical cell in the example 5.

FIG. 13 is a graph illustrating a current density measured using the electrochemical cell in the example 6.

FIG. 14 is a graph illustrating a current density measured using the electrochemical cell in the example 7.

FIG. 15 is a graph illustrating a current density measured using the electrochemical cell in the example 8.

FIG. 16 is a graph illustrating a current density measured using the electrochemical cell in the example 9.

FIG. 17 is a graph illustrating a current density measured using the electrochemical cell in the example 10.

#### BEST MODE FOR CARRYING OUT THE INVENTION

**[0009]** Microorganisms according to the present invention have an extracellular electron transfer capability to discharge electrons to the organisms via cytochrome localized in a cell membrane. Electrons are transferred to an external electrode to produce a current. The present invention provides a microbial fuel cell utilizing the properties of these microorganisms.

**[0010]** There are a multiple of factors for determining a current generation capability in a microbial fuel cell. A

specific surface area of an electrode, a device scale and a selection of an electrode material are common factors in a microbial fuel cell as well in a chemical cell, while the electron transfer from microorganisms to an electrode is unique to a microbial fuel cell, which is the most important factor above all. Nevertheless, there is little or no research paper which has studied the reaction mechanism of the electron transfer from microorganisms to an electrode and led to achievement of an increase in current density. As a reason for that, it can be pointed out that a system has been not known which was suitable to electrochemically study an electrode reaction of a living microorganism for generating a current. With the focus on this point, the present inventors accomplished the present invention as a result of performing an electrochemical study.

**[0011]** In addition, the following description is given with *Shewanella*, being a type of microorganism, taken as an example. *Shewanella* has an extracellular electron transfer capability to transfer electrons directly to an electrode via cytochrome localized in a cell membrane. Besides, *Shewanella* has a capability to reduce metallic ions and insoluble metallic oxide (a metal-reducing bacterium).

**[0012]** FIG. 1 shows a relationship between a concentration of *Shewanella* and a steady current value. The concentration of *Shewanella* was measured by a light transmission amount, which is called an OD method. In addition, OD (600nm) means an intensity of 600nm light when a suspending solution of microorganisms is put in a cell having a light path length 1cm. Here, a rough indication for the number of the microorganisms is 10<sup>18</sup> pieces/ml, when OD=1.0. As is clear from FIG. 1, the steady current value has been proved to be out of relation to the *Shewanella* concentration. A generated current has been proved to be relevant not to an amount of microorganisms but to an amount of the microorganisms existing in the vicinity of an electrode.

**[0013]** As a result of having studied the microbial fuel cell utilizing this *Shewanella*, electron transfer is carried out only in the *Shewanella* present in the vicinity of a surface of the electrode, while little or no electron transfer was carried out in the *Shewanella* suspended far away from the electrode and hence this *Shewanella* contributed to no current generation. Then, it was found that such a noncontributory condition of this *Shewanella* disabled a large current density to be obtained.

**[0014]** Specifically, as shown in FIG. 2(a), in an electrode 103 of the traditional microbial fuel cell 100, only the *Shewanella* 302 present in the vicinity of the electrode 103 carries out the electron transfer, whereas the *Shewanella* 301 suspended far away from the electrode carries out little or no electron transfer. Accordingly, if the *Shewanella* 301 suspended far away from the electrode 103 can be made to infallibly carry out the electron transfer, it is considered that a current density of a microbial fuel cell 100 can be dramatically increased as compared to the traditional one.

**[0015]** Then, the present inventors found out that Shewanella specifically adsorbed conductive fine particles and agglomerated with the conductive fine particles in a solution to form 3-dimensionally-structured agglomerate and a network made up of the conductive fine particles in the agglomerates allowed electrons to transfer from the Shewanella to the electrode and as a result Shewanella was led to have a function to enable electrons to be transferred even from the Shewanella suspended far away from the electrode to the electrode. Here, the agglomerate means a 3-dimensionally-structured state where the agglomerate is equipped with the Shewanella, being a microorganism, and the conductive fine particles and the Shewanella specifically adsorbed the conductive fine particles. Besides, as the conductive fine particles, a variety of matters is taken into account. Fine particles that comprise any one or a combination of ferric oxide, manganese oxide and ferric sulfide, are used. In the microbial fuel cell 1 according to the present example, as shown in FIG. 2(b), on a surface of the electrode 103, the 3-dimensionally-structured agglomerate is formed from the conductive fine particles 2 and Shewanella 3. In this agglomerate 4, the conductive fine particles 2 disperse among respective pieces of the Shewanella 3, and the conductive fine particles 2 are coupled to one another to hold the Shewanella 3, thus forming the 3-dimensional structure as a whole. Accordingly, the conductive fine particles 2 can hold the Shewanella 3 including Shewanella 3a on the surface of the electrode 103 and even Shewanella 3b positioned in a vertical direction a distance away from the surface of the electrode 103. As described above, in the microbial fuel cell 1 according to the present invention, the Shewanella 3 is allowed to be held by the conductive fine particles 2, extensively, i.e., particularly over a range of zone extending vertically away from the surface of the electrode 103. Hence, more pieces of the Shewanella 3 are allowed to transfer electrons. Besides, the Shewanella 3 is held by means of the conductive fine particles 2 and therefore electrons  $e^-$  can be infallibly transferred to the electrode 103 even from positions away from the electrode 103. Accordingly, in the microbial fuel cell 1 according to the present example, its current density can be dramatically increased.

**[0016]** As described above, in the microbial fuel cell in which the conductive fine particles represented by ferric oxide and Shewanella form the 3-dimensionally-structured agglomerate, as compared to the traditional microbial fuel cell where no conductive fine particle exists, the current density can be dramatically increased by Shewanella. In this case, as ferric oxide,  $\alpha$ - $\text{Fe}_2\text{O}_3$ ,  $\alpha$ - $\text{FeOOH}$ ,  $\gamma$ - $\text{Fe}_2\text{O}_3$ ,  $\varepsilon$ - $\text{Fe}_2\text{O}_3$  or  $\text{Fe}_3\text{O}_4$  are applicable.

**[0017]** Furthermore, as a conductive fine particle, ferric sulfide can be employed. In this case, ferric sulfide can be obtained by biosynthesis caused by a reduction action between ferric ions of microorganisms and sulfide ions thereof in an environment where ferric ions and sulfide ions are present.

**[0018]** Further, in terms of electric characteristics, as

conductive fine particles, a semiconductor and a metal are recommended. In addition,  $\alpha$ - $\text{Fe}_2\text{O}_3$ ,  $\alpha$ - $\text{FeOOH}$ ,  $\gamma$ - $\text{Fe}_2\text{O}_3$ ,  $\varepsilon$ - $\text{Fe}_2\text{O}_3$ , which are described above, are semiconductors, while  $\text{Fe}_3\text{O}_4$  and manganese oxide are metals.

**[0019]** In the microbial fuel cell employed in the present invention, between pieces of Shewanella or on a surface of Shewanella, metallic oxide acting as a conductive fine particle, nanosized ferric oxide fine particles, e.g., exist to form 3-dimensionally-structured agglomerate as a whole. A microbial fuel cell, in which metallic oxide exists between pieces of Shewanella or on the surface of Shewanella and 3-dimensionally-structured agglomerate are formed, has a generated current value increased by fifty or more times as large as that of the traditional microbial fuel cell without metallic oxide between pieces of Shewanella or on the surface of Shewanella and the 3-dimensional agglomerate, thus dramatically improving efficiency. Furthermore, the microbial fuel cell according to the present invention dispenses with a mediator or the like which has been traditionally employed, e.g., a mediator made of a quinone derivative or the like, thus permitting an inexpensive and highly safe fuel cell to be obtained.

**[0020]** As for a mechanism for increasing a current density, by adding  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles,

- (1) an amount of current generated from each pieces of Shewanella has increased,
- (2) the transfer and dispersion of Shewanella to the electrode has been accelerated and
- (3)  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles spontaneously agglomerated functions as a long-distance electron transferring material.

**[0021]** Thus three possibilities are estimated. As for the item (1), even when the same  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles exist, a generated current value on an  $\alpha$ - $\text{Fe}_2\text{O}_3$  thin-film electrode where no 3-dimensional structure of  $\alpha$ - $\text{Fe}_2\text{O}_3$ /Shewanella is formed was much smaller as compared to the generated current value in the case where the  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles were added into a cell for suspending microorganisms and fine particles existing in a solution. This fact indicates that the observed dramatic increase in current density is unaccountable only by an increase in generated current value of Shewanella.

**[0022]** Furthermore, as for the item (2), with regard to the possibility that the transfer and dispersion of Shewanella to an ITO electrode acting as a negative electrode were accelerated by adding the  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles, from an aspect of the ITO (indium Tin Oxide; indium tin oxide) electrode after current measurement, Shewanella has been observed to form a robust and bulky biofilm on the ITO electrode in the presence of the  $\alpha$ - $\text{Fe}_2\text{O}_3$  fine particles as compared to the absence thereof. From this phenomenon, it is concluded that there is little or no possibility that the transfer of Shewanella to the ITO electrode is accelerated in the presence of the  $\alpha$ -

Fe<sub>2</sub>O<sub>3</sub> fine particles. In addition, the negative electrode is schemed so that the metabolism of Shewanella is utilized as a catalyst process to consume fuel and by transferring electrons e<sup>-</sup> discharged as metabolic waste products of Shewanella, electric energy can be extracted. In addition, the ITO electrode generally has high transmittance of visible lights and conductivity and therefore is employed as a transparent electrode.

**[0023]** Considering the context described above, it can be concluded that a dramatic increase in generated current value, found out by the present study, is caused by the increase in the number of Shewanella attributable to the current generation, a result of the above item (3), i.e., the phenomenon that the α-Fe<sub>2</sub>O<sub>3</sub> fine particles spontaneously agglomerated without an external aid function as the long-distance electron transferring material.

**[0024]** The description was given for α-Fe<sub>2</sub>O<sub>3</sub>. However, the ferric oxide such as α-FeOOH, γ-Fe<sub>2</sub>O<sub>3</sub>, ε-Fe<sub>2</sub>O<sub>3</sub> and Fe<sub>3</sub>O<sub>4</sub> are also likewise effective as the long-distance electron transferring material.

**[0025]** Ferric sulfide can be also effective as the long-distance electron transferring material as is the case with ferric oxide. In an environment where ferric ions and sulfide ions coexist, when in an ionized state, the ferric sulfide acts as a mediator, whereas when having returned to ferric sulfide, the ferric sulfide acts as the long-distance electron transferring material as is the case with the ferric oxide. Ferric ions and sulfide ions are widely distributed throughout nature. Only ferric ions and sulfide ions generate no ferric sulfide. Bacteria, being microorganisms with a metal-reducing capability (metal-reducing bacteria), can easily produce ferric sulfide from ferric ions and sulfide ions. The produced ferric sulfide functions as a long-distance electron transferring material as is the case with ferric oxide. Besides, it is not easy to synthesize ferric sulfide and it is industrially easier that microorganisms synthesize ferric sulfide by adding ferric ions and sulfide ions than performing a process of adding ferric sulfide to microorganisms.

**[0026]** In manganese oxide, in addition to the effect of the long-distance electron transferring material described above, Mn<sup>2+</sup> ions partially melted act as a mediator to improve a current generating function.

**[0027]** The present invention is not limited to the present example and various modifications are possible within the scope of the present invention. In the example described above, the description has been given, e.g., for the case where Shewanella was utilized as an example of bacteria, being microorganisms. The present invention is not limited to this case and instead of Shewanella, other bacteria, e.g., Geobacter that is bacterium (metal-reducing bacterium) with the same metal-reducing capability as Shewanella or a mixed bio-group, called mix culture, whose type cannot be specified, or bacteria making its habitat in paddy field may be applicable. Microorganisms are effective, such as particularly Geobacter (see a document: Molecular Microbiology (2007) 65(1), 12-20) with an extracellular electron trans-

fer capability, Rhodoferrax group or Pseudomonas (see a document: Journal of Japanese society of Microbial Ecology (2008) Vol. 23 No.2, P.58).

## 5 Examples

**[0028]** Next, examples of the present invention are described. In addition, it goes without saying that the present invention is not limited to these examples. In addition, Shewanella loihica PV-4 and Shewanella oneidensis MR-1 which are employed in the examples described below were bought from ATCC (American Type Culture Collection). Among these, a catalogue number (2008 year version) of Shewanella loihica PV-4 is BAA-1088 and a catalogue number (2008 year version) of Shewanella oneidensis MR-1 is BAA-1096.

### (Example 1)

**[0029]** As metallic oxide, α-Fe<sub>2</sub>O<sub>3</sub> fine particles were employed. A water solution of α-Fe<sub>2</sub>O<sub>3</sub> fine particles is made by dropping an FeCl<sub>3</sub> solution into boiling purified water. As microorganism, Shewanella loihica PV-4 was employed. For electrochemical measurement, an electrochemical cell 9 shown in FIG. 3 was employed. The electrochemical cell 9 is equipped with an active electrode 10 acting as a negative electrode, a counter electrode 11 acting as a positive electrode, a reference electrode 12 and a reaction tank 13. The active electrode 10, the counter electrode 11 and the reference electrode 12 are electrically connected with a potentiostat acting as an external circuit. Besides, the electrochemical cell 9 is held to a glass plate 14 via a sheet 17 made of silicon rubber

**[0030]** Shewanella loihica PV-4 was cultured by the following procedure. A colony stored on an agar culture medium (Marine Broth 20 gL<sup>-1</sup>, Agar 15 gL<sup>-1</sup>) was isolated to be suspended in an MB (Marine Broth 20 gL<sup>-1</sup>) culture medium of 10ml within a centrifuge tube of 50ml and then was cultured for one to two nights under an anaerobic condition. An amount of 10ml of a suspending solution of Shewanella loihica PV-4 was centrifugally separated at 3,500rpm for 10 minutes to allow Shewanella loihica PV-4 to be precipitated and thereafter the supernatants were entirely discarded to be converted into an electrolyte of 10ml as a solution. As an electrolyte, DM-L (10mM) was employed. Further, after being subjected to shake culture for one night or more, the cultured electrolyte was employed for electrochemical measurement. The shake culture was carried out using BR-40LF (TAITEC) under the condition of 30 degrees C and 120rpm.

**[0031]** In addition, DM is the abbreviation of Defined Media and its composition (each indicated in unit of gL<sup>-1</sup>) includes NaHCO<sub>3</sub> 2.5, CaCl<sub>2</sub>·2H<sub>2</sub>O 0.08, NH<sub>4</sub>Cl 1.0, MgCl<sub>2</sub>·6H<sub>2</sub>O 0.2, NaCl 10, 2-[4-(2-Hydroxyethyl)-1-piperazinyl]ethanesulfonic acid (HEPES, a buffering liquid) 7.2. As an electron donor to Shewanella loihica PV-4, Sodium Lactate (10mM) or a yeast extract of 0.5gL<sup>-1</sup> for

feeding fuel used to allow *Shewanella loihica* PV-4 to generate a minute quantity of required energy were added Hereunder, a DM culture medium containing Lactate is described as, e.g., DM-L (10mM) and letters in the parenthesis are defined as a Lactate concentration. Further, DM-L was employed, which had been subjected to N<sub>2</sub> bubbling for ten minutes or more and to an anaerobic condition.

**[0032]** A 5ml suspending solution of *Shewanella loihica* PV-4 cultured for electrochemical measurement was centrifugally separated for 10 minutes at 3,500rpm to precipitate *Shewanella loihica* PV-4. Afterward, all supernatants were discarded to resuspend *Shewanella loihica* PV-4 using a 0.2ml DM-L (10mM) and the *Shewanella loihica* PV-4 collected by a syringe was poured into the electrochemical cell 9 through a silicon rubber plug 15 of the electrochemical cell 9. Then, the water solution of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles was poured into the electrochemical cell 9. In addition, inside the electrochemical cell 9, a 4ml electrolyte acting as a solution was poured in advance. As the electrolyte, the above DM-L (10mM) was employed.

**[0033]** In the present example, in the electrochemical cell 9, an ITO electrode (the electrode area was 2.0cm<sup>2</sup>), a platinum wire, and an Ag|AgCl|KCl<sub>sat.</sub> electrode were employed as an active electrode 10, a counter electrode 11 and a reference electrode 12, respectively. The Ag|AgCl|KCl<sub>sat.</sub> electrode is one which was created in such a manner that a silver chloride layer was attached to a surface of a silver member and subsequently the member thus processed was inserted into a water solution of potassium chloride.

**[0034]** For electric measurement, a potentiostat HSV-100 (made by Hokuto Denko) was employed. A potential of the active electrode 10 was fixed at +0.2V over that of the reference electrode 12. Temperature was set at ambient temperature and the electrochemical cell 9 was shielded from light so as not to be exposed to light. The example 1 was practiced by pouring the water solution of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles into the cell 9 so that the concentration of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles inside the cell 9 became 7.5mM. In the diameter of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particle, its first-order particle diameter is on the order of 20nm and when the particles agglomerate, its diameter gets into hundreds of nm. In this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) is 2.0 in OD (600nm) and the concentration of the water solution of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles inside the cell 9 is 7.5mM as described above. Specifically, the concentration is equivalent to that created by putting  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles of about 5mg into a 4ml solution. In addition, the OD (600nm) means an intensity of 600nm light when a microbial suspending solution is put in a cell with 1cm light path length.

**[0035]** Besides, instead of pouring the water solution of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particle in the example 1, a comparative example 1 was practiced by adding iron citrate (III). As for the rest, the same arrangement and conditions as

those in the example 1 were applied to the comparative example 1.

**[0036]** Further, instead of pouring the water solution of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles in the example 1, a comparative example 2 was practiced by adding nothing. As for the rest, the same conditions as those in example 1 were applied to the comparative example 2.

**[0037]** The result is shown in FIG. 4. In FIG. 4, (b) and (c) are the results of the example 1, the comparative example 1 and the comparative example 2, respectively. It could be verified that the generated current value obtained in the example 1 was dramatically improved by 50 times or more as compared to that in the case where no  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particle was added.

**[0038]** At the same time, in the comparative example 1 where Fe<sup>3+</sup> ions were added to DM-L (10mM) and in the comparative example 2 where nothing was added, such an increase in generated current value as to be obtained when the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles were added, was not observed.

**[0039]** Besides, FIG. 5 shows SEM images after 28 hours have elapsed since the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles had been added. It can be learnt that the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles acting as the conductive fine particles and the agglomerate 4 of *Shewanella loihica* PV-4 acting as microorganisms have formed a 3-dimensional structure. No  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particle was observed in a position where *Shewanella loihica* PV-4 was absent. Further, when the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particle was not added, suchlike agglomerate 4 containing *Shewanella loihica* PV-4 was not observed.

**[0040]** These results prove the fact that the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles and *Shewanella loihica* PV-4 were coupled strongly to one another and as a result, the 3-dimensionally structured agglomerate 4 was formed. Furthermore, the above results prove the fact that in fact, the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles and *Shewanella loihica* PV-4 spontaneously form the agglomerate 4 and the agglomerate 4 functions as the long-distance electron transferring material.

**[0041]** The dramatic increase in current density, found in the present invention, is due to the fact that the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles spontaneously agglomerated and functioned as the long-distance electron transferring material, and whereby *Shewanella loihica* PV-4 attributable to the current generation increased. This can be learnt from the results of the redox potential measurement (CV measurement) performed after current measurement (refer to FIG. 6). Symbols (1), (2) in FIG. 6 are the results of the comparative example 1 and the example 1, respectively. From these results, it could be verified that by adding the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles (in the example 1), a larger peak current value could be obtained as compared to the comparative example 1. In addition, the ambient temperature was 30 degrees C. The increase in the redox potential attributable to cytochrome present on the surface of *Shewanella loihica* PV-4 indicates an increase in the number of *Shewanella loihica* PV-4 responsible for current generation. In this manner, an approach of increasing the number of microorganisms responsible for

current generation without adding a mediator and increasing the surface area of the electrode to increase a generated current value is a novel invention never before achieved.

**[0042]** Further, in order to verify a function as the long-distance electron transferring material, i.e., a function as a pathway (hereunder, described as a transfer pathway) made available when the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles couple together to transfer electrons resulting from a characteristic of an n-type semiconductor over a long distance, an effect of light irradiation on the generated current value was examined. Specifically, if a generated current value at the time of stopping light irradiation is nearly equal to that at the time of performing the light irradiation, the generated current value in this case can be said to be responsible for the thickness of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles. Hence, it was ascertained that by measuring this generated current value, the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles functioned as the transfer pathway.

**[0043]** With regard to light irradiation, FIG. 7 shows variations, due to white light irradiation (wavelengths of 430nm or less were cut), in generated current value brought about by *Shewanella loihica* PV-4 when the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> was added and current (hereunder, referred to as "light current") values generated when light was irradiated. A photoelectric current value was determined by a difference obtained by subtracting a current value just before the light irradiation from a maximum current value during the light irradiation. In addition, the timings of light irradiation were shown by arrows in FIG. 7 (a). Besides, peak currents measured in the case of irradiating light were plotted, as shown in FIG. 7 (b).

**[0044]** With regard to the process in which generated current value increased by *Shewanella loihica* PV-4, it was learnt that the photoelectric current value continued to increase corresponding to a generated current value, and when generated current value reached the maximum value, the generated current value ceased to increase. Here, the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> possesses a characteristic of an n-type semiconductor and hence an electron in a valence band is photoexcited in the conductive band due to the transition between the bands of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> to be allowed to move to an electrode, thus causing a photoelectric current. Therefore, if the intensity of light irradiation is constant, the magnitude of a photoelectric current is determined by the thickness of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles which are connected with the ITO electrode and absorb light. This result demonstrates that by making up a 3-dimensional structure, not only the number of the pieces of *Shewanella loihica* PV-4 contributable to the current generation increased, but the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles can function as the transfer pathway. In addition, the photoexcitation means a process in which the number of atoms and atomic systems which are within a certain energy level vary depending on absorption of light impinging on a material.

(Example 2)

**[0045]** Unlike the example 1, a graphite electrode was employed as the active electrode 10 of the electrochemical cell 9, whereas the rest part of its arrangement and conditions remained the same as those of the example 1 (example 2). Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. In addition, the graphite electrode is made of a powder sintered body containing carbon as its main component. According to the present example, a graphite electrode was employed, instead of an ITO electrode, since light irradiation was not carried out.

**[0046]** Further, unlike the example 2, in a comparative example 3, nothing was added to the microorganisms instead of pouring a water solution of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles to the electrochemical cell 9, whereas the rest remained the same as those of the example 2.

**[0047]** The result of the example 2 is shown in FIG.8. FIG.8(a) represents the result of the example 2, while FIG.8(b) represents the result of the comparative example 3. As is clearly shown in FIG.8, such an increase in generated current value as that in the example 1 was also observed in the example 2. In the comparative example 3 where nothing was added, there could not be observed such an increase in generated current value as to be achieved in the case where  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles. According to the result and microbial fuel cell 1 of the present invention, the same effect as that in the example 1 in which an ITO electrode was employed could be achieved even if a graphite electrode was employed as the active electrode 10.

(Example 3)

**[0048]** Unlike the example 1, in an example 3, *Shewanella oneidensis* MR-1 was employed as microorganisms, whereas the rest part of its arrangement and conditions remained the same as those of the example 1 (example 3). Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella oneidensis* MR-1 under the condition of 30 degrees C and 120 rpm.

**[0049]** Further, unlike the example 3, in a comparative example 4, nothing was added to the microorganisms instead of pouring a water solution of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles to the electrochemical cell 9, whereas the rest remained the same as those of the example 3.

**[0050]** The result of the example 3 is shown in FIG.9. FIG.9(a) represents the result of the example 3, while FIG.9(b) represents the result of the comparative example 4. As is clear from FIG.9, such a significant increase in generated current value as that obtained in the example 1 was also observed in the example 3. In the comparative example 4 where nothing was added, such an increase in generated current value as to be achieved in the case where  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> fine particles were added was

not observed. According to such a result, in the microbial fuel cell 1 of the present invention, it was verified that the same effect as that obtained in the example 1 in which *Shewanella loihica* PV-4 was employed could be achieved even if *Shewanella loihica* MR-1 was employed as microorganisms.

(Example 4)

**[0051]** An example 4 in which ferric sulfide fine particles were employed as the conductive fine particles is described hereinafter. *Shewanella loihica* PV-4 was cultured in the similar way as was done in the example 1 in an environment in which  $\text{Fe}^{3+}$  ions and  $\text{S}_2\text{O}_3^{2-}$  ions co-exist. A colony stored on an agar medium (Marine Broth  $20\text{gL}^{-1}$ , Agar  $15\text{gL}^{-1}$ ) was cultured under an anaerobic condition for one night. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. At that time,  $\text{Fe}^{3+}$  was reduced to  $\text{Fe}^{2+}$ , and  $\text{S}_2\text{O}_3^{2-}$  was reduced to  $\text{S}^{2-}$ , thereby producing FeS. The first-order particle diameter of a ferric sulfide fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. After subjected to centrifugal separation, the suspending solution of *Shewanella loihica* PV-4 was poured through a silicon rubber plug 15 of the electrochemical cell 9 for electrochemical measurement. In this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD(600nm), and the concentration of a water solution of ferric sulfide fine particles inside the electrochemical cell 9 was 7.5mM.

**[0052]** A picture and an absorption spectrum of the precipitate thus obtained (20 days after culturing) are shown in FIG.10. In FIG.10, (a) represents the precipitate in the presence of *Shewanella loihica* PV-4, while (b) represents the precipitate in the absence of *Shewanella loihica* PV-4. The formation of black precipitates was observed in the presence of *Shewanella loihica* PV-4. Further, since the absorption spectrum of the black precipitates reached near-infrared region, the black precipitates were proved to be ferric sulfide. However, the observed absorption spectrum up to 600nm in the absence of *Shewanella loihica* PV-4 was caused by ferric hydroxide.

**[0053]** FIG.11 is a current versus time chart when the ferric sulfide fine particles thus obtained and the suspending solution of *Shewanella loihica* PV-4 were poured into the electrochemical cell 9. In FIG.11, (a) represents the result of a case in which ferric sulfide fine particles were present (Example 4), whereas (b) represents the result of a case in which ferric sulfide particles were absent (only *Shewanella loihica* PV-4 existed in a comparative example 5). According to the present example, the generated current value dramatically increased by 30 times as compared to that obtained in the case where ferric sulfide fine particles were absent. This result indicates that the same effect as that in the example 1 in which  $\alpha\text{-Fe}_2\text{O}_3$  was employed could also be achieved for the ferric sulfide fine particles.

(Example 5)

**[0054]** Unlike the example 1, an example 5 is described hereinafter, in which  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were employed as the conductive fine particles (the example 5). Except using  $\gamma\text{-Fe}_2\text{O}_3$  fine particles as the conductive fine particles, the example 5 employed the same method as that of the example 1 to culture *Shewanella loihica* PV-4 under an anaerobic condition. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. The first-order particle diameter of a  $\gamma\text{-Fe}_2\text{O}_3$  fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. FIG.12 shows a current density versus time chart when a water solution of the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles obtained by dissolving the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles in purified water was poured into the electrochemical cell 9 so that the concentration inside the cell became 7.5mM. In addition, in this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD (600nm), and the concentration of the water solution of the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles inside the cell was 7.5mM as mentioned above. Specifically, the concentration was equivalent to that created by putting the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles of about 5mg into a 4ml solution. In FIG. 12, (a) represents the result of a case in which the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were present (the example 5), whereas (b) represents the result of a case in which the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were absent (only *Shewanella loihica* PV-4 existed, in a comparative example 6). According to the present example, the current density substantially doubled as compared to that obtained in the case in which the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were absent.

**[0055]** In addition, the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were produced according to a method described in a document (Y.S. Kang, S.Risbud, J.F.Rabolt, P.Stroeve Chem.Mater., 1996, 8, 2209). In the beginning,  $\text{FeCl}_3 \times 6\text{H}_2\text{O}$  (52mM) and  $\text{FeCl}_2 \times 4\text{H}_2\text{O}$  (26mM) were dissolved in 40ml of a nitrogen saturated ultrapure water, in a manner that the molar ratio between  $\text{FeCl}_3 \times 6\text{H}_2\text{O}$  and  $\text{FeCl}_2 \times 4\text{H}_2\text{O}$  became 2:1, followed by adding 1.4ml of concentrated hydrochloric acid to the solution thus obtained. Next, the solution thus obtained was dropped into 415ml of a NaOH solution with 1.5M while carrying out intensive stirring. Black precipitates were produced due to the dropping of the aforementioned solution, and the supernatants thereof were discarded, followed by cleansing the precipitates with an ultrapure water for several times, and adding concentrated hydrochloric acid to neutralize the solution as a whole, thereby obtaining a solution of  $\text{Fe}_3\text{O}_4$ . From the solution of  $\text{Fe}_3\text{O}_4$  synthesized in the above manner,  $\text{Fe}_3\text{O}_4$  was precipitated and dried to be collected as a powder. Further, after heating the powders at a temperature of 250 degrees C for three hours, the  $\gamma\text{-Fe}_2\text{O}_3$  fine particles were obtained.

(Example 6)

**[0056]** An example 6 is described hereinafter in which  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were employed as the conductive fine particles (the example 6), differently from the example 1. Except using the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles as the conductive fine particles, the example 6 employed the same method as that in the example 1 to culture *Shewanella loihica* PV-4 under an anaerobic condition. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. The first-order particle diameter of a  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. FIG. 13 shows a current density versus time chart when a water solution of the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles obtained by dissolving the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles in purified water was poured into the electrochemical cell 9 so that the concentration inside the cell became 7.5mM. In addition, in this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD (600nm), and the concentration of the water solution of the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles inside the electrochemical cell 9 was 7.5mM as mentioned above. Specifically, the concentration was equivalent to that created by putting the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles of about 5mg into a 4ml solution. In FIG. 13, (a) represents the result of a case in which  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were present as the conductive fine particles (the example 6), whereas (b) represents the result of a case in which the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were absent (only *Shewanella loihica* PV-4 existed in a comparative example 7). According to the present example, the current density substantially doubled as compared to that obtained in the case in which the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were absent.

**[0057]** In addition, the  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were produced according to a method described in a document (Journal of the Physical Society of Japan, Vol.74, No.7, July, 2005, pp. 1946-1949). More specifically, in the beginning, a micellar solution was obtained by dissolving a surface-active agent (such as cetyltrimethylammonium bromide) on the aqueous phase of a solution having n-octane as its oil phase. Ferric nitrate (III) and indium nitrate (III) are dissolved in this micellar solution and barium nitrate is added thereto as a shape-control agent, thereby obtaining a raw material solution. Also, in addition to obtaining such raw material solution, a neutralizer solution was obtained by mixing the neutralizer such as a water solution of ammonia with a micellar solution obtained by dissolving a surface-active agent (such as cetyltrimethylammonium bromide) on the aqueous phase of a solution having n-octane as its oil phase.

**[0058]** Subsequently, using a reverse-micelle method, a mixed solution was produced by stirring and mixing both the aforementioned raw material solution and the neutralizer solution. An appropriate amount of tetraethylorthosilane solution was added to this mixed solution as a silane compound, thereby covering the surfaces of ferric hydroxide compound particles with silica via a sol-gel

method so as to produce silica-covered ferric hydroxide compound particles.

**[0059]** Next, the silica-covered ferric hydroxide compound particles were separated from the mixed solution, and subjected to a baking treatment at a predetermined temperature (within 700 to 1300 degrees C) under the atmospheric condition. Through such baking treatment, microscopic  $\epsilon$ - $\text{Fe}_2\text{O}_3$  fine particles were produced due to the oxidation reaction inside the silica shell in the silica-covered ferric hydroxide compound particles.

(Example 7)

**[0060]** Unlike the example 1, an example 7 is described hereinafter, in which  $\alpha$ - $\text{FeOOH}$  fine particles were employed as the conductive fine particles. Except using  $\alpha$ - $\text{FeOOH}$  fine particles as the conductive fine particles, the example 7 employed the same method as that of the example 1 to culture *Shewanella loihica* PV-4 under an anaerobic condition. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. The first-order particle diameter of the  $\alpha$ - $\text{FeOOH}$  fine particle is approximately 20nm, but becomes as long as hundreds of nm when the particles agglomerate. FIG.14 shows a current density versus time chart when a water solution of the  $\alpha$ - $\text{FeOOH}$  fine particles was poured into the electrochemical cell 9 so that the concentration inside the cell became 7.5mM. In addition, in this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD (600nm), and the concentration of the water solution of the  $\alpha$ - $\text{FeOOH}$  fine particles inside the electrochemical cell 9 was 7.5mM as mentioned above. In FIG. 14, (a) represents the result of a case in which  $\alpha$ - $\text{FeOOH}$  fine particles were employed (an example 7), whereas (b) represents the result of a case in which  $\alpha$ - $\text{FeOOH}$  fine particles were absent (only *Shewanella loihica* PV-4, as in a comparative example 8). According to the present example, the current density dramatically increased (by approximately 50 times) as compared to that obtained in the case in which the  $\alpha$ - $\text{FeOOH}$  fine particles were absent (only *Shewanella loihica* PV-4, as in a comparative example 8). However, a decrease in the current density observed after 15 hours was caused by the consumption of lactate employed as a fuel.

**[0061]** In addition, the water solution of the  $\alpha$ - $\text{FeOOH}$  fine particles was produced according to a method described in a document (Ref. R.J. Atkinson, A.M. Posner, and J.P. Quirk J.Phys.Chem., 1967, 71, 550). In the beginning, 40ml of a NaOH solution with 2.5M was added to 160ml of a  $\text{FeCl}_3$  solution with 0.1M, followed by heating the solution thus obtained at a temperature of 60 degrees C for 24 hours. Subsequently, the solution thus obtained was dialyzed with a dialysis membrane (molar weight cut into 6000 to 8000) made of cellulose, thereby obtaining the water solution of the  $\alpha$ - $\text{FeOOH}$  fine particles.

(Example 8)

**[0062]** Unlike the example 1, an example 8 is described hereinafter, in which  $\text{Fe}_3\text{O}_4$  fine particles were employed as the conductive fine particles. Except using the  $\text{Fe}_3\text{O}_4$  fine particles as the conductive fine particles, the example 8 employed the same method as that of the example 1 to culture *Shewanella loihica* PV-4 under an anaerobic condition. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120rpm. The first-order particle diameter of a  $\text{Fe}_3\text{O}_4$  fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. FIG. 15 shows a current density versus time chart when a water solution of the  $\text{Fe}_3\text{O}_4$  fine particles was poured into the electrochemical cell 9 so that the concentration inside the cell became 7.5mM. In addition, in this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD (600nm), and the concentration of the water solution of the  $\text{Fe}_3\text{O}_4$  fine particles inside the electrochemical cell 9 was 7.5mM as mentioned above. Specifically, the concentration is equivalent to that created by putting the  $\text{Fe}_3\text{O}_4$  fine particles of about 5mg into a 4ml solution. In FIG. 15, (a) represents the result of a case in which the  $\text{Fe}_3\text{O}_4$  fine particles were present (in the example 8), whereas (b) represents the result of a case in which the  $\text{Fe}_3\text{O}_4$  fine particles were absent (only *Shewanella loihica* PV-4 in a comparative example 9). According to the present example, the current density substantially tripled as compared to that obtained in the case in which the  $\text{Fe}_3\text{O}_4$  fine particles were absent (only *Shewanella loihica* PV-4, in the comparative example 9).

**[0063]** In addition, the water solution of the  $\text{Fe}_3\text{O}_4$  fine particles was produced according to a method described in a document (Ref. Y.S.Kang, S.Risbud, J.F.Rabolt, P.Stroeve Chem.Mater., 1996, 8, 2209). In the beginning,  $\text{FeCl}_3 \times 6\text{H}_2\text{O}$  (52mM) and  $\text{FeCl}_2 \times 4\text{H}_2\text{O}$  (26mM) were dissolved in 40ml of a nitrogen saturated ultrapure water so that the molar ratio between  $\text{FeCl}_3 \times 6\text{H}_2\text{O}$  and  $\text{FeCl}_2 \times 4\text{H}_2\text{O}$  became 2:1, followed by adding 1.4ml of concentrated hydrochloric acid to the solution thus obtained. Next, the solution thus obtained was dropped into 415ml of a NaOH solution with 1.5M while carrying out intensive stirring. Black precipitates were produced due to the dropping of the aforementioned solution, and the supernatants thereof were discarded, followed by cleansing the precipitates with an ultrapure water for several times, and further adding concentrated hydrochloric acid to neutralize the solution, thereby obtaining the water solution of the  $\text{Fe}_3\text{O}_4$  fine particles.

(Example 9)

**[0064]** Unlike the example 1, an example 9 is described hereinafter, in which manganese oxide ( $\text{MnO}_2$ ) fine particles were employed as the conductive fine particles. Except using the manganese oxide fine particles as the

conductive fine particles, the example 9 employed the same method as that of the example 1 to culture *Shewanella loihica* PV-4 under an anaerobic condition. Further, BR-40LF (TAITEC) was employed to perform shake culture of *Shewanella loihica* PV-4 under the condition of 30 degrees C and 120 rpm. The first-order particle diameter of the manganese oxide fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. FIG.16 shows a current density versus time chart when a water solution of the manganese oxide fine particles obtained by dissolving manganese oxide fine particles in purified water was poured into the electrochemical cell 9 so that the concentration inside the cell became 7.5mM. In addition, in this case, the concentration of *Shewanella loihica* PV-4 to DM-L (10mM) was 2.0 in OD (600nm), and the concentration of the water solution of the manganese oxide fine particles inside the electrochemical cell 9 was 7.5mM as mentioned above. In FIG.16, (a) represents the result of a case in which the manganese oxide fine particles were present (the example 9), whereas (b) represents the result of a case in which the manganese oxide fine particles were absent (only *Shewanella loihica* PV-4, in a comparative example 10). According to the present example, the current density octupled as compared to that obtained in the case in which the manganese oxide fine particles were absent (only *Shewanella loihica* PV-4, in the comparative example 10).

**[0065]** In addition, the manganese oxide fine particles were produced according to a method described in document (Ref. R.M.McKenzie Mineral.Mag., 1971, 38, 493). In the beginning, a  $\text{Mn}(\text{NO}_3)_3$  solution was heated so that its moisture was almost evaporated, and was further heated at a temperature of 180 degrees C for 48 hours. The solid substance thus obtained was then dissolved in a concentrated hydrochloric acid, and the solution thus obtained was further dropped into ultrapure water while being subjected to filtration. Dark brown precipitates were obtained, followed by cleansing as well as filtering the same to obtain the manganese oxide fine particles.

(Example 10)

**[0066]** An example 10 is described hereinafter, in which microorganisms collected from a paddy soil were employed. The example 10 examined the case in which  $\alpha\text{-Fe}_2\text{O}_3$  fine particles were employed as the conductive fine particles and the case in which the  $\text{Fe}_3\text{O}_4$  fine particles were employed as the conductive fine particles. In addition,  $\alpha\text{-Fe}_2\text{O}_3$  fine particles were produced using the same procedures as described in the example 1, while  $\text{Fe}_3\text{O}_4$  fine particles were produced using the same procedures as described in the example 8.

**[0067]** The microorganisms collected from a paddy soil were cultured using the following procedures. First of all, 12 mL of a PS culture medium was employed to culture the microorganisms. When culturing the microorgan-

isms, sodium acetate (10mM) was added as an electron donor. As a source of microorganisms, 20mg (wet weight) of the paddy soil was added to the PS culture medium. The microorganisms were cultured at a temperature of 30 degrees C, and sodium acetate (10mM) was added again when the current density was in low level (due to deficiency in acetic acid).

**[0068]** In addition, the PS culture medium comprises  $\text{NH}_4\text{Cl}$  10mM,  $\text{KH}_2\text{PO}_4$  1mM,  $\text{MgCl}_2$  0.5mM,  $\text{CaCl}_2$  0.5mM,  $\text{NaHCO}_3$  5mM, HEPES 10mM, and Yeast extract 0.5g/L.

**[0069]** Sodium Acetate (10mM) was added as an electron donor to the microorganisms, and  $0.5\text{gL}^{-1}$  of yeast extract was also added to supply fuel required for the microorganisms in minute amounts.

**[0070]** For electrochemical measurement, an electrochemical cell 9 shown in FIG.3 was employed. An ITO electrode (2.8cm in diameter,  $6.2\text{cm}^2$  in electrode area), a platinum wire, and an  $\text{Ag}|\text{AgCl}|\text{KCl}_{\text{sat}}$  electrode were employed as an active electrode 10, a counter electrode 11 and a reference electrode 12, respectively. The electrochemical cell 9 was held by a glass plate 14. Further, 4.0ml of an electrolyte acting as a solution was poured into the electrochemical cell 9 in advance. The DM-L (10mM) was employed as the electrolyte.

**[0071]** Such electrolyte was subjected to  $\text{N}_2$  bubbling for ten minutes or more to create an anaerobic condition, and then used for electrochemical measurement. A 5ml suspending solution of the microorganisms cultured for electrochemical measurement was centrifugally separated for 10 minutes at 3,500rpm, to precipitate the microorganisms. Afterward, all supernatants were discarded to resuspend the microorganisms with 0.2ml DM-L (10mM). The suspending solution thus obtained was collected by a syringe, and was poured into the electrochemical cell 9 through the silicon rubber plug 15.

**[0072]** HSV-100 (made by Hokuto Denko) was employed for electrical measurement. The electric potential of the active electrode 10 was set as +0.2V to the reference electrode 12. The measurement was carried out at an ambient temperature, and light shielding was laid to prevent the electrochemical cell 9 from being exposed to light. In an example 10 (1), the water solution of the  $\alpha\text{-Fe}_2\text{O}_3$  fine particles, described above, was poured to render the fine-particulate concentration into 5mM. In an example 10 (2), the water solution of  $\text{Fe}_3\text{O}_4$  fine particles was poured to render the fine-particulate concentration into 3.3mM. The first-order particle diameter of a  $\alpha\text{-Fe}_2\text{O}_3$  fine particle is approximately 20nm, but becomes hundreds of nm when the particles agglomerate. In this case, the concentration of the paddy-soil microorganisms to DM-L (10mM) was 2.0 in OD (600nm), while the  $\alpha\text{-Fe}_2\text{O}_3$  fine particles and the  $\text{Fe}_3\text{O}_4$  fine particles were added so that the concentration made up of both the particles became 10mM in terms of Fe atoms.

**[0073]** Unlike the example 10, instead of adding the water solution of the  $\alpha\text{-Fe}_2\text{O}_3$  fine particles and the water solution of  $\text{Fe}_3\text{O}_4$  fine particles, in a comparative example

11, nothing was added to the microorganisms. However, the rest part of the comparative example 11 remains the same as the example 10.

**[0074]** The results of the example 10 and the comparative example 11 are shown in FIG.17. In FIG.17, (a) represents the result when the  $\alpha\text{-Fe}_2\text{O}_3$  fine particles were added (the example 10 (1)), whereas (b) represents the result when the  $\text{Fe}_3\text{O}_4$  fine particles were added (the example 10 (2)), and (c) represents the result of the comparative example 11. When the microorganisms collected from the paddy soil were employed, the current density observed in the example 10 was dramatically improved by 50 times or more as compared to that of the comparative example 11 in which neither  $\alpha\text{-Fe}_2\text{O}_3$  fine particles nor  $\text{Fe}_3\text{O}_4$  fine particles were added.

**[0075]** However, in the comparative example 11 in which no conductive fine particle was added, such a significant increase in current density as to be obtained in the case in which  $\alpha\text{-Fe}_2\text{O}_3$  fine particles were added was not observed.

**[0076]** A group of genes of the microorganisms inside a biofilm formed on the surface of the electrodes after culturing, was analyzed using the 16S rRNA gene clone library method.

**[0077]** In the beginning, DNA was extracted from the microorganisms inside the biofilm formed on the surface of the electrodes, using a FastDNA Spin Kit for Soil (MP bio). Next, the DNA was amplified by applying a unique primer (27F:5'-AGAGTTTGATCCTGGCTCAG, 517R: ATACCGCGGCTGCTGG) to a bacterial 16S rRNA gene, using a polymerase chain reaction method (PCR). The PCR products thus obtained were cloned in a pGEM-T Easy vector (Promega), and then, introduced to E.coli JM109 (Promega) to clone the products.

**[0078]** Further, the analysis of the sequence (using a sequencer made by Takara Co., Ltd.) cloned was carried out. The result of the sequence analysis shows that 21/48 clones (44%) in the example 10 (1) in which the  $\alpha\text{-Fe}_2\text{O}_3$  fine particles were added, and 17/48 clones (35%) in the example 10 (2) in which  $\text{Fe}_3\text{O}_4$  was added, were each found to possess a sequence approximate to Geobacter group. In addition, in the comparative example 11 in which conductive fine particles were not added, 7/48 clones (15%) were found to possess a sequence approximate to Geobacter group. Further, the rate of the Geobacter group in the original paddy soil was found to be 1% or less.

Industrial application potency of the present invention invention

**[0079]** Nowadays, there has been known many studies on chemical fuel cells using platinum. However, the platinum itself is highly rare and expensive. Further, such a chemical fuel cell hardly contributes to a carbon dioxide reduction, due to the difficulty of removing carbon when hydrogen is produced. A microbial fuel cell capable of directly generating electrons from microorganisms is

simple in structure and is characterized by carbon neutral (while carbon dioxide is generated, the flow of carbon cycling is not deranged due to the independence of fossil fuel). In this sense, the microbial fuel cell of the present invention, which can significantly increase the current density thereof, should be highly useful.

Explanation of the reference numbers

#### [0080]

- 1. microbial fuel cell
- 2. conductive fine particle
- 3. microorganism
- 4. agglomerate
- 9. electrochemical cell
- 10. active electrode (negative electrode)
- 11. counter electrode
- 12. reference electrode
- 13. reaction tank
- 14. glass plate
- 15. silicon rubber tap
- 16. potentiostat (outer circuit)
- 17. silicon rubber sheet
- 100. microbial fuel cell
- 103. electrode
- 301, 302 microorganism

#### Claims

1. A microbial fuel cell equipped with a pair of electrodes and an external circuit electrically connecting a pair of said electrodes, **characterized by** 3-dimensionally structured agglomerates formed of electrically-conductive fine particles and microorganisms with an extracellular electron transfer capability and formed on a negative electrode that is one of said electrodes in a solution containing the electrically-conductive fine particles and the microorganisms, wherein in the agglomerates said electrically-conductive fine particles hold the microorganisms on the surface of the negative electrode and in a distance away from the surface of the negative electrode in the vertical direction and said electrically-conductive fine particles are dispersed among said microorganisms, and said electrically-conductive fine particles comprise any one or a combination of ferric oxide, manganese oxide and ferric sulfide.
2. The microbial fuel cell according to claim 1, **characterized in that** said electrically-conductive fine particles include  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>,  $\alpha$ -FeOOH,  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>,  $\epsilon$ -Fe<sub>2</sub>O<sub>3</sub> or Fe<sub>3</sub>O<sub>4</sub>.
3. The microbial fuel cell according to claim 1, **characterized in that** said electrically-conductive fine par-

ticles are obtained by biosynthesis of microorganisms in an environment where ferric ions and sulfide ions coexist.

4. The microbial fuel cell according to any of claims 1 to 3, **characterized in that** said microorganisms are metal-reducing bacteria.
5. The microbial fuel cell according to claim 4, **characterized in that** said metal-reducing bacteria include bacteria of a Shewanella group, a Geobacter group, a Rhodoferrax group or a Pseudomonas group.
6. The microbial fuel cell according to claim 4, **characterized in that** said metal-reducing bacteria contain Shewanella loihica or Shewanella oneidensis.

#### Patentansprüche

1. Mikrobielle Brennstoffzelle, die mit einem Paar Elektroden und einer externen Schaltung ausgestattet ist, die ein Paar der Elektroden elektrisch verbindet, **gekennzeichnet durch** dreidimensional strukturierte Agglomerate, die aus elektrisch leitenden Feinteilchen und Mikroorganismen mit einem extrazellulären Elektronentransfervermögen gebildet und auf einer negativen Elektrode, die eine der Elektroden ist, in einer Lösung gebildet sind, die die elektrisch leitenden Feinteilchen und die Mikroorganismen enthält, wobei in den Agglomeraten die elektrisch leitenden Feinteilchen die Mikroorganismen auf der Oberfläche der negativen Elektrode und in einem Abstand weg von der Oberfläche der negativen Elektrode in vertikaler Richtung halten und die elektrisch leitenden Feinteilchen unter den Mikroorganismen dispergiert sind und die elektrisch leitenden Feinteilchen Eisenoxid, Manganoxid oder Eisensulfid oder eine Kombination davon aufweisen.
2. Mikrobielle Brennstoffzelle nach Anspruch 1, **dadurch gekennzeichnet, dass** die elektrisch leitenden Feinteilchen  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>,  $\alpha$ -FeOOH,  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>,  $\epsilon$ -Fe<sub>2</sub>O<sub>3</sub> oder Fe<sub>3</sub>O<sub>4</sub> aufweisen.
3. Mikrobielle Brennstoffzelle nach Anspruch 1, **dadurch gekennzeichnet, dass** die elektrisch leitenden Feinteilchen durch Biosynthese von Mikroorganismen in einer Umgebung erhalten werden, in der Eisenionen und Sulfidionen koexistieren.
4. Mikrobielle Brennstoffzelle nach einem der Ansprüche 1 bis 3, **dadurch gekennzeichnet, dass** die Mikroorganismen metallreduzierende Bakterien sind.
5. Mikrobielle Brennstoffzelle nach Anspruch 4, **dadurch gekennzeichnet, dass** die metallreduzierenden

den Bakterien Bakterien einer Shewanella-Gruppe, einer Geobacter-Gruppe, einer Rhodoferrax-Gruppe oder einer Pseudomonas-Gruppe aufweisen.

réductrices de métaux contiennent des Shewanella loihica ou des Shewanella oneidensis.

6. Mikrobielle Brennstoffzelle nach Anspruch 4, **dadurch gekennzeichnet, dass** die metallreduzierenden Bakterien Shewanella loihica oder Shewanella oneidensis enthalten.

5

10

## Revendications

1. Pile à combustible microbienne munie d'une paire d'électrodes et d'un circuit externe connectant électriquement une paire desdites électrodes, **caractérisée par** des agglomérats à structure tridimensionnelle qui sont composés de particules fines électro-conductrices et de microorganismes avec une capacité de transfert extracellulaire d'électrons et formés sur une électrode négative qui est une desdites électrodes dans une solution contenant les particules fines électro-conductrices et les microorganismes, lesdites particules fines électro-conductrices maintenant les microorganismes, dans les agglomérats, sur la surface de l'électrode négative et à distance de celle-ci, dans le sens vertical, et lesdites particules fines électro-conductrices étant dispersées parmi lesdits microorganismes, et lesdites particules fines électro-conductrices comprenant un parmi l'oxyde ferrique, l'oxyde de manganèse et le sulfure de fer ou une combinaison de ceux-ci.
2. Pile à combustible microbienne suivant la revendication 1, **caractérisée en ce que** lesdites particules fines électro-conductrices comprennent  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>,  $\alpha$ -FeOOH,  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>,  $\varepsilon$ -Fe<sub>2</sub>O<sub>3</sub> ou Fe<sub>3</sub>O<sub>4</sub>.
3. Pile à combustible microbienne suivant la revendication 1, **caractérisée en ce que** lesdites particules fines électro-conductrices sont obtenues par biosynthèse de microorganismes dans un environnement, dans lequel des ions ferriques et des ions de sulfure coexistent.
4. Pile à combustible microbienne suivant une quelconque des revendications 1 à 3, **caractérisée en ce que** lesdits microorganismes sont des bactéries réductrices de métaux.
5. Pile à combustible microbienne suivant la revendication 4, **caractérisée en ce que** lesdites bactéries réductrices de métaux comprennent des bactéries d'un groupe Shewanella, d'un groupe Geobacter, d'un groupe Rhodoferrax ou d'un groupe Pseudomonas.
6. Pile à combustible microbienne suivant la revendication 4, **caractérisée en ce que** lesdites bactéries

15

20

25

30

35

40

45

50

55

FIG.1




FIG.2




FIG.3




FIG.4




FIG.5




FIG.6




FIG.7




FIG.8




FIG.9




FIG.10




FIG.11




FIG.12




FIG.13




FIG.14




FIG.15




FIG.16





FIG.17



## REFERENCES CITED IN THE DESCRIPTION

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

## Patent documents cited in the description

- JP 2006081963 A [0003]

## Non-patent literature cited in the description

- **LOVELY D. R.** *Nat.Rev.Microbiol.*, 2006, vol. 4, 497-508 [0003]
- **GRALNICK, J. A. ; NEWMAN, D. K.** *Molecul. Microbiol.*, 2007, vol. 65, 1-11 [0003]
- **HERNANDEZ, M. E. ; NEWMAN, D. K.** *Cell. Mol.Life Sci.*, 2001, vol. 58, 1562-1571 [0003]
- *Journal of Japanese Society of Microbial Ecology*, 2008, vol. 23 (2), 58 [0003]
- Electricity-producing bacterial communities in microbial fuel cells. **LOGAN B. E. et al.** TRENDS IN MICROBIOLOGY. ELSEVIER SCIENCE LTD, 01 December 2006, vol. 14, 512-518 [0003]
- *Molecular Microbiology*, 2007, vol. 65 (1), 12-20 [0027]
- *Journal of Japanese society of Microbial Ecology*, 2008, vol. 23 (2), 58 [0027]
- **Y.S. KANG ; S.RISBUD ; J.F.RABOLT ; P.STRO-EVE.** *Chem.Mater.*, 1996, vol. 8, 2209 [0055]
- *Journal of the Physical Society of Japan*, July 2005, vol. 74 (7), 1946-1949 [0057]
- **R.J. ATKINSON ; A.M.POSNER ; J.P.Q UIRK.** *J.Phys.Chem.*, 1967, vol. 71, 550 [0061]
- **Y.S.KANG ; S.RISBUD ; J.F.RABOLT ; P.STRO-EVE.** *Chem.Mater.*, 1996, vol. 8, 2209 [0063]
- **R.M.MCKENZIE.** *Mineral.Mag.*, 1971, vol. 38, 493 [0065]