

(19)



(11)

**EP 1 411 067 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:  
**22.09.2010 Bulletin 2010/38**

(51) Int Cl.:  
**C08F 12/00** <sup>(2006.01)</sup> **C08L 25/00** <sup>(2006.01)</sup>  
**C08K 5/00** <sup>(2006.01)</sup>

(21) Application number: **02720591.3**

(86) International application number:  
**PCT/JP2002/004120**

(22) Date of filing: **24.04.2002**

(87) International publication number:  
**WO 2002/088202 (07.11.2002 Gazette 2002/45)**

(54) **POLYMER HAVING UNIQUE OPTICAL PROPERTY**

POLYMER MIT EINZIGARTIGER OPTISCHER EIGENSCHAFT

POLYMERE PRESENTANT UNE PROPRIETE OPTIQUE UNIQUE

(84) Designated Contracting States:  
**CH DE FR GB LI NL SE**

(72) Inventor: **NAKANO, Tamaki**  
**Nara, Nara 631-0805 (JP)**

(30) Priority: **27.04.2001 JP 2001130872**

(74) Representative: **Wilson Gunn**  
**5th Floor**  
**Blackfriars House**  
**The Parsonage**  
**Manchester**  
**M3 2JA (GB)**

(43) Date of publication of application:  
**21.04.2004 Bulletin 2004/17**

(73) Proprietor: **Japan Science and Technology Agency**  
**Kawaguchi-shi**  
**Saitama (JP)**

(56) References cited:  
**EP-A1- 0 773 232 WO-A1-95/06274**  
**WO-A1-97/05184**

**EP 1 411 067 B1**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**Description**Field of the Invention

5 **[0001]** This invention relates to a polymer compound having a functional group in the side-chain containing a cyclic part with aromatic properties (abbreviated as aromatic ring) comprising C, H and/or C,H, X (X is a hetero atom), having a stack structure and a hypochromic effect, and which permits a highly efficient excimer emission. It further relates to a composition containing this polymer compound.

10 Background of the Invention

**[0002]** As disclosed in William Rhodea, JACS, 83, 3690 (1961), it is known that heterocyclic rings forming DNA bases strongly absorb ultraviolet light (vicinity of 260nm), and a hypochromic effect occurs wherein, due to the overlapping of the heterocyclic rings of the bases inside the double helix (stack structure), the optical absorption decreases. However, it is difficult to synthesize these types of polymer materials, and it is also difficult to control their optical properties. For example, as disclosed in Japanese Patent No. 2659245, a polymer wherein the side-chain is a functional group comprising an aromatic ring may be obtained by polymerizing a methacrylic acid ester having a triphenylmethyl group as the ester group. However, in this case, the aromatic rings in the functional group of the side-chain are not parallel and it is difficult to obtain a structure wherein they sufficiently overlap, so it was difficult to manifest optical properties.

20 **[0003]** As described in Yokoyama, M. Macromolecules, 8 (1975), 101 and Itaya, A, Chem. Phys. Lett. 138 (1987), 231, poly(N-vinylcarbazole) is a polymer wherein the side-chain is a functional group comprising an aromatic ring, and when it is present as a film, it is known to emit a blue light due to a carbazole excimer. However, as the functional group in the side-chain of this polymer cannot assume a stable stack structure, efficient excimer light emission does not occur.

25 **[0004]** As described in Nakano, Preliminary reports of the 48th Annual Meeting of the Society of Polymer Science, Japan (Polymer Preprints, Japan, 48(7), 1279(1999)), it is known that dibenzofulvene polymerizes, but as the polymer obtained has poor solubility and miscibility with other polymers, its detailed optical properties were not known.

**[0005]** The Inventor therefore studied the optical properties of polymers comprising dibenzofulvene. As a result, he discovered that polymers obtained using dibenzofulvene having a substituent group had improved solubility; certain of these polymer compounds having a group containing certain aromatic rings in the side-chain had specific optical properties suggesting application as an ultraviolet transmitting material, electroluminescent material or laser material; and compositions wherein an electron acceptor compound or electron donor compound was added to these polymer compounds could be used as charge transfer materials. He thereby arrived at the present invention.

30 **[0006]** It is therefore a first object of the present invention to provide a polymer compound having a stable stack structure, showing a large hypochromic effect and which can be used as a light-resistant polymer material or ultraviolet transmitting material.

**[0007]** It is a second object of the invention to provide a composition containing a polymer compound having specific optical properties exhibiting highly efficient excimer light emission, emitting light from the ultraviolet region into the blue region, and which has application as an electroluminescent material or laser-emitting material.

**[0008]** It is a third object of the invention to provide a charge transfer material having a high charge mobility.


40 **[0009]** It is a fourth object of the invention to provide a polymerizing monomer to be used as a starting material for the aforesaid polymer compound.

Summary of the Invention

45 **[0010]** The aforesaid objects of the invention are achieved by a polymer compound having special optical properties represented by the following structural formula 1, having in the side-chain a functional group containing an aromatic ring comprising C, H and/or C,H, and hetero atom, and a number average molecular weight of 250-1,000,000, wherein the molar absorption coefficient due to the aromatic ring is 70% or less than the molar absorption coefficient due to the aromatic ring in the polymerizing monomer used to introduce the aromatic ring; and a composition comprising at least this polymer compound, and an electron acceptor compound or electron donor compound.

50 **[0011]** The polymer compound is represented by the following general formula (1):

55



wherein, Ar is an aromatic ring, R<sup>1</sup> and R<sup>2</sup> are substituents, R<sup>5</sup> and R<sup>6</sup> are hydrogen atoms, alkyl groups, aromatic groups, a group selected from among -CN and ester groups, X is not present, or is one moiety selected from among -CH<sub>2</sub>, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH=CH-, -C(=O)- and a hetero atom, and m is an integer equal to 2 or more.

[0012] The number average molecular weight of the polymer compound of this invention is preferably 250-10,000, but more preferably 250-5,000. The molar absorption coefficient of the polymer compound due to the aromatic ring is preferably 40% or more than the molar absorption coefficient due to the aromatic ring in the polymerizing monomer.

#### Brief Description of the Drawings

##### [0013]

Fig. 1 is an optical absorption spectrum of a polymer compound obtained in a first example. In the figure, A is the measurement for a fluorene, B is the measurement for a fluorene dimer, C is the measurement for a THF solution of the trimer-17-mer (homopolymer consisting of 17 monomeric units) of a fluorene.

Fig. 2 is the fluorescence spectrum of the polymer compound obtained in the example.

[0014] Fig. 3 is a diagram showing the single crystal structure of DBF hexamer.

#### Description of the Preferred Embodiments

[0015] The functional group containing an aromatic ring comprising C and H in this invention, is a functional group having a structure represented by formula 1. A particularly preferred aromatic ring in this invention is a fluorene ring. Suitable substituent groups can be introduced into this fluorene ring. Herein, stack structure means a structure wherein the aromatic rings of the functional group of the side-chain are stacked on top of each other.

[0016] When these aromatic rings are superimposed, there is naturally a mutual interaction between two aromatic rings. This mutual interaction is stronger, the smaller the distance is between the overlapping aromatic rings, and the special optical properties of the polymer compound are correspondingly increased.

[0017] For example, in the case of aromatic rings having a planar structure, if the inter-plane distance is 0.5 nm or less, there is a strong mutual interaction between the electrons of the two rings. If it is more than 0.5 nm, energy transfer between the aromatic rings and the efficiency of electron transfer are poorer. Therefore, the inter-plane distance between the aromatic rings in the polymer compound of this invention is preferably 0.5 nm or less.


[0018] The inter-plane distance of the aromatic rings also depends on the polymerization degree of the polymer compound. In particular, from the viewpoint of conferring excimer light emission properties, the polymerization degree is preferably 4 or more. When it is less than 4, light may be emitted at an emission wavelength identical to that of the polymerizing monomer in addition to the excimer emission. Therefore, the polymer compound of this invention also contains an oligomer in addition to the ordinary polymer. Considering this polymerization degree, the molecular weight of the polymer compound of this invention must be 250-1,000,000; taking account of ease of manufacture, it is preferably 250-10,000; and taking account also of ease of handling and light emission properties of the polymer compound, it is preferably 250-5,000.

[0019] In this invention, in order to easily produce the aforesaid aromatic ring stack structure and stabilize it, or to increase the mutual interaction between aromatic rings, it is preferred to use a composition wherein an electron acceptor compound or electron donor compound is added to the polymer compound of this invention.


**[0020]** This electron acceptor compound means a compound with a stronger electron affinity than the polymer compound of this invention, specific examples being halogens such as I<sub>2</sub>, Br<sub>2</sub>, Cl<sub>2</sub>, ICl, ICl<sub>3</sub>, IBr and IF, Lewis acids such as BF<sub>3</sub>, PF<sub>5</sub>, AsF<sub>5</sub>, SbF<sub>5</sub>, SO<sub>3</sub>, BBr<sub>5</sub>, BF<sub>4</sub><sup>-</sup>, PF<sub>6</sub><sup>-</sup>, AsF<sub>6</sub><sup>-</sup>, SbF<sub>6</sub><sup>-</sup>, ClO<sub>4</sub><sup>-</sup>, protonic acids such as HNO<sub>3</sub>, H<sub>2</sub>SO<sub>4</sub>, HClO<sub>4</sub>, HF, HCl, FSO<sub>3</sub>H, CF<sub>3</sub>SO<sub>3</sub>H, transition metal halides such as FeCl<sub>3</sub>, MoCl<sub>5</sub>, WCl<sub>5</sub>, SnCl<sub>4</sub>, MoF<sub>5</sub>, FeOCl, RuF<sub>5</sub>, TaBr<sub>5</sub>, SnI<sub>4</sub> and LnCl<sub>3</sub> (Ln = La, Ce, Pr, Nd, Sm), and 9-fluorenylidene acetonitrile, 9-fluorenylidene malonitrile, 2,4,7-trinitro-9-fluorenylidene acetonitrile, 2,4,7-trinitro-9-fluorenylidene malonitrile, o-dinitrobenzene, m-dinitrobenzene, p-dinitrobenzene, 2,4,7-trinitrobenzene, 2,4,7-trinitrotoluene, TCNQ, TCNE and DDQ.

**[0021]** The electron donor compound means a compound having a smaller ionization potential than that of the polymer compound of this invention, specific examples being hexamethylbenzene, alkali metals, ammonium ions and lanthanoids.

**[0022]** The polymerizing monomer used to obtain the polymer compound of this invention must be at least one type of polymerizing monomer containing an aromatic ring comprising C and H, or C, H and X, and if necessary a polymerizing monomer not containing the aforesaid aromatic ring may be used in conjunction therewith. The polymerizing monomer containing the aromatic ring comprising C and H, or C, H and X, is preferably a polymerizing monomer represented by the following general formula (2):




wherein, R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub>, R<sub>4</sub> are substituent groups, for example groups selected from among hydrogen atoms, alkyl groups, -OR, aromatic groups, -NRR', -SR, halogen,




**[0023]** These may be identical or different, but it is preferred that all of them are not hydrogen atoms.

**[0024]** X<sup>1</sup> may not be present (the atoms at both ends are then directly bonded together), or is preferably one moiety selected from among -CH<sub>2</sub>-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH=CH-, -CO-, -S-, -O-, -Si(R)(R')-, -NR- and -N(COR)-. R<sup>5</sup>, R<sup>6</sup> are preferably groups selected from among hydrogen atoms, alkyl groups, aromatic groups, -CN and ester groups, and they may be identical or different. R, R' are hydrogen atoms, alkyl groups having 1-50 carbon atoms. ---AR<sup>1</sup>--- and ---AR<sup>2</sup>--- of the dotted portion are cyclic parts exhibiting aromatic properties, and may be heterocyclic rings containing a hetero atom X<sup>2</sup>. ---AR<sup>1</sup>--- and ---AR<sup>2</sup>--- may also be identical or different. Examples of X<sup>2</sup> are N, O, S, Si, Ge, Sn, Pb, P, As, Sb, Bi, Se and Te, but in this invention N, O, Si, Ge are preferred, and N or O is particularly preferred.

**[0025]** In this invention, of the aforesaid polymerizing monomers, the compounds represented by the following structures are particularly preferred:




[0026] R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> are substituent groups, for example hydrogen atoms, alkyl groups, -OR, aromatic groups, -NRR', -SR or halogen, but it is preferred that R<sup>1</sup>-R<sup>4</sup> are not all hydrogen atoms. R<sup>5</sup>, R<sup>6</sup> are hydrogen atoms, straight chain alkyl groups, aromatic groups, -CN or ester groups, and n is 0, 1 or 2.




[0027] R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> are substituent groups, for example hydrogen atoms, alkyl groups, -OR, aromatic groups, -NRR', -SR or halogen, but it is preferred that R<sup>1</sup>-R<sup>4</sup> are not all hydrogen atoms. R<sup>5</sup>, R<sup>6</sup> are hydrogen atoms, straight chain alkyl groups, aromatic groups, -CN or ester groups, and n is 0, 1 or 2.

[0028] X<sup>1</sup> is -S-, -O-, -Si(R)(R')- or -NR, and R, R' are H or alkyl groups having 1-50 carbon atoms.



[0029] R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> are substituent groups, for example hydrogen atoms, alkyl groups, -OR, aromatic groups, -NRR', -SR or halogen, but it is preferred that R<sup>1</sup>-R<sup>4</sup> are not all hydrogen atoms. R<sup>5</sup>, R<sup>6</sup> are hydrogen atoms, straight chain alkyl groups, aromatic groups, -CN or ester groups, and n is 0, 1 or 2.

[0030] Of these, the following dibenzofulvene is particularly preferred.





**[0037]** The polymerizing monomer thus obtained can then be polymerized by any polymerization method known in the art such as radical polymerization, anion polymerization or cation polymerization. A radical polymerization initiator is a compound which can initiate radical polymerization by light irradiation or generate radicals by heating. It is more preferred to initiate the radical polymerization by light irradiation. Examples of direct cleavage radical polymerization initiators are aryl-alkyl ketones, oxime ketones, acyl phosphine oxides, S-phenyl thiobenzoic acid and titanocene; examples of hydrogen extraction radical polymerization initiators are aromatic ketones, thioxanthone, benzyl and quinone derivatives, and ketocumarine.

**[0038]** Examples of complex radical polymerization initiators are organic peroxide/electron donor pigments, bis-imidazole, onium salt/electron donor pigments, N-phenylglycine/electron attracting pigments and N-phenylglycine/diphenyliodonium salt/sensitizers.

**[0039]** Examples of anion polymerization initiators are counter ions such as alkali metals, alkaline earth metals and ammonium, and anions such as carbon, nitrogen, oxygen and sulfur. Examples of these anion polymerization initiators are  $\text{RMgX}$ ,  $\text{R}_2\text{Mg}$ ,  $\text{RCaX}$ ,  $\text{Al}(\text{C}_2\text{H}_5)_3$ ,  $\text{LiAlH}_4$ ,  $\text{NaR}$  and  $\text{KR}$  (R is an alkyl group, aralkyl group or aromatic group having 1-50 but preferably 1-20 carbon atoms such as butyl, benzyl and phenyl, and in this specification, in the above compounds, X represents halogen). An anion polymerization initiator obtained from a secondary amine represented for example by  $(\text{R}^1)(\text{R}^2)\text{NM}$  ( $\text{R}^1$ ,  $\text{R}^2$  are alkyl groups, aralkyl groups or aromatic groups having 1-50 but preferably 1-20 carbon atoms, and M is a counter ion), may also be used.

**[0040]** The polymer of this invention can be polymerized by solid phase polymerization, liquid phase polymerization, block polymerization, emulsion polymerization, seed emulsion polymerization, suspension polymerization and dispersion polymerization.

**[0041]** For example, a monomer dissolved in THF is introduced into an ampule which has been vacuum dried and filled with nitrogen, and cooled to  $-78^\circ\text{C}$ . An amount of n-BuLi equivalent to approx. 1/20 the amount of monomer is added to this solution, and reacted for 24 hours. Subsequently, the n-BuLi is inactivated with MeOH, and an equivalent amount of MeOH to that of the solution is added. The precipitate thus obtained is recovered by centrifugation, and dissolved in THF.

**[0042]** In this invention, at least one of the polymerizing monomers of the invention can be polymerized or copolymerized, and may also be copolymerized with other copolymerizable monomers. Examples of such other monomers are compounds having polymerizing unsaturated bonds such as  $\text{R-C=C-R}'$  or  $\text{R-C}\equiv\text{C-R}'$  (R, R': organic groups), compounds having vinyl groups such as (meth)acryloyl groups, and other compounds having radical polymerization initiating double bonds.

**[0043]** Specific examples of compounds having a (meth)acryloyl radical as vinyl group are (meth)acrylic acid; and (meth)acrylic acid alkyl esters such as ethyl acrylate ester, (meth)acrylic acid n-propyl ester, (meth)acrylic acid isopropylester, (meth)acrylic acid n-butyl ester, (meth)acrylic acid sec-butyl ester, (meth)acrylic acid pentyl, (meth)acrylic acid hexyl, cyclohexyl methacrylate ester, (meth)acrylic acid heptyl, (meth)acrylic acid n-octyl ester, (meth)acrylic acid isooctylester, (meth)acrylic acid 2-ethylhexyl ester, (meth)acrylic acid decyl, (meth)acrylic acid isononyl ester, (meth)acrylic acid hydroxyethyl ester, (meth)acrylic acid iso myristyl ester, (meth)acrylic acid iso stearyl ester, (meth)acrylic acid stearyl ester, (meth)acrylic acid lauryl ester, glycidyl (meth)acrylate, 2-hydroxyethyl (meth)acrylate, (meth)acrylic acid n-butoxy ethyl, (meth)acrylic acid phenoxy ethyl, (meth)acrylic acid tetrahydro furfuryl, (meth)acrylic acid benzil, (meth)acrylic acid tribromophenyl, (meth)acrylic acid 2,3-dichloro propyl,  $\epsilon$ -(poly)caprolactone acrylate and tetrahydrofuranlyl acrylate.

**[0044]** Epoxy ester compounds such as urethane acrylate obtained by reaction of a compound having an isocyanate radical with a (meth)acrylic monomer having an active hydrogen, or an epoxy ester compound obtained by reaction of a compound having an epoxy group with acrylic acid or a (meth)acrylic monomer having a hydroxyl group; polyester acrylate; alkylene glycol mono(meth)acrylates, dialkylene glycol mono(meth)acrylates, polyalkylene glycol (meth)acrylates; alkylene glycol di(meth)acrylates, polyalkylene glycol di (meth)acrylates, glycerine mono (meth)acrylates, glycerine di(meth)acrylates and glycerine tri(meth)acrylates obtained by reaction of an alkylene glycol such as ethylene glycol or propylene glycol with acrylic acid; trimethylolalkane tri-(meth)acrylates; acrylamide; silicone acrylate; polybutadiene acrylate; ethylene oxide adduct dimethacrylates such as ethylene glycol dimethacrylate, diethylene glycol dimethacrylate, 1,4-butane diol dimethacrylate, 1,6-hexane diol dimethacrylate, 1,9-nonane diol dimethacrylate, trimethylolpropane, trimethacrylate, glycerine dimethacrylate, 2-hydroxy-3-acryloyloxypropylmethacrylate and bisphenol A; and trimethylolpropane trimethacrylate, trimethylolpropane PO-modified trimethacrylate, trimethylolpropane EO-modified trimethylacrylate, pentaerythritol triacrylate, dipentaerythritol pentacrylate, dipentaerythritol hexacrylate, di-trimethylolpropane tetracrylate and pentaerythritol tetracrylate, can also be used.

**[0045]** Examples of other compounds having radical polymerizing double bonds are acrylic acid amino alkyl esters such as acrylic acid N,N-dimethylaminoethyl, acrylic acid N,N-diethylaminoethyl, acrylic acid N,t-butylaminoethyl; (meth)acrylonitrile; butadiene; isoprene; vinyl chloride; vinylidene chloride; vinyl acetate; vinyl ketone; N-vinylpyrrolidone; vinylpyridine; (meth)acrylamide and vinyl carbazole; divinylbenzene;  $\alpha$ -methylstyrene, vinyltoluene, chlorostyrene, t-butylstyrene; vinyl ether monomers such as methyl vinyl ether, ethyl vinyl ether and isobutyl vinyl ether; fumaric acid; maleic

## EP 1 411 067 B1

acid; itaconic acid; phthalic acid; monoalkyl esters of fumaric acid, dialkyl esters of fumaric acid; monoalkyl esters of maleic acid, dialkyl esters of maleic acid; monoalkyl esters of itaconic acid, dialkyl esters of itaconic acid; and monoalkyl esters of phthalic acid, dialkyl esters of phthalic acid.

**[0046]** The polymer compound of this invention obtained as described above comprises an aromatic group having C, H and/or C, H, X in the side-chain. As this aromatic ring easily assumes a stack configuration, a hypochromic effect is produced, and the optical absorption coefficient due to this aromatic ring is 70% or less of the optical absorption coefficient due to the aromatic ring in the polymerizing monomer used to introduce the aromatic ring. Therefore, the polymer compound of this invention may be used as an ultra-violet light transmitting material and is useful as a light resistant polymer material. It also has application as a laser material or electroluminescent material by using excimer light emission. In particular, as it can also be made to emit excimer light from blue to ultraviolet, it has many industrial applications.

### Examples

**[0047]** This invention will now be described in detail by way of examples and comparative examples, but this invention is not limited in any way thereby.

### Examples 1-4

#### <Synthesis of monomer>

**[0048]** Fluorene (30.1g) (Wako Pure Pharmaceuticals), 100g  $\text{AlCl}_3$  (Wako Pure Pharmaceuticals) and 400ml  $\text{CS}_2$  were introduced to a four-neck 3 liter flask fitted with a mechanical stirrer and hydrogen chloride trap which had been flame-dried and filled with nitrogen, and stirred. Next, 64 ml valeroyl chloride (Wako Pure Pharmaceuticals) was slowly dripped in for 30 minutes, the reaction solution was stirred at room temperature for 8 hours, and slowly poured into a 2 liter Meyer flask containing ice with stirring to stop the reaction. After neutralizing with HCl, the organic layer was extracted twice using methylene chloride, the extracted organic layer was washed twice by a 2 wt% NaOH aqueous solution, washed once with saturated salt solution, and dried using  $\text{MgSO}_4$ . After drying with ethyl acetate, this solution was cerite filtered, and concentrated under reduced pressure to give 61g of a brown, viscous liquid. After recrystallization, 52g of a red solid was obtained. The compound so obtained was taken as Compound 1. The NMR spectrum of Compound 1 was as follows.  $^1\text{H-NMR}$  (500MHz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 8.164(s, 2H), 8.028(d, J=8.0Hz, 2H), 7.880(d, J=8.0Hz, 2H), 4.002(s, 2H), 3.019(t, J=7.5Hz, 4H), 1.752(quin, J=7.5Hz, 4H), 1.435(sex, J=7.5Hz, 4H), 0.970(t, J=7.5Hz, 6H)  $^{13}\text{C-NMR}$  (125Mz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 200.289 144.798 136.420 127.484 124.837 120.617 38.534 36.931 26.592 22.494 13.948

**[0049]** A Dean-Stark trap with reflux condenser was fitted to a 1 liter conical flask, and 30.4g of Compound 1, 44.2g hydrazine monohydrate (Wako Pure Pharmaceuticals) and 400ml diethylene glycol (Wako Pure Pharmaceuticals) were introduced and heated at 130°C for 2 hours, then 20.6g KOH (Wako Pure Pharmaceuticals) was added and heated at 200°C for 3 hours. After returning the reaction liquid to room temperature, water was added to stop the reaction, and the organic layer was extracted twice with ether. The organic layer was washed with 1N-HCl, saturated sodium bicarbonate solution, water (twice) and a saturated salt solution in order, and dried using  $\text{MgSO}_4$ . The dried solution was filtered, and concentrated under reduced pressure to obtain 27.7g of a yellow solid. From the solid obtained, 26.2g of a white solid were obtained by silica gel chromatography (hexane). This was taken as Compound 2. The NMR spectrum of Compound 2 was as follows.

$^1\text{H-NMR}$  (500MHz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 7.694(d, J=7.5Hz, 2H), 7.174(d, J=7.5Hz, 2H), 3.840(s, 2H), 3.019(t, J=7.5Hz, 4H), 1.697-1.636(m, 4H), 1.370-1.340(m, 8H), 0.912(t, J=7.0Hz, 6H)  $^{13}\text{C-NMR}$  (125Mz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 143.326 141.220 139.419 126.897 124.989 119.220 36.695 36.115 31.575 31.521 22.586 14.055 Anal. Calcd for  $\text{C}_{23}\text{H}_{30}$  C, 90.13; H, 9.87. Found; C, 90.40; H, 10.0

**[0050]** Compound 2 (5.0g), 280ml toluene and 7.4ml TMEDA were introduced to a three-neck 1 liter flask which had been flame-dried and filled with nitrogen, and stirred at 0°C for 10 minutes.

n-BuLi/hexane (1.6M, 31ml) (Wako Pure Pharmaceuticals) was dripped into this solution during 10 minutes, and stirred for 5 minutes. Paraformaldehyde (1.58g) (Wako Pure Pharmaceuticals) and 20ml toluene were added to the solution, stirred at 0°C for 80 minutes, then water was added to the reaction solution to stop the reaction, and the organic layer was extracted twice with ethyl acetate. The extracted organic layer was washed with saturated salt solution, and dried using  $\text{MgSO}_4$ . The dried solution was filtered, and was concentrated under reduced pressure to obtain 8.5g of a yellow liquid. From this liquid, 3.1g of a pink solid were obtained by silica gel chromatography (hexane/ethyl acetate =15:1). This was taken as Compound 3. The NMR spectrum of Compound 3 was as follows.

$^1\text{H-NMR}$  (500MHz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 7.6621(d, J=7.5Hz, 2H), 7.394(s, 2H), 7.191(d, J=8.0Hz, 2H), 4.045(s, 3H), 2.669(t, J=7.5Hz, 4H), 1.660(quin, J=7.0Hz, 4H), 1.363-1.334(m, 8H), 0.901(t, J=7.0Hz, 6H)




## EP 1 411 067 B1

$^{13}\text{C}$ -NMR (125Mz,  $\text{CDCl}_3$ ,  $\text{CHCl}_3$ ) d 144.363 141.685 139.251 127.736 124.623 119.449 65.287 50.148 36.161 31.605 31.483 22.563 14.055

**[0051]** Compound 3 (1.62g), 30ml MeOH and 230ml THF were introduced to a 200ml conical flask fitted with a reflux condenser, and stirred at  $0^\circ\text{C}$  for 10 minutes. t-BuOK (1.63g) was introduced to the reaction solution, and after stirring for 5 minutes at the reflux temperature, water was added to stop the reaction. Next, the organic layer was extracted from the reaction liquid twice with hexane, the extracted organic layer was washed with saturated salt solution, and dried with  $\text{MgSO}_4$ . The dried solution was cerite filtered, and concentrated under reduced pressure to obtain 1.57g of a yellow liquid. From this yellow liquid, 1.4g of a yellow liquid was obtained by silica gel chromatography. This was taken as Compound 4.

**[0052]** Structural formula of Compound 4:



<Synthesis of polymer>

**[0053]** A solution of 0.4g of Compound 4 dissolved in 8ml THF was introduced into an ampule which had been vacuum dried and filled with nitrogen, cooled to  $-78^\circ\text{C}$ , then an amount of n-BuLi equal to 1/5 equivalents of Compound 4 was added, and reacted for 24 hours. After reaction, MeOH was added to stop the reaction. An equivalent amount of MeOH to that of the solution was added, and the precipitate obtained was recovered by centrifugal separation (0.38g). The polymer thus obtained was taken as Polymer 1. The number average molecular weight of this Polymer 1 was 1,000 (Example 1).

**[0054]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/10 equivalents of n-BuLi were added. The number average molecular weight of this Polymer 2 was 2,000

(Example 2).

**[0055]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/15 equivalents of n-BuLi were added. The number average molecular weight of this Polymer 2 was 3,000 (Example 3).

**[0056]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/25 equivalents of n-BuLi were added. The number average molecular weight of this Polymer 2 was 5,000 (Example 4).


### Comparative Examples 1-4

<Synthesis of monomer>

**[0057]** Fluorene (5.0g), 280ml toluene and 7.4ml TMEDA were introduced to a three-neck 1 liter flask which had been flame-dried and filled with nitrogen, and stirred at  $0^\circ\text{C}$  for 10 minutes.

n-BuLi/hexane (1.6M, 31ml) (Wako Pure Pharmaceuticals) was dripped into this solution during 10 minutes, and stirred for 5 minutes. 1.58g paraformaldehyde (Wako Pure Pharmaceuticals) and 20ml toluene were added to the solution, stirred at  $0^\circ\text{C}$  for 80 minutes, then water was added to the reaction solution to stop the reaction, and the organic layer was extracted twice with ethyl acetate. The extracted organic layer was washed with saturated salt solution, and dried using  $\text{MgSO}_4$ . The dried solution was filtered, and was concentrated under reduced pressure to obtain 8.5g of a yellow liquid. From this liquid, 3.1g of a pink solid were obtained by silica gel chromatography (hexane/ethyl acetate =15:1). This was taken as Compound 5.

**[0058]** Compound 5 (1.62g), 30ml MeOH and 230ml THF were introduced to a 200ml conical flask fitted with a reflux condenser, and stirred at  $0^\circ\text{C}$  for 10 minutes. t-BuOK (1.63g) was introduced to the reaction solution, and after stirring for 5 minutes at the reflux temperature, water was added to stop the reaction. Next, the organic layer was extracted from the reaction liquid twice with hexane, the extracted organic layer was washed with saturated salt solution, and dried with  $\text{MgSO}_4$ . The dried solution was cerite filtered, and concentrated under reduced pressure to obtain 1.57g of a yellow liquid. From this yellow liquid, 1.4g of a yellow liquid was obtained by silica gel chromatography. This was taken as Compound 6.



<Synthesis of polymer>

**[0059]** A solution of 0.4g of Compound 6 dissolved in 8ml THF was introduced into an ampule which had been vacuum dried and filled with nitrogen, cooled to  $-78^{\circ}\text{C}$ , then an amount of n-BuLi equal to 1/5 equivalents of Compound 6 was added, and reacted for 24 hours. MeOH was added to stop the reaction, then an equivalent amount of MeOH to that of the solution was added, and the precipitate obtained was recovered by centrifugal separation. The polymer thus obtained was taken as Polymer 5. The number average molecular weight of this Polymer 5 was 1,000 (Comparative Example 1).

**[0060]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/10 equivalents of n-BuLi were added. The number average molecular weight of this polymer 6 was 2,000 (Comparative Example 2).

**[0061]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/15 equivalents of n-BuLi were added. The number average molecular weight of this polymer 7 was 3,000 (Comparative Example 3).

**[0062]** A polymer was synthesized in an identical way to that of Polymer 1, except that 1/25 equivalents of n-BuLi were added. The number average molecular weight of this polymer 8 was 5,000 (Comparative Example 4).

#### Solubility in THF

**[0063]** The solubility was examined by adding 5g of each of the above polymers 1-8 to 100g THF, and stirring at room temperature for 1 hour. Table 1 shows the results. Polymers which dissolved completely are shown by  $\circ$ , those which dissolved slightly but left a residue are shown by  $\triangle$ , and those which hardly dissolved at all are shown by  $\times$ .

	Polymer compound	Solubility
Example 1	Polymer 1	$\circ$
Example 2	Polymer 2	$\circ$
Example 3	Polymer 3	$\circ$
Example 4	Polymer 4	$\circ$
Comparative Example 1	Polymer 5	$\circ$
Comparative Example 2	Polymer 6	$\circ$
Comparative Example 3	Polymer 7	$\triangle$
Comparative Example 4	Polymer 8	$\times$

**[0064]** The above results show that although the solubility of polymer compounds having a fluorene ring without a substituent group rapidly becomes poorer as the molecular weight increases, the solubility improves in the case where they have a fluorene ring with  $-\text{C}_5\text{H}_{11}$  as a substituent group.

#### Example 5

##### Synthesis of dibenzofulvene

**[0065]** 9-Hydroxymethylfluorene (10g) and 1g KOH were dissolved in 90ml of methanol and reacted at  $60^{\circ}\text{C}$  for 1 hour, and the methanol was evaporated. From the solid thus obtained, dibenzofulvene was extracted using hexane and water, and washed with water until the hexane phase containing dibenzofulvene was neutral. After separating off the hexane phase, the hexane was evaporated, and the solid obtained was recrystallized from a mixed solvent of hexane-diethyl ether (4/6 v/v) to obtain dibenzofulvene. The melting point of the dibenzofulvene was  $50-52^{\circ}\text{C}$ .

[0066] The dibenzofulvene (0.5 mol) was dissolved in THF, and a polymer of dibenzofulvene was obtained by reacting at -78°C for 24 hours, using 0.025 mol of n-BuLi as polymerization initiator. Subsequently, polymers from the dimer to the 17th homopolymer of dibenzofulvene were separated by GPC according to the degree of polymerization.

[0067] The molar extinction coefficient was measured by measuring the optical absorbance of a THF solution at room temperature (Fig. 1).

#### Measurement of fluorescence spectrum

[0068] The emission spectrum of a THF solution was measured using excitation light of 267nm at room temperature (Fig. 2).

[0069] From the optical absorption spectrum, it was found that when the degree of polymerization was 3 or more, the molar extinction coefficient was approx. 40% less than the molar extinction coefficient at 265nm of the monomer. This shows that the fluorene ring of this dibenzofulvene polymer adopts a stack configuration. In addition, the absorption edge shifted to 318nm from the absorption edge of 306nm of the monomer. Further, from measurement of the fluorescence spectrum, when the degree of polymerization was 4 or more, a light emission peak due to excimer light emission was observed at a wavelength of 400nm (peak width 340-550nm) which was different from the light emission peak wavelength of 305nm of the monomer (peak width 295nm to 375nm). This also shows that the fluorene ring in this dibenzofulvene polymer adopts a stack configuration.

#### Example 6 (Copolymerization)

##### <Synthesis of 2,7-di-t-butyl dibenzofulvene>

[0070] Fluorene (30.4764g, 183.5928mmol), FeCl<sub>3</sub> (0.5eq., 14.7517g) and CS<sub>2</sub> (300ml) were introduced to a three-neck 1 liter flask fitted with a mechanical stirrer and hydrogen chloride trap which had been flame-dried and filled with nitrogen, and stirred. t-BuCl (2.5eq., 50ml) was dripped into this solution during 10 minutes. The reaction solution was stirred at room temperature for 7 hours, then water was added to quench the reaction. Next, the organic layer was extracted twice with methylene chloride, the extracted organic layer was washed with saturated salt solution, and dried using MgSO<sub>4</sub>. The dried solution was filtered, and was concentrated under reduced pressure to give a crude product (49.4598g, brown solid). This crude product was refined by silica gel column chromatography (hexane), and the target product 2,7-di-t-butylfluorene (43.6058g, 85%, white solid) was thus obtained. For the reaction, no further purification was carried out, but for measurement of analysis data, a sample which had been recrystallized from EtOH was used. Mp: 120.1-120.6°C; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, CHCl<sub>3</sub>) δ: 7.68 (d, J=8.0Hz, 2H), 7.58 (s, 2H), 7.41 (d, J=8.0Hz, 2H), 3.88 (s, 2H), 1.40 (s, 18H); <sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 149.42, 143.25, 139.12, 123.76, 121.84, 119.07, 37.08, 34.80, 31.62; IR (KBr): 2959, 2895, 2868, 1473, 1358, 1261, 1163, 817, 716cm<sup>-1</sup>; HRMS (EI) Calcd. for C<sub>21</sub>H<sub>26</sub>: 278.2034. Found: 278.2038.

2,7-Di-t-butylfluorene (10.0083g, 36.9712mmol), toluene(570ml) and N,N,N',N'-tetramethylene diamine (17ml) were introduced to a three-neck 1 liter flask which had been flame-dried and filled with nitrogen, and stirred at 0°C for 10 minutes. A hexane solution (1.6M, 68ml) of n-BuLi was dripped into this reaction solution during 10 minutes, and stirred for 5 minutes. Paraformaldehyde (3.2467g) and toluene (30ml) were added to the solution obtained, and stirred at 0°C for 150 minutes, then the reaction solution was quenched with water, and the organic layer was extracted twice with ethyl acetate.

[0071] The organic layer obtained was washed with saturated sodium bicarbonate and saturated salt solution, and dried by magnesium sulfate. This solution was filtered, and concentrated under reduced pressure to obtain a crude product (21.0154g, yellow liquid). This crude product was purified by silica gel chromatography (hexane/ethyl acetate = 15:1), and 2,7-di-t-butyl-9-hydroxymethylfluorene (6.7477g, 59%, light yellow solid) was isolated.

Mp: 101.5-103.0 °C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, TMS) δ : 7.64 (d, J=8.0Hz, 2H), 7.61 (d, J=2.0Hz, 2H), 7.34 (dd, J=8.0, 2.0Hz, 2H), 4.06 (s, 3H), 1.54 (br s, 1H), 1.37 (s, 18H); <sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ : 149.89, 144.29, 138.93, 124.66, 121.39, 119.26, 65.33, 50.47, 34.87, 31.61; IR (KBr): 3322, 2955, 2866, 1476, 1361, 1259, 1058, 817, 735cm<sup>-1</sup>. HRMS (EI) Calcd. for C<sub>22</sub>H<sub>28</sub>O: 308.2140. Found: 308.2138. 2,7-Di-t-butyl-9-hydroxymethylfluorene (2.0383g, 6.6179mmol), MeOH (40ml), THF (40ml) and t-BuOK (2.3048g) were introduced in a 200ml conical flask fitted with a reflux condenser, and stirred at reflux temperature for 10 minutes. The reaction solution was quenched with water, and the organic layer was extracted twice with hexane, washed with saturated salt solution, and dried by MgSO<sub>4</sub>. The solution obtained was filtered, and concentrated under reduced pressure to obtain a crude product (1.8975g, yellow solid). The crude product was purified by silica gel column chromatography (hexane), and 2,7-di-t-butyl dibenzofulvene (1.7840g, 93%, yellow solid) was isolated. Mp: 158.6-160.5°C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, TMS) δ : 7.74 (d, J=1.0Hz, 2H), 7.56 (d, J=8.0Hz, 2H), 7.39 (dd, J=8.0, 2.0 Hz, 2H), 6.05 (s, 2H), 1.38 (s, 18H); <sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ : 149.81, 144.02, 138.12, 137.70, 125.97, 119.04, 117.68, 106.47, 34.89, 31.52; IR (KBr): 2959, 1474, 1361, 1253, 1102, 888, 823, 754, 684cm<sup>-1</sup>;

## EP 1 411 067 B1

HRMS (EI) Calcd. for  $C_{22}H_{26}$ : 290.2034. Found: 290.2029. Anal. Calcd. for  $C_{22}H_{20}$ : C, 90.98. H, 9.02. Found: C, 91.02. H, 9.07.

<Synthesis of soluble n-stack polymer by copolymerization of 2,7-di-t-butyl dibenzofulvene>

**[0072]** 2,7-Di-t-butyl dibenzofulvene (499.6mg, 1.7202mmol), a THF solution (0.87M, 1.8ml) of DBF and THF (3.9ml) were introduced into an ampule which had been flame-dried and filled with nitrogen. The reaction solution was cooled to  $-78^{\circ}C$ , a hexane solution (1.6M, 0.05ml) of n-BuLi was added to start the polymerization, and polymerization was continued at  $-78^{\circ}C$  for 24 hours. After 24 hours, MeOH (0.2ml) was added to the reaction solution at this temperature to stop the polymerization. The reaction mixture was added to  $CDCl_3$ , the  $^1H$ -NMR was measured, and the conversion ratio of monomer was found using the solvent as an internal reference (monomer conversion ratio: DBF $\rightarrow$ 99%, 2,7-t-butyl dibenzofulvene = 6%). The solvent was removed from the reaction solution, and the residue divided into a THF insoluble fraction (117.6mg, 15%) and soluble fraction. MeOH was added to the THF soluble fraction to reprecipitate it, and a MeOH insoluble fraction (156.0mg, 20%) was obtained.

Fraction which is soluble in THF but insoluble in MeOH: Molecular weight,  $M_n = 7900$ ,  $M_w/M_n = 1.13$  [GPC, vs. polystyrene]; Absorption spectrum,  $\epsilon = 22792$  (222nm),  $\epsilon = 10714$  (264nm), hypochromic rate 49% (264 nm) [THF,  $23^{\circ}C$ ] [Reference data (monomer unit model, 2,7-di-t-butylfluorene):  $\epsilon = 28988$  (222nm),  $\epsilon = 26477$  (264nm)] [Reference data (monomer unit model, fluorene):  $\epsilon = 19638$  (222nm),  $\epsilon = 20486$  (264nm)]; Emission spectrum,  $\lambda_{max} = 397nm$  [ $\lambda_{Ex} = 265nm$ , THF,  $23^{\circ}C$ ]

[Reference data (monomer unit model, 2,7-di-t-butylfluorene):  $\lambda_{max} = 311nm$ ]  
[Reference data (monomer unit model, fluorene),  $\lambda_{max} = 311nm$ ]

Example 7 (Polymer 1 with substituent in side-chain)

<Synthesis of 2,7-di-n-pentyl dibenzofulvene>

**[0073]** Fluorene (30.0855g, 181.2380mmol),  $AlCl_3$  (100.1639g) and  $CS_2$  (400ml) were introduced to a four-neck 3 liter flask fitted with a mechanical stirrer and hydrogen chloride trap which had been flame-dried and filled with nitrogen, and stirred. Valeroyl chloride (64ml) was slowly dripped in for 30 minutes. During this process, a large amount of hydrogen chloride gas was generated. The reaction solution obtained was stirred at room temperature for 8 hours, and quenched by slowly pouring it into a 21 Meyer flask containing ice with stirring. The organic layer was extracted twice using methylene chloride, the organic layer was washed twice by a 2wt% NaOH aqueous solution, washed once with saturated salt solution, and dried by  $MgSO_4$ . Next, this organic layer solution was cerite filtered, and concentrated under reduced pressure to give a crude product (61.0123g, brown solid). The crude product was recrystallized from ethyl acetate to obtain 2,7-di(1-oxopentyl)fluorene (52.4458g, 87%, red solid).

**[0074]** Mp: 147.3-149.1 $^{\circ}C$ ;  $^1H$ -NMR (500MHz,  $CDCl_3$ , TMS)  $\delta$ : 8.18 (s, 2H), 8.04 (d, J=8.0Hz, 2H), 7.90 (d, J=8.0Hz, 2H), 4.02 (s, 2H), 3.03 (t, J=7.0Hz, 4H), .76(quin, J=7.0Hz, 4H), 1.44 (sex, J=7.0Hz, 4H), 0.98 (t, J=7.0Hz, 6H);  $^{13}C$ -NMR (125MHz,  $CDCl_3$ )  $\delta$ : 200.29, 144.77, 144.46, 136.44, 127.43, 124.81, 120.59, 38.51, 36.92, 26.58, 22.49, 13.93; IR (KBr): 2957, 2937, 2895, 2870, 1680, 1605, 1213, 1137, 843, 798, 754, 731 $cm^{-1}$ ; HRMS (EI) Calcd. for  $C_{23}H_{26}O_2$ : 334.1933. Found: 334.1933.

**[0075]** A Dean-Stark trap with reflux condenser was fitted to a 1 liter conical flask, and 2,7-di(1-oxopentyl)fluorene (30.4129g, 91.0566mmol), hydrazine monohydrate (44.2ml) and diethylene glycol (400ml) were introduced and heated at  $130^{\circ}C$ . After 2 hours, KOH (20.5628g) was added and heated at  $200^{\circ}C$ . After 3 hours, the reaction liquid was returned to room temperature, water was added, and the organic layer was extracted twice with ether. The organic layer was washed with 1N-HCl, saturated sodium bicarbonate solution, water (twice) and a saturated salt solution, and dried using  $MgSO_4$ . The solution obtained was filtered, and concentrated under reduced pressure to obtain a crude product (27.6591g, yellow solid). The crude product was purified by silica gel chromatography (hexane) to obtain 2,7-din-pentylfluorene (26.2137g, yellow solid).

Mp: 98.9-99.6  $^{\circ}C$ ;  $^1H$ -NMR (500MHz,  $CDCl_3$ , TMS)  $\delta$ : 7.63 (d, J=8.0Hz, 2H), 7.33 (s, 2H), 7.16 (d, J=8.0Hz, 2H), 3.83 (s, 2H), 2.67-2.64 (m, 4H), 1.68-1.62 (m, 4H), 1.53-1.33 (m, 8H), 0.91-0.88 (m, 6H);  $^{13}C$ -NMR (125MHz,  $CDCl_3$ )  $\delta$ : 143.33, 141.24, 139.43, 126.91, 124.80, 119.23, 36.70, 36.12, 31.56, 31.51, 22.59, 14.06; IR (KBr): 2953, 2925, 2870, 2855, 1467, 1420, 2397, 864, 811  $cm^{-1}$ ; HRMS (EI) Calcd. for  $C_{23}H_{30}$ : 306.2348. Found: 306.2339; Anal. Calcd. for  $C_{23}H_{30}$ : C, 90.13. H, 9.87. Found: C, 90.40, H, 10.0.

**[0076]** 2,7-Di-n-pentylfluorene (5.0407g, 16.4727mmol), toluene(280ml) and N,N,N',N'-tetramethylene diamine (17ml) were introduced to a three-neck 1 liter flask which had been flame-dried and filled with nitrogen, and stirred at  $0^{\circ}C$  for 10 minutes. A hexane solution (1.6M, 68ml) of n-BuLi was dripped into this reaction solution during 10 minutes, and stirred at this temperature for 5 minutes. Paraformaldehyde (1.5844g) and toluene (20ml) were added to the solution obtained, and stirred at  $0^{\circ}C$  for 80 minutes. The reaction solution was quenched with water, and the organic layer was

extracted twice with ethyl acetate. The extracted organic layer was washed with saturated sodium bicarbonate and saturated salt solution, dried by magnesium sulfate, filtered, and concentrated under reduced pressure to obtain a crude product (8.5301g, yellow liquid). This crude product was purified by silica gel chromatography (hexane/ethyl acetate =15:1), and 9-hydroxymethyl-2, 7-di-n-pentylfluorene (3.1360g, 57%, pink solid) was isolated.

Mp: 61.3-63.7 °C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, TMS) δ : 7.62 (d, J=8.0Hz, 2H), 7.39 (s, 2H), 7.19 (d, J=8.0Hz, 2H), 4.05 (s, 3H), 2.68-2.65 (m, 4H), 1.69-1.63 (m, 4H), 1.51(br s, 1H), 1.36-1.33 (m, 8H), 0.91-0.89 (m, 6H);

<sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 144.36, 141.69, 139.25, 127.74, 124.62, 119.45, 65.29, 50.15, 36.16, 31.61, 31.48, 22.56, 14.06; IR (KBr): 3311, 2926, 2855, 1467, 1418, 1062, 023, 896, 809, 732 cm<sup>-1</sup>;

HRMS (EI) Calcd. for C<sub>24</sub>H<sub>32</sub>O: 336.2453. Found: 336.2446.

**[0077]** 9-Hydroxymethyl-2, 7-di-n-pentylfluorene (1.6210g, 4.8171mmol), MeOH (30ml) and THF (230ml) were introduced in a 200ml conical flask fitted with a reflux condenser, and stirred at 0°C for 10 minutes. t-BuOK (1.6330g) was added to the reaction solution at this temperature, and stirred at reflux temperature for 5 minutes. Next, water was added to the reaction solution to quench, the organic layer was extracted twice with hexane, washed with saturated salt solution, and dried by MgSO<sub>4</sub>. This solution was cerite filtered, and concentrated under reduced pressure to obtain a crude product (1.5743g, yellow liquid). The crude product was purified by silica gel column chromatography (hexane), and 2,7-di-n-pentyl dibenzofulvene (1.4020g, 91%, yellow liquid) was obtained. As this compound starts polymerizing when left as an oil without a solvent at room temperature, it was rapidly extracted and purified by column chromatography and used for polymerization.

<sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, CHCl<sub>3</sub>) δ: 7.56 (d, J=8.0Hz, 2H), 7.54(s, 2H), 7.19 (d, J=8.0Hz, 2H), 6.05 (s, 2H), 2.71-2.68 (m, 4H), 1.72-1.66 (m, 4H), 1.39-1.37 (m, 8H), 0.95-0.92 (m, 6H); <sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 143.66, 141.59, 138.28, 138.06, 128.98, 120.90, 119.17, 106.81, 36.16, 31.54, 31.40, 22.57, 14.04;

IR (neat) 2929, 2855, 1465, 1376, 1298, 889, 817, 754cm<sup>-1</sup>.

HRMS (EI) Calcd. for C<sub>24</sub>H<sub>30</sub>: 318.2348. Found: 318.2363.

<Synthesis of soluble n-stack polymer by polymerization of 2,7-di-n-pentyl dibenzofulvene>

**[0078]** A dry hexane solution of 2,7-di-n-pentyl dibenzofulvene (0.97M, 1.65ml, 1.60mmol) was introduced to an ampule which had been flame-dried and filled with nitrogen, and hexane was distilled off under reduced pressure. Dry THF (2.6ml) was added to dissolve the monomer, and the solution was cooled to -78°C. A hexane solution (1.6M, 0.1ml) of n-BuLi was added to start the polymerization, and polymerization was continued for 24 hours. MeOH (0.2ml) was added while the reaction solution was kept at -78°C to stop the polymerization. Part of the reaction mixture was diluted with CDCl<sub>3</sub>, the <sup>1</sup>H-NMR was measured, and from the intensity ratio of the peak of the solvent used as internal reference to the absorption of the vinyl protons in the remaining monomer, the monomer conversion ratio was determined (monomer conversion ratio: >99%).

**[0079]** The solvent was distilled off from the reaction solution, the crude product obtained was dissolved in THF, and reprecipitated by MeOH to obtain a MeOH insoluble fraction (320.8mg, 62%).

MeOH insoluble fraction

Molecular weight, Mn = 3100, Mw/Mn = 1.24 [GPC, vs. polystyrene];

Absorption spectrum, ε = 12751 (282nm), ε = 12701 (274nm), hypochromic rate 55% (274 nm)

[THF, 25°C]

[Reference data (monomer unit model, 2,7-di-n-pentylfluorene): ε = 20436 (282m), = 28315 (274nm) [THF, r.t.];

Emission spectrum, λ<sub>max</sub> = 404nm [λ<sub>Ex</sub> = 282nm, THF, r.t.]

[Reference data (monomer unit model, 2,7-di-n-pentylfluorene): λ<sub>max</sub> = 315nm]

[Ex. = 282nm, THF, r.t.].

Solubility: soluble in toluene, chloroform and THF.

Example 8 (Polymer 2 with substituent group in side-chain)

**[0080]** 2,7-Dibromofluorene (25.1251g, 77.5442mmol), NiCl<sub>2</sub>dppp (4.2480g) and Et<sub>2</sub>O (300ml) were introduced to a three-neck 1 liter flask fitted with a dropping funnel which had been flame-dried and filled with nitrogen, and stirred at 0 °C for 15 minutes. An Et<sub>2</sub>O solution of 3-methylpropyl magnesium bromide (1.53M, 302ml) was added to the reaction solution, stirred at 0°C for 10 minutes, and stirred at room temperature for 40 hours. The reaction solution was quenched by slowly pouring it into a 2 liter Meyer flask containing ice with stirring and extracted twice with ethyl acetate, the organic layer was washed by saturated sodium bicarbonate solution and saturated salt solution, and dried by anhydrous MgSO<sub>4</sub>. This solution was cerite filtered, and concentrated under reduced pressure to give a crude product (22.3459g, brown solid). The crude product (17.2926g) was filtered by silica gel column chromatography (hexane), and this was divided into an EtOH soluble fraction (16.9854g) and insoluble fraction (0.3072g). The EtOH soluble fraction was recrystallized from EtOH to obtain 2,7-di(2-methylpropyl)fluorene (5.6111g, 26%, light yellow solid).

## EP 1 411 067 B1

Mp: 76.0-77.5; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, CHCl<sub>3</sub>) δ: 7.65 (d, J=8.0Hz, 2H), 7.31 (s, 2H), 7.13 (d, J=8.0Hz, 2H), 3.84 (s, 2H), 2.54 (t, J=7.0Hz, 4H), 1.87-1.95 (m, 2H), 0.93 (d, J=7.0Hz, 12H);

<sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 143.18, 139.99, 139.47, 127.62, 125.69, 119.07, 45.62, 36.70, 30.48, 22.41;

IR (KBr): 2950, 2922, 2866, 1465, 839, 800, 745, 703cm<sup>-1</sup>;

HRMS (EI) Calcd. for C<sub>21</sub>H<sub>26</sub>: 278.2034. Found: 278.2029

**[0081]** A Dean-Stark trap with reflux condenser was fitted to a 1 liter conical flask, and 2,7-di(1-oxopentyl)fluorene (30.4129g, 91.0566mmol), hydrazine monohydrate (44.2ml) and diethylene glycol (400ml) were introduced and heated at 130°C. After 2 hours, KOH (20.5628g) was added and heated at 200°C. After 3 hours, the reaction liquid was returned to room temperature, water was added, and the organic layer was extracted twice with ether. The organic layer was washed with 1N-HCl, saturated sodium bicarbonate solution, water (twice) and a saturated salt solution, and dried using MgSO<sub>4</sub>. The solution obtained was filtered, and concentrated under reduced pressure to obtain a crude product (27.6591g, yellow solid). The crude product was purified by silica gel chromatography (hexane) to obtain 2,7-din-pentylfluorene (26.2137g, yellow solid).

Mp: 98.9-99.6 °C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, TMS) δ : 7.63 (d, J=8.0Hz, 2H), 7.33 (s, 2H), 7.16 (d, J=8.0Hz, 2H), 3.83 (s, 2H), 2.67-2.64 (m, 4H), 1.68-1.62 (m, 4H), 1.53-1.33 (m, 8H), 0.91-0.88 (m, 6H);

<sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 143.33, 141.24, 139.43, 126.91, 124.80, 119.23, 36.70, 36.12, 31.56, 31.51, 22.59, 14.06;

IR (KBr): 2953, 2925, 2870, 2855, 1467, 1420, 2397, 864, 811 cm<sup>-1</sup>; HRMS (EI) Calcd. for C<sub>23</sub>H<sub>30</sub>: 306.2348. Found: 306.2339; Anal. Calcd. for C<sub>23</sub>H<sub>30</sub>: C, 90.13. H, 9.87. Found: C, 90.40, H, 10.0.

**[0082]** 2,7-Di-(2-methylpropyl)fluorene (10.0194g, 35.9853mmol), toluene(600ml) and N,N,N',N'-tetramethylene diamine (16.3ml) were introduced to a two-neck 2 liter flask which had been flame-dried and filled with nitrogen, and stirred at 0°C for 15 minutes. A hexane solution (1.6M, 68ml) of n-BuLi was dripped into this reaction solution, and stirred for 5 minutes. Next, paraformaldehyde (3.3552g) was added to this solution, stirred at 0°C for 70 minutes and quenched with water, and the organic layer was extracted twice with ethyl acetate. This organic layer was washed with saturated salt solution, dried by MgSO<sub>4</sub>, filtered, and concentrated under reduced pressure to obtain a crude product (25.1026g, yellow liquid). This crude product was purified by silica gel chromatography (hexane/ethyl acetate =20:1), and the target product, 9-hydroxymethyl-2,7-di-(2-methylpropyl)fluorene (6.3921g, 58%, white solid) was thus obtained.

Mp: 104.6-105.4 °C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, CHCl<sub>3</sub>) δ : 7.63 (d, J=8.0Hz, 2H), 7.63 (s, 2H), 7.16 (d, J=8.0Hz, 2H), 4.07-4.04 (m, 3H), 2.55 (d, J=7.0Hz, 4H), 1.94-1.86 (m, 2H), 1.50-1.48 (m, 1H),

0.94-0.92 (m, 12H); <sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 144.25, 140.44, 139.30, 128.48, 125.34, 119.30, 65.35, 50.16, 45.63,

30.46, 22.42, 22.38; IR (KBr): 3347, 2952, 2922, 1467, 1059, 1025, 887, 838, 791, 636cm<sup>-1</sup>;

HRMS (EI) Calcd. for C<sub>22</sub>H<sub>28</sub>O: 308.2140. Found: 308.2139.

**[0083]** 9-Hydroxymethyl-2,7-di-methylpropylfluorene (4.0273g, 13.0563mmol), MeOH (50ml) and THF (50ml) were introduced in a 200ml conical flask fitted with a reflux condenser, and stirred at 0°C for 10 minutes. t-BuOK (4.4273g) was added to the reaction solution at this temperature, stirred at reflux temperature for 10 minutes and quenched with water. The organic layer was extracted twice with hexane, washed with saturated salt solution, and dried by MgSO<sub>4</sub>. Next, the solution was cerite filtered, and concentrated under reduced pressure to obtain a crude product (3.7852g, yellow solid). The crude product was purified by silica gel column chromatography (hexane), and 2,7-di(2-methylpropyl) dibenzofulvene (3.5023g, 92%, light yellow solid) was obtained.

Mp: 71.9-73.7 °C ; <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>, CHCl<sub>3</sub>) δ : 7.54 (d, J=8.0Hz, 2H), 7.49 (s, 2H), 7.14 (d, J=8.0Hz, 2H), 6.02 (s, 2H), 2.54 (d, J=7.0Hz, 4H), 1.96-1.88 (m, 2H), 0.94 (d, J=7.0Hz, 12H);

<sup>13</sup>C-NMR (125MHz, CDCl<sub>3</sub>) δ: 143.68, 140.39, 138.17, 138.11, 129.71, 121.58, 119.03, 106.81, 45.65, 30.42, 22.38;

IR (KBr): 2947, 1463, 1427, 896, 833, 801, 754, 667cm<sup>-1</sup>; HRMS (EI) Calcd. for C<sub>22</sub>H<sub>26</sub>: 290.2034. Found: 290.2028.

<Synthesis of soluble π-stack polymer by polymerization of 2,7-di-isobutyl dibenzofulvene>

**[0084]** 2,7-Di-isobutyldibenzofulvene (233mg, 0.80mmol) was dissolved in dry toluene (1.3ml) in an ampule which had been flame-dried and filled with nitrogen. The solution was cooled to -78 °C , n-BuLi (1.6M, 0.05ml) was added to start the polymerization, and polymerization was continued for 24 hours. MeOH (0.2ml) was added while the reaction solution was kept at -78 °C to stop the polymerization. Part of the reaction mixture was diluted with CDCl<sub>3</sub>, the <sup>1</sup>H-NMR was measured, and from the intensity ratio of the peak of the solvent used as internal reference to the absorption of the vinyl protons in the remaining monomer, the monomer conversion ratio was determined (monomer conversion ratio: >99%).

**[0085]** The solvent was distilled off from the reaction solution, the crude product obtained was dissolved in THF, and reprecipitated by MeOH to obtain a MeOH insoluble fraction (210.7mg, 89%).

MeOH insoluble fraction

**[0086]** Molecular weight, Mn = 3150, Mw/Mn =1.17 [GPC, vs. polystyrene]; Absorption spectrum, ε = 11486 (294nm),

## EP 1 411 067 B1

$\epsilon = 10813$  (274nm), hypochromic rate 64% (264 nm)

[THF, 25°C]

[Reference data (monomer unit model, 2,7-isobutylfluorene):  $\epsilon = 7075$  (294nm),  $\epsilon = 30021$  (274nm) [THF, r.t.];

Emission spectrum,  $\lambda_{\max}$  405nm [ $\lambda_{\text{Ex.}} = 294\text{nm}$ , THF, r.t.]

[Reference data (monomer unit model, 2,7-isobutylfluorene):  $\lambda_{\max} = 315\text{nm}$

[ $\lambda_{\text{Ex.}} = 294\text{nm}$ , THF, r.t.].

Solubility: soluble in toluene, chloroform and THF.

Example 9 (Energy transfer).

<Synthesis of polydibenzofulvene having a 1-pyrenyloxy group in start terminal>

**[0087]** THF (0.97 ml) was introduced into an ampule which had been flame dried and filled with dry nitrogen, 1-pyrenyl methoxy potassium THF solution (0.4M, 2.5 ml) was added at -78°C, and DBF THF solution (0.654M, 1.53 ml) was dripped in to start the polymerization. The 1-pyrenyl methoxy potassium THF solution was prepared by introducing 1-pyrenyl methanol (464.6 mg, 2.0 mmol) and potassium hydroxide (81.3 mg, 2.0 mmol) into an ampule which had been flame dried and filled with dry nitrogen, adding THF (4.5 ml), and leaving at room temperature for 10 minutes. The reaction mixture was added to  $\text{CDCl}_3$ , the  $^1\text{H-NMR}$  was measured, and the monomer conversion ratio was found using the solvent as internal reference (monomer conversion ratio: after 24 hours, >99%). After polymerization at -78°C for 24 hours, methanol (1.0 ml) was added to the reaction mixture to stop the polymerization. Approx. 50ml THF was added to the reaction mixture, and the mixture divided into a THF soluble fraction (313 mg, 60mg after subtracting residual initiator, 27%) and an insoluble fraction (164mg, 73%). The THF soluble fraction was purified by aliquot GPC to obtain a polydibenzofulvene having a 1-pyrenyl methoxy group in the start terminal (GPC [ $M_n=1522$ ,  $M_w/M_n=1.06$ ]; end-group determination of  $^1\text{H-NMR}$  [ $M_n=3066$ ]).

<Measurement of energy transfer efficiency>

**[0088]** A light emission due only to the pyrenyl group was observed in the fluorescence spectrum of the polydibenzofulvene having a 1-pyrenyl methoxy group in the start terminal (in THF, nitrogen bubbling for 10 minutes, room temperature, exciting light 287nm, concentration 7.50M), and the fluorescent yield  $\Phi_{\text{FL}}$  was 0.43 (standard sample: 9,10-diphenylanthracene ( $\Phi_{\text{FL}}=0.90$ )). Assuming that the value of the fluorescent yield does not vary regardless of the excitation method, and the fluorescent yield of the pyrenyl group at the end of the polydibenzofulvene having a 1-pyrenyl methoxy group at the start end coincided with the fluorescent yield of 1-pyrenyl methanol ( $\Phi_{\text{FL}}=0.49$ , measured by the same method as for poly dibenzofulvene), the energy transfer efficiency  $\Phi_{\text{ET}}$  was calculated ( $\Phi_{\text{ET}}=0.86$ ).

Example 10 (Conductivity: Time of flight measurement of soluble oligomer).

**[0089]** 2,4,7-Trinitrofluorene malononitrile (1%) was added to and dissolved in a  $\text{CH}_2\text{Cl}_2$  solution of a mixture of polymers having polymerization degrees of approx. 2-20 (main component was dimer - to 5th homopolymer). The solution was cast on an ITO glass plate, and dried to give a thin film (1 $\mu\text{m}$  thickness). Aluminum was then vapor deposited on this thin film (thickness 1000Å, area 5mm  $\times$  5mm). Using TOF301 (Optel Co., Ltd.), a voltage of 5.0V was applied between ITO and aluminum, pulsed laser light of 337nm was simultaneously irradiated from the ITO side (nitrogen laser, pulse width 1ns, 150  $\mu\text{J}$ ), and the time of flight was measured. From the measurement results at room temperature, the hole migration was determined to be  $1.02 \times 10^{-4} \text{cm}^2 \text{V}^{-1} \text{sec}^{-1}$ .

Example 11 (Conductivity: electrical resistance measurement)

**[0090]** A polymer insoluble in solvents having a degree of polymerization of approx. 20 was kneaded with 2,4,7-trinitrofluorene malononitrile (TNFMN) in a mortar, and compression molding was then performed to give a film of approx. 0.2mm thickness using a table press. This was fixed on a glass plate using epoxy adhesive, aluminum electrodes of width 5mm and thickness 1000Å were vapor deposited with an inter-electrode distance of 90 $\mu\text{m}$ , an alternating current voltage of 10mV was applied in a dark location, and the electrical conductivity was measured. As a result, when the doping amount of TNFMN was 0.1%, a value of  $4.29 \times 10^{-6} \text{S/cm}$  was obtained, and when the doping amount of TNFMN was 1%, a value of  $1.13 \times 10^{-5} \text{S/cm}$  was obtained. Also, the electrical resistance was a non-ohmic resistance pattern and a threshold was observed between 5-7V, so the material clearly had semiconductor properties.

Example 12 (Monocrystal structural analysis: demonstration of n-stack structure)

<Synthesis, isolation, single crystal preparation and structural analysis of dibenzofulvene hexamer having methyl group at start end, and ethyl group at stop end>

[0091] THF(33.1 ml) was introduced into an ampule which had been flame dried and filled with dry nitrogen, methyl-lithium THF solution (1.0M, 2ml) was added at -78°C, and a THF solution of DBF (0.67M, 14.9ml) was dripped in to start the polymerization. The reaction mixture was added to CDCl<sub>3</sub>, the <sup>1</sup>H-NMR was measured, and the monomer conversion ratio was found using the solvent as internal reference (monomer conversion ratio: after 48 hours, 84%). After carrying out the polymerization at -78°C for 48 hours, ethane iodide (2.0ml, 25mmol) was added to the reaction mixture to stop the polymerization. Approx. 50ml THF was added to the reaction mixture, the mixture divided into a THF soluble fraction (758mg, 98%) and insoluble fraction (15mg, 2%), and the THF soluble fraction separated by recycle aliquot GPC to obtain a hexamer (MALDI-Mass mass number M/z = 1135.25, calculated value 1136.46). From <sup>1</sup>H-NMR, it was found that the hexamer had six fluorene units each having a methyl group and an ethyl group. This was recrystallized from chloroform to give 1mm × 1mm × 1mm colorless, transparent single crystals (crystal cell constant a=10.402 Å; b=19.7052 Å; c=29.916 Å; β = 92.6521°; Space group P21/n; R=0.097, Rw=0.145). From crystal analysis, it was found that the spacing of aromatic rings was 0.37-0.46nm (Fig. 3).


#### Industrial Field of Application

[0092] The polymer compound of this invention may be used as an ultra-violet light transparent material, and is useful as a light resistant polymer material. It may also have application as a laser material and electroluminescent material by using excimer light emission. In particular, as it can be made to emit excimer light from blue to ultraviolet, it has wide-ranging potential in industrial applications.

#### Claims

1. A polymer compound represented by the following structural formula 1 having in a side chain a functional group comprising a cyclic part with aromatic properties comprising C and H and/or C, H, X and a number average molecular weight of 250-1,000,000, said polymer compound being **characterized in that** the molar extinction coefficient due to the cyclic part having these aromatic properties as determined by measuring the optical absorbance of a THF solution at room temperature is 70% or less than the molar extinction coefficient due to the cyclic part having said aromatic properties in the polymerizing monomer used to introduce the cyclic part having said aromatic properties, wherein Ar is an aromatic ring, R<sup>1</sup> and R<sup>2</sup>, are substituent groups, R<sup>5</sup> and R<sup>6</sup> are groups selected from among hydrogen atoms, alkyl groups, aromatic groups, -CN and ester groups, X is not present, or is one moiety selected from among -CH<sub>2</sub>-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH=CH-, -C(=O)- and hetero atoms, and m is 2 or more.

Structural formula 1



2. The polymer compound according to Claim 1, wherein said number average molecular weight is 250-10,000.
3. The polymer compound according to Claim 1 or 2, wherein said functional group comprising a cyclic part having aromatic properties is a fluorene derivative.




4. The polymer compound according to any of Claims 1 to 3, wherein the cyclic part having said aromatic properties has a stack structure.
5. The polymer compound according to any of Claims 1 to 4, wherein the interplane distance between cyclic parts having aromatic properties is 0.5 nm or less.
6. The polymer compound according to any of Claims 1 to 5, wherein the polymer compound having particular optical properties has a light emission wavelength which is different from the light emission wavelength of the monomer forming the polymer compound.
7. The polymer compound according to Claim 6, wherein the light emission of said polymer is excimer light emission.
8. The polymer compound according to Claim 7, wherein the cyclic part having said aromatic properties has a stack structure.
9. A composition comprising an electron-acceptor compound or electro-donor compound and the polymer compound described in Claims 1-8.
10. The composition according to Claim 9, wherein said composition is a charge transfer complex.
11. A charge transport material comprising the composition described in Claim 10.

Patentansprüche

1. Polymerverbindung, dargestellt durch die folgende Strukturformel 1, die in einer Seitenkette eine funktionelle Gruppe, die einen zyklischen Teil mit aromatischen Eigenschaften umfasst, der C und H und/oder C, H, X umfasst, und ein Zahlenmittel des Molekulargewichts von 250 bis 1.000.000 besitzt, wobei besagte Polymerverbindung **dadurch gekennzeichnet ist, dass** der molare Extinktionskoeffizient aufgrund des zyklischen Teils, der diese aromatischen Eigenschaften besitzt, bestimmt durch Messen der optischen Absorbenz einer THF-Lösung bei Raumtemperatur, 70% oder weniger ist als der molare Extinktionskoeffizient aufgrund des zyklischen Teils, der besagte aromatische Eigenschaften besitzt, im polymerisierenden Monomer, das verwendet wird, um den zyklischen Teil, der besagte aromatische Eigenschaften besitzt, einzuführen, wobei Ar ein aromatischer Ring ist, R<sup>1</sup> und R<sup>2</sup> Substituentengruppen sind, R<sup>5</sup> und R<sup>6</sup> Gruppen sind, die ausgewählt sind unter Wasserstoffatomen, Alkylgruppen, aromatischen Gruppen, -CN und Estergruppen, X nicht anwesend ist oder eine Gruppe ist, die ausgewählt ist unter -CH<sub>2</sub>-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH=CH-, -C(=O)- und Heteroatomen, und m zwei oder mehr ist.

Strukturformel 1



2. Polymerverbindung gemäß Anspruch 1, wobei das Zahlenmittel des Molekulargewichts 250-10.000 ist.
3. Polymerverbindung gemäß Anspruch 1 oder 2, wobei besagte funktionelle Gruppe, die einen zyklischen Teil umfasst,

der aromatische Eigenschaften besitzt, ein Fluorenderivat ist.

4. Polymerverbindung gemäß einem der Ansprüche 1 bis 3, wobei der zyklische Teil, der besagte aromatische Eigenschaften besitzt, eine Stapelstruktur besitzt.

5. Polymerverbindung gemäß einem der Ansprüche 1 bis 4, wobei der Zwischenebenenabstand zwischen zyklischen Teilen, die aromatische Eigenschaften besitzen, 0,5 nm oder weniger ist.

6. Polymerverbindung gemäß einem der Ansprüche 1 bis 5, wobei die Polymerverbindung, die besondere optische Eigenschaften besitzt, eine Lichtemissionswellenlänge besitzt, die verschieden von der Lichtemissionswellenlänge des Monomers ist, das die Polymerverbindung bildet.

7. Polymerverbindung gemäß Anspruch 6, wobei die Lichtemission des besagten Polymers eine Excimerlichtemission ist.

8. Polymerverbindung gemäß Anspruch 7, wobei der zyklische Teil, der besagte aromatische Eigenschaften besitzt, eine Stapelstruktur besitzt.

9. Zusammensetzung, umfassend eine Elektronenakzeptorverbindung oder Elektronendonoverbindung und die Polymerverbindung wie in den Ansprüchen 1-8 beschrieben.


10. Verbindung gemäß Anspruch 9, wobei besagte Verbindung ein Ladungstransferkomplex ist.

11. Ladungstransportmaterial, umfassend die Zusammensetzung wie in Anspruch 10 beschrieben.

### Revendications

1. Composé polymère représenté par la formule structurelle 1 suivante ayant dans une chaîne latérale un groupe fonctionnel comprenant une partie cyclique ayant des propriétés aromatiques comprenant C et H et/ou C, H, X et un poids moléculaire moyen en nombre de 250 à 1 000 000, ledit composé polymère étant **caractérisé en ce que** le coefficient d'extinction molaire dû à la partie cyclique ayant ces propriétés aromatiques, tel que déterminé par la mesure de l'absorbance optique d'une solution de THF à température ambiante, est de 70 % ou moins que le coefficient d'extinction molaire dû à la partie cyclique ayant lesdites propriétés aromatiques dans le monomère de polymérisation utilisé pour introduire la partie cyclique ayant lesdites propriétés aromatiques, dans lequel Ar est un noyau aromatique, R<sup>1</sup> et R<sup>2</sup> sont des groupes substituants, R<sup>5</sup> et R<sup>6</sup> sont des groupes choisis parmi des atomes d'hydrogène, des groupes alkyle, des groupes aromatiques, des groupes -CN et ester, X n'est pas présent, ou est une fraction choisie parmi -CH<sub>2</sub>-, -CH<sub>2</sub>-CH<sub>2</sub>-, -CH=CH-, -C(=O)- et des hétéroatomes, et m vaut 2 ou plus.

Formule structurelle 1



2. Composé polymère selon la revendication 1, dans lequel ledit poids moléculaire moyen en nombre est 250 à 10 000.

## EP 1 411 067 B1

3. Composé polymère selon la revendication 1 ou 2, dans lequel ledit groupe fonctionnel comprenant une partie cyclique ayant des propriétés aromatiques est un dérivé du fluorène.
- 5 4. Composé polymère selon l'une quelconque des revendications 1 à 3, dans lequel la partie cyclique ayant lesdites propriétés aromatiques a une structure à empilement.
5. Composé polymère selon l'une quelconque des revendications 1 à 4, dans lequel la distance interplanaire entre des parties cycliques ayant des propriétés aromatiques est de 0,5 nm ou moins.
- 10 6. Composé polymère selon l'une quelconque des revendications 1 à 5, dans lequel le composé polymère ayant des propriétés optiques particulières a une longueur d'onde d'émission de lumière qui est différente de la longueur d'onde d'émission de lumière du monomère formant le composé polymère.
- 15 7. Composé polymère selon la revendication 6, dans lequel l'émission de lumière dudit polymère est une émission de lumière excimère.
8. Composé polymère selon la revendication 7, dans lequel la partie cyclique ayant lesdites propriétés aromatiques a une structure à empilement.
- 20 9. Composition comprenant un composé accepteur d'électrons ou un composé donneur d'électrons et le composé polymère décrit dans les revendications 1 à 8.
10. Composition selon la revendication 9, dans laquelle ladite composition est un complexe de transport de charge.
- 25 11. Matière de transport de charge comprenant la composition décrite dans la revendication 10.

30

35


40

45


50

55

Fig 1.




Absorption spectrum of fluorene (A), debenzofulvene oligomer (dimer (B)) and mixture of trimer-homopolymer consisting of 17 monomeric units (C)) in THF at room temperature (approx.  $23^\circ\text{C}$ ).  
Fig 2.



Emission spectrum of fluorene (A), debenzofulvene oligomer (dimer (B)) and mixture of trimer-homopolymer consisting of 17 monomeric units (C)) in THF at room temperature (approx.  $23^\circ\text{C}$ ). Absorption intensity is normalized to a concentration of  $1.0 \times 10^{-5} \text{ M}$  (excitation wavelength is 265 nm (A), 267 nm (B, C)).

Fig 3.



**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- JP 2659245 B [0002]

**Non-patent literature cited in the description**

- **William Rhodea**. *JACS*, 1961, vol. 83, 3690 [0002]
- **Yokoyama, M.** *Macromolecules*, 1975, vol. 8, 101 [0003]
- **Itaya, A.** *Chem. Phys. Lett.*, 1987, vol. 138, 231 [0003]
- *Polymer Preprints, Japan*, 1999, vol. 48 (7), 1279 [0004]
- *Bull. Chem. Soc. Jpn.*, 1986, vol. 59, 97-103 [0032]