



(11) **EP 1 505 096 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:  
**05.12.2007 Bulletin 2007/49**

(21) Application number: **03728040.1**

(22) Date of filing: **07.05.2003**

(51) Int Cl.:  
**C08G 63/06 (2006.01)**

(86) International application number:  
**PCT/JP2003/005727**

(87) International publication number:  
**WO 2003/095519 (20.11.2003 Gazette 2003/47)**

(54) **NOVEL POLYESTER HAVING  $\pi$ -CONJUGATED GROUP IN SIDE CHAIN AND CHARGE TRANSPORTING MATERIAL USING THE SAME**

NEUER POLYESTER MIT  $\pi$ -KONJUGIERTER GRUPPE IN DER SEITENKETTE UND LADUNGSTRANSPORTMATERIAL, BEI DEM DIESER ZUR ANWENDUNG KOMMT

NOUVEAU POLYESTER COMPRENANT UN GROUPE A CONJUGAISON  $\pi$ (P) DANS LA CHAÎNE LATÉRALE ET UN MATÉRIAU DE TRANSPORT DE CHARGE UTILISANT CELUI-CI

(84) Designated Contracting States:  
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LI LU MC NL PT RO SE SI SK TR**

(30) Priority: **08.05.2002 JP 2002132598**

(43) Date of publication of application:  
**09.02.2005 Bulletin 2005/06**

(73) Proprietor: **Japan Science and Technology Corporation**  
**Kawaguchi-shi,**  
**Saitama 332-0012 (JP)**

(72) Inventor: **NAKANO, Tamaki**  
**Nara-shi, Nara 630-0101 (JP)**

(74) Representative: **Wilson Gunn**  
**Chancery House,**  
**Chancery Lane**  
**London WC2A 1QU (GB)**

(56) References cited:  
**EP-A- 0 443 542 EP-A- 0 583 609**  
**CH-A- 515 740 FR-A- 1 590 574**  
**JP-A- 2002 080 734**

**EP 1 505 096 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**Description**

FIELD OF THE INVENTION

5 **[0001]** This invention relates to a novel polymer compound having a fluorene residue in a side chain. In particular, it relates to a novel polymer compound which can form a charge transfer complex with an electron acceptor compound or an electron donor compound, and a charge transfer complex formed by addition of the electron acceptor compound or electron donor compound.

10 BACKGROUND OF THE INVENTION

**[0002]** As described in Tokkai 2000-319366, a polyester with a fluorene residue is already known. This polyester has excellent heat-resistance and transparency, high refractive index, low birefringence and low water absorptivity, and is therefore suitable as an optical instrument material. However, as there was almost no overlap of fluorene residues, it was difficult to make it express electrical characteristics using the properties of  $\pi$ -conjugated electrons.

15 **[0003]** It is also known that by adding an electron acceptor compound or an electron donor compound to a polymer material with a  $\pi$ -conjugated group such as polyacetylene or polyfluorene, a material exhibiting charge transport qualities will be obtained. However, as such a material is degraded by water or oxygen, there was a problem as to its stability as a material exhibiting charge transport qualities.

20

SUMMARY OF THE INVENTION

**[0004]** The inventor made a detailed study of polymer compounds having special electrical qualities due to the properties of  $n$ -conjugated electrons. As a result, it was discovered that a polyester having a fluorene residue in a side chain had unique electrical qualities, and forms a charge transfer complex of excellent stability with a suitable electron acceptor compound or electron donor compound, which led to the present invention.

25

**[0005]** It is therefore a first object of this invention to provide a polyester having  $\pi$ -conjugated electrons, that is a polyester having unique electrical qualities due to the properties of  $\pi$ -conjugated electrons.

**[0006]** It is a second object of this invention to provide a composition which forms a stable charge transfer complex with an electron acceptor compound or an electron donor compound.

30

**[0007]** The aforesaid objects of this invention are attained by a polyester expressed by the following structural formula 1.

**[0008]** In the formula,  $m$  is an integer equal to 2 or more.

35


**Structural formula 1:**

40

45

50

55



**[0009]** In addition, in the aforesaid structural formula, Ar is an aromatic group and this aromatic group may contain a heterocyclic ring.

**[0010]** R<sup>1</sup> is a carbon atom or absent (direct bond), R<sup>2</sup>-R<sup>9</sup> are hydrogen atoms, electron donor groups or electron attracting groups, R<sup>20</sup>, R<sup>21</sup> are hydrogen atoms or organic groups, and X is a hetero atom, hetero atom-containing group, organic group or absent (direct bond).

**[0011]** In this invention, it is preferred that R<sup>1</sup> is absent, i.e., that it is the end of a polymerizing unit.

#### DETAILED DESCRIPTION OF THE INVENTION

**[0012]** The hetero atom X in the structural formula 1 is -O-, -NR- or -S-. The organic group is preferably -(CH<sub>2</sub>)- or an aromatic group.

**[0013]** The electron donor group in the aforesaid structural formula 1 of this invention is a functional group which, due to the introduction of a substituent, has an increased electron density in the fluorene residue and enhanced electron donor properties in the fluorene residue. This electron donor group may for example be -F, -Cl, -Br, -I, -OH, -OR, -O(C=O)R, -NR<sup>10</sup>R<sup>11</sup>, -SR, -SH or an alkyl group, but among these, -C<sub>5</sub>H<sub>11</sub>, -t-C<sub>4</sub>H<sub>9</sub> and -NR<sup>10</sup>R<sup>11</sup> are preferred. R, R<sup>10</sup> and R<sup>11</sup> may be H or an organic group, but preferably an aromatic group or an alkyl group. R<sup>20</sup>, R<sup>21</sup> may be a hydrogen atom, alkyl group, aromatic group, -CN or ester group.

**[0014]** The electron attracting group is a functional group which, due to the introduction of a substituent, has a decreased electron density in the fluorene residue, and enhanced electron acceptor properties in the fluorene residue. This electron acceptor group may for example be -C≡N, -(C=O)R, -SO<sub>2</sub>-, -NO<sub>2</sub>, phenyl, -COOH or -COOR, but -C≡N and -NO<sub>2</sub> are preferred.

**[0015]** By introducing the aforesaid electron-attracting group and electron donor group into the polymer, a more stable charge-transfer complex is obtained when an electron donor compound and electron acceptor compound, described later, are added.

**[0016]** Preferred combinations of R<sup>2</sup>-R<sup>9</sup> are:

- (1) all of R<sup>2</sup>-R<sup>9</sup> are H;
- (2) R<sup>3</sup>, R<sup>8</sup> are NR<sup>10</sup>R<sup>11</sup> (R<sup>10</sup>, R<sup>11</sup> are respectively H, an alkyl group or an aromatic group), and R<sup>2</sup>, R<sup>4</sup>-R<sup>7</sup>, R<sup>9</sup> are H;
- (3) R<sup>3</sup>, R<sup>8</sup> are NH<sub>2</sub>, and R<sup>2</sup>, R<sup>4</sup>-R<sup>7</sup>, R<sup>9</sup> are H;
- (4) R<sup>3</sup>, R<sup>8</sup> are -N(C<sub>6</sub>H<sub>5</sub>)<sub>2</sub>, and R<sup>2</sup>, R<sup>4</sup>-R<sup>7</sup>, R<sup>9</sup> are H;
- (5) R<sup>3</sup>, R<sup>8</sup>, R<sup>6</sup> are NO<sub>2</sub>, and R<sup>2</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>7</sup>, R<sup>9</sup> are H;
- (6) R<sup>3</sup>, R<sup>8</sup> are NO<sub>2</sub>, and R<sup>2</sup>, R<sup>4</sup>-R<sup>7</sup>, R<sup>9</sup> are H;

EP 1 505 096 B1

(7) R<sup>3</sup>, R<sup>8</sup>, R<sup>6</sup> are CN, and R<sup>2</sup>, R<sup>4</sup>, R<sup>5</sup>, R<sup>7</sup>, R<sup>9</sup> are H;

(8) R<sup>3</sup>, R<sup>8</sup> are CN, R<sup>2</sup>, R<sup>4</sup>-R<sup>7</sup>, R<sup>9</sup> are H.

[0017] The electron acceptor compound described above is a compound having a stronger electron affinity than the polymer of structural formula 1. Examples are the following halogens, Lewis acids, proton acids and transition metal halogens etc.

Halogens: I<sub>2</sub>, Br<sub>2</sub>, Cl<sub>2</sub>, ICl, ICl<sub>3</sub>, IBr, IF

Lewis acids: BF<sub>3</sub>, PF<sub>5</sub>, AsF<sub>5</sub>, SbF<sub>5</sub>, SO<sub>3</sub>, BBr<sub>3</sub>, BF<sub>4</sub><sup>-</sup>, PF<sub>6</sub><sup>-</sup>, AsF<sub>6</sub><sup>-</sup>, SbF<sub>6</sub><sup>-</sup>, ClO<sub>4</sub><sup>-</sup>

Proton acids: HNO<sub>3</sub>, H<sub>2</sub>SO<sub>4</sub>, HClO<sub>4</sub>, HF, HCl, FSO<sub>3</sub>H, CF<sub>3</sub>SO<sub>3</sub>H

Transition metal halides: FeCl<sub>3</sub>, MoCl<sub>5</sub>, WCl<sub>5</sub>, SnCl<sub>4</sub>, MoF<sub>5</sub>, FeOCl, RuF<sub>5</sub>, TaBr<sub>5</sub>, SnI<sub>4</sub>, LnCl<sub>3</sub> (Ln is La, Ce, Pr, Nd or Sm)

Others: (9-fluorenylidene)acetonitrile,

(9-fluorenylidene)malononitrile,

(2,4,7-trinitro-9-fluorenylidene)acetonitrile,

(2,4,7-trinitro-9-fluorenylidene)malononitrile,


o-dinitrobenzene, m-dinitrobenzene, p-dinitrobenzene, 2,4,7-trinitrobenzene, 2,4,7-trinitrotoluene, TCNQ, TCNE, DDQ.


[0018] On the other hand, the electron donor compound is a compound having a smaller ionization potential than the polymer of structural formula 1. Examples are hexamethylbenzene, alkali metals, ammonium ion and lanthanoids.

[0019] When an electron-attracting functional group is introduced into a fluorene residue, an electron donor compound is preferably added, and when an electron donor functional group is introduced into a fluorene residue, an electron acceptor compound is preferably added. A stable charge-transfer type complex is thus obtained.

(Synthesis method)

[0020] To synthesize the polymer of this invention, for example, the following compounds may be polycondensed using the usual catalyst.



5  
10  
15  
2025  
30  
35

**[0021]** R<sup>1</sup>-R<sup>9</sup>, and R<sup>20</sup>, R<sup>21</sup> are respectively identical to R<sup>1</sup>-R<sup>9</sup>, and R<sup>20</sup>, R<sup>21</sup> in structural formula 1.

**[0022]** The molecular weight of the polymer is preferably 400-1 million but more preferably 800-100,000 in terms of number average molecular weight. If it is less than 400, it is rare for an electron acceptor compound or electron donor compound to enter between fluorene residues, and if it is more than 1 million, the solubility decreases.

**[0023]** The distance between fluorene residues is 4-20Å, but preferably 5-10Å. If it is less than 4Å, the electron acceptor compound or electron donor compound cannot enter between fluorene residues. If it is more than 20Å, the electron acceptor compound or electron donor compound which entered between fluorene residues cannot easily form an electron donor-acceptor complex.

**[0024]** T<sub>g</sub> of the polymer is preferably 30-300°C, but more preferably 80-200°C. When T<sub>g</sub> is less than 30°C, formation of the electron donor-acceptor complex is blocked by structural change of the polymer due to temperature change.

**[0025]** If the aforesaid conditions are satisfied, a stable electron donor-acceptor complex can be obtained. Such a stable electron donor-acceptor complex is suitable as a charge transport material, for example as a hole transport layer of an organic EL or a solar cell. Such a charge transport material can be easily manufactured by a known method, such as spin coating.

#### EXAMPLES

40  
45

**[0026]** Hereafter, this invention will be described in further detail referring to examples, but this invention is not to be construed as being limited in any way thereby.

#### Example 1: (Polymer synthesis).

<Synthesis of 9-hydroxymethyl-9-fluorene carboxylic acid (monomer)>

50  
55

**[0027]** 9-fluorene carboxylic acid (4.98g, 23.7mmol) and anhydrous THF (300ml) were introduced into a flame-dried reaction vessel in which the atmosphere had been replaced by nitrogen, the reaction solution was cooled to -78°C, and n-butyl lithium (41.0ml of 1.6M hexane solution, 71.0mmol) was added. After stirring the reaction solution at -78°C for 30 minutes, paraformaldehyde (2.30g, 75.0mmol) dissolved in anhydrous THF (100ml) was added at -78°C, and stirred at room temperature for 13 hours. Distilled water was added, the solution was extracted with ether, and the pH of the aqueous layer was adjusted to 2 using 1N hydrochloric acid. It was then extracted again with chloroform, and the organic layer was dried by anhydrous magnesium sulfate. The low-boiling fraction was distilled under reduced pressure with the rotary evaporator, and 4.21g of crude product was thus obtained. The methylene chloride-insoluble fraction of this crude product was collected, and the target compound (4.60g, 19.3mmol, 80.5%) was thus obtained. <sup>1</sup>H-NMR (500MHz, CDCl<sub>3</sub>) δ: 7.78 (d, J= 7.5, 2H), 7.67 (d, J= 7.5, 2H), 7.46 (dd, J= 7.0, 2H), 7.54 (dd, J= 8.0, 2H), 4.02(s, 4H).

## EP 1 505 096 B1

<Synthesis of polymer using 9-hydroxymethyl-9-fluorene carboxylic acid as starting material>

5 **[0028]** 9-hydroxymethyl-9-fluorene carboxylic acid (50.4mg, 0.21mmol) and 0.9mg of a catalyst  $(CF_3SO_3)_2Sn$  were introduced into a reaction vessel (9mm  $\Phi$   $\times$  50mm), and the mixture was shaken to render it uniform. Subsequently, it was heated at 180°C for 3 hours while blowing in nitrogen (a syringe needle was fixed over about 2mm of compound). After 3 hours, the obtained compound was separated by decantation into a THF soluble part (47.1mg) and a THF-insoluble part (2.20mg). The dried and weighed THF-soluble part was re-dissolved in THF (3ml), diazomethane (ether solution, 1ml) was slowly dripped in with stirring, and stirred at room temperature for 5 hours. After 5 hours, the solvent and volatile component were distilled off with the rotary evaporator, the obtained crude product was divided into a methanol-soluble part (8.10mg) and methanol-insoluble part (34.9mg), and the methanol-insoluble part was divided into a THF-soluble part (14.19mg) and a THF-insoluble part (20.64mg). The part which was insoluble in methanol but soluble in THF had a molecular weight distribution of approx. 1,000 to  $10^5$  (SEC, polystyrene conversion).

15 Example 2: (Polymer synthesis)

20 **[0029]** Anhydrous methylene chloride (17ml) was added to 9-hydroxy-9-fluorene carboxylic acid (1.01g, 4.42mmol) in a flame-dried reaction vessel in which the atmosphere had been replaced by nitrogen, and stirred at room temperature for 5 minutes to give a uniform solution. Anhydrous triethylamine (0.62ml, 4.502mmol) was then dripped in. The reaction solution was stirred at room temperature for 30 minutes, and an anhydrous methylene chloride (3ml) solution of p-tosyl chloride (762mg, 4.42mmol) was dripped in. The reaction solution was stirred at room temperature for 15 hours and extracted with chloroform, and the organic layer was dried by anhydrous magnesium sulfate. The solvent was distilled off under reduced pressure with the rotary evaporator, and the obtained crude product was classified into a hexane-soluble part (111mg) and a hexane-insoluble part (777mg). The hexane-insoluble part was dissolved in THF (20ml), diazomethane (ether solution, 3ml) was gradually dripped in with stirring, and the solution stirred at room temperature for 5 hours. The reaction product was a mixture of polymers consisting of 2-10 monomers. This polymer mixture was classified by recycling liquid chromatography, and the pure dimer, trimer and tetramer were thus obtained.

25 Example 3: (D-A complexing, spectrometry)

30 <Formation of D-A complex from poly(9-hydroxymethyl-9-fluorene carboxylic acid) and m-dinitrobenzene (DNB)>

1. Absorption spectrum measurement in solution

35 **[0030]** The polymer (2.98mg) and DNB (1.80mg, 0.01mmol) were dissolved in THF for ultraviolet absorption spectra to give 10ml of solution. This was diluted 100 times, and used for absorption spectrum measurements (quartz cell; 10mm) at room temperature. The absorption intensity of the polymer and DNB mixture was smaller than the absorption intensity of the polymer alone. The intensity which was 0.140 at 242nm changed to 0.108 after adding DNB. This change depended on the concentration, and when the DNB concentration was changed to  $2.5 \times 10^{-5}M$  and  $5.0 \times 10^{-5}M$ , the absorption intensity at 242nm changed to 0.077 and 0.059, respectively. This hypochromic effect proved that the fluorene ring of the polymer and DNB formed a stacked complex.

40 **[0031]** The absorption at long wavelength extended from 310nm to 345nm.

2. D-A complexing in solid state

45 **[0032]** The polymer (100mg) and m-nitrobenzene (100mg) were taken up as a  $CH_2Cl_2$  solution, and the light red solid produced while distilling off the solvent was collected. When this was again dissolved in  $CH_2Cl_2$  and the solvent was distilled off, thin red acicular crystals were obtained.

50 Example 4:

<Formation of D-A complex using poly(9-hydroxy-9-fluorene carboxylic acid) and 2,4,7-trinitro-9-fluorenylidene malononitrile (TNFMN)>

55 1. Absorption spectrum measurement in solution

**[0033]** TNFMN (363.3mg, 1.0mmol) was dissolved in methylene chloride solvent for ultraviolet absorption spectra to give 100ml of solution. Next, a polymer (10.4mg of a mixture of polymer consisting of 2-10 monomers, 0.05mmol in monomer units) was dissolved using this solution. The absorption spectrum was measured at room temperature on 1ml

## EP 1 505 096 B1

of solution (quartz cell; 0.1mm). As a result of this measurement, new peaks due to a D-A complex, 386nm ( $\lambda_{\max} = 0.038$ ) and 488nm ( $\lambda_{\max} = 0.009$ ), were observed.

### 2. D-A complexing in solid state

**[0034]** TNFMN (15.1mg, 0.04mmol) and a polymer (10.4mg, 0.05mmol in monomer units) were put into methylene chloride solution, and the solvent was distilled off to dryness to give an orange-red solid. A composition analysis by  $^1\text{H}$ NMR of this solid showed that the proportion of monomer units:TNFMN was 1:1.

### Example 5:

<D-A complexing using trimer of 9-hydroxy-9-fluorene carboxylic acid and TNFMN>

#### 1. Absorption spectrum measurement in solution

**[0035]** TNFMN (363.3mg, 1.0mmol) was dissolved in methylene chloride solvent for ultraviolet absorption spectra to give 100ml of solution. Next, the trimer (10.4mg, 0.05mmol in monomer units) was dissolved using this solution, and the absorption spectrum was measured at room temperature on 1ml of solution (quartz cell; 0.1mm). As a result, new peaks due to the D-A complex, 388nm ( $\lambda_{\max} = 0.037$ ) and 489nm ( $\lambda_{\max} = 0.009$ ), were observed. These absorption intensities depended on concentration, and when the concentration of fluorene was changed to 0.03M and 0.04M, the absorption intensity at 388nm changed to 0.022 and 0.029, respectively.

#### 2. D-A complexing in solid state

**[0036]** TNFMN (15.1mg, 0.04mmol) and a trimer (10.4mg, 0.05mmol in monomer units) were put into methylene chloride solution, and the solvent was distilled off to dryness to give an orange solid. A composition analysis by  $^1\text{H}$ NMR of this solid showed the proportion of monomer units:TNFMN was 1:1.

### Example 6: (Conductivity: Time of flight measurement)

**[0037]** A mixture having a polymerization degree of approx. 20 (principal components are dimer-tetramer) was taken in  $\text{CH}_2\text{Cl}_2$  solution, 1% 2,4,7-trinitrofluorene malononitrile was added to this, and dissolved. The solution was then spread on an ITO glass substrate, and dried to produce a thin film (1 $\mu\text{m}$  thickness). Aluminum was deposited on the obtained film (thickness 1000 $\text{\AA}$ , area 5mm  $\times$  5mm). A voltage of 5.0V was applied between the ITO and aluminum using TOF301 (Optel, Inc.), a 337nm pulse laser (nitrogen laser, pulse width, 1ns, 150 $\mu\text{J}$ ) was simultaneously irradiated from the ITO side, and the time of flight was measured. From the test results at room temperature, the hole mobility was determined as  $1.20 \times 10^{-4} \text{cm}^2 \text{V}^{-1} \text{sec}^{-1}$ .

### Industrial Application

**[0038]** The polyester of this invention has a fluorene residue in a side chain, and it can form a charge transfer complex having excellent stability with an electron acceptor compound or electron donor compound. It is therefore suitable as a charge transport material such as an organic EL material, or the hole transport layer of a solar cell.

### **Claims**


1. A polyester expressed by the following structural formula 1:

5

10

15

20



25

In the aforesaid structural formula, Ar is an aromatic group and this aromatic group may contain a heterocyclic ring. R<sup>1</sup> is a carbon atom or absent (direct bond), R<sup>2</sup>-R<sup>9</sup> are hydrogen atoms, electron donor groups or electron attracting groups, R<sup>20</sup>, R<sup>21</sup> are hydrogen atoms or organic groups, and X is a hetero atom, hetero atom-containing group, organic group or absent (direct bond), and m is an integer equal to 2 or more.

30

2. The polyester according to Claim 1, wherein the molecular weight of said polyester is 400-1 million in terms of number average molecular weight.

3. The polyester according to Claim 2, wherein the distance between fluorene residues in said polyester is 4-20Å.

35

4. The polyester according to Claim 1, wherein Tg of said polyester is 30-300°C.

5. A composition obtained by adding an electron acceptor compound or an electron donor compound to the polyester according to Claim 1.

40

6. The composition according to Claim 5, wherein said composition forms a charge transfer complex.

7. A charge transport material formed using the composition according to Claim 6.


#### Patentansprüche

45

1. Polyester, der durch die folgende Strukturformel 1 wiedergegeben wird:

50

55



25 wobei in der oben genannten Strukturformel m eine ganze Zahl gleich 2 oder mehr ist, Ar eine aromatische Gruppe ist und diese aromatische Gruppe einen heterocyclischen Ring enthalten kann, R<sup>1</sup> ein Kohlenstoffatom oder nicht vorhanden (direkte Bindung) ist, R<sup>2</sup>-R<sup>9</sup> Wasserstoffatome, Elektronendonorgruppen oder elektronenziehende Gruppen sind, R<sup>20</sup>, R<sup>21</sup> Wasserstoffatome oder organische Gruppen sind und X ein Heteroatom, eine heteroatomhaltige Gruppe, eine organische Gruppe oder nicht vorhanden (direkte Bindung) ist.

- 30
2. Polyester nach Anspruch 1, wobei das Molekulargewicht des Polyesters 400-1 Million, angegeben als Molekulargewicht-Zahlenmittel, beträgt.
  3. Polyester nach Anspruch 2, wobei der Abstand zwischen Fluorenresten in dem Polyester 4-20 Å beträgt.
  - 35 4. Polyester nach Anspruch 1, wobei die T<sub>g</sub> des Polyesters 30-300 °C beträgt.
  5. Zusammensetzung, erhalten durch Hinzufügen einer Elektronenakzeptorverbindung oder einer Elektronendonorverbindung zu dem Polyester nach Anspruch 1.
  - 40 6. Zusammensetzung nach Anspruch 5, wobei die Zusammensetzung einen Charge-Transfer-Komplex bildet.
  7. Ladungstransportmaterial, gebildet unter Verwendung der Zusammensetzung nach Anspruch 6.

45

#### Revendications

1. Polyester exprimé par la formule structurelle 1 suivante :

50


55

5

10

15

20



25

dans laquelle,  $R^1$  est  $C_nH_{2n}$ ,  $n$  est un nombre entier égal à 0 ou plus,  $R^2$  à  $R^9$  sont des atomes d'hydrogène, des groupes donneurs d'électrons ou des groupes attirant des électrons, et  $m$  est un nombre entier égal à 2 ou plus.

Dans la formule structurale susmentionnée, Ar est un groupe aromatique et ce groupe aromatique peut contenir un anneau hétérocyclique.

$R^1$  est un atome de carbone ou est absent (liaison directe),  $R^2$  à  $R^9$  sont des atomes d'hydrogène, des groupes donneurs d'électrons ou des groupes attirant des électrons,  $R^{20}$ ,  $R^{21}$  sont des atomes d'hydrogène ou des groupes organiques, et X est un hétéroatome, un groupe contenant des hétéroatomes, un groupe organique ou est absent (liaison directe).

30

2. Polyester selon la revendication 1, dans lequel le poids moléculaire dudit polyester est compris entre 400 et 1 million en termes de poids moléculaire moyen en nombre.

35

3. Polyester selon la revendication 2, dans lequel la distance entre des résidus de fluorène dans ledit polyester est comprise entre 4 et 20Å.

4. Polyester selon la revendication 1, dans lequel Tg dudit polyester est compris entre 30 et 300 °C.

40

5. Composition obtenue en ajoutant un composé accepteur d'électrons ou un composé donneur d'électrons au polyester selon la revendication 1.

6. Composition selon la revendication 5, dans laquelle ladite composition forme un complexe de transfert de charge.

45

7. Matériau de transport de charge formé en utilisant la composition selon la revendication 6.

50

55

**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- JP 2000319366 A [0002]